UNIVERSIDAD POLITÉCNICA DE MADRID

ESCUELA TÉCNICA SUPERIOR DE

INGENIEROS DE CAMINOS, CANALES Y PUERTOS

**Ignition Delaying and Smoke Suppression Study
of Fire-Retardant Polymer Composites**

TESIS DOCTORAL

Zhi Li

Ingeniero de Materiales

2018

Departamento de Ciencia de Materiales

Escuela Técnica Superior De

Ingenieros de Caminos, Canales y Puertos

Universidad Politécnica de Madrid

**Ignition Delaying and Smoke Suppression Study
of Fire-Retardant Polymer Composites**

TESIS DOCTORAL

Zhi Li

Ingeniero de Materiales

Directores de Tesis

De-Yi Wang

Dr. Polymer Chemistry and Physics

2018

ACKNOWLEDGEMENTS

As I start to write this section, a memory of last four years of hardship but colorfulness comes to my mind. I am grateful that my PhD supervisor Prof. De-Yi Wang offers me the opportunity to carry out PhD work. He selects the pioneering and challenging PhD topic for me related to delaying ignition and smoke suppression of polymers. I always remember the touching moments when Prof. De-Yi Wang is elaborately cultivating my ability to design ideas, operate experiments, write scientific papers and deliver presentations. I am strongly impressed by his capacious academic horizons and intensive dedication for mentorship.

Acknowledgement goes to my financial funding by Spanish Ministry of Economy and Competitiveness with project number RTC-2014-2033-4.

I would like to thank IMDEA Materials Institute for providing conveniently accessible facilities and comfortable working environment. Specially, Dr. Juan Pedro Fernández, Dr. Miguel Castillo and Dr. José Sánchez del Río Saez are acknowledged for their constant help in characterization. The impressive help from all administrative staffs including Rosa María Bazán, Mariana Huerta and Dr. Eduardo Troche are appreciated.

I give my sincere gratitude to my intern student DUFOSSE François, Alejandro Jiménez González, Daniel Fernández Expósito, Sara Montero Lira, Ainoa Paradelo Rodriguez and final-year-project student Lejing Liu for their assistance in experiment.

My faithful gratitude goes to Dr. Vignesh Babu Heeralal, Dr. Xiaomin Zhao, Dr. Ehsan Naderi Kalali, Dr. Junhao Zhang, Dr. Weijun Yang, Dr. Jintao Wan, Dr. Xin Wen, Dr. Xin Wang, Dan Xiao, Nerea Pérez González, Ye-Tang Pan, Lu Zhang, Pablo Acuña, Jimena de la Vega, Jing Zhang, Can Fu, Yuxian Yang, Wei Liu and other group members for their help in PhD work and daily life. I will not forget the happy time with Dr. Lingwei Yang, Chuanyun Wang, Jingya Wang, Na Li, Jifeng Li, Xiangxing Deng *etc.*

Special thanks are given to my old grandfather, parents and little brother. Your deepest love and courage energize me to finish my PhD research and continue to strive in the future. Also, I show my most sincere grate to Ms. Xian-Zi Luo for her encouragement. Her optimistic mood lightens my world.

Zhi Li
October

RESUMEN

El peligro de incendio de los polímeros causa enormes pérdidas de fatalidad y propiedad. La evaluación integral de riesgo de incendio involucra la ignición, liberación de calor, producción de humo y efluentes tóxicos. El comportamiento de la liberación de calor de diferentes polímeros ignífugos se ha investigado sistemáticamente. El estudio del retardo de la ignición y supresión de humo de polímeros ignífugos rara vez estuvo involucrado, particularmente en términos de polímeros basados en rellenos a escala nano (nanofillers). La tesis tuvo como objetivo el estudio del retardo de la ignición y la supresión del humo de los polímeros ignífugos. Las soluciones jerárquicas basadas en nanoestructuras para retrasar la ignición y suprimir el humo se exploraron por separado mediante la investigación del mecanismo a diferentes niveles (molécula, mesoescala y macroescala). En detalle, las estrategias basadas en conceptos novedosos fueron adoptadas para retrasar la ignición (Capítulo 3) y suprimir el humo (Capítulo 4). La combinación de retardo de encendido y supresión de humo en un mismo sistema se demostró en el Capítulo 5.

1) En términos del sistema con retardo de ignición, la explotación del agente de extinción por mecanismo radicalario ofreció una solución factible. Se investigó principalmente un agente de extinción mediante radicales de nueva generación (ferroceno). 3% en peso de ferroceno aumentó el tiempo de ignición (t_{ig}) de poliestireno (PS) de $95 \pm 2s$ a $112 \pm 2s$ (prueba de calorímetro de cono, $25kW/m^2$). El efecto de extinción por radicales de las especies de Fe derivadas del ferroceno explica el aumento de la t_{ig} y la temperatura de ignición (T_{ig}). Aparte de eso, el comportamiento de liberación lenta de volátiles actuó como una ruta viable para retrasar la ignición. Originalmente encontramos la solución de adsorción-desorción de volátiles a través de material mesoporoso modificado. La sílice SBA-15 mesoporosa se dopaba con nanopartículas de Co_3O_4 ultrafinas preferentemente en la pared interior. El material compuesto PS con el 2% en peso resultante de SBA-15@ Co_3O_4 (PS/2SBA-15@ Co_3O_4) poseía t_{ig} de $116 \pm 2s$ en comparación con $98 \pm 1s$ del PS puro (CCT, $25kW/m^2$) debido a una T_{ig} notablemente más alto. El aumento de T_{ig} se originó a partir de la liberación retardada de volátiles (gases inflamables) debido a la adsorción-desorción intensificada.

En paralelo, el comportamiento sostenible de liberación lenta del retardante de llama se ideó originalmente para inducir un efecto de extinción de radicales altamente eficiente. Los nanotubos

de halloysita (HNT) se funcionalizaron secuencialmente con anhídrido maleico (MAH) y 10-óxido de 9,10-dihidro-9-oxa-10-fosfafenantreno (DOPO). 5% en peso de HNT@MAH@DOPO impartido en ácido poliláctico (PLA) resultó en una *t_{ig}* retrasada (75 ± 5 s) en comparación con los 60 ± 2 s de PLA puro (CCT, 35kW/m^2). Antes de la ignición, la muestra PLA/5HNT@MAH@DOPO poseía un estado estable con una temperatura de superficie casi constante (lo que indica más *t_{ig}*) debido al efecto de extinción radicalaria sostenible por los radicales $\text{PO}^\cdot$.

2) En términos del sistema de supresión de humo, el mecanismo de fase de vapor del ferroceno no estaba claro. 3% en peso de ferroceno impartido en PS, resultó en un pico de tasa de producción de humo máxima (peak SPR) y producción total de humo (TSP) reducidos en un 55.2% y 56.9% respectivamente. El mecanismo de fase de vapor estuvo involucrado en la degradación mediante oxidación térmica promovida por el intermediario del humo (hollín) de PS/3Ferroceno debido a las nanopartículas de $\gamma\text{-Fe}_2\text{O}_3$. Se observó el mecanismo débil de fase condensada. Paralelamente, con el objetivo de resolver el problema de la baja temperatura de sublimación, la molécula de ferroceno se incluyó en el nanovehículo de ciclodextrina sulfonada intercalada en hidróxido de doble capa (LDH-CD) a través de la química anfitrión-huésped (host-guest). El 6% en peso de LDH-CD@Ferr resultante disminuyó el peak SPR y TSP en un 42,9% y un 54,4% por separado en relación con el de EP. El mecanismo de fase condensada se asoció con la carbonización catalítica hacia una capa carbonosa de mejor calidad. El mecanismo de fase de vapor estuvo involucrado en una menor estabilidad térmica del hollín de la muestra EP/6LDH-CD@Ferr.

Además, con el objetivo de alcanzar la supresión de humo altamente eficiente, el concepto de catálisis interfacial se propuso originalmente hacia una carbonización catalítica más potente. El nanocatalizador ultrafino de Ni(OH)_2 se diseñó en la superficie externa de dodecilmecenosenosulfonato intercalando LDH (LDH-DBS). 3% en peso resultante de LDH-DBS@ Ni(OH)_2 dotado en EP obtuvo unos 50,0% y 65,5% de reducción en el peak SPR y TSP en 200s. El mecanismo de fase condensada sobre la formación de capas carbonosas robustas representó una mejor supresión de humo. El estudio a nivel molecular mostró el mayor grado de poliaromaticidad y la reducción de precursores de humo (compuestos aromáticos y de doble enlace). El hollín de EP/6LDH-DBS@ Ni(OH)_2 no demostró la menor estabilidad de oxidación térmica con relación a EP/6LDH-DBS, que indicaba el mecanismo débil de fase de vapor.

3) En términos de sistema de retardo de encendido y supresión de humo, la solución eficiente fue ajustar la conductividad térmica y el efecto de barrera a través de la incorporación de nanofillers funcionalizados térmicamente conductores. Las nanoláminas de nitruro de boro (BN) exfoliadas térmicamente se funcionalizaron secuencialmente con polidopamina bioinducida (PDA) y nanocatalizador de hierro derivado (Fe). La adición de 6wt% BN, BN@PDA y BN@PDA@Fe respectivamente aumentó t_{ig} a $102 \pm 3s$, $98 \pm 3s$ y $89 \pm 1s$ en comparación con EP con t_{ig} de $80 \pm 3s$. Los factores para influir en la ignición se analizaron mediante estudio contrastivo y simulación numérica. EP/6BN poseía t_{ig} retardado debido a la incrementada conductividad térmica. EP/6BN@PDA mostró un valor t_{ig} ligeramente menor en comparación con EP/6BN debido a la disminución de la capacidad del calor específico. EP/6BN@PDA@Fe exhibió un valor de t_{ig} ligeramente menor en comparación con EP/6BN@PDA debido a la menor estabilidad de oxidación térmica.

EP/6BN@PDA@Fe mostró una reducción del 24,6% y 28,6% del peak SPR y TSP a 350 s en comparación con el EP puro. El mecanismo de fase condensada se asoció con la formación de ceniza de mayor calidad. La catálisis interfacial de Fe (ubicada entre BN y EP) promovió la formación de una capa carbonosa de refuerzo de BN dispersada homogéneamente. La investigación del hollín no mostró un mecanismo de fase de vapor detectable.

ABSTRACT

Fire hazard of polymers causes enormous losses of fatality and property. The integral fire-hazard assessment was involved in ignition behavior, heat release, smoke production and toxic effluents. Heat release behavior of different fire-retardant polymers has been systematically investigated. The ignition-delaying and smoke-suppression study of fire-retardant polymers was seldom involved, particularly in terms of nanofillers-based polymers. The thesis aimed at the study of ignition delaying and smoke suppression of fire-retardant polymers. The hierarchical nanostructure-based solutions to delay ignition and suppress smoke were explored separately with mechanism investigation at different levels (molecule, mesoscale and macroscale). In detail, the strategies based on novel concepts were adopted to delay ignition (Chapter 3) and suppress smoke (Chapter 4). The combination of ignition delaying and smoke suppression into one system was demonstrated in Chapter 5.

1) In terms of ignition-delaying system, the exploitation of radical-quenching agent offered a feasible solution. A new-generation radical-quenching agent (ferrocene) was primarily investigated. 3wt% ferrocene increased ignition time (t_{ig}) of polystyrene (PS) from $95\pm 2s$ to $112\pm 2s$ (cone calorimeter test, $25kW/m^2$). The radical-quenching effect of Fe species derived from ferrocene accounted for the increased t_{ig} and ignition temperature (T_{ig}). Apart from it, the slow-release behavior of volatiles acted as a viable route to delay ignition. We originally found the solution of adsorption-desorption of volatiles via modified mesoporous material. Mesoporous SBA-15 silica was doped with ultrafine Co_3O_4 nanoparticles preferentially on interior wall. PS composite with 2wt% resultant SBA-15@ Co_3O_4 (PS/2SBA-15@ Co_3O_4) possessed t_{ig} of $116\pm 2s$ compared with $98\pm 1s$ of neat PS (CCT, $25kW/m^2$) due to notably higher T_{ig} . The increase of T_{ig} was originated from the delayed release of volatiles (flammable gases) due to the intensified adsorption-desorption.

In parallel, the sustainable slow-release behavior of fire retardant was originally figured out to induce highly efficient radical-quenching effect. Halloysite nanotubes (HNT) were sequentially functionalized by maleic anhydride (MAH) and 9,10-dihydro-9-oxa-10-phosphaphenanthrene-10-oxide (DOPO). 5wt% resultant HNT@MAH@DOPO imparted polylactide (PLA) with delayed t_{ig} ($75\pm 5s$) compared with $60\pm 2s$ of neat PLA (CCT, $35kW/m^2$). Prior to ignition,

PLA/5HNT@MAH@DOPO possessed a steady state with almost constant surface temperature (indicating more t_{ig}) due to the sustainable radical-quenching effect from $PO\cdot$ radicals.

2) In terms of smoke-suppression system, the vapor-phase mechanism of ferrocene was unclear. 3wt% ferrocene imparted PS with reduced peak smoke production rate (peak SPR) and total smoke production (TSP) by 55.2% and 56.9% respectively. Vapor-phase mechanism was involved in the promoted thermal-oxidation degradation of smoke intermediate (soot) of PS/3Ferrocene due to $\gamma\text{-Fe}_2\text{O}_3$ nanoparticles. The weak condensed-phase mechanism was observed. In parallel, aiming to solve the problem of low sublimation temperature, the ferrocene molecule was included into the nanocarrier of sulfonated cyclodextrin intercalated layered double hydroxide (LDH-CD) via host-guest chemistry. 6wt% resultant LDH-CD@Ferr decreased peak SPR and TSP by 42.9% and 54.4% separately relative to that of EP. The condensed-phase mechanism was associated with the catalytic charring toward better-quality carbonaceous layer. Vapor-phase mechanism was involved in lower thermal-oxidation stability of soot of EP/6LDH-CD@Ferr.

Apart from it, aiming to attain the highly efficient smoke suppression, the concept of interfacial catalysis was originally put forward toward stronger catalytic charring. The ultrafine $\text{Ni}(\text{OH})_2$ nanocatalyst was engineered on external surface of dodecylbenzenesulfonate intercalating LDH (LDH-DBS). 3wt% resultant LDH-DBS@ $\text{Ni}(\text{OH})_2$ endowed EP with 50.0% and 65.5% reduction in peak SPR and TSP at 200s. The condensed-phase mechanism about the formation of robust carbonaceous layers accounted for improved smoke suppression. The molecule-level study illustrated the higher polyaromatic degree and reduced smoke precursors (aromatic and double-bond compounds). The soot of EP/6LDH-DBS@ $\text{Ni}(\text{OH})_2$ did not demonstrate the lower thermal-oxidation stability relative to EP/6LDH-DBS, which indicated the weak vapor-phase mechanism.

3) In terms of ignition-delaying and smoke-suppression system, the efficient solution was to tune thermal conductivity and barrier effect via the incorporation of functional thermally conductive nanofillers. The thermally exfoliated boron nitride nanosheets (BN) were sequentially functionalized with bio-inspired polydopamine (PDA) and iron-derived nanocatalyst (Fe). The addition of 6wt% BN, BN@PDA and BN@PDA@Fe respectively increased t_{ig} to $102\pm 3\text{s}$, $98\pm 3\text{s}$ and $89\pm 1\text{s}$ compared with EP with t_{ig} of $80\pm 3\text{s}$. The factors to influence ignition was analyzed via contrastive study and numerical simulation. EP/6BN possessed delayed t_{ig} due to the increased

thermal conductivity. EP/6BN@PDA showed slightly lower t_{ig} value compared to EP/6BN owing to the decreased specific heat of capacity. EP/6BN@PDA@Fe exhibited slightly lower t_{ig} value in comparison to EP/6BN@PDA due to lower thermal-oxidation stability.

EP/6BN@PDA@Fe showed 24.6% and 28.6% reduction of peak SPR and TSP at 350s compared to neat EP. The condensed-phase mechanism was associated with the formation of higher-quality char. The interfacial catalysis of Fe (located between BN and EP) promoted the formation of homogeneously dispersed BN-reinforcing carbonaceous layer. The investigation of soot illustrated no detectable vapor-phase mechanism.

Contents

ABBREVIATIONS	III
LIST OF SCHEMES	V
LIST OF FIGURES	VII
LIST OF TABLES	XIX
1 Introduction	1
1.1 Background and motivation of the study	1
1.2 State of the art	2
1.2.1 Combustion behavior	2
1.2.2 Fire retardancy	3
1.2.3 Delaying ignition	17
1.2.4 Smoke suppression	32
1.3 Objective of the thesis	38
2 Materials and Experimental Techniques	41
2.1 Materials	41
2.2 Experimental technique	41
3 Ignition delaying via flame inhibition and volatile slow-release	53
3.1 Introduction	53
3.2 Preparation and characterization of targeted nanohybrid	54
3.2.1 Preparation of SBA-15@Co ₃ O ₄	54
3.2.2 Characterization of SBA-15@Co ₃ O ₄	56
3.2.3 Preparation of HNT@MAH@DOPO	59
3.2.4 Characterization of HNT@MAH@DOPO	60
3.2.5 Preparation of composites	66
3.3 Property and mechanism of composites	67
3.3.1 PS/Ferrocene composites	68
3.3.2 PS/SBA@Co ₃ O ₄ composites	72
3.3.3 PLA/HNT@MAH@DOPO composites	86
4 Smoke suppression via vapor and condensed-phase mechanism	101
4.1 Introduction	101
4.2 Preparation and characterization of targeted nanohybrid	103
4.2.1 Preparation of LDH-CD@Ferr	103
4.2.2 Characterization of LDH-CD@Ferr	104
4.2.3 Preparation of LDH-DBS@Ni(OH) ₂	108

4.2.4 Characterization of LDH-DBS@Ni(OH) ₂	109
4.2.5 Preparation and characterization of composites	112
4.3 Property and mechanism of composites	114
4.3.1 PS/Ferrocene composites	114
4.3.2 EP/LDH-CD@Ferr composites	123
4.3.3 EP/LDH-DBS@Ni(OH) ₂	136
5 Rational design of ignition-delayed and smoke-suppression system	155
5.1 Introduction	155
5.2 Preparation and characterization of targeted nanohybrid	157
5.2.1 Preparation of BN@PDA@Fe	157
5.2.2 Characterization of BN@PDA@Fe	158
5.2.3 Preparation of composites	161
5.2.4 Dispersion of nanofillers in EP matrix	161
5.3 Property and mechanism of EP/BN@PDA@Fe	162
5.3.1 Ignition behavior of EP/BN@PDA@Fe	162
5.3.2 Ignition mechanism of EP/BN@PDA@Fe	163
5.3.3 Smoke-suppression behavior of EP/BN@PDA@Fe	174
5.3.4 Smoke-suppression mechanism of EP/BN@PDA@Fe	176
5.3.5 Fire retardancy of EP/BN@PDA@Fe	180
5.3.6 Fire-retardant mechanism of EP/BN@PDA@Fe	184
6 Conclusion and future work	187
6.1 Conclusion	187
6.1.1 Ignition delaying	187
6.1.2 Smoke suppression	189
6.1.3 Combination of ignition delaying and smoke suppression	191
6.2 Future work	192
6.2.1 Ignition delaying	192
6.2.2 Smoke suppression	193
7 List of publications and conferences	195
Reference	199

ABBREVIATIONS

t_{ig}	Time to ignition (ignition time)
T_{ig}	Ignition temperature
T_g	Glass transition temperature
$T_{5wt\%}$	Temperature at 5% mass loss
T_{max}	Temperature at maximum mass loss rate
$T_{50wt\%}$	Temperature at 50% mass loss
pHRR	Peak heat release rate
MCC	Micro combustion calorimeter
CCT	Cone calorimeter test
TG	Thermogravimetric analysis
DTG	Derivative thermogravimetric analysis
LOI	Limiting oxygen index
DSC	Differential scanning calorimeter
NMR	Nuclear magnetic resonance
FTIR	Fourier transformation infrared spectroscopy
vt-FTIR	Variable-temperature Fourier transformation infrared spectroscopy
TG-FTIR	Thermogravimetric analysis coupled with Fourier transformation infrared spectroscopy
XPS	X-ray photoelectron energy spectroscopy
MLR	Mass loss rate
DOPO	9,10-dihydro-9-oxa-10-phosphaphenanthrene-10-oxide
EP	Epoxy resin
PLA	Poly lactide
PS	Polystyrene
LDH	Layered double hydroxide
PAH	Polyaromatic compound
IFR	Intumescent fire retardant
TSP	Total smoke production
SPR	Smoke production rate
Peak SPR	Peak smoke production rate
SBA-15	Hexagonal mesoporous silica
HNT	Halloysite nanotube
β-CD (CD)	β -cyclodextrin
BN	Thermally exfoliated boron nitride nanosheets
PDA	Polydopamine

Fe	Iron-derived nanocatalyst
LDH-DBS	Dodecylbenzenesulfonate-intercalating layered double hydroxide
LDH-NO₃	Nitrate-intercalating layered double hydroxide
MAH	Maleic anhydride
DDS	4,4'-diaminodiphenylmethane
TG-GC-MS	Thermogravimetric analysis with gas chromatograph and mass spectroscopy
TG-MS	Thermogravimetric analysis with mass spectroscopy
XRD	X-ray diffraction spectroscopy
XPS	X-ray photoelectron spectroscopy
TEM	Transmission electron microscopy
SEM	Scanning electron microscopy
EDS	Dispersive X-ray spectroscopy
SAED	Selected area electron diffraction
DMA	Dynamic mechanical analysis
FE	Finite element simulation
THR	Total heat release
AHRR	Average heat release rate
FIGRA	Fire growth index
av-EHC	Average efficient heat of combustion
AMLR	Average mass loss rate
Ferr	Ferrocene
FIGRA	Fire growth index
COP	CO production rate
CO₂P	CO ₂ production rate
CY	Char yield

LIST OF SCHEMES

Scheme 1-1 (a) Heat release profiles and (b) smoke production profile during combustion	2
Scheme 1-2 (a) Combustion process of polymers; (b) chemical and physical behaviors in combustion process	3
Scheme 1-3 (a) Chemical reactions during combustion (b) vapor-phase fire inhibition of halogenated compound MX; (c) vapor-phase fire inhibition of phosphorus-containing compound P _x ; (d) digital image and (e) SEM image of intumescent fire-retardant char; (f) digital image (Reproduced with permission from The Royal Society of Chemistry) and (g) TEM image of nanofiller-based fire-retardant char; (h) cooling effect via moisture-releasing behavior of Mg(OH) ₂ -based composites	5
Scheme 1-4 (a) Different organic phosphorous-containing compounds; (b) degradation route of O=P(OCH ₃) ₂ NH ₂	9
Scheme 1-5 Fire-retardant mechanism of different phosphorous-containing fire retardants in (a) DGEBA/DMC and (b) RTM6	9
Scheme 1-6 Azobenzene-azobenzene, azobenzene-phenylethynyl and phenylethynyl-phenylethynyl	10
Scheme 1-7 Heat profile in the horizontal location prior to ignition	19
Scheme 1-8 (a) Polyaromatic reaction due to protection effect of char; (b) possible reaction toward formation of PAH; (c) nucleation and growth to form soot and smoke	33
Scheme 3-1 Normal release versus sustainable slow release	54
Scheme 3-2 Schematic illustration of SBA-15 preparation process	55
Scheme 3-3 Preparation of SBA-15@Co ₃ O ₄ nano-architecture	56
Scheme 3-4 Preparation route of HNT and its derivatives	60
Scheme 3-5 Slow-release behavior of DOPO and its derivatives of HNT@MAH@DOPO	66
Scheme 3-6 (a) Schematic illustration of pre-ignition of PS/Ferrocene; (b) The radical reaction prior to ignition; (c) The proposed reaction route to consume H [·] and OH [·]	72
Scheme 3-7 (a) Benzyl radicals from the hemolytic cleavage of benzyl dimer and (b) degradation route to produce isopropenyl benzene structure (m/z=118)	80
Scheme 3-8 (a) Heating process of PS/SBA-15@Co ₃ O ₄ ; (b) radical reaction during ignition; (c)	

adsorption-desorption process of volatiles	81
Scheme 3-9 Proposed mechanism for improved fire retardancy	84
Scheme 3-10 (a) Schematic illustration of pre-ignition of PLA/HNT@MAH@DOPO; (b) radical reaction of degraded products of PLA prior to ignition; (c) slow-release mode of phosphorous-containing components and (d) radical-quenching process of $H\cdot$ and $OH\cdot$	92
Scheme 3-11 Main non-radical and radical route to thermally decompose PLA	96
Scheme 4-1 Schematic illustration of precipitation and host-guest interaction.....	104
Scheme 4-2 Schematic illustration of LDH-DBS and LDH-DBS@Ni(OH) ₂	109
Scheme 4-3 Schematic illustration of preparation process of EP composites	114
Scheme 4-4 (a) Condensed-phase mechanism and (b) vapor-phase mechanism for smoke suppression of EP/6LDH-CD@Ferr	133
Scheme 4-5 (a) Simplified thermal degradation route of EP and (b) proposed catalytic charring reaction at the interface	151
Scheme 4-6 Condensed-phase mechanism based on interfacial catalysis for smoke suppression	151
Scheme 5-1 Preparation process of BN@PDA and BN@PDA@Fe	157
Scheme 5-2 1D thermally-conductive model based on up-to-down microelement.....	165
Scheme 5-3 Proposed fire-retardant mechanism for EP/6BN@PDA@Fe	185
Scheme 6-1 Novel strategies to delaying ignition	188
Scheme 6-2 Vapor-phase and condensed-phase mechanism of smoke-suppression.....	190

LIST OF FIGURES

Fig.1-1 (a) Average number of fires per 1000 inhabitants and (b) fire death number per 100,000 inhabitant.....	2
Fig.1-2 (a) Structure of APP and modified APP; (b) heat release rate curves of PP and PP composites; (c) proposed chemical reaction mechanism	7
Fig.1-3 (a) Viscosity versus temperature in terms of APP/PER filled polyurethane (PU); (b) polyoxometalate based ionic liquid (PIL); (c) β -cyclodextrin-based microencapsulation; (d) combustion model of PP/APP/PER; (e) numerical and experimental value of surface temperature	7
Fig.1-4 (a) Nanofillers with different morphologies; (b) bubble and charring behavior during combustion of nanofiller-based composites.....	12
Fig.1-5 Char after gasification test at 50kW/m ² of (a) PMMA/0.5wt% SWNT at good dispersion state and (b) PMMA/0.5wt% SWNT at poor dispersion state; Char after gasification test at 50kW/m ² of PS/2wt% MWNT at (c) L/D=150 and (d) L/D=90; (e) mass loss rate of PMMA/0.5wt% SWNT at good and poor dispersion at 50kW/m ² ; (f) comparison of fire-retardant efficiency between PS/Cloisite15A and PS/MWNT with different viscoelasticity	13
Fig.1-6 (a) Surface grafting of polymer block with phosphorous-containing moiety; (b) multifunctional intercalation of layered double hydroxide (LDH)	14
Fig.1-7 (a) In-situ grown MoO ₃ and Cu ₂ O on graphene nanosheets and (b) electrostatic assembly of LDH and graphene oxide nanosheets on hollow SiO ₂ sphere	15
Fig.1-8 (a) Schematic illustration of COF; (b) and (c) SEM and TEM images of Fe-MOF; (d) and (e) SEM and TEM images of Co-MOF; (f) schematic illustration of hierarchical modification of polyphosphazene nanotube; (g) blowing-out mechanism of EP/DOPO-POSS	16
Fig.1-9 (a) Firepoint apparatus with C, F and G sample, radiation and load cell; (b) self-made apparatus for ignition test; (c) temperature prior to ignition with the flash period and (d) gasification apparatus.....	18
Fig.1-10 Images of polymer melt at ignition in CCT of (a) PP, (b) PS, (c) PLA and (d) epoxy resin (EP).....	20
Fig.1-11 Temperature curves of (a) thermoplastic and (b) thermosetting polymers (t_{ig1} and t_{ig2}	

represented the ignition time of sample 1 and 2)	20
Fig.1-12 Thermal degradation curves of (a) hyperbranched poly(phosphamide ester), (b) phenyl phosphonate-based fire retardant and (c) phenyl phosphoric-based fire retardant.....	24
Fig.1-13 (a) TG and DTG curves of intumescent fire-retardant PLA; (b) increased dynamic viscosity of intumescent fire-retardant PP; (c) illustration of upward movement of incident bubbles; (d) mechanism of delayed t_{ig} of PE/IFR/CuSAO	27
Fig.1-14 (a) Surface temperature of PET nanocomposites; (b) (c) (d) cross-section of samples at ignition of PET, PET/CNa ⁺ and PET/C30B; (e) surface temperature of PA6 nanocomposites; (f) formation of char film to shield heat.	28
Fig.1-15 (a) t_{ig} value and (b) T_{ig} value of PP and PP composites at different heat flux	29
Fig.1-16 (a) Organic hybridization of BN nanosheets; (b) thermal conductivity of bismaleimide composites with non-modified BN (hBN) and organically modified BN (CPBN); (c) TEM images of graphene modified by Ni-Fe LDH.....	30
Fig.1-17 (a) LBL process; (b) TEM images of coated fabric; (c) delaying ignition of cotton after LBL coatings in CCT	32
Fig.1-18 (a) Structure of ferrocene; (b) premixed flame; (c) diffusion flame including the counter-flow and co-flow mode	36
Fig.1-19 (a) Chemical reaction of ferrocene; (b) FeCl ₃ -involved dehydrochlorination; (c) smoke density, CO and CO ₂ products at different temperature; (d) smoke suppression mechanism of MoO ₃ toward PVC and (e) smoke suppression mechanism based coupling reaction.....	37
Fig.1-20 Possible smoke suppression of Graphene/MoO ₃ and Graphene/Cu ₂ O in PU	38
Fig.2-1 Schematic illustration of core components of vt-FTIR	42
Fig.2-2 Schematic illustration of core components of TG-FTIR (volatiles moving from right TG furnace to left FTIR chamber).....	42
Fig.2-3 Schematic illustration of core components of TG-GC-MS (volatiles moving from right TG furnace to middle GC column finally to left MS chamber)	43
Fig.2-4 Schematic illustration of core components of MCC	44
Fig.2-5 Schematic illustration of limiting oxygen indexer	44
Fig.2-6 Schematic illustration of (a) vertical burning test and (b) horizontal burning test.....	46
Fig.2-7 Schematic illustration of cone calorimeter from different perspectives	47

Fig.2-8 Schematic illustration of (a) ignition apparatus and (b) laser apparatus	47
Fig.2-9 Schematic illustration of triple-milling machine with the generated shear and extensional force	48
Fig.2-10 Schematic illustration of micro-compounder and flowing circuit of polymer melt	48
Fig.2-11 (a) temperature detection prior to ignition using thermocouple and (b) temperature detection during combustion using infrared detector	49
Fig.2-12 The soot collection process during the combustion	49
Fig.3-1 (a) FTIR spectra of SBA-15 and SBA-15@Co ₃ O ₄ (b) Raman spectra of SBA-15 and SBA-15@Co ₃ O ₄	57
Fig.3-2 XRD spectra of SBA-15 and SBA-15@Co ₃ O ₄ (a) at the small angle and (b) at the wide angle.....	57
Fig.3-3 TEM observations of (a,c) SBA-15, (b,d) SBA-15@Co ₃ O ₄ in different magnifications and (e) high magnification TEM image of SBA-15@Co ₃ O ₄ with marked Co ₃ O ₄ ultrafine nanoparticles and model SBA-15@Co ₃ O ₄ ; EDS spectra of (f) SBA-15 and (g) SBA-15@Co ₃ O ₄ with the inset mapping results and atomic percentage	58
Fig.3-4 (a) FTIR spectra and (b) XRD spectra of HNT, HNT@MAH, HNT@MAH @DOPO and DOPO.....	61
Fig.3-5 TEM images with inset SAED patterns of (a) HNT, (c) HNT@MAH and (e) HNT@MAH@DOPO; EDS of (b) Si mapping of HNT, (d) C mapping of HNT@MAH and (f) P mapping of HNT@MAH@DOPO.....	62
Fig.3-6 (a) XPS spectra of HNT@MAH and HNT@MAH@DOPO; (b) C1s spectra of HNT@MAH; (c) C1s spectra of HNT@MAH@DOPO; (d) P2p spectra of HNT@MAH@DOPO	63
Fig.3-7 (a) TG curves and (b) DTG curves of DOPO and HNT derivatives	65
Fig.3-8 Evolution of the m/z values of (a) 63, (b) 64 and (c) 76; (d) schematic illustration of degraded fragments	66
Fig.3-9 (a) HRR curves and (b) weight profile at ignition stage of PS, PS/1Ferrocene and PS/3Ferrocene	69
Fig.3-10 (a) Temperature profile at the top surface of PS and PS/3Ferrocene prior to ignition and (b) temperature-rising rate at the surface of PS and PS/3Ferrocene	70

Fig.3-11 (a) TG analysis of PS and PS/3Ferrocene at air at 40°C/min; (b) digital image of PS at ignition; (c) digital image of PS/3Ferrocene at ignition.....	71
Fig.3-12 Evolution of (a) Fe, FeO, FeOH, Fe(OH) ₂ and FeO ₂ and (b) FeH and ferrocene	71
Fig.3-13 Ignition time reflected by (a) HRR and (b) mass profile.....	73
Fig.3-14 Top-surface temperature of PS and PS/2SBA-15@Co ₃ O ₄ prior to ignition at 25kW/m ²	73
Fig.3-15 (a) and (c) TG and DTG curves at 10°C/min at N ₂ atmosphere; (b) and (d) TG and DTG curves at 10°C/min at air atmosphere of PS, PS/2SBA-15 and PS/2SBA-15@Co ₃ O ₄	75
Fig.3-16 3D graphics of (a) PS, (b) PS/2SBA-15 and (c) PS/2SBA-15@Co ₃ O ₄	77
Fig.3-17 Combustible gaseous evolution ((a) whole intensity, (b) -CH ₃ compounds, (c) -CH ₂ - compounds, (d) aromatic compounds and (e) double bond containing compounds) of PS, PS/2SBA-15 and PS/2SBA-15@Co ₃ O ₄	77
Fig.3-18 The main gaseous decomposed fragments of PS, PS/2SBA-15 and PS/2SBA-15@Co ₃ O ₄	78
Fig.3-19 The evolution of main decomposed gaseous fragments with the corresponding structure PS/2SBA-15 and PS/2SBA-15@Co ₃ O ₄	79
Fig.3-20 Evolution of the ion fragments (m/z=91 and 118)	80
Fig.3-21 (a) HRR, (b) THR, (c) TSP and (d) weight curves of PS and PS composites	82
Fig.3-22 Residue after CCT of (a) PS, (b) PS/2SBA-15 and (c) PS/2SBA-15@Co ₃ O ₄	83
Fig.3-23 XRD results of residue from PS/2SBA-15@Co ₃ O ₄ at (a) small angles and (b) high angles	84
Fig.3-24 (a) Tensile behaviour of PS, PS/2SBA-15 and PS/2SBA-15@Co ₃ O ₄ (b) stress analysis of PS/2SBA-15@Co ₃ O ₄ (<i>F</i> : force; <i>F_{interface}</i> : the force at the interface; <i>F_{PS}</i> : force applied on PS phase; <i>F_{fillers}</i> : the force at the fillers; <i>S</i> : transverse size).....	86
Fig.3-25 SEM image of cryo-fractured surface of (a) PS/2SBA-15 and (b) PS/2SBA-15@Co ₃ O ₄ ; EDS spectra of selected point from (a) PS/2SBA-15 and (b) PS/2SBA-15@Co ₃ O ₄	86
Fig.3-26 (a) HRR versus time at the ignition and (b) top-surface temperature of PLA and PLA composites prior to ignition	87
Fig.3-27 (a) Temperature-rising rate at the top surface of PLA and PLA/5HNT@HNT@MAH@DOPO and (b) DSC curves at the heating process of PLA and PLA composites.....	89

Fig.3-28 (a) TG and (b) DTG curves at 10°C/min at air atmosphere of PLA and PLA composites; (c) TG and (d) DTG curves at 40°C/min at air atmosphere of PLA and PLA composites.....	90
Fig.3-29 (a) DTG curves of PLA, PLA/5HNT@MAH@DOPO and PLA/5HNT@MAH-DOPO and (b) simplified feeding of DOPO and DOPO derivatives.....	91
Fig.3-30 (a) LOI and UL-94 results (b) HRR, (c) THR and (d) TSP of PLA and PLA	94
Fig.3-31 Average efficient heat of combustion (av-EHC) versus time	96
Fig.3-32 Digital images of char from (a) PLA, (b) PLA/5HNT, (c) PLA/5HNT@MAH, (d) PLA/5HNT@MAH-DOPO and (e) PLA/5HNT@MAH@DOPO; (f) HRR curves in MCC of PLA and PLA composites; (g) R_2 versus R_1	98
Fig.3-33 (a) FTIR spectra of PLA and PLA/5HNT@MAH@DOPO; evolution of (b) whole intensity and (d) aliphatic compounds; integral values of (c) whole intensity and (e) aliphatic compounds	98
Fig.3-34 (a) DTG curves of PLA, HNT@PDA@DOPO and HNT@MAH-DOPO; (b) schematic illustration of combustion in CCT.....	99
Fig.4-1 (a) ^1H -NMR spectra of sulfonate β -cyclodextrin (β -CD) and (b) XRD patterns of LDH-CD, LDH-CD@Ferr and Ferr.....	104
Fig.4-2 (a) Full spectra of LDH-CD and LDH-CD@Ferr; C1s spectra of (b) LDH-CD and (c) LDH-CD@Ferr; (d) Fe2p spectra of LDH-CD@Ferr.....	106
Fig.4-3 TEM images of (a), (b) LDH-CD and (c), (d) LDH-CD@Ferr at different magnifications; (f) EDS spectra with atomic percentage of LDH-CD@Ferr; (e) High-angle angular dark field (HAADF) with Mg, S and Fe mapping of LDH-CD@Ferr	107
Fig.4-4 (a) TG and (b) DTG curves of LDH-CD, LDH-CD@Ferr before and after purification.	108
Fig.4-5 XRD patterns of LDH-DBS and LDH-DBS@Ni(OH) ₂ at (a) 1°-10° and (b) 10°-70°; (c) full XPS spectra of LDH-DBS@Ni(OH) ₂ and (d) Ni2p spectra of LDH-DBS@Ni(OH) ₂	110
Fig.4-6 TEM images of (a) (d) LDH-DBS and (b) (c) LDH-DBS@Ni(OH) ₂ at different magnifications; (e), (f), (g) and (h) Mg, Al, S, and Ni mapping of LDH-DBS@Ni(OH) ₂ ; (i) EDS spectra of LDH-DBS@Ni(OH) ₂	111
Fig.4-7 FIB-SEM images of (a) LDH-DBS and (b) LDH-DBS@Ni(OH) ₂	111
Fig.4-8 (a) Isothermal curves of LDH-DBS and LDH-DBS@Ni(OH) ₂ in N ₂ sorption; (b) TG curves of LDH-DBS and LDH-DBS@Ni(OH) ₂	112

Fig.4-9 (a) DSC curves of PS, PS/1Ferrocene and PS/3Ferrocene and (b) TG and DTG curves of PS and PS/3Ferrocene	113
Fig.4-10 (a) HRR, (b) THR, (c) SPR, (d) TSP, (e) derivation of weight and (f) weight profiles of PS, PS/1Ferrocene and PS/3Ferrocene	115
Fig.4-11 Digital images after CCT of (a) PS and (b) PS/3Ferrocene.....	116
Fig.4-12 (a) COP and (b) CO ₂ P of PS, PS/1Ferrocene and PS/3Ferrocene	116
Fig.4-13 Thermal-oxidation degradation of virgin PS.....	117
Fig.4-14 TEM images of different magnifications of the smoke from pure PS (a, c and e) and PS/3Ferrocene (b, d and f)	118
Fig.4-15 Selected area electron diffraction (SAED) patterns of smoke from (a) PS and (b) PS/3Ferrocene; (c, d and f) High angle angular dark field (HAADF), Fe mapping and EDS spectrum of PS/3Ferrocene; (e) High Resolution TEM (HRTEM) of smoke intermediates of PS/3Ferrocene.....	118
Fig.4-16 (a) Thermal-oxidation degradation profile of smoke intermediates from PS and PS/3Ferrocene and (b) Temperature profile of PS on the external surface during CCT	120
Fig.4-17 FTIR 3D graphics of (a) PS, (b) PS/3Ferrocene and (c) FTIR spectrum at the maximum intensity of PS and PS/3Ferrocene.....	121
Fig.4-18 Volatiles evolution of (a) whole intensity, (b, c, d and e) substituted benzene and (f and h) double bond structure.....	122
Fig.4-19 (a) Illustration of different smoke-production behaviors; (b) proposed thermal-oxidation mechanism of smoke intermediate.....	123
Fig.4-20 TEM images of (a) EP/6LDH-CD and (b, c) EP/6LDH-CD@Ferr; (d) HAADF image, (e) S mapping and (f) Fe mapping of EP/6LDH-CD@Ferr	124
Fig.4-21 (a) Smoke production rate and (b) total smoke production of EP, EP/6LDH-CD and EP/6LDH-CD@Ferr	125
Fig.4-22 (a-1), (b-1), (c-1) side view and (a-2), (b-2), (c-2) top view of char of EP, EP/6LDH-CD and EP/6LDH-CD@Ferr.....	126
Fig.4-23 Digital images of (a), (c), (e) interior and (b), (d), (f) exterior char of EP, EP/6LDH-CD and EP/6LDH-CD@Ferr respectively	126
Fig.4-24 (a) SEM image of interior char of the selected area of EP/6LDH-CD@Ferr and (b) EDS	

spectra; Weight profile in (c) CCT and (d) TG of EP, EP/6LDH-CD and EP/6LDH-CD@Ferr ..	127
Fig.4-25 (a) Ratio of transient value of and (b) ratio of integral value at the degradation period (40-55min) and of EP, EP/6LDH-CD and EP/6LDH-CD@Ferr.....	128
Fig.4-26 (a) TG-FTIR 3D image of EP/6LDH-CD@Ferr; (b) FTIR spectra at the maximum intensity of volatiles of EP, EP/6LDH-CD and EP/6LDH-CD@Ferr	129
Fig.4-27 Evolved intensity of (a) aromatic and (c) double-bond compounds; Intensity integration of evolved volatiles of (b) aromatic and (d) double-bond compounds	130
Fig.4-28 (a) (b) TEM images, (c) selected area electron diffraction (SAED), (d) HAADF image and (e) (f) C and O mapping of soot of neat EP; (g) (h) TEM images, (i) SAED, (j) HAADF image and (k) (l) C and O mapping of soot of EP/6LDH-CD@Ferr.....	131
Fig.4-29 (a) EDS spectra of smoke intermediate from EP/6LDH-CD and EP/6LDH-CD@Ferr; (b) HAADF image with Fe and S mapping of smoke intermediate from EP/6LDH-CD@Ferr.....	131
Fig.4-30 (a) TG and (b) DTG curves of soot from EP, EP/6LDH-CD and EP/6LDH-CD@Ferr.	132
Fig.4-31 Temperature at combustion zone of EP at 50kW/m ²	132
Fig.4-32 LOI value of EP and EP composites.....	134
Fig.4-33 (a) HRR and (b) THR of EP and EP composites	135
Fig.4-34 (a) TG curves and (b) DTG curves at air atmosphere of EP and EP composites	135
Fig.4-35 (a) XRD patterns of EP and EP nanocomposites; (b) schematic illustration of the shear-induced intercalation of LDH-DBS in EP matrix; (c), (d) and (e) TEM images of EP/3LDH-DBS with inset selected area electron diffraction (SAED); (f), (g) and (h) TEM images of EP/3LDH-DBS with SEAD.....	136
Fig.4-36 (a) SPR and (b) TSP of EP and EP nanocomposites.....	137
Fig.4-37 Horizontal view (a-1), (b-1), (c-1), (d-1) and top view (a-2), (b-2), (c-2), (d-2) of EP, EP/3LDH-NO ₃ , LDH-DBS and LDH-DBS@Ni(OH) ₂ respectively; Interior char (a-3), (b-3), (c-3), (d-3), exterior char (a-4), (b-4), (c-4), (d-4) and EDS spectra (a-5), (b-5), (c-5), (d-5) of the interior char from EP, EP/3LDH-NO ₃ , EP/3LDH-DBS and EP/3LDH-DBS@Ni(OH) ₂ respectively	139
Fig.4-38 Vertical section of char from (a) EP/3LDH-DBS and (b) EP/3LDH-DBS@Ni(OH) ₂ ; transverse section of char from (c) EP/3LDH-DBS and (d) EP/3LDH-DBS@Ni(OH) ₂	139
Fig.4-39 (a) XRD pattern of char from EP/3LDH-DBS@Ni(OH) ₂ ; (b) Raman spectra of EP, EP/3LDH-NO ₃ , EP/3LDH-DBS and EP/3LDH-DBS@Ni(OH) ₂	140

Fig.4-40 (a) Heating thermal degradation behavior of EP, EP/3LDH-DBS, EP/3LDH-DBS@Ni(OH) ₂ and calculated EP/3LDH-DBS@Ni(OH) ₂ ; (b) difference between experimental and calculated value at heating thermal analysis; (c) invariable-temperature thermal degradation behavior of EP, EP/3LDH-DBS, EP/3LDH-DBS@Ni(OH) ₂ and calculated value of EP/3LDH-DBS@Ni(OH) ₂ ; (d) difference between experimental and calculated value of EP/3LDH-DBS@Ni(OH) ₂ at invariable-temperature thermal analysis; (e) vt-FTIR spectra of EP/3LDH-DBS@Ni(OH) ₂ at different times; (f) vt-FTIR spectra of EP, EP/3LDH-DBS and EP/3LDH-DBS@Ni(OH) ₂ at 40min	141
Fig.4-41 (a-1) front view and (a-2) top view of char of EP/3LDH-DBS; (b-1) front view and (b-2) top view of char of EP/3LDH-DBS@Ni(OH) ₂ at the moment of 157s during CCT	143
Fig.4-42 SEM images of interior surface of char from (a), (c) EP/3LDH-DBS and (b) (d) EP/3LDH-DBS@Ni(OH) ₂ ; exterior surface of char from (e), (g) EP/3LDH-DBS and (f) (g) EP/3LDH-DBS@Ni(OH) ₂	143
Fig.4-43 Digital images of vertical section of char in CCT at 157s of (a) EP/3LDH-DBS and EP/3LDH-DBS@Ni(OH) ₂	143
Fig.4-44 Comparison of (a) middle temperature and (b) bottom temperature of EP, EP/3LDH-DBS and EP/3LDH-DBS@Ni(OH) ₂ ; top, central and bottom temperature of (a) EP/3LDH-DBS and EP/3LDH-DBS@Ni(OH) ₂	144
Fig.4-45 Top, middle and bottom temperature of EP at CCT	145
Fig.4-46 (a) and (b) TEM images of char from EP/3LDH-DBS@Ni(OH) ₂ ; (c) Mg mapping; (d) high angle angular dark field (HAADF) images with Ni and Al mapping	146
Fig.4-47 FTIR spectra at maximum volatile release rate of (a) EP, (b) EP/3LDH-DBS and (c) EP/3LDH-DBS@Ni(OH) ₂	147
Fig.4-48 Volatile evolution of (a) phenol compounds, (b) aromatic compounds and (c) double-bond compounds of EP, EP/3LDH-DBS and EP/3LDH-DBS@Ni(OH) ₂	147
Fig.4-49 (a) Ratio of aliphatic and aromatic compounds; (b) Ratio of integral value of aliphatic and aromatic compounds in TG-FTIR	148
Fig.4-50 (a) GC spectra of EP and EP/3LDH-DBS@Ni(OH) ₂ ; mass spectra at (b) 20.6dmin, (c) 25.5min and (d) 29.5min; (e) GC spectra of EP and EP/10LDH-DBS@Ni(OH) ₂ ; (f) mass spectra	

at 35min	149
Fig.4-51 (a) TG and (b) DTG curves of soot from EP, EP/3LDH-DBS and EP/3LDH-DBS@Ni(OH) ₂	150
Fig.4-52 (a) LOI value and UL-94 ratings with inset flaming time; (b), (c), (d) digital images at different combustion time of EP after first 10s flaming; (e), (f) digital images of EP/3LDH-DBS@Ni(OH) ₂ after first 10s flaming; (e), (f) digital images of EP/3LDH-DBS@Ni(OH) ₂ after second 10s flaming	152
Fig.4-53 (a) HRR, (b) THR, (c) ratio of COP and CO ₂ P and (d) weight profiles of EP and EP nanocomposites at 50kW/m ²	153
Fig.4-54 Storage modulus and tan delta of EP, EP/3LDH-DBS and EP/3LDH-DBS@Ni(OH) ₂ in dynamic mechanical analysis	154
Fig.5-1 (a) Raman Spectra and (b) XRD spectra of BN, BN@PDA and BN@PDA@Fe	159
Fig.5-2 (a) Full XPS spectra; (b) O1s spectra; (c) N1s spectra and (d) Fe2p spectra of BN@PDA@Fe	159
Fig.5-3 SEM images of (a) BN, (c) BN@PDA and (e) BN@PDA@Fe; TEM images with inset (SAED) of (b) BN, (d) BN@PDA and (f, l) BN@PDA@Fe; (g) high angle angular dark field (HAADF) with (h) B and N mapping and (i) O mapping of thermally exfoliated BN; (j) HAADF of BN@PDA; (k) Fe mapping of BN@PDA@Fe	160
Fig.5-4 XRD patterns of EP, EP/6BN and EP/6BN@PDA@Fe	161
Fig.5-5 Cyro-fractured surface of (a) EP, (b) EP/6BN with inset EDS spectra and B mapping of selected area, (c) EP/6BN@PDA with inset B mapping of selected area and (d) EP/6BN@PDA@Fe; schematic illustration of (e) EP/6BN and (f) EP/6BN@PDA@Fe	162
Fig.5-6 (a) Visualization assessment of t_{ig} , (b) HRR profile and (c) mass profile around ignition	163
Fig.5-7 Digital images at the ignition moment of (a) EP, (b) EP/6BN, (c) EP/6BN@PDA and (d) EP/6BN@PDA@Fe	165
Fig.5-8 (a) TG and (b) DTG curves of EP, EP/6BN, EP/6BN@PDA and EP/6BN@PDA@Fe at 10°C/min	166
Fig.5-9 3D diagram in TG-FTIR of (a) EP, (b) EP/6BN, (c) EP/6BN@PDA and (d) EP/6BN@PDA@Fe	167

Fig.5-10 FTIR spectra at maximum degradation rate of EP, EP/6BN, EP/6BN@PDA and EP/6BN@PDA@Fe.....	167
Fig.5-11 Integral curves of intensity versus time of (a) aromatic and (b) aliphatic compounds; (c) the integral amount ratio of aliphatic to aromatic compounds of EP, EP/6BN, EP/6BN@PDA and EP/6BN@PDA@Fe.....	168
Fig.5-12 Integral curves of intensity of (a) phenol, (b) double-bond and (c) carbonyl compounds of EP, EP/6BN, EP/6BN@PDA and EP/6BN@PDA@Fe in TG-FTIR test	169
Fig.5-13 (a) Temperature profile of EP, EP/6BN, EP/6BN@PDA and EP/6BN@PDA@Fe; comparison of (b) EP and EP/6BN, (c) EP/6BN and EP/6BN@PDA and (d) EP/6BN@PDA@Fe	170
Fig.5-14 Simulated surface temperature prior to ignition of EP, EP/6BN, EP/6BN@PDA and EP/6BN@PDA@Fe.....	172
Fig.5-15 Temperature curves at different downward thickness (0mm, 0.5mm, 1mm, 1.5mm, 2mm, 2.5mm, 3mm, 3.5mm, 4mm) of (a) EP, (b) EP/6BN, (c) EP/6BN@PDA and (d)EP/6BN@PDA@Fe	173
Fig.5-16 (a) SPR and (b) TSP curves of EP and EP nanocomposites	175
Fig.5-17 TG curves of EP and EP nanocomposites with the amplified part	176
Fig.5-18 Digital images of (a1) side and (a2) top views of EP, (b1) side and (b2) top views of EP/6BN, (c1) side and (c2) top views of EP/6BN@PDA and (d1) side and (d2) top views of EP/6BN@PDA@Fe.....	177
Fig.5-19 SEM images of interior surface with inset high-magnification images of (a) EP, (b) EP/6BN, (c) EP/6BN@PDA and (d) EP/6BN@PDA@Fe	178
Fig.5-20 (a) XRD pattern of the obtained char after CCT; (b) the amount ratio of aliphatic and aromatic compounds of EP, EP/6BN, EP/6BN@PDA and EP/6BN@PDA@Fe.....	178
Fig.5-21 Integral curves of intensity versus time of (a) aromatic compounds, (b) phenol compounds and (c) double-bond compounds	179
Fig.5-22 (a) TG and (b) DTG curves of soot of EP, EP/6BN, EP/6BN@PDA and EP/6BN@PDA@Fe.....	180
Fig.5-23 LOI value of EP and EP nanocomposites.....	181
Fig.5-24 Horizontal burning profiles of (a) EP, (b) EP/6BN, (c) EP/6BN@PDA and (d)	

EP/6BN@PDA@Fe.....	181
Fig.5-25 (a) HRR, (b) THR, (c) weight profile and (d) COP of EP and EP nanocomposites	183
Fig.5-26 (a) Weight of CO production and (b) ratio of COP and CO ₂ P of EP, EP/6BN, EP/6BN@PDA and EP/6BN@PDA@Fe.....	184
Fig.5-27 (a) Whole intensity and (b) integration of whole intensity of EP and EP composites....	184
Fig.6-1 In-situ detection of volatiles in (a) CCT with (b) FTIR spectroscopy.....	193

LIST OF TABLES

Table 1-1 t_{ig} value change of intumescent fire-retardant (IFR) systems.....	26
Table 1-2 Ignition time (t_{ig}) of nanofiller-based polymers	28
Table 1-3 Relationship between smoke suppression with different additives	35
Table 2-1 Materials classifications	45
Table 3-1 Parameters from N_2 adsorption and desorption of SBA-15 and SBA-15@ Co_3O_4	59
Table 3-2 Thermal degradation data of PS, PS/2SBA-15 and PS/2SBA-15@ Co_3O_4 at 10°C/min	76
Table 3-3 CCT data of PS, PS/2SBA-15 and PS/2SBA-15@ Co_3O_4 (25kW/m ²).....	83
Table 3-4 Tensile data of PS, PS/2SBA-15 and PS/2SBA-15@ Co_3O_4	86
Table 3-5 TG results of PLA and PLA composites at 10°C/min and 40°C/min at air atmosphere .	90
Table 3-6 CCT, LOI and UL-94 results of PLA and PLA composites	95
Table 4-1 CCT data of PS and PS composites.....	115
Table 4-2 Peak locations and their assignments	121
Table 4-3 CCT data of EP and EP composites (50kW/m ²).....	125
Table 4-4 CCT data of EP and EP nanocomposites (50kW/m ²)	137
Table 5-1 TG result of EP, EP/6BN, EP/6BN@PDA and EP/6BN@PDA@Fe	166
Table 5-2 Specific heat of capacity and thermal conductivity at ambient temperature	172
Table 5-3 Temperature (°C) at different downward thickness (0mm, 0.5mm, 1mm, 1.5mm, 2mm, 2.5mm, 3mm, 3.5mm, 4mm) at ignition moment of (a) EP, (b) EP/6BN, (c) EP/6BN@PDA and (d) EP/6BN@PDA@Fe.....	173
Table 5-4 Integration of chemical and physical factors on ignition time	174
Table 5-5 CCT data of EP and EP composites (35kW/m ²).....	175
Table 5-6 TG result of EP, EP/6BN, EP/6BN@PDA and EP/6BN@PDA@Fe	176

CHAPTER 1

Introduction

“Whoever is careless with the truth in small matters cannot be trusted in important matters”

-Albert Einstein

1.1 Background and motivation of the study

Fire hazards cause tremendous losses of fatality and property. According to the bulletin from World Fire Statistics Centre (WFSC), the property loss in 2014 is assessed as roughly 1% of GDP with death toll reaching several thousands in European Union. In **Fig. 1-1** (a) and (b), the average number of fires and average fire death number remain relatively high level with the dominant sources of cooking, cigarettes and short circuit [1]. Particularly, as plastic, rubber, fiber, adhesive and coating products enjoy wider applications in our daily life, fire hazards that occur in household make up the majority. Therefore, it is essential to eliminate fire hazard of polymeric materials from economic and social perspective. Smoke inhalation is perceived to account for 50%-80% fire death due to serious respiratory complications [2]. During fire scenario in **Scheme 1-1** (a), the crucial target is to be in pursuit of versatile approaches to suppress smoke production (peak smoke production rate and total smoke production). In parallel, in **Scheme 1-1** (b), the ignition time (t_{ig}) is a key parameter to determine the possibility of escape and/or rescue. In addition, heat release profile reflects fire intensity and fire spreading capacity, which is firmly correlated to burn injury. Hence, it is reasonable that heat release, smoke production and ignition profile constitutes the main parts in fire hazard.

What motivates the study is to delay the occurrence of ignition and to decrease the post-ignition fire hazard of polymeric materials toward lower smoke production, accompanied by higher fire performance index. The fire performance is defined as t_{ig} divided by peak heat release rate (pHRR) [3]. In consideration of the lack of adequate mechanisms to navigate the design of effective fire-retardant strategies for delaying ignition and suppressing post-ignition fire hazards, the need of mechanism investigation and establishment of proper relevant models are also the motivation.

Fig.1-1 (a) Average number of fires per 1000 inhabitants and (b) fire death number per 100,000 inhabitant [1]

Scheme 1-1 (a) Heat release profiles and (b) smoke production profile during combustion

1.2 State of the art

1.2.1 Combustion behavior

During combustion, the chemical and physical process coexisted with chemical reaction-induced re-balance of mass, heat and momentum. Chemical reaction in typical combustion occurred in the vapor phase and condensed phase (**Scheme 1-2** (a) and (b)) [4]. In the condensed phase, the thermal degradation via random scissoring, unzipping, elimination reaction and ringing reaction *etc.*, resulted in the release of volatiles, which fueled the flaming zone. In the flaming zone, the fuel underwent intensive thermal-oxidation degradation with the circular attack of $H\cdot$ and $OH\cdot$. The residue was further attacked by oxygen (O_2) especially at the late stage of combustion. In parallel, the physical behavior was mainly associated with the transportation of heat, O_2 and flammable volatiles. The dominant flaming behavior occurred in the vapor phase and at the surface of polymer sample with the heat balanced by flaming heat, cone heat, gasification heat (dissipation via gasification), thermal conductivity (dissipation via downward conductivity), thermal convection and black-body emission (**Scheme 1-2** (b)) [4]. The mass transportation proceeded via the penetration of O_2 from air to pyrolyzed zone (and flaming zone) and flammable

volatiles from pyrolyzed layer to flaming zone. In the process of pre-ignition (non-flaming), ignition, developed combustion and flameout, the parameters of ignition time, heat release rate and smoke production rate were empirically considered as the predominant controlling factors of fire hazards [4-6]. The following sections (**1.2.2**, **1.2.3** and **1.2.4**) were focused on the analysis of heat release rate, ignition time and smoke production respectively.

1.2.2 Fire retardancy

According to ISO/IEC 13943, fire retardancy is defined to delay ignition or reduce the rate of combustion [7]. In terms of delaying ignition, section **1.2.3** will give the detailed discussion. Herein, the concept of fire retardancy is focused on reduction of heat release. The combustion behavior of polymeric materials is evaluated in different scales including milligram-scale micro combustion calorimeter (MCC) and thermogravimetric analysis (TG), bench-scale limiting oxygen index (LOI), UL-94, cone calorimeter test (CCT), single burning item (SBI) and full-scale room and corner test and furniture calorimetry *etc.*[4]

Scheme 1-2 (a) Combustion process of polymers; (b) chemical and physical behaviors in combustion process [4]

Generally, the strategies to endow reduced heat release included additive fire retardants and intrinsic fire retardants (**Scheme 1-3**) with the mechanisms based on the termination of chemical and physical process during combustion (**Scheme 1-3** (a)). The additive fire retardants were classified into halogenated and nonhalogenated. The additive fire retardant underwent the historical stages of natural fillers, brominated, organophosphorus-containing and intumescent fire retardants and microscale (nanoscale) particles (and/or hybrids) [8]. Synergistic agents were categorized as additive fire retardants. Halogenated fire retardants exerted high-efficient functions

based on flame inhibition (radical entrapment) in vapor phase (**Scheme 1-3 (b)**) [9]. However, some halogenated fire retardant (*e.g.* decabromodiphenyl oxide) were restricted by various regulations (*e.g.* Stockholm Convention, WEEE, RoHS [10] and REACH [11]) due to bio-accumulation [12-14]. Organophosphorus-containing fire retardants possessed relatively high fire-retardant efficiency [15], but some of them tended to deteriorate thermal stability of matrix resin [16]. The fire-retardant mechanism varied remarkably according to the chemical valance of phosphorus atom between condensed-phase and vapor-phase mechanism (**Scheme 1-3 (c)**) [17-19]. Intumescent fire retardants imparted polymeric matrix with excellent fire retardancy on basis of formation of intumescent protective carbonaceous layer via the reaction between acid agent (*e.g.* ammonia polyphosphate (APP)), blowing agent (*e.g.* melamine cyanurate (MCA)) and charring agent (*e.g.* pentaerythritol (PER)) (**Scheme 1-3 (d) and (e)**) [20, 21]. However, the high loading was required to obtain satisfied fire retardancy, which resultantly deteriorated the mechanical property of matrix [22, 23].

Intrinsic fire retardants included fire-retardant polymers without fire-retardant elements (*e.g.* poly-p-phenylene benzobisoxazole (PBO)) [24, 25] and polymers with fire-retardant elements [26]. Some research groups conducted abundant works in preparing intrinsic phosphorous-containing fire retardant polymers (*e.g.* polyester, polyether and epoxy resin) [27-29]. The study of intrinsic fire-retardant polymeric materials suffered difficult in achieving the up-to-standard integral property due to the deterioration of polymer structure [30]. Microparticles (*e.g.* magnesium hydroxide, aluminum hydroxide) were capable to impart polymers with satisfactory fire retardancy predominantly via cooling effect in vapor phase (**Scheme 1-3 (h)**) and the condensed-phase protection [31].

Nanofillers played increasingly important roles in retarding ignition and post-ignition fire hazard especially in the form of polymer nanocomposites [32-35]. Camino's [32-35] and Wilkie's group [33] *etc.*, investigated the fire-retardant mechanism insightfully with preference on chemical factors. The generalized mechanism to account for improved fire retardancy was the formation of carbonaceous layer with strong gas and heat shielding effect (**Scheme 1-3 (f) and (g)**) [36]. In addition, the surface treatment was systematically studied by Alongi's and Grunlan's group as effective fire retardant technique for membrane and fiber [37-40]. The surface treatment was involved in the employment of various fire retardants (*e.g.* charged nanofillers and

polyelectrolytes) to spread on the composite via layer by layer and sol-gel technique with spraying and dipping method [38, 41-44]. It was also reported that the polymers covered with high volume fraction of intumescent fire retardant or mono-component aerosol and hydrogel were used as barrier layer to protect the underlying composites [45, 46]. The underpinning mechanism was the intumescent or high-quality barrier effect to shield the fire.

Currently, to pursue high efficiency and environmental benignness is the target of fire retardancy. Based on the target, novel fire-retardant strategy and mechanism were put forward. The state-of-art progress was described below with focuses on intumescent fire retardants, phosphorous-containing fire retardants and nanofillers.

Scheme 1-3 (a) Chemical reactions during combustion (b) vapor-phase fire inhibition of halogenated compound MX; (c) vapor-phase fire inhibition of phosphorus-containing compound P_x ; (d) digital image [20] and (e) SEM image of intumescent fire-retardant char [21]; (f) digital image [36] (Reproduced with permission from The Royal Society of Chemistry) and (g) TEM image of nanofiller-based fire-retardant char [47]; (h) cooling effect via moisture-releasing behavior of $Mg(OH)_2$ -based composites [31]

Intumescent fire retardant

Intumescent fire retardants passed the historical stage of unconsciously-designed formulations

(protective coating) toward systematically-investigated intumescent behavior, aiming to improve the intumescent fire-retardant efficiency [8]. The study of intumescent behavior was focused on the chemical reactions [48-54] (*e.g.* esterification reaction, dehydration reaction and ammonia-removal reaction) and physical reactions [55-57] (*e.g.* swelling behavior, hole-formation structure and temperature profile) during combustion, accompanied by the stationary investigation of char structure [58] (chemical composition and morphology) after combustion. In the typical chemical profile, APP underwent pyrolysis with the generation of NH_3 (entering flammable zone) and polyphosphoric acid, which reacted with charring agents [48-50, 59-62]. The further heating forced the deep dehydration and esterification toward protective carbonaceous char (detected by differential scanning calorimeter (DSC) [23], thermogravimetric analysis (TG), solid nuclear magnetic resonance (SNMR) [51, 63, 64], variable-temperature Fourier transformation infrared spectroscopy (vt-FTIR) [65, 66], thermogravimetric analysis coupled with Fourier transformation infrared spectroscopy (TG-FTIR) [67-69] and X-ray photoelectron energy spectroscopy (XPS) [52, 54]). In the physical profile, polymer composite melted during heating, followed by increased melt viscosity due to esterification (**Fig.1-3 (a)**) [70]. NH_3 and other flammable gases interplayed with polymer melt to yield the cellular structure, characterized by rheometer [71] and X-ray computed tomography (XCT) [58, 72]. Based on the studies, a complete set of methodology were established for seeking for high-efficient intumescent formulation.

The pursuit of high-efficient and water-resistant intumescent fire retardant became the hotpoint. Wang' group prepared modified APP with pendant groups of high charring capacity and systematically investigated the fire-retardant behavior (**Fig.1-2 (a)**) [73-75]. Compared with neat APP, the modified APP imparted polypropylene (PP) with dramatically reduced peak heat release rate (pHRR) (**Fig.1-2 (b)**) based on the promoted esterification (**Fig.1-2 (c)**). Merely 22wt% mono-component PA-APP endowed PP with UL-94 V-0 rating. In parallel, Juan's group used the highly synergistic agent of polyoxometalate based ionic liquid (PIL) to tremendously assist traditional intumescent fire retardant (IFR, APP/PER=3:1) in PP. Merely 15wt% (14.5% IFR+0.5% PIL) loading enabled the achievement of UL-94 V-0 (**Fig.1-3 (b)**) [76].

APP suffered the moisture-absorption issue in the practical application, which deteriorated the fire retardancy and hand-feeling of composites. Researchers put forward the microencapsulation of microscale APP to avoid the contact with moisture [77, 78]. The microencapsulation on APP

micro-spheres inhibited the moisture-adsorption effectively, accompanied by the enhancement of fire-retardant efficiency [79]. Silica [80], melamine formaldehyde [81] and β -cyclodextrin [82] (Fig.1-3 (c)) acted as bricks to construct the micro-shell.

Fig.1-2 (a) Structure of APP and modified APP; (b) heat release rate curves of PP and PP composites; (c) proposed chemical reaction mechanism [73-75]

Fig.1-3 (a) Viscosity versus temperature in terms of APP/PER filled polyurethane (PU) [70]; (b) polyoxometalate based ionic liquid (PIL) [76]; (c) β -cyclodextrin-based microencapsulation [82]; (d) combustion model of PP/APP/PER [56]; (e) numerical and experimental value of surface temperature [56]

Furthermore, in the design of intumescent fire-retardant system, the virtual test (numerical simulation) of fire behavior offered viable and convenient approaches toward optimized formulations [56]. Based on the pre-test temperate-dependent thermal conductivity (k), specific

heat of capacity (c) and thermal degradation behavior, one dimensional (1D) unsteady dynamic model was established with the assumption that the frontier expansion behavior was the phase change (**Fig.1-3** (d)). The calculated surface temperature swelling rate and mass loss rate (MLR) of intumescent system were in good match with experiments (**Fig.1-3** (e)), which promoted the understanding of the intumescent process [56].

Phosphorus-containing fire retardant

Phosphorous-containing fire retardants enjoyed similar attentions to halogenated fire retardant with remarkable varieties and high efficiency. Phosphorous-containing fire retardants generally possessed organic and inorganic types. Organic phosphorous-containing type included organic phosphate, phosphonate, phosphinate and phosphine (**Scheme 1-4** (a)). Actually, P-O bond in phosphorous-containing compounds were selectively substituted by P-N bond, which gave rise to phosphamide or phosphoramidate with variable fire-retardant efficiency [83, 84]. Industrially used organic phosphorous-containing compounds were exemplified by bisphenol A bis(diphenyl phosphate) (BDP), resorcinol bis(diphenyl phosphate) (RDP), triphenyl phosphate (TPP) and 9,10-dihydro-9-oxa-10-phosphaphenanthrene-10-oxide (DOPO) [8]. Recently, some research groups systematically investigated the effect of different phosphorus oxidation states and different substituted phosphate and phosphoramidate on fire retardancy of polymers (*e.g.* rigid polyurethane and epoxy resin) [18, 19]. Results demonstrated that the fire retardants with the lower valance of phosphorus was inclined to flame inhibition and quenching in vapor phase rather than in condensed phase [19]. Gaan's group presented that the phosphoramidates with different substitutes on nitrogen atom generated different fire retardancy [83]. The hydroxyl ethyl substitution possessed better fire retardancy toward the formation of acidic intermediates compared to ethyl substitution [83]. They profoundly studied the quenching behavior of phosphorous-containing radicals by photoion photoelectron coincidence spectroscopy in combination with vacuum ultraviolet synchrotron radiation. Results showed that $P\equiv N$ intermediate was the dominant component for quenching effect in terms of the structure of $O=P(OCH_3)_2NH_2$ (**Scheme 1-4** (b)) [84]. Apart from it, Scharrel's group explored the effect of difference matrix on fire-retardant behavior [15]. The identical polymer matrix with different structure changed the fire-retardant mechanism via the analysis of two-step model with the great dependence of fire retardant's

evaporation, hydrolysis and degradation temperature on polymer matrix (**Scheme 1-5** (a) and (b)) [15]. Resultantly, the vapor-phase fire inhibition, condensed-phase charring and charring protective effect were re-arranged.

Scheme 1-4 (a) Different organic phosphorous-containing compounds; (b) degradation route of $O=P(OCH_3)_2NH_2$ [84]

Scheme 1-5 Fire-retardant mechanism of different phosphorous-containing fire retardants in (a) DGEBA/DMC and (b) RTM6 [15]

The inorganic phosphorous-containing compounds were concentrated on aluminum and magnesium phosphinate with seeking for prominent synergistic agents (*e.g.* MCA) and synergistic mechanism in glass-fiber reinforced engineering plastics [63, 85-87]. Wang's group profoundly investigated the different fire-retardant behavior of different alkyl-substituted inorganic phosphorous-containing compounds [88]. The different alkyl-substituted aluminum phosphinate (AlPi) presented different fire-retardant efficiency with longer alkyl substitutes higher fire inhibition [88]. Structurally tailored AlPi held great industrial prospects due to the balanced integral property (*e.g.* mechanical property, thermal resistance, thermal stability and physical peculiarity *etc.*) in matrix.

Intrinsic fire-retardant polymers with thermally crosslinking structure

In order to solve the dripping issue and enhance the fire retardancy, the special reactive groups

were covalently connected to the backbone and pendent chains of polymers, which were capable to generate the crosslinking structure at the particular temperature (above processing temperature) [89]. Wang' group carried out the pioneering work in the field [89]. The employed reactions in the thermally crosslinking system included azobenzene-azobenzene crosslinking at roughly 370°C [90], azobenzene-phenylethynyl crosslinking at about 400°C and phenylethynyl-phenylethynyl crosslinking at 350°C (**Scheme 1-6**) [91]. The enhanced fire retardancy with suppressed dripping was originated from the improved charring reaction from thermally crosslinking effect. The thermally crosslinking reaction resulted in the enhanced melt viscosity at combustion temperature, which inhibited the dripping behavior [89]. In parallel, the char from thermally crosslinking polyaromatic reaction acted as the excellent barrier layer against heat and volatiles for enhanced fire retardancy. Compared with the traditional approach of additive-type fire retardants, the intrinsic and thermally crosslinking method possessed the advantage of no fire-retardant elements, which furthers sustained or improved the other properties. [89]

Scheme 1-6 Azobenzene-azobenzene, azobenzene-phenylethynyl and phenylethynyl-phenylethynyl crosslinking reaction [91]

Nanofillers-based fire retardant

Particles confined in nanoscale of less than 100 nm illuminated particular features relative to microparticles due to the increased specific area and surface tension, exposure of atoms and crystal faces and distorted electron distribution. The special behaviors in dispersion, thermal, photo and electricity behavior were generated [92]. In the field of polymer nanocomposites, nanoparticles (mainly inorganic nanoparticles) included different geometries with

zero-dimensional (0D) nanosphere, one-dimensional (1D) nano-fiber, nano-rod and nanotube and two-dimensional (2D) nanosheet (**Fig.1-4 (a)**). The physical factors to influence the fire retardancy were systematically investigated by Kashiwagi's research group [93-96]. In order to promote the understanding the effect of nanofillers on fire behavior, the charring process and char (residue) structure were stressed [36, 97]. The charring process and char (residue) structure of pure polymers were affected by melt process and thermal degradation (melt intensity and viscosity) [94]. In terms of nanoparticles-filled thermoplastic polymer composites (*e.g.* PP, PMMA and PS), the melt viscosity was increased according to Equation (1.1) [98, 99], (1.2) [100-102] and (1.3) [103].

$$\eta_r = \frac{\eta}{\eta_m} = 1 + [\eta]\phi + O(\phi^2) \quad (1.1)$$

$$\eta_r = \frac{\eta}{\eta_m} = 1 + [\eta]\phi + k_I\phi^2 + O(\phi^2) \quad (1.2)$$

$$\eta_r = \left(1 - \frac{\phi}{\phi_m}\right)^{-[\eta]\phi_m} \quad (1.3)$$

Where, η_r was the steady viscosity ratio of particle-filled suspension and neat polymer melt η . $[\eta]$, ϕ , ϕ_m and k_I were respectively intrinsic viscosity, volume percentage of filler, maximum volume percentage of filler (dependent on the property of fillers and polymer melt and the type of flow field) and interaction parameter of particle aggregates. Equation (1.1) (Einstein Equation) [98, 99], Equation (1.2) (Batchelor Equation) [100-102] and Equation (1.3) (K-D Equation) [103] were respectively associated with dilute suspension (<5% in volume percentage), medium concentrated suspension (<20% in volume percentage) and high volume percentage suspension (< ϕ_m).

Melt intensity also played an important role in char structure [94], which was represented by dynamic storage modulus (G'). The melt suspension possessed G' with contributions from polymer melt and the interface between fillers and polymer melt [104]. The stronger interfacial interaction resulted in the higher melt intensity, which weakened the melt fracture (**Fig.1-4 (b)**). The volatiles from thermal degradation moved upward in melt suspension, which resulted in the extensional and shear flow field [105]. The viscosity of polymer melt was reduced due to decreased molecular weight ($\lg\eta_0 \propto \lg M_w$, η_0 and M_w represented zero-shear viscosity and weight-average molecular weight separately) and shear thinning. Resultantly in terms of thermoplastic polymers, the dynamic structure was formed with dehydrated nanofillers reinforcing

porous suspension. The porous structure was difficult to remain in the solid char due to the low suspension viscosity [94]. The dynamic structure was determined by thermal degradation of polymer composites, the peculiarity of nanofillers and external condition (sample dimension and heat flux). In terms of thermosetting polymers (*e.g.* EP), thermal degradation resulted in the decrease of molecular weight, which drove the transition of glassy state to viscos state. At the late stage of thermal degradation, the crosslinking reaction (*i.e.* charring reaction) occurred dramatically with the melt viscosity increasing significantly [89]. Highly crosslinking thermosetting polymers lost the liquid period during combustion. Thermoplastic polymers underwent the similar transition of solid-liquid-solid [71, 106-108]. It was harder to form continuous char structure for thermoplastic polymers relative to thermosetting polymers due to the lower melt viscosity and melt intensity. Actually, the in-situ dynamic char structure rather than the after-flame char structure impacted fire behaviors [108]. Higher dynamic viscoelasticity induced by fillers favored the formation of more continuous char structure [94].

Fig.1-4 (a) Nanofillers with different morphologies; (b) bubble and charring behavior during combustion of nanofiller-based composites

2D lamellar nanoparticles generally overperformed 1D and 0D nanoparticles due to the stronger shielding effect of the resulting char during combustion [109]. 2D nanosheets with higher lateral size and 1D nanotubes with higher length diameter ratio (L/D) possessed relatively higher fire retardancy due to less aggregation and more tendency to connect the microstructural char (Fig.1-5 (c) and (d)) [110]. Herein, the less aggregation and more tendency to form the percolation structure gave rise to higher viscosity and storage modulus (more interface contribution), which favored the formation of more continuous char [107, 108]. Furthermore, the different dispersion

state of 1D nanotube in polymer matrix and increased viscoelasticity of polymer nanocomposite played a critical role in fire behavior [94]. The better dispersion (**Fig.1-5** (a) and (b)) and stronger viscoelasticity of polymer nanocomposites resulted in better fire retardancy due to the higher-quality char with less fracture and holes (**Fig.1-5** (e) and (f)) [93, 94].

Fig.1-5 Char after gasification test at 50kW/m² of (a) PMMA/0.5wt% SWNT at good dispersion state and (b) PMMA/0.5wt% SWNT at poor dispersion state; Char after gasification test at 50kW/m² of PS/2wt% MWNT at (c) L/D=150 and (d) L/D=90 [110]; (e) mass loss rate of PMMA/0.5wt% SWNT at good and poor dispersion at 50kW/m² [93]; (f) comparison of fire-retardant efficiency between PS/Cloisite15A and PS/MWNT with different viscoelasticity [93, 94, 109]

Aiming to enhance fire-retardant efficiency of nanofiller-based polymer nanocomposites (or microcomposites), the functionalization of nanofiller was employed with concentration on surface organic and inorganic modification and organic intercalation [111-113]. In detail, organic modification was generally associated with the employment of surface grafting of compatible polymer chains to improve the dispersion of nanofillers [114]. The incorporation of fire-retardant segments into the grafting compatible polymer chains further improved fire-retardant efficiency based on the combination of improved nano-dispersion and fire-retardant behavior (**Fig.1-6** (a)) [115]. In parallel, the organic molecules with/without fire-retardant elements were intercalated in

the gallery of lamellar nano-structure, aiming to promoting the exfoliation of nanosheets and incident fire retardancy (**Fig.1-6 (b)**) [113, 116, 117]. Alternatively, the anti-UV functional moieties were also incorporated into lamellar gallery to incite the multifunction of polymer nanocomposites (**Fig.1-6 (b)**) [113, 118]. Generally, the naturally occurred nanoclays (*e.g.* montmorillonite (MMT) and hydrotalcite) acted as the brilliant candidates for intercalation of various organic molecules, which further imparted the composites with required properties [119].

Fig.1-6 (a) Surface grafting of polymer block with phosphorous-containing moiety [115]; (b) multifunctional intercalation of layered double hydroxide (LDH) [113]

The inorganic modification (decoration) on surface of nanofillers or the element doping on the molecular structure of nanofillers opened a perspective window to enhance the targeted behavior [36, 120]. Hu's and Wang's group performed pioneering works [36, 121]. In terms of inorganic modification, the in-situ growth approach and electrostatic assembly were generally utilized with the decoration of zero-valent metal [122], metal oxide [123], metal hydroxide [124], insoluble metal salt [125], layered double hybrid (LDH) [126] and metal organic framework (MOF) [127] *etc.* The substrates such as boron nitride (BN) nanosheets [128] and nanotubes [129], molybdenum disulfide (MoS_2) [130], graphene [131] and carbon nanotube (CNT) [132] were requested with higher L/D with aim to supplying adequate active sites for homogeneous and high-loading decoration of hybrids. The diversified in-situ grown inorganic decorations (*e.g.* SiO_2 [133], ZrO_2 [134], MnO_2 [135], Co_3O_4 [121], ZnS [136], Cu_2O [137], MoO_3 [138], FeOOH [139], $\text{Co}(\text{OH})_2$ [121] and $\text{Ni}(\text{OH})_2$ [134]) on graphene nanosheets (**Fig.1-7 (a)**) were investigated systematically with respect to fire retardancy of epoxy resin (EP), polymethylmethacrylate (PMMA), polylactide (PLA) and polystyrene (PS) *etc.* Results showed that the fire retardancy was enhanced with the

mechanism dominantly in condensed phase via the formation of higher-quality char structure [36]. Apart from it, the electrostatic assembly provided a viable approach to construct structure with abundant morphologies [140] (**Fig.1-7** (b)).

However, the deep study of the fire-retardant mechanism was absent, which resulted in the unconscious-designed structure toward high-efficient fire retardancy. The basic fire-retardant mechanism was synergy between different components. Actually, the investigation of the relationship between nanostructure and fire retardancy was seriously lacking at the molecular level, which made the study constantly at the trial stage. Based on the above evaluation, the work in the thesis will be dedicated to design the suitable nanostructure and insightfully study the relationship of structure and property.

Fig.1-7 (a) In-situ grown MoO_3 and Cu_2O on graphene nanosheets [138] and (b) electrostatic assembly of LDH and graphene oxide nanosheets on hollow SiO_2 sphere [140]

Additionally, organic nanofillers and microfillers exploited a novel route to endow fire retardancy to polymers. The representative compounds were the covalent organic frameworks (COF) (**Fig.1-8** (a)) [141], metal organic framework (MOF) (**Fig.1-8** (b), (c), (d) and (e)) [142], polyphosphazene (**Fig.1-8** (f)) [143] and their derivatives. The hierarchical modification with respect to the organic nanofillers and microfillers was employed in order to enhance fire retardancy [141-143]. Fe-MOF and Co-MOF were effective in slightly decreasing fire intensity of PS with the generation of the protective char [142]. The similar case did exist in COF nanosheets-filled TPU composites [141]. In addition, Polyphosphazene nanotubes encapsulated by mesoporous silica supporting bimetallic phosphide exhibited slightly lower peak heat release rate of thermoplastic polyurethane (TPU) than the references [143]. Therefore, the fire-retardancy with organic nanofillers (and/or microfillers) was promising but not satisfactory.

Fig.1-8 (a) Schematic illustration of COF [141]; (b) and (c) SEM and TEM images of Fe-MOF [142]; (d) and (e) SEM and TEM images of Co-MOF [142]; (f) schematic illustration of hierarchical modification of polyphosphazene nanotube [143]; (g) blowing-out mechanism of EP/DOPO-POSS [144]

Besides, various polyhedral oligomeric silsesquioxane (POSS) molecules, once incorporated into polymer matrix, tended to phase separate and resulted in the formation of POSS nanophase-filled polymer nanocomposites [145-147]. Enormous investigations illustrated that the incorporation of POSS or its derivatives notably increased the fire retardancy of PP [148, 149], PU [150], PLA [151, 152] and EP [153, 154] *etc.*, with the preferential result in reduced pHRR. The generalized explanation of mechanism was due to the formation of silicon-rich carbonaceous layers to shield the underlying matrix from heat and flammable gases. The silicon-containing compounds with the higher surface tension were apt to migrate to the surface easily, which promoted the charring formation [155]. The compositional variation of POSS revealed the changed fire retardancy based on the different volatilization behavior, different charring capacity and different dispersion in matrix [148]. Compared with alkyl-POSS, octaphenyl-POSS showed limited volatilization at air and N₂ atmosphere, which left more POSS in the polymer matrix. Compared with other metals, Al and Zn-containing POSS possessed higher charring capacity towards PP, which resulted in better fire retardancy [148]. Octaisobutyl-POSS possessed more

homogeneous dispersion in PP than octamethyl-POSS, which also gave rise to better fire retardancy. Meanwhile, the silicon-phosphorous synergy in modified POSS was also detected [149]. Merely 2.5wt% DOPO-POSS imparted EP (cured with DDS) with V-1 ratings due to the special blowing-out mechanism (**Fig.1-8 (h)**) [144].

1.2.3 Delaying ignition

The ignition behavior was the first step of fire hazard, which determined its importance in reducing fire risk. Significantly delayed ignition time (t_{ig}) was expected as the adequate rescuing time was obligated during fire hazard. The study of ignition behavior dated back to 1960's with focus on developing numerical simulation of ignition based on the progressively insightful understanding of ignition mechanism [156-160]. Ignition behavior was a complicated process with the enormous chemical and concurrent physical reactions. Ignition behavior occurred with or without external heat resource (pilot flaming or sparking) when the concentration of flammable gases from decomposition of polymers reached the critical value [161].

The measurement of ignition behavior was involved in t_{ig} , ignition temperature (T_{ig}), and thermal oxidation-based gasification. The measurement of ignition behavior was not confined in fixed apparatus and ignition ways. Basically, the commonly used ignition test was firepoint apparatus (**Fig.1-9 (a)**) [162], self-made apparatus (**Fig.1-9 (b)**) [163] and cone calorimeter. The t_{ig} was obtained generally via visual observation of flaming occurrence toward developed flame. In cone calorimeter test (CCT), t_{ig} was also obtained through analysis of heat and mass profile, both of which were sensitive to ignition [164]. The critical mass loss rate and heat release rate were 1-6 g·s⁻¹·m⁻² and 20-100kW/m² respectively in consideration of the presence of flash phenomenon prior to ignition (**Fig.1-9 (c)**) [164]. The temperature measurement was performed on sample surface with the thermocouple attached. In terms of polymer melt, the attachment of thermocouple was relatively difficult with remarkable tendency to test the temperature of underlying melt or top air [165]. The infrared temperature detector was evidenced to be not accurate as the infrared beam was apt to test the temperature of dense smoke and/or volatiles. In addition, the gasification behavior was measured generally on the thermogravimetric analyzer with the ignorance of in-depth degradation behavior. More precise measurement required the self-made facility with the focus on the high-accuracy electrical balance (**Fig.1-9 (d)**) [96, 166].

Fig.1-9 (a) Firepoint apparatus with C, F and G sample, radiation and load cell [162]; (b) self-made apparatus for ignition test [163]; (c) temperature prior to ignition with the flash period [162] and (d) gasification apparatus [96]

Ignition process

Different from the combustion process with the category of charring and non-charring type, the study of ignition propelled the classification of thermoplastic and thermosetting type based on the different pre-ignition behavior [156-158, 161, 167]. Thermoplastic polymers (*e.g.* PS, PP, PE, PLA and PS) underwent the heating, melt, thermal-oxidation degradation, gasification and ignition [160, 162, 168-170]. The heat absorbed on the top surface was conducted toward the bottom surface with the gradient temperature distribution along the transportation direct [171]. When the surface temperature reached the initial thermal-oxidation temperature, the polymer underwent the decomposition with volatile bubbles generated (**Fig.1-10** (a) (b) and (c)). Gradually, the bubbles moved from the bottom position to top position with bubble size turning bigger in viscoelastic polymer melt [4]. As the volatiles concentration reached the critical value, the ignition behavior occurred in combination with the adequate heat (evaluated by T_{ig}) and oxygen concentration.

Over past decades, some research groups took into account all the influencing factors [160, 163, 165, 168, 170, 172, 173]. All the influencing factors functioned in the simulation via influencing heat profile. The basic schematic illustration of the heat profile was showed in **Scheme 1-7**. The heat radiation (*e.g.* CO₂ laser or electrical heated coils) arrived at the top surface and penetrated

into the polymer. The heat proceeded with the reflection loss and in-depth adsorption in terms of transparent slabs. The reflected radiation usually made up 10% of the total radiation [174]. In-depth adsorption depended on the spectroscopic interaction between polymer molecules and infrared light [175]. Besides, the thermal conductivity, convection radiation and black-body radiation were the additional heat-loss ways [176]. Subsequently, the gradient temperature distribution emerged dependent on thermal conductivity (k) and specific heat of capacity (c) [160].

Scheme 1-7 Heat profile in the horizontal location prior to ignition [96, 163, 168, 172, 174, 176]

As the temperature was above initial thermal-oxidation degradation temperature, the degradation occurred with the degradation heat generated [169, 174]. More importantly, the degraded oligomers with lower molecular weight possessed lower gasification temperature [174]. The gasification process carried away enormous heat, which resulted in the relatively balanced temperature in combination of thermal conductivity, thermal convection and black-body radiation (**Fig.1-11** (a)) [161, 174]. Meanwhile, the gasification resulted in enormous volatiles that stayed above the sample surface and blocked the external radiation. Consequently, the radiation attenuation emerged [163]. It was reported by Kashiwagi's group that the thermal-oxidation degradation played significantly more important roles compared with the melt viscosity, which was correlated to the movement of the bubbles [95]. In-depth adsorption and gas adsorption played indispensable roles in simulating the ignition behavior and understating the ignition process [175]. Herein the mass profile of the experimental sample was concentrated on the gasification process.

The heat profile of thermosetting polymers resembled the thermoplastic polymer without the generation of bubbles (**Fig.1-10** (d)). The ignition simulation of thermosetting was referred to the

solid fuel. The parameters k and c were dependent on temperature, which made the simulation more complicated. The simulated temperature illustrated the trend in **Fig.1-11** (b).

Fig.1-10 Images of polymer melt at ignition in CCT of (a) PP, (b) PS, (c) PLA and (d) epoxy resin (EP)

Fig.1-11 Temperature curves of (a) thermoplastic and (b) thermosetting polymers (t_{ig1} and t_{ig2} represented the ignition time of sample 1 and 2)

Ignition simulation

The numerical simulation of fire behavior of polymers was concentrated on ignition and the mass loss rate [176-179]. The simulation of ignition behavior was based on the fact that the ignition occurred when temperature reached T_{ig} . Generally, one-dimensional (1D) conductive equation was used with the variations of distance and time (Equation (1-4)) [180]. Herein, ρ was sample density.

$$\rho c \frac{\partial T}{\partial t} = \frac{\partial}{\partial x} \left(k \frac{\partial T}{\partial x} \right) \quad (1-4)$$

In contrast, the simulation of combustion intensity was based on the mass loss rate, which was further relied on the thermal degradation kinetics of the polymers [166, 177]. The soaring of mass loss rate was employed to acquire t_{ig} , which was relatively inaccurate compared with the first method (evaluated by T_{ig}) [177-179]. In order to perform the more accurate simulation using T_{ig} ,

the heat attenuation from gas adsorption and the in-depth adsorption (in terms of the transparent polymers) were taken into account [163]. In the simulation, an important issue was to distinguish the thermally thick and thermally thin polymer slabs. In fact, the rear temperature revealed the high-rate increasing tendency to homogenize the temperature distribution along the heat transportation direction as for thermally thin samples. The constant temperature (ambient temperature) remained at the rear surface for thermally thick samples. In between, the generally increasing tendency at the rear surface possessed the combination of thermally thin and thermally thick dual-property. The critical thickness was determined by enormous parameters [165].

$$l_c \leq \frac{k}{10(h + \varepsilon\sigma(T_{ig} + T_0)(T_{ig}^2 + T_0^2))} \times \frac{Q_{cri}}{Q_{ext} - Q_{cri}} \quad (1-5)$$

$$Q_{cri} = \varepsilon\sigma(T_{ig}^4 - T_0^4) + h(T_{ig} - T_0) \quad (1-6)$$

Here k , l_c , h , ε , σ , Q_{cri} , Q_{ext} and T_0 were thermal conductivity, critical thickness, convective coefficient, emissivity, Boltzmann radiation constant, critical radiation, external radiation and ambient temperature respectively [165]. Notably, the higher thermal conductivity and external radiation resulted in the higher critical thickness. Commonly-used thickness with 3-4mm in CCT belonged to the combined state of thermally thin and thick at heat flux of 25kW/m², 35kW/m² and 50kW/m². The prediction of the relationship between t_{ig} and Q_{ext} was located between the linear correlation between t_{ig}^{-1} and Q_{ext} and the linear correlation between $t_{ig}^{-1/2}$ and Q_{ext} . The usually-used sample with thickness of 25mm was assigned to thermally thick sample. According to the established models, the thermally thin and thick samples possessed t_{ig} in Equation (1-7) and (1-8) separately [165].

$$t_{ig} = \frac{\rho cl(T_{ig} - T_0)}{Q_{cri}} \ln\left(\frac{Q_{ext}}{Q_{ext} - Q_{cri}}\right) \quad (1-7)$$

$$t_{ig}^{1/2} = \frac{\sqrt{\frac{\pi}{4}} k \rho c (T_{ig} - T_0)}{Q_{cri}} \ln\left(\frac{Q_{ext}}{Q_{ext} - Q_{cri}}\right) \quad (1-8)$$

Furthermore, Q_{cri} was much lower than that of Q_{ext} , both equations were simplified to (1-9) and (1-10) respectively.

$$t_{ig} = \frac{\rho cl(T_{ig} - T_0)}{Q_{ext} - Q_{cri}} \quad (1-9)$$

$$t_{ig}^{1/2} = \frac{\sqrt{\frac{\pi}{4}} k \rho c (T_{ig} - T_0)}{Q_{ext} - Q_{cri}} \quad (1-10)$$

From Equation (1-9), t_{ig} was proportional to sample thickness (l), density (ρ) and specific heat of capacity (c). Higher external radiation resulted in the lower t_{ig} . From Equation (1-10), t_{ig} was proportional to thermal inertia ($k\rho c$). As for the samples with 3-4mm thickness, which was classified as the combined property, the t_{ig} value possessed the limited correlation to thermal conductivity k . It was noted that the generally-used samples with thickness of 3-4mm behaved more like the thermally-thick sample [165, 181]. Higher external radiation resulted in the lower t_{ig} . These two equations were regarded as the guideline to approximately predict the ignition time. Moreover, Equation (1-10) demonstrated a strong precision based on the linear correlation of $t_{ig}^{-1/2}$ and Q_{ext} . The critical heat flux value was also calculated via the extrapolation to $t_{ig}^{-1/2}=0$ [174].

However, the above equations were obtained via the simple 1D conductive equation, which merely considered the physical aspect and ignored the chemical aspect. In the fire-retardant polymers, the fire retardants actually gave rise to the alteration of physical and chemical aspects. In different fire-retardant polymers, the physical and chemical aspects were differently considered.

Ignition behavior of fire-retardant polymers

a. Halogenated fire-retardant polymers

Considering that the thermal-oxidation degradation temperature of halogenated fire retardants was usually lower than the ignition temperature, the halogenated free radicals were accordingly generated and distributed around the flaming zone [8]. These halogenated free radicals exerted important roles in inhibiting the occurrence of ignition [8]. Wang's group reported that the addition of antimony trioxide (Sb_2O_3) gave rise to the delaying of t_{ig} of polymers such as poly(vinyl chloride) (PVC) [182]. In contrast, in consideration of the alteration of physical properties (*e.g.* ρ and c) and deteriorated thermal-oxidation degradation of polymer backbone after the incorporation of halogenated fire retardants, the t_{ig} value was actually unpredictable with the positive effect from radicals and negative effect from altered physical properties and deteriorated thermal-oxidation stability [183]. However, t_{ig} value of polymeric materials with addition of halogenated fire retardants was normally delayed with the predominant inhibition of free radicals [184, 185].

b. Microfillers-based polymers

Microscale magnesium hydroxide ($\text{Mg}(\text{OH})_2$) and aluminum trihydroxide ($\text{Al}(\text{OH})_3$) were industrialized fire retardants in consideration of strong fire-safe liability, cost-effectiveness and extensive availability [186, 187]. As the fire retardant, the mechanism was mainly involved in the moisture-releasing effect to cool down the flaming zone and the formation of the protective carbonaceous layers. Similarly, the moisture at the flaming zone acted as the excellent alternatives to inhibiting ignition via reducing the combustion efficiency (χ) [5, 6]. The dehydration reaction occurred at 350°C and 300°C in terms of $\text{Mg}(\text{OH})_2$ and $\text{Al}(\text{OH})_3$, which were generally lower than or comparable to ignition temperature [188]. Additionally, the lower dehydration temperature illuminated that more water was released into the flaming zone as for $\text{Mg}(\text{OH})_2$ -filled polymers, which caused the higher t_{ig} compared to $\text{Al}(\text{OH})_3$ -based polymers. Meanwhile, the incorporation of $\text{Mg}(\text{OH})_2$ and $\text{Al}(\text{OH})_3$ increased the thermal conductivity and density of polymer matrix due to the higher conductivity of fillers. In combination with the chemical aspect from cooling effect and physical aspect from increased k and ρ , the t_{ig} of polymer was usually delayed [189-192]. Amongst, $\text{Mg}(\text{OH})_2$ showed the closer dehydration temperature to the T_{ig} value, which imparted less delayed t_{ig} . The microfillers including the calcium carbonate (CaCO_3), mica, wollastonite and boehmite *etc.*, presented the similar trend of the ignition behavior of polymers [193, 194]

Additionally, the commercialized Al_2O_3 possessed the ρ , c and k of $3.96 \text{ g}\cdot\text{mL}^{-1}$, $0.75 \text{ J}\cdot\text{g}^{-1}\cdot\text{K}^{-1}$ and $29.36 \text{ W}\cdot\text{m}^{-1}\cdot\text{K}^{-1}$ respectively [195-197], which showed significant difference with the matrix resin. It was reported [195-197] that the addition of Al_2O_3 microspheres remarkably delayed the ignition behavior of PMMA. The basic mechanism was due to the improved thermal-oxidation stability, which offered less flammable gases and the significantly increased thermal conductivity, which made the heating rate of the top surface more slowly even though the specific heat of capacity was slightly decreased.

c. Phosphorous-containing fire retardant-based polymers

Polymers composites with phosphorous-containing fire retardants (organic and inorganic phosphorous-containing fire retardants) showed magnificent complexity in studying the ignition behavior due to the multiple influencing factors [15, 198]. In terms of the physical property, the addition of phosphorous-containing fire retardant was considered to have neglectable influence on

the ρ , c and k especially at low loadings [8]. The important change happened in the thermal-oxidation stability of polymer matrix and the generation of $\text{PO}\cdot$ radicals. Normally, the phosphorous-containing bond (P-O, P-N and P-C *etc.*) illustrated relatively lower bond energy compared with C-C bond, which resulted in the earlier thermal-oxidation degradation than polymer matrix prior to ignition [199]. The resultant degraded products further promoted the thermal-oxidation degradation of polymer matrix. More flammable fuels accordingly were released into the flaming zone. Besides, the low-boiling-point phosphorous-containing fire retardants were directly evaporated into flaming zone prior to ignition, the thermal-oxidation degradation of which occurred below and roughly at the ignition temperature (**Fig.1-12**) [18, 200-202]. The different degraded products varied with different phosphorous valence and structure with the lower-phosphorus-valence more $\text{PO}\cdot$ radicals [18]. The resultant $\text{PO}\cdot$ radicals were supposed to retard the ignition process. According to the three basic elements for combustion, the increased flammable gases and the more $\text{PO}\cdot$ radicals competed to determine the ignition behavior. BDP, RDP and TPP were evidenced to delay the ignition time to different degrees [203-205]. Intrinsic phosphorous-containing fire-retardant polymers exhibited the delayed t_{ig} [206-208].

Fig.1-12 Thermal degradation curves of (a) hyperbranched poly(phosphamide ester) [200], (b) phenyl phosphonate-based fire retardant and (c) phenyl phosphoric-based fire retardant [18]

Apart from it, Schartel' group systematically investigated the influence of the type of polymer

matrix on the ignition behavior from two aspects [15]. Firstly, thermal-oxidation degradation of different polymer matrix determined the amount and species of degraded products. Secondly, the polymer matrix changed the degradation routes of phosphorous-containing fire retardants [15]. For instance, EP with different curing agents changed the fire-retardant mechanism between condensed phase and vapor phase (**Scheme 1-5**), which indicated that the degradation route of fire retardant changed. The phenyl phosphoric based fire retardant (**Fig.1-12 (c)**) delayed the ignition time of PLA but decreased the ignition of EP [18, 209]. It was inferred that thermosetting polymers interacted with phosphorous-containing fire retardants more intensively than that of thermoplastic polymers. The intrinsic phosphorous-containing fire retardants illustrated a similar behavior to additive-type fire retardant based polymers. In addition, the inorganic phosphorous-containing fire retardants also revealed the delaying tendency of ignition, exemplified by aluminum phosphinate [63, 85, 210]. In contrast, another type of inorganic phosphorous-containing fire retardants (calcium hypophosphite and lanthanum hypophosphite) generally reduced the t_{ig} of PLA and polyamide 6 (PA6) due to the remarkably deteriorated thermal-oxidation stability [211-213].

d. Intumescent fire retardant-based polymers

Intumescent fire retardant based thermoplastic polymers (*e.g.* PP, PS, PLA and PU) exhibited shortened ignition time [82, 214-219]. In contrast, the intumescent fire retardant based thermosetting polymers exhibited nearly unpredicted ignition time [220-225] (**Table 1-1**). Until now, the ignition mechanism of intumescent fire retardant-based polymers was not supported by enough data and investigations. In terms of thermoplastic polymers with intumescent fire retardants, the physical property of k and c presented unpredicted changes with the density ρ slightly increased. The thermal-oxidation stability of polymers with intumescent fire retardants was generally deteriorated due to the impact of APP on thermal-oxidation of polymer matrix (**Fig.1-13 (a)**) [226]. The deteriorated thermal-oxidation stability hinted a larger amount of flammable fuels to the flaming zone. The increased amount of degraded products acted as a factor to induce the ignition after the analysis of the three elements for sustained fire (temperature, oxygen and volatiles) [95]. Without consideration of the impact of c , k and ρ , t_{ig} was shortened slightly according to decreased T_{ig} (Q_{cri} was considered as invariable according to Equation (1-9)

and (1-10)). The impact of heat and mass transfer between different location of the sample was weak due to relatively low thermal-oxidation temperature and the significantly increased viscosity (**Fig.1-13** (b)) [22]. Accordingly, the downward movement of polymer melt (bubble upward) presented a limited effect on the heat dissipation of top surface and incident t_{ig} (**Fig.1-13** (c)) [95, 96]. The thermosetting EP with intumescent fire retardants presented divergent results with the most cases of shortened ignition due to the deteriorated thermal-oxidation stability (**Table 1-1**). As for the case of delayed ignition of epoxy resin (EP), it was considered to originate from t_{ig} derivatives and different types of raw materials.

Particularly, Wang *et al.*, found that t_{ig} of intumescent fire-retardant polyethylene (PE/IFR, 70/30) was significantly increased by 102s via the substitution of 0.2% IFR by metal chelate (CuSAO) (**Fig.1-13** (d)) [227]. The finding of the significantly increased t_{ig} was due to the generation of char film prior to ignition. The generation of the char film was due to intensive catalysis of CuSAO. The heat was magnificently shielding with the temperature below the char film increasing slowly (**Fig.1-13** (d)). The ignition time (t_{ig}) was delayed significantly.

Table 1-1 t_{ig} value change of intumescent fire-retardant (IFR) systems

Matrix	IPR with weight percentage	Change of t_{ig} relative to neat matrix (s)	Heat Flux (kW/m ²)
PP [75]	Piperazine-APP (25%)	-8	50
PP [219]	APP (25%)	-12	35
PP [216]	APP (30%)	-16	35
PP [228]	APP + charring agent (30%)	+8	35
PP [229]	APP (20%)	-4	35
EP [218]	APP (10%)	-19	35
EP [224]	APP (5%)	-3	35
EP [223]	APP + CoSA3 (5%)	+1	35
PLA [226]	APP+MA+ β -CD (20%)	-5	35
EVA [82]	APP+ β -CD (40%)	-7	unknown
EVA [82]	β -CD encapsulating APP (40%)	+2	unknown
PS [230]	APP (30%)	-7	35
PS [215]	APP (5%)	-25	35

Fig.1-13 (a) TG and DTG curves of intumescent fire-retardant PLA [226]; (b) increased dynamic viscosity of intumescent fire-retardant PP [22]; (c) illustration of upward movement of incident bubbles; (d) mechanism of delayed t_{ig} of PE/IFR/CuSAO [227]

e. Nanofiller-based polymers

Nanofillers, as the prevailing fire-retardant reinforcement in Section 1.2.2, showed a promising prospect in delaying ignition behavior of polymers. However, as far as the authors knew, the investigation of ignition behavior and mechanism was merely carried out except MMT-filled PP, polyethylene terephthalate (PET) and EP by Fina *et al.* [161, 167], Bourbigot *et al.* [55] and ScharTEL *et al.* [174]. In most studies of nanofiller-based polymers, merely t_{ig} was provided without mechanistic investigation. The selected results of nanofiller-based polymer nanocomposites were exhibited in **Table 1-2**. In terms of PET nanocomposites, the addition of 5wt% C-Na⁺ and C20A shorted t_{ig} value of roughly 100s and 250s respectively at 25kW/m² compared with that of neat PET [161]. The investigation of surface temperature illuminated that the addition of C-Na⁺ and C20A did not change the melt stage notably, accompanied by the significant decrease of degradation time (gasification time) (**Fig.1-14** (a)). The melting temperature and the time of melting period after the addition of C-Na⁺ and C20A were slightly increased due to the heterogeneous nucleating effect of MMT in PET [161]. The gasification temperature after addition of C-Na⁺ and C20A were slightly decreased due to the more intensive thermal-oxidation degradation, which carried away the more heat from the top surface (**Fig.1-14** (b) (c) and (d))

[161].

Table 1-2 Ignition time (t_{ig}) of nanofiller-based polymers

Fillers with weight percentage	Matrix	Change of t_{ig} relative to neat matrix (s)	Heat Flux (kW/m ²)
Phosphorous-grafting POSS (2-5wt%) [231-233]	EP	+(5-12)	50
Modified boron nitride (BN) (10wt%) [234]	Bismaleimide Resin	+95	35
Silica Modified BN (1wt%) [235]	EP	+24	35
Graphene [236]	EP	+18	35
C ₆₀ [237]	PP	+15	35
Organic Modified MMT [161]	PET	-250	25
Organic Modified MMT [161]	PA6	-85	25
Hectorit [238]	PS	-10	35
[Fe(bpy) ₃] ²⁺ -modified hectorit [238]	PS	+8	35

Fig.1-14 (a) Surface temperature of PET nanocomposites; (b) (c) (d) cross-section of samples at

ignition of PET, PET/CNa⁺ and PET/C30B; (e) surface temperature of PA6 nanocomposites; (f) formation of char film to shield heat [161].

In addition, the organic MMT (30B) conferred PA6 with reduced ignition (**Fig.1-14** (e)). Distinct from PET [161], the melting process was not reflected via surface temperature with higher ignition temperature in terms of PA6/30B, which was attributed to the fast formation of carbonaceous film. The case was similar to that reflected by the intumescent fire-retardant PE with CuSAO (**Fig.1-14** (f)). In terms of PP composites with 5wt% CNa⁺ and C20A, the t_{ig} exhibited complicated trends at different heat flux compared with neat PP (**Fig.1-15** (a)) [167]. The $t_{ig}^{-1/2}$ was approximately proportional to heat flux, which illuminated that the sample belonged to the thermally thick. The thermal-oxidation stability of PP was slightly enhanced with CNa⁺ and C20A, which theoretically resulted in delayed ignition. The reverse result of shortened ignition time (t_{ig}) was due to the decreased thermal inertia (ρck) and changed T_{ig} .

Fig.1-15 (a) t_{ig} value and (b) T_{ig} value of PP and PP composites at different heat flux [167]

The attenuated total reflection Fourier transferred infrared spectroscopy (ATR-FTIR) investigation of surface prior to ignition and post-ignition demonstrated that MMT nanosheets accumulated on the surface and acted as the barrier of the heat and oxygen, which resulted in the decreased c . T_{ig} values showed the interesting change with the reduction at 35kW/m² and 50kW/m² and the invariable trend at 25kW/m² after addition of CNa⁺ and C20A. The different heat flux incited different heating rate of PP composites and different thermal inertia, which resulted in the complicated change of T_{ig} . Hausner *et al.* found that the metal complexation intercalated hectorite nanoclay endowed PS with 19s delaying of t_{ig} compared to the pristine hectorite-filled PS composites [238]. The promoted dispersion of nanoclay in combination of the

incorporation of catalyst of metal complexation in matrix PS jointly promoted the formation of the carbonaceous film, which effectively delayed t_{ig} . Blasi's group studied the ignition behavior of carbon nanotube (CNT) filled PMMA nanocomposites via multi-step kinetic transient 1D model [239]. It was shown that the addition of CNT delayed and shortened t_{ig} of PMMA at low and high heat flux due to the early formation of shielding char and the local adsorption of heat respectively.

In addition, BN and graphene nanosheets were found to impart thermosetting and charring EP and bismaleimide resin with delayed ignition behavior respectively [234-236] (**Table 1-2**). The thermal conductivity (k) and increased thermal-oxidation stability played the predominant roles, which separately slowed down the heating rate of top surface and slightly increased T_{ig} . The similar case was detected in C_{60} -based PP nanocomposite [237]. More importantly, the hierarchical functionalization of graphene nanosheets with LDH and BN nanosheets with organic compounds further contributed to the delaying of t_{ig} significantly, which was due to the higher c from better nanodispersion (**Fig.1-16** (a), (b) and (c)) [234].

Actually, the above hierarchical functionalization opened the window for further delaying ignition behavior. The mechanism was constrained in the alternation of thermal-oxidation stability and thermal inertia [109, 111, 136, 142, 191]. More novel mechanism to delay ignition should be explored urgently.

Fig.1-16 (a) Organic hybridization of BN nanosheets [234]; (b) thermal conductivity of bismaleimide composites with non-modified BN (hBN) and organically modified BN (CPBN)

[234]; (c) TEM images of graphene modified by Ni-Fe LDH [236]

f. Surface treatment on film, foam and fabric

Surface treatment technique enjoyed the popularity recently due to operation-simplicity and cost-effectiveness in improving fire retardancy and delaying ignition. The surface treatment included nanoparticle adsorption, layer by layer (LBL) assembly, sol-gel technique and bio-macromolecule deposition [240]. Actually, the performance of delaying ignition was dependent on the type of matrix and coating, the amount of coating and external heat flux. In terms of the nanoparticle adsorption, the investigation demonstrated different rules with effective component of MMT- Na^+ and halloysite in delayed ignition of polyester fabric and MMT- Na^+ and POSS in delayed ignition of cotton [241]. The mechanism to account for the delayed ignition was due to the remarkable barrier effect, which shielded from the heat attack [242]. The underlying polymer matrix actually received the less heat and incited less thermal-oxidation/thermal degradation. Simultaneously, the adsorbed inorganic nanoparticles possessed the higher resistance toward ignition.

In parallel, the LBL technique was the extension of nanoparticle adsorption based on the multiple adsorptions of oppositely-charged organic and/or inorganic components (**Fig.1-17 (a)**) [243]. The organic components (polyethyleneimine (PEI) [244], ammonia polyphosphate (APP) [245] and sodium polyacrylate *etc.*) and inorganic components (MMT [243], LDH [246], SiO_2 [247], POSS [248], halloysite [242], carbon nanotube (CNT) [249] and graphene oxide (GO) [250] *etc.*) were employed to form the multi-lamellar film by alternative adsorption of oppositely-charged components. The film was characterized by ellipsometer and electron microscopy in terms of thickness and morphology respectively (**Fig.1-17 (b)**) [251]. Herein, it was very uncertain whether the ignition was delayed due to the unconfirmed ignition-resistance of polymer matrix and coated film. In order to attain the delayed ignition (**Fig.1-17 (c)**) [252], the proper organic/inorganic ion pairs were selected (phytic acid/silica, sodium polyaminophosphonate/ SiO_2 , polyallylamine/MMT and halloysite/ SiO_2 *etc.*) [241].

In addition, the sol-gel technique of silica or titania and the adsorption of bio-macromolecules were the feasible approaches to delaying ignition, relying on the relative ignition-resistance of matrix and coatings. In most cases, the incorporation of silica and bio-macromolecules was not

capable to delaying the ignition effectively in terms of cotton and polyester fabric [37, 43, 253]

Fig.1-17 (a) LBL process [243]; (b) TEM images of coated fabric [251]; (c) delaying ignition of cotton after LBL coatings in CCT [252]

1.2.4 Smoke suppression

Smoke was a collection of airborne solid and liquid particulates emitted when materials underwent combustion or pyrolysis (smoldering) [254]. Smoke hazard constituted the key part of fire hazard based on the serious harm to fatality. However, the adequate attentions and focuses were not put on investigating physical and chemical aspects of smoke production and smoke suppression for the intentional design of smoke suppressant [255]. In order to figure out approaches to studying smoke suppression, the smoke production process was first discussed. The condensed-phase and vapor-phase smoke-production mechanism were put forward, which reflected that the smoke was produced in condensed and vapor phase respectively [8]. The mere molecule-level interpretation of PVC did not enable the understanding the general specific physic and chemical process of polymers [8, 256, 257].

The smoke production behavior differed in non-flaming and flaming combustion, which introduced the different heating ways [258]. As for the flaming combustion, the polymer matrix underwent the thermal degradation process in the oxygen-defect environment with the generation of volatiles (aliphatic and aromatic compounds) and char [258]. The volatiles were further released to the vapor phase and underwent the intensive thermal-oxidation reaction towards smoke and fire [258]. In terms of the charring polymer (*e.g.* EP), the char formed initially covered on the underlying unreacted polymer matrix, which notably inhabited the release of volatiles [139, 259, 260]. The volatiles confined under the resultant char were capable to be converted towards high-molecular-weight volatiles or char precursors (**Scheme 1-8** (a) and (b)) [261]. When the high-molecular-weight volatiles (polycyclic aromatic compounds, PAH) were released into the vapor phase, the nucleation and growth of carbon particulates (main components of smoke) turned simpler (**Scheme 1-8** (c)) [262]. Conversely, the combustion of high-molecular-weight volatiles became more difficult. It was considered traditionally that the char fractured due to the limited mechanical strength, which acted as the smoke sources.

The non-charring polymer (PS, PP and PE *etc.*) generated small-molecular-weight volatiles, which were directly released into the vapor phase [263]. Without the conversion into high-molecular-weight PAH, the nucleating and growth of carbon particulates towards smoke intermediates became more different, which resulted in the less formation of smoke compared with charring polymers.

Scheme 1-8 (a) Polyaromatic reaction due to protection effect of char; (b) possible reaction

toward formation of PAH; (c) nucleation and growth to form soot and smoke

In terms of non-flaming combustion (smoldering), the polymer matrix underwent the thermal-oxidative process with less char yield [254] [264]. In the similar way, the degraded volatiles entered the vapor phase and were converted into soot (smoke intermediate) and smoke. Furthermore, the heat flux toward the pristine polymer matrix remarkably decreased due to the absence of flame radiation, which incited the incomplete thermal-oxidation process. Compared with the flaming combustion, the non-flaming combustion thus generated relatively denser smoke due to the dominant factor of heat flux [254].

In the flaming combustion of the entire combustion process, the smoke-production mechanism was presented. Simply, the polymer matrix underwent intensive thermal degradation with the degraded volatiles entering the vapor phase. The volatiles underwent the further thermal-oxidation and were converted into smoke precursors (PAH) with high molecular weight, which subsequently preceded the nucleation and growth towards soot and smoke [265]. The fracture of the char was considered to offer the small pieces of char, which fled to the flaming zone as the smoke. As the combustion entered the smoldering period, the smoke production was enhanced due to incomplete thermal-oxidation process [254]. Different polymer matrix possessed different smoke-production capacity. The polymers (EP, PS, PVC and acrylonitrile-butadiene-styrene copolymer, ABS *etc.*) with the stronger tendency to form polyaromatic compounds during degradation possessed the potentials to generate smoke. The higher heat flux drove the formation of smoke with higher aromatic degree.

Based on the above assessment, the approaches to cutting off the formation process of smoke were considered via the chemical and physical aspects. The condensed-phase and vapor-phase smoke-suppression mechanism were discussed respectively. In the condensed-phase mechanism, the various metal-containing compounds were employed to promote smoke suppression with improved fire retardancy [256, 257, 266]. In the vapor-phase mechanism, the particular metallic iron complexations demonstrated the notable effect in reducing smoke production [267]. The smoke profiles were confirmed by the cone calorimeter test (CCT) and smoke density chamber [268].

Vapor-phase mechanism

Vapor-phase mechanism was investigated predominantly based on the ferrocene and/or its derivatives. Ferrocene, as the metallic iron (Fe) complexation (**Fig.1-18 (a)**), was first employed in decreasing the smoke production of aviation fuels [262, 267]. Previously, the premixed flame (**Fig.1-18 (b)**) and diffusion flame (**Fig.1-18 (c)**) were employed to investigate the smoke behavior [269]. The employment of ferrocene in premixed fuel certified that remarkable smoke suppression effect was due to the vapor-phase mechanism, which was involved in the promoted catalytic degradation of smoke intermediates by the iron-containing derivatives [262, 270, 271]. When ferrocene molecules were applied in polymers, the situation became more complicated. The study showed that ferrocene suppressed the smoke production of poly(vinyl alcohol) (PVA) and PVC remarkably with the most dominant mechanism in vapor phase and condensed phase respectively [272]. Ferrocene improved the charring of PVC with LOI value increasing notably but possessed no effect in PVA charring behavior with ferrocene volatilized.

In terms of the iron-based metal complexation-filled non-halogenated polymer (*e.g.* ABS), the evaporated amount of the iron-based complexation was proportional to the decrease of the smoke density. Interestingly, the halogenated ABS showed the interesting result with the evaporated amount inversely proportional to the decrease of smoke density (**Table 1-3**) [8]. The result indicated that halogen incorporation changed smoke suppression from vapor phase to condensed phase [272].

Table 1-3 Relationship between smoke suppression with different additives [8]

Polymers	Additives	Smoke suppression (%)	Evaporation of metal (%)
ABS	No	-	-
	Ferrocene	70	100
	Ferrobenzyl phenyl ketone	60	60
	Ferric acetylacetonate	30	20
Halogenated ABS	No	-	-
	Ferrocene	24	100
	Ferrobenzyl phenyl ketone	38	60
	Ferric acetylacetonate	55	20

Fig.1-18 (a) Structure of ferrocene [262, 267]; (b) premixed flame; (c) diffusion flame including the counter-flow and co-flow mode [269]

Condensed-phase mechanism

The condensed-phase mechanism was involved in the smoke suppression occurring via the charring effect and/or charring-protection effect, which was exemplified by ferrocene-filled PVC. Ferrocene promoted the dehydrochlorination reaction and charring reaction, which resulted in a significant enhancement in fire retardancy simultaneously [256, 258, 270, 273-275]. The mechanistic investigation via thermogravimetric coupled with Fourier transformation (TG-FTIR), gas chromatograph and mass spectroscopy (TG-MS) [274] and Mossbauer analysis [258] *etc.*, indicated that ferrocene molecules interacted with hydrochloride (from dehydrochlorination of PVC over temperature range between 350°C and 450°C) to generate the complexation (**Fig.1-19** (a)). The complexation of ferrocene and HCl retained the ferrocene in condensed phase, which properly accounted for the switch of smoke suppression mechanism from vapor phase to condensed phase. The resultant ferrocene-hydrochloride complexation was further converted into FeCl_2 , FeCl_3 and Fe_2O_3 , which acted as the effective catalyst to promote the charring reaction (detected by the increase of aromatic compounds) [256]. The charring reaction proceeded via the complexation effect between iron and PVC chain, which inversely enhanced the dehydrochlorination reaction (**Fig.1-19** (b)) [272]. Approximately 1/2 to 2/3 portion of iron element was retained in the condensed phase. The other iron derivatives entered the vapor phase to perform the vapor-phase mechanism.

Notably, the smoke production behavior differed in the flaming and non-flaming combustion (smoldering) with the amount of smoke lower and higher respectively, which was attributed to the

catalytic charring effect at oxygen-defect atmosphere and the catalytic degradation of resultant char at oxygen-rich atmosphere (**Fig.1-19** (c)). The heavy tars and light tars (PAH) were generated at the oxygen-defect and oxygen-rich atmospheres respectively [258]. Apart from it, the other smoke suppressants included molybdenum trioxide (MoO_3) [257] and zero-valent copper ($\text{Cu}(0)$) [266] *etc.*, MoO_3 performed the smoke suppression via 1) the promoted conversion of cis-polyenes to trans-polyenes (the precursor of benzene and PAH) and 2) the promoted crosslinking reaction through Friedel-Crafts and Diels-Alder reactions in condensed phase (**Fig.1-19** (d)) [8]. In contrast, the zero-valent copper $\text{Cu}(0)$ performed the smoke suppression through the coupling reaction (**Fig.1-19** (e)), which was evidenced by the fast gel reaction in TG.

Fig.1-19 (a) Chemical reaction of ferrocene [256]; (b) FeCl_3 -involved dehydrochlorination [273]; (c) smoke density, CO and CO_2 products at different temperature [258]; (d) smoke suppression mechanism of MoO_3 toward PVC [8] and (e) smoke suppression mechanism based coupling reaction [8]

Recently, various nanoparticles (MMT [276], LDH [259, 277], graphene [260], BN [235] and halloysite [277], *etc.*) were employed by Hu's group to suppress the smoke production based on the barrier effect towards smoke precursors. The smoke suppression curves in CCT (evaluated by total smoke production (TSP) and smoke production rate (SPR)) demonstrated the similar trend to the heat profile [5]. However, in order to improve the smoke-suppression efficiency, the approach to doping highly efficient charring catalyst on nanoparticles was employed [139, 260]. The highly efficient charring catalyst [278, 279] was generally assigned as the metal-based compounds (*e.g.* Fe [260], Cu [280], Co [281] and Mo [282]) or mesoporous materials (*e.g.* MCM-41 [283] and SBA-15). The MoO_3 and Cu_2O decorating graphene (**Fig.1-7** (a)) revealed better smoke

suppression compared to the mono-component in thermoplastic polyurethane (PU) based on the synergistic charring of charring catalysts (performed by MoO_3 and Cu_2O) and the barrier effect (performed by graphene) (**Fig.1-20**) [282]. According to the similarity of the heat and smoke curves, the nanoparticles to impart fire retardancy based on the barrier effect (condensed-phase fire-retardant mechanism) were usually regarded as the smoke suppressants (*e.g.* $\text{Mg}(\text{OH})_2$, $\text{Al}(\text{OH})_3$ and talc) [8, 284]. In contrast, the vapor-phase fire retardants (*e.g.* triphenyl phosphate (TPP), DOPO and halogenated fire retardants [120]) endowed polymers with increased smoke production based on the dehydrogenation reaction toward the polyaromatic volatiles [4]. The condensed-phase smoke-suppression possessed the lower efficiency than that in vapor phase due to the more difficulty to form high-barrier layer at low loadings.

However, the aforementioned approaches to utilizing nanoparticles or nanohybrids illustrated the low smoke-suppression efficiency. The smoke-suppression mechanism at the mesoscale level and molecule level was unclear. In addition, the investigation of vapor-phase smoke-suppression mechanism was limited on ferrocene-based PVC and mixed fuel. The molecule-level study of vapor-phase mechanism toward polymers was unclear. Based on the above evaluation, the current work was to seek for the optimized strategies to improving smoke suppression via various molecule design and novel mechanisms.

Fig.1-20 Possible smoke suppression of Graphene/ MoO_3 and Graphene/ Cu_2O in PU [282]

1.3 Objective of the thesis

In consideration of reducing fire hazard of polymeric materials, the objectives of the thesis are to rationally design fire retardants to delay ignition and decrease post-ignition fire hazard

(predominantly on smoke suppression). The delayed ignition and suppressed smoke production were performed at multi-scale (*i.e.* molecule level, mesoscopic scale and macroscopic scale). The prerequisite was that the fire retardancy should be reduced or at least maintained. To be detailed, the objectives are concluded as:

1) *To design efficient strategies to delay ignition and suppress smoke for fire-retardant polymers*

In terms of delaying ignition, the first composite system was the exploitation of a new-generation radical-quenching agent (ferrocene) of polystyrene (PS). The second ignition-delaying system was to use mesoporous silica (SBA-15) to delay the slow-release of degraded products from PS. The decoration of ultrafine Co_3O_4 nanoparticles in the interior wall of SBA-15 enhanced the slow-release behavior of degraded products. The third ignition-delaying system was to develop halloysite (HNT)-based nanohybrid as the nanocarrier to generate the sustainable release of $\text{PO}\cdot$ radicals.

In terms of smoke suppression, the first composite system was the insightful investigation of vapor-phase smoke suppression of ferrocene in PS matrix. The second smoke-suppression system was to solve the low sublimation temperature of ferrocene via the inclusion of ferrocene into the nanocarrier of sulfonated cyclodextrin intercalated layered double hydroxide (LDH-CD). The partial evaporation of ferrocene generated the combination of vapor-phase and condensed-phase mechanism. The third smoke-suppression system was to use organic LDH to suppress smoke production of EP. The ultrafine $\text{Ni}(\text{OH})_2$ nanocatalyst decorated on the exterior surface of LDH enhanced the smoke suppression via the novel catalytic charring at the interface.

In terms of ignition-delaying and smoke-suppression system, the composite system was to control the physical parameters (k , c and ρ) and chemical parameters (thermal-oxidation degradation) for delaying ignition and manipulate the catalytic charring to suppress smoke production of EP matrix. Thermal exfoliated boron nitride nanosheets (BN) were functionalized by polydopamine (PDA) and iron-derived nanocatalyst (Fe) on the surface.

2) *To study the mechanism of delaying ignition*

The mechanism of above four ignition-delaying systems was systematically investigated from the macroscopic, mesoporous and molecule level. The ignition process occurred with the sequential processes of temperature-rising process of surface, thermal-oxidation degradation and the final

interplay of oxygen, flammable gases and ignition temperature (T_{ig}). Macroscopic level included temperature-rising process and thermal-oxidation behavior. Mesoscopic level included the nanostructure of nanofillers and structure of polymer composites. Molecule level included the molecular interpretation of thermal-oxidation degradation and interaction of degraded products and nanofillers. In particular, we investigated the effect of physical factors (thermal inertia) and chemical factors (thermal-oxidation degradation) on ignition via comparative experiments and virtual simulations. The mechanism study paid attention on depth (multi-level interpretation) and width (comprehensiveness).

3) To study the mechanism of smoke suppression

The mechanism of above four smoke-suppression systems was systematically investigated from the macroscopic, mesoporous and molecule level. As the combustion occurred, the thermal degradation of polymers provided smoke precursors of polyaromatic compounds in the condensed phase. The formation of protective char decreased the release of polyaromatic compounds. In the vapor phase, smoke precursors nucleated and grew to smoke intermediates (soot). Macroscopic level included the thermal degradation of composites and thermal-oxidation stability of soot. Mesoscopic level included the nanostructure of nanofillers and structure of polymer composites. Molecule level included the molecular interpretation of charring behavior of composites and thermal-oxidation of soot. The mechanism study paid attention on depth (multi-level interpretation) and width (comprehensiveness).

4) To establish a proper model to simulate sample temperature

The proper model was established to simulate surface temperature with the assumption of pure solid fuel without chemical reaction. For one hand, the simulated result assisted the experimental results to analyze the effect of physical and chemical factors on temperature-rising profile of top surface. For another hand, the simulated temperature along the thickness direction of samples disclosed the information of pyrolyzed depth, which was hard to obtain via experiment. The pyrolyzed depth influenced by physical factors played an important role in volatile concentration, which belonged to chemical factors.

5) To maintain or improve other properties (thermal stability and mechanical property etc.)

CHAPTER 2

Materials and Experimental Techniques

“Silence is a true friend whoever never betrays”

-Confucius

2.1 Materials

The following chemicals were purchased from Sigma-Aldrich: Ferrocene, β -cyclodextrin (β -CD), 1,4-butane sultone (BS), ethyl ether, polystyrene (PS, $M_w=192000\text{g/mol}$), PEO₂₀-PPO₇₀-PEO₂₀ (P123, $M_w=5800\text{g/mol}$), ammonium fluoride (NH₄F), hydrochloric acid (HCl, 37wt%), heptane, triethyl orthosilicate (TEOS), urea, cobalt(II) chloride hexahydrate (CoCl₂·6H₂O), maleic anhydride (MAH), acetone, toluene, aluminum nitrate nonahydrate (Al(NO₃)₃·9H₂O), magnesium nitrate hexahydrate (Mg(NO₃)₂·6H₂O), sodium hydroxide (NaOH), sodium dodecylbenzenesulfonate (SDBS), nickel nonahydrate (Ni(NO₃)₂·6H₂O), trisodium citrate dihydrate (C₆H₅Na₃O₇·2H₂O), hexagonal BN powder, dopamine hydrochloride (DA·HCl), tris(hydroxymethyl)aminomethane (tris), iron (III) chloride (FeCl₃), sodium borohydride (NaBH₄) and diethylenetriamine (DETA). Halloysite nanotube (HNT) was bought from Benahadux Corporation (Almeria, Spain). 9,10-Dihydro-9-oxa-10-phosphaphenanthrene-10-oxide (DOPO) and 4,4'-diaminodiphenylmethane (DDS) were purchased by TCI Corporation. Polylactide (PLA) (3251D) was provided by NatureWorks Corporation. Epoxydharz C was obtained from Faserverbundwerkstoffe Composite Technology Company. 1.8 M HCl aqueous solution was prepared through diluting dense HCl solution with deionized water. LDH-NO₃ was kindly supplied by Prolabin & Tefarm Company, Italy. Tris(hydroxymethyl)aminomethane buffer solution with pH value of 8.5 and concentration of 0.05mol/L was prepared by ourselves. Deionized water was self-prepared in our institute.

2.2 Experimental technique

Fourier transformation infrared spectroscopy (FTIR)

FTIR measurement was carried out using the spectrometer (Nicolet iS50, TA Instrument) from 400

cm^{-1} to 4000 cm^{-1} with the resolution of 4 cm^{-1} . The powder-like samples were mixed with KBr prior to milling and pressing into pellets. Before each measurement, the background spectra were collected with the neat KBr pellet. Variable-temperature FTIR (vt-FTIR) was conducted on the identical spectrometer (Nicolet iS50, TA Instrument) facilitated with the heating ring to control heating procedure (**Fig.2-1**). The KBr/Sample pellet was located at the hold and applied with the heating program: from 50°C to 400°C in 35min and invariable at 400°C for 10min. Simultaneously, FTIR spectra were acquired every 30s from 400 cm^{-1} to 4000 cm^{-1} with the resolution of 4 cm^{-1} . Software *Omnic* was used to analysis the 3D FTIR result.

Fig.2-1 Schematic illustration of core components of vt-FTIR

Thermogravimetric analyzer with Fourier transformation infrared spectroscopy (TG-FTIR)

TG-FTIR was operated on FTIR spectrometer (Nicolet iS50) connected with TG analyzer (Q50, TA Instruments) through a heated pipe (**Fig.2-2**).

Fig.2-2 Schematic illustration of core components of TG-FTIR (volatiles moving from right TG furnace to left FTIR chamber)

The invariable weight ($15 \pm 0.2 \text{ mg}$) sample underwent heating from ambient temperature to 800°C with heating rate of $10^\circ\text{C}/\text{min}$. The evolved volatiles were directed to gas chamber for FTIR measurement. FTIR spectra were acquired every 30s from 500 cm^{-1} to 4000 cm^{-1} with the resolution of 4 cm^{-1} . Software *Omnic* was used to analysis the 3D FTIR result.

Thermogravimetric analyzer with gas chromatograph and mass spectroscopy (TG-GC-MS)

TG-GC-MS was performed in Agilent 6890/5973N GC/MSD System. $15 \pm 0.2 \text{ mg}$ sample underwent heating from ambient temperature to 800°C at $10^\circ\text{C}/\text{min}$ with pyrolyzed products directed to gas chromatograph (GC) via heated pipe. Further, volatiles from the outlet of GC were directed to the mass spectroscopy (MS) with the procedure of ionization, accelerating and selection (**Fig.2-3**).

Fig.2-3 Schematic illustration of core components of TG-GC-MS (volatiles moving from right TG furnace to middle GC column finally to left MS chamber)

Thermogravimetric analyzer with mass spectroscopy (TG-MS)

TG-MS were operated in the facility with an electron-impact quadrupole mass-selective detector (model Thermostar QMS200 M3). The sample ($15 \pm 0.2 \text{ mg}$) was heated from ambient temperature to 700°C at $10^\circ\text{C}/\text{min}$ at argon atmosphere. The evolved gas was directed into MS. The schematic illustration was similar to TG-GC-MS in **Fig.2-3** without GC stage. The mass charge ratio (m/z) for the MS detection was limited not more than 150.

Micro combustion calorimeter (MCC)

MCC was executed in the facility (MCC-1, FTT) based on the oxygen-depletion mechanism. The combustion heat with consuming 1g oxygen was fixed at 13.1 KJ with 4% derivation. The oxygen depletion was recorded via flow meter and O_2 meter. Herein, 2-4 mg sample was heated from 150

°C to 700 °C at 1 K/s under nitrogen. The anaerobic thermal-degradation products were mixed with oxygen stream prior to conveying to 900 °C combustion furnace (**Fig.2-4**). Heat release rate (HRR, W/g) and heat of combustion (J/g) were available via the calculation of the heat generated by unit-weight sample.

Fig.2-4 Schematic illustration of core components of MCC

Limiting oxygen index (LOI)

LOI value was employed to assess the flammability of polymers, which was defined as minimum oxygen concentration in mixed O₂/N₂ to permit the persistent flaming. Herein, LOI measurement was carried out according to ASTM D2863-13 on the sample of 12.7mm×6.5mm×3.0 mm. The flame flowed upward, which weakened the heat transfer to underlying pristine polymers. Resultantly, the fire intensity in LOI test was reduced.

Fig.2-5 Schematic illustration of limiting oxygen index

UL-94 test

Vertical burning test

UL-94 vertical burning test was performed on samples of 127.0mm×12.7 mm×3.0mm according

to ASTM D3801-10 (**Fig.2-6** (a)). The persistent combustion times were recorded after twice 10-second flaming, which were assigned as t_1 and t_2 . t_3 was defined as the afterglow time after the second flaming application. In terms of the dripping sample, the burner was tilted of $45^\circ \pm 2^\circ$. At least 2 sets of specimens were prepared. The UL-94 vertical burning ratings were assessed by **Table 2-1**. The flame moved upward, which directly heated the underlying polymers. The fire intensity was enhanced.

Table 2-1 Materials classifications

Criteria Conditions	V-0	V-1	V-2
Afterflame time, t_1 or t_2 for each specimen	$\leq 10s$	$\leq 30s$	$\leq 30s$
Total afterflame time ($t_1 + t_2$ for five specimens)	$\leq 50s$	$\leq 250s$	$\leq 250s$
Afterflame + afterglow time ($t_2 + t_3$ for each specimen)	$\leq 30s$	$\leq 60s$	$\leq 60s$
Afterflame or afterglow of any specimen to holding clamp	No	No	No
Cotton ignited by flaming drops	No	No	Yes

Note: If only one specimen from a set of five specimens does not comply with the requirements, another set of five specimens shall be tested. In the case of the total number of seconds of flaming, an additional set of five specimens shall be tested if the totals are in the range from 51 to 55 s for V-0 and from 251 to 255 s for V-1 and V-2. All specimens from this second set shall comply with the appropriate requirements in order for the material in that thickness to be classified V-0, V-1, or V-2.

Horizontal burning test

Compared to vertical burning test, horizontal burning test imposed a lower requirement in consideration of the transport mode of heat. The specimens with $127.0\text{mm} \times 12.7\text{mm} \times 3.0\text{mm}$ were marked at 25mm and 100mm along the length direction and installed according to **Fig.2-6** (b). In terms of the dripping sample, the burner was tilted of $45^\circ \pm 2^\circ$. The horizontal burning test in our experiment showed a derivation to the standard operation in ASTM D635. Herein, the combustion process was videoed, in which the snapshot was performed. The combustion length and combustion time of different samples after 25-second flaming were compared. In terms of one sample, 3 specimens should be tested for the preciseness. The flame moved upward, which transferred the heat horizontally to the underlying polymers. The fire intensity was enhanced at the medium degree.

Fig.2-6 Schematic illustration of (a) vertical burning test and (b) horizontal burning test

Cone calorimeter test (CCT) [285]

Cone calorimeter test (CCT, FTT) was considered to be the benchmark fire test, which was closest to realistic scenario. The CCT was performed according to standard ISO 5660-1 (**Fig.2-7**). The heat flux and the specimen thickness played important roles on the fire results. Herein, the thermosetting polymers possessed the unified dimension of 100.0 mm×100.0 mm×4.0 mm and thermoplastic polymers 100.0 mm×100.0 mm×3.0 mm. The heat flux depended on the investigation with the options of 25kW/m², 35kW/m² and 50kW/m².

In order to analyze the dynamic charring process, the combustion analysis in CCT was terminated by water or liquid nitrogen at the designated moment (herein at the time to peak heat release rate of pure EP at 50kW/m², 157s). The char structure was investigated.

The ignition behavior was carried out via external sparkling installed in cone calorimeter. The sparkling was located at the centre of the square sample. The distance between sparking point and the top surface of sample was fixed at 25mm. The amplified image was in **Fig.2-8** (a). The smoke production was tested using the laser (**Fig.2-8** (b)). When the ventilation piping was free without any smoke, the laser penetrated the piping completely, generating the voltage signal V_0 . In contrast, when the laser was blocked completely without any penetration, the sensor read the voltage V_1 . Reasonably, the smoke from the combustion blocked the laser partially, which generated the voltage V_s . Accordingly, the smoke production was assessed as the $(V_0 - V_s)/(V_0 - V_1)$, which reflected the blockage of laser due to the smoke. The heat release was obtained based on the oxygen consumption principle (similar to MCC). Experimentally, the heat release rate was calculated via the data read in CCT. The formula was listed in Equation (2-1).

$$\dot{q}'' = \left(\frac{\Delta h_c}{r_0} \right) \frac{32}{28.97} C \sqrt{\left(\frac{\Delta P}{T_e} \right)} \frac{1}{1 - X_{O_2} - X_{CO_2} / \left\{ \left[X_{O_2}^0 (1 - X_{CO_2}) - X_{O_2} (1 - X_{CO_2}^0) \right] + (b - 1) \right\}} \frac{1}{A_s} \quad (2-1)$$

Where $\Delta h_c/r_0$ was the heat of combustion per kg oxygen consumed. ΔP and T_e were orifice meter pressure differential and temperature separately. C was the intrinsic factor. X represented the mole fraction with the subscript the initial value. A_s and b presented the sample size and stoichiometric factor. Equation (2-1) clearly illustrated the influence of C factor calibration, O_2 and CO_2 concentration on the heat release.

Fig.2-7 Schematic illustration of cone calorimeter from different perspectives

Fig.2-8 Schematic illustration of (a) ignition apparatus and (b) laser apparatus

Triple-milling machine

Triple-milling machine was used to disperse nanofillers in thermosetting polymers (*e.g.* EP) based on shear and extensional deformation between the rollers (**Fig.2-9**). The gap distance and rotation speed were adapted to control the shear and extensional deformation. The less roller distance contributed to the extensional flow. The higher difference of rotation speed favoured shear flow.

Fig.2-9 Schematic illustration of triple-milling machine with the generated shear and extensional force

Micro-compounder

Micro-compounder (MC 15, Xplore) was employed to blend thermoplastic polymers and nanofillers. The co-rotating twin screws were installed into the barrel, which generated intensive shear and extensional deformation for the dispersion of fillers (**Fig.2-10**). During processing, the flowing circuit of polymer melt was formed with the flow rate determined by processing condition and rheological property of polymers. In terms of different polymers, the different processing conditions were utilized, which was detailed in the respective sections.

Fig.2-10 Schematic illustration of micro-compounder and flowing circuit of polymer melt

Temperature detection

Surface and bottom temperature were detected via K-type thermocouple (**Fig.2-11 (a)**). Particularly, the temperature at the middle layer was tested via putting the thermocouple into the holes after mechanical drilling. The sample surface temperature was tested with one end of

thermocouple attached on the central point. In terms of the temperature detection all over the entire combustion process, the thermocouple of the top surface was hold by hand to accommodate the intumescence.. Alternatively, the combustion temperature was detected with infrared temperature detector (**Fig.2-11** (b)). At least 2 specimens were tested for checking the repeatability. The detection using the infrared beam reflected the smoke temperature considering that the infrared beam was not able to penetrated through the smoke particles.

Fig.2-11 (a) temperature detection prior to ignition using thermocouple and (b) temperature detection during combustion using infrared detector

Acquisition of soot

The soot collection process was performed in the self-designed apparatus (**Fig.2-12**). UL-94 specimen was horizontally ignited from one end. The produced soot was collected using the arc-like glass slides with the bulge upwards. Specially, in order to confirm that the produced soot just pertained to the initially formed components, the distance between the glass slide and the UL-94 specimen was kept 20mm, which was comparable to the flame length. The glass collector plane was located at the flame.

Fig.2-12 The soot collection process during the combustion

X-ray diffraction spectroscopy

XRD was recorded with diffractometer (Empyrean, PANalytical) using Cu K α ($\lambda=0.154$ nm) as the anode resource and Ni filter. The voltage and current were 45kV and 40mA respectively. The sample was scanned over the angle range of 2° - 70° or 5° - 70° . The polymer sample should be more than 3mm in thickness. In terms of fluorescence-emitting materials (Co₃O₄ *etc.*), the secondary monochromator was used to obtain the acceptable scan.

X-ray photoelectron spectroscopy (XPS)

XPS was carried out on VG ESCALAB MK II spectrometer with Al K α X-ray radiation. The operation voltage and current were 10kV and 10mA respectively.

Raman Spectroscopy

Raman spectra were recorded using Raman microscopy system (Renishaw PLC) equipped with a 532nm Nd:YAG laser (50 mW at 532 nm) and a diffraction grating of 1800 l/mm. Wire 4.1 software was used to fit the peak and calculate the peak size.

Scanning electron microscopy (SEM)

SEM observation was manipulated on the equipment (EVO MA15, Zeiss) facilitated with dispersive X-ray spectra (EDS) (Oxford INCA 350). The powder specimen was spread on the holder with the conductive tape. Polymer specimens were supposed to undergo cryo-fracture or impact-fracture. Finally, the conductive gold layer was sputtered on the sample surface prior to observation. The operation voltage was chosen as 20kV. FIB-FEGSEM dual-beam microscopy was operated on the equipment (Helios NanoLab 600i, FEI).

Transmission electron microscopy (TEM)

TEM observation was carried out on FEG S/TEM microscope (Talos F200X, FEI) equipped with EDS. The accelerating voltage was 200kV and 80kV dependent on the actual requirement. STEM mode was employed to analyze element and its distribution. The powder sample was dispersed in acetone and applied with the ultrasonication for 20 min prior to dropping onto the copper grid. After evaporation, the power sample was observed with normal TEM, selective area electron diffraction (SAED) and energy dispersive spectroscopy (EDS). In terms of EP composites, the ultrathin section was prepared using the ultramicrotomy to ca. 80 nm in thickness.

Dynamic mechanical analysis (DMA)

Dynamic mechanical behavior was analyzed on dynamic mechanical analyzer (DMA, Q800, TA instruments) on single cantilever. In terms of EP matrix, the measurement proceeded with temperature rising from room temperature to 270°C at 3°C/min at the amplitude of 30μm and frequency of 1Hz.

Differential scanning calorimeter (DSC)

DSC was performed on the facility (Q200, TA instruments). Approximately 8mg sample was charged into the hermetic pan and then was applied with the temperature following program: 1) Heating from 0°C to 200°C at the rate of 20°C/min 2) Isothermal for 10min 3) Cooling from 200°C to 0°C at the rate of 10°C/min 4) Isothermal for 5min 5) Heating from 0°C to 200°C at the rate of 10°C/min.

Thermogravimetric analysis (TG)

TG was performed on Q50 (TA Instrument) from ambient temperature to 800°C at heating rate of 10°C/min and 40°C/min at N₂ and air atmosphere. Apart from it, aiming to study the charring process, the invariable-temperature degradation process was performed at N₂ atmosphere via the rapid heating at 30°C/min to 350°C and subsequently keeping invariable temperature for 30min.

Thermal conductivity and specific heat of capacity [286, 287]

Thermal conductivity was conducted in Hot Disk Thermal Constants Analyzer (Switzerland). The heater and temperature detector was installed between two samples with the thickness more than 6mm. The bulk and isotropic heat radiation mode was adopted. Through the test, the thermal conductivity (k), specific heat of capacity (c) and thermal diffusion were acquired.

N₂ sorption test

N₂ sorption was conducted with Micromeritics ASAP 2010 surface area and pore size analyzer. Brunauer-Emmett-Teller (BET) method and Barrett-Joyner-Halenda (BJH) model were separately used to calculate the specific surface area and the pore size distribution.

Tensile test

Tensile behavior was characterized on the dual column tabletop universal testing system (INSTRON 5966) according to ASTM D 638-10. The dogbone sample (Type I) was drawn with

extension rate of 0.5mm/min. The data were obtained as average values of 5 samples.

Temperature simulation

The finite element simulation (FE) was in commercial FE software Abaqus/standard. A user subroutine DFLUX is developed to describe the in-situ heat flux at top surface. The simple 1-D thermally conductive model was established. Within the plain, heat conductivity was considered to be absent.

¹H Nuclear magnetic resonance spectroscopy (¹H-NMR)

¹H-NMR spectra were recorded on a Bruker DRX 500 with dimethyl sulfoxide-d₆ (DMSO-D₆) as solvent. Tetramethylsilane (TMS) was used as the internal standard.

CHAPTER 3

Ignition delaying via flame inhibition and volatile slow-release

“The only true wisdom is in knowing you know nothing”

-Socrates

3.1 Introduction

Recent investigation of ignition behavior was confined in the development of more accurate models to simulate the ignition behavior of neat polymers, which propelled the better understanding of the ignition. However, the systematic study of delaying ignition of polymers was awfully inadequate due to the lacking of efficient approaches. The flame inhibition from phosphorous-containing and halogenated fire retardants accounted for delaying ignition of polymers. However, the efficiency to delay ignition was full of significant uncertainty. Therefore, it was necessary to develop novel flame-inhibition agents (or radical-quenching agents), efficient flame-inhibition strategies and other novel ignition-delaying strategies. Based on above assessment, the detailed aims were set in the chapter, which were involved in 1) development of novel ignition-delaying agent based on flame inhibition 2) development of novel ignition-delaying strategy to improve efficiency of traditional flame-inhibition agent and 3) development of novel ignition-delaying strategy using novel volatile slow-release approach. In addition, the fire retardancy of the ignition-delayed polymer composites should be maintained or enhanced, which was considered as the prerequisite.

In consideration of the difference prior to ignition and after ignition, traditional design of hierarchically structural nanofillers lost the partial effectiveness [120]. Hence, in order to rationally design the targeted nanostructure, the novel strategies should be tentatively developed. Inspired by the slow-release fertilizer, the slow-release behavior of flame-inhibition fire retardants was regarded to strengthen flame-inhibition behavior due to sustainable effect (**Scheme 3-1**). Based on the consideration, the traditional flame-inhibition agents and the slow-release carriers were properly selected. Halloysite nanotubes (HNT) ($\text{Al}_2\text{Si}_2\text{O}_5(\text{OH})_4 \cdot n\text{H}_2\text{O}$) as a typical 1D nanotube [288] demonstrated a remarkable effect in sustainable release of various inclusions from

the internal cavity [289-291]. HNT with inclusion of fire retardant (*i.e.*, dimethyl methyl phosphonate, DMMP) exhibited the fast evaporation without any difference with mono-component DMMP, which illuminated that the slow-release behavior turned invalid during heating process [292]. Fortunately, HNT nanotubes with lumen-like structure supplied a large area of interior and exterior surface for grafting modification, accompanied by partial encapsulation of fire retardant inside nanotubes. Also, HNT revealed a reinforcement effect in fire retardancy [293, 294] and mechanical property [295-297].

Scheme 3-1 Normal release versus sustainable slow release

Apart from it, it was anticipated that the volatiles from degradation of polymers were manipulated towards slow-release behavior. Compared with the normal ignition behavior, the slow-release system required longer time to reach the critical concentration of flammable gases. According to the previous references [298-300], mesoporous materials with pore size between 2nm and 50nm exhibited the capacity to delay release of volatiles. The ignition and fire behavior of typical mesoporous silica SBA-15 filling polymers were not investigated clearly [301]. In order to enhance the slow-release effect, the hierarchical functionalization of SBA-15 was required.

In parallel, inspired by the flame-inhibition effect of ferrocene in premixed and diffused flame (**Fig.1-18**), the effect of ferrocene on ignition-delaying of polymers were investigated [302-305]. The study was aimed at seeking for an effective and novel ignition-delaying agent with understanding of delaying ignition.

3.2 Preparation and characterization of targeted nanohybrid

3.2.1 Preparation of SBA-15@Co₃O₄

Preparation of SBA-15 mesoporous silica

SBA-15 was prepared according to the reference [306]. 9.6 g of P123, 0.112 g of NH_4F and 160 mL of 1.8 M HCl were charged to a single-necked flask with magnetic stirring. The temperature was kept at 17 °C steadily. The stirring was maintained until P123 was fully dissolved. Subsequently, 34 mL of heptane and 11 mL of TEOS were added at the same condition and kept for 4min. After additional 3h static treatment, the mixture was transferred to 200 mL autoclaves and kept at 100°C for 24h. The resulting product was filtered and washed repeatedly for 6 times with deionized water and then dried overnight in vacuum oven. Subsequently, the product was calcined in the muffle at 550 °C for 4h to remove the structure directing agent P123. Schematic illustration was shown in **Scheme 3-2**.

Scheme 3-2 Schematic illustration of SBA-15 preparation process

Preparation of SBA-15@ Co_3O_4 nano-architecture

10.56 g of urea and 10.24 g of $\text{CoCl}_2 \cdot 6\text{H}_2\text{O}$ were dissolved in 800 mL deionized water in a beaker with properly magnetic stirring. Until totally clear solution formed, 4g of the resultant SBA-15 was added into the solution. In order to guarantee the adequate contact between the final solution and interior pore walls of SBA-15, this procedure was maintained 24 h. Then the mixture was put in a household microwave oven with the power 700 W and frequency 2450 MHz for microwave reaction of 10min. After that, the mixture was taken out and cooled down naturally. This procedure would be repeated additional twice in order to ensure effective reaction. Eventually, the resultant product was filtered and washed with deionized water, followed by washing with 1M HCl solution for 3 times quickly to remove $\text{Co}(\text{OH})_2$ on the exterior surface of SBA-15. The product was dried overnight in the vacuum oven and calcined in muffle at 320 °C for 3h at air

atmosphere. Finally, dark brown powder was obtained as the Co_3O_4 nanoparticles doped SBA-15.

The specific schematic illustration was shown in **Scheme 3-3**.

Scheme 3-3 Preparation of SBA-15@ Co_3O_4 nano-architecture

3.2.2 Characterization of SBA-15@ Co_3O_4

FTIR and Raman Spectra

FTIR spectra of SBA-15 and SBA-15@ Co_3O_4 were shown in **Fig.3-1** (a). The presence of SBA-15 was evidenced by the peaks at 3727cm^{-1} and 1048cm^{-1} , which were attributed to the stretching vibrations of silanol groups and Si-O-Si groups respectively. The peaks at 3430cm^{-1} and 3420cm^{-1} were assigned to the stretching vibrations of hydroxyl groups of the absorbed water on SBA-15 and SBA-15@ Co_3O_4 separately. The slight alteration of the hydroxyl location of SBA-15@ Co_3O_4 was due to the formation of strong hydrogen bonds between Co-OH and hydroxyl groups of absorbed water molecules [307]. In parallel, the relative intensity of Si-O- peak (962cm^{-1}) in SBA-15 was higher than that of SBA-15@ Co_3O_4 , which indicated that Si-O- group became Si-OH structure with the incorporation of Co_3O_4 . Meanwhile, Raman spectra were executed and showed in **Fig.3-1** (b). The peaks at 675cm^{-1} and 470cm^{-1} were respectively assigned to A_{1g} and E_g vibration mode of Co_3O_4 in SBA-15@ Co_3O_4 [308]. In contrast, no corresponding peaks emerged in the SBA-15.

Fig.3-1 (a) FTIR spectra of SBA-15 and SBA-15@Co₃O₄ (b) Raman spectra of SBA-15 and SBA-15@Co₃O₄

XRD analysis

XRD spectra of SBA-15 and SBA-15@Co₃O₄ were portrayed in **Fig.3-2** (a) and (b). Over the small angle range from 0.2° to 5°, three notable peaks were assigned to (100), (110) and (200) crystal faces, which revealed the hexagonal structure in both SBA-15 and SBA-15@Co₃O₄. Interestingly, SBA-15 and SBA-15@Co₃O₄ possessed the identical 2 theta angle in terms of the three peaks, which illuminated the identical crystal face spacing, i.e. 12.3nm, 7.4nm and 6.4nm respectively based on the Braggs' Equation.

Fig.3-2 XRD spectra of SBA-15 and SBA-15@Co₃O₄ (a) at the small angle and (b) at the wide angle

In addition, SBA-15@Co₃O₄ possessed extra peaks over the wide angle from 10° to 70°, which was due to the incorporation of heterogeneous substances. The new peaks were assigned to the crystal faces (110), (220), (311), (400), (422), (511) and (440) of the cubic spinel Co₃O₄ based on the standard card of Co₃O₄ (JCPDS card No.42-1462) [309]. Moreover, the crystal face spacing

(0.23nm) of (311) showed slightly different trend with non-confined Co_3O_4 , which was indicative of the confined crystal growth in mesopores.

TEM and EDS analysis

TEM and EDS analysis were exhibited in **Fig.3-3** In **Fig.3-3** (a) and (b), SBA-15 and $\text{SBA-15@Co}_3\text{O}_4$ both revealed rod-like geometry, which was consistent with SEM result (not shown here). In **Fig.3-3** (c) and (d), the regularly hexagonal mesopores were presented in SBA-15 and $\text{SBA-15@Co}_3\text{O}_4$ with approximate pore size 10nm, which was in good consistence with N_2 sorption result (**Table 3-1**). In terms of $\text{SBA-15@Co}_3\text{O}_4$, Co_3O_4 was homogeneously aligned on SBA-15 interior walls with ultrafine nano-scale size (2-5nm) (red circle in **Fig.3-3** (e)).

Fig.3-3 TEM observations of (a,c) SBA-15, (b,d) $\text{SBA-15@Co}_3\text{O}_4$ in different magnifications and (e) high magnification TEM image of $\text{SBA-15@Co}_3\text{O}_4$ with marked Co_3O_4 ultrafine nanoparticles and model $\text{SBA-15@Co}_3\text{O}_4$; EDS spectra of (f) SBA-15 and (g) $\text{SBA-15@Co}_3\text{O}_4$ with the inset mapping results and atomic percentage

EDS analysis (**Fig.3-3** (f)) showed that SBA-15 contained two elements (Si and O), while $\text{SBA-15@Co}_3\text{O}_4$ possessed the additional element cobalt (Co). Co element (bright dots) was

aligned preferentially along the pore direction in SBA-15@Co₃O₄ with the cobalt atomic percentage was 1.0%. The results indicated that Co₃O₄ nanoparticles were judiciously located along SBA-15 interior walls, which was due to the alternative treatment of Co²⁺ diffusion and microwave radiation in terms of SBA-15. The Co²⁺ diffusion supplied precursors and the microwave radiation promoted the transformation of precursors into Co(OH)₂.

Table 3-1 Parameters from N₂ adsorption and desorption of SBA-15 and SBA-15@Co₃O₄

Samples	Specific area (m ² /g)	pore size(nm)
SBA-15	605	9.8
SBA-15@Co ₃ O ₄	395	9.8

3.2.3 Preparation of HNT@MAH@DOPO

Preparation of maleic anhydride modified halloysite (HNT@MAH)[120]

The HNT modification was based on the reaction between hydroxyl groups on HNT surface and anhydride groups in MAH. In a typical procedure, 3g MAH and 17g HNT were charged into 500mL three-necked equipped with 200mL toluene. The modification reaction proceeded with vigorous magnetic stirring under the reflux condition for 24h. The white product labelled as HNT@MAH was obtained after washing with acetone several times and drying overnight. The schematic illustration was demonstrated in **Scheme 3-4**.

Preparation of HNT@MAH@DOPO [120]

The DOPO grafting reaction was based on the reaction between P-H groups in DOPO and double bonds in MAH molecules [310]. 10g DOPO was poured into the resultant HNT@MAH toluene suspension in 2.2 under the vigorous magnetic stirring and N₂ atmosphere. After the reaction for 24h, the product was collected after filtration and washing with ethanol for several times. Finally, the light-yellow powder labelled as DOPO@HNT@MAH was acquired after drying overnight. The specific illustration was exhibited in **Scheme 3-4**.

Scheme 3-4 Preparation route of HNT and its derivatives

3.2.4 Characterization of HNT@MAH@DOPO

FTIR spectra

FTIR spectra (**Fig.3-4** (a)) were employed to analyze the chemical reactions in HNT modifications. Notably, the peak located at 1038cm^{-1} , which was assigned to the stretching vibration of Si-O (HNT), was retained in HNT@MAH and HNT@MAH@DOPO. It illuminated that HNT component was not destroyed during the modification. Besides, the comparison of HNT and HNT@MAH spectra showed that -OH groups on the exterior surface (3424cm^{-1} , stretching vibration mode) of HNT vanished after MAH modification [311], which indicated that MAH modification occurred at the exterior surface. Meanwhile, the new peaks at 3552cm^{-1} (-OH in carboxyl group), 3067cm^{-1} (=C-H, stretching vibration), 1720cm^{-1} (carbonyl group) and 1448cm^{-1} (C-H bending vibration) appeared, which was due to the reaction between hydroxyl groups and anhydride groups. The sharp peak located at 3622cm^{-1} (interior hydroxyls on the surfaces) became slightly weaker after MAH modification relative to the peak at 3703cm^{-1} , which evidenced the occurrence of the reaction between interior hydroxyls and anhydrides. Conclusively, the MAH grafting modification occurred on both interior and exterior surface.

The analysis of HNT@MAH, HNT@MAH@DOPO and DOPO illustrated that the new peak at 2940cm^{-1} (C-H stretching vibration, $-\text{CH}_2-$) emerged in contrast to NHT@DOPO. The peak of 2385cm^{-1} (P-H) in DOPO structure totally vanished, which manifested the reaction between P-H and double bonds. Comparatively, 1584cm^{-1} (P-Ph) and 1191cm^{-1} (P=O) in DOPO molecules was kept in HNT@MAH@DOPO, which indicated the presence of the DOPO structure. Conclusively, HNT@MAH@DOPO was successfully synthesized through the successive reaction between HNT,

MAH and DOPO [312].

XRD spectra

XRD spectra (**Fig.3-4 (b)**) were employed to investigate the crystalline of HNT and its derivatives. In terms of HNT, the peaks at 2 theta of 11.7° and 24.7° were respectively attributed to the (001) and (002) crystal faces, which were corresponding to 7.1 Å and 3.6 Å based on the Braggs' equations. After the MAH modification, no visible change was detected, which indicated that MAH reaction with the hydroxyls did not destroy the crystalline structure of halloysite nanotubes. In parallel, after the incorporation of DOPO structure into HNT@MAH, the peak locations of the main crystal faces (001) and (002) remained invariable, which demonstrated the main lamellar structure was kept well in HNT@MAH@DOPO. Besides, two tiny peaks emerged at around 5°, which was attributed to the partial intercalation of halloysite lamellar structure [296]. Actually, in consideration of the fact that no peaks emerged at around 5° in terms of HNT@MAH, it was obtained that MAH@DOPO structure rather than merely MAH structure was able to intercalate halloysite. In addition, two peaks located at around 15° emerged compared to HNT@MAH were present, which belonged to free DOPO crystalline. It indicated that some free DOPO crystalline existed in the halloysite nanotubes. Conclusively, HNT@MAH@DOPO kept the similar crystalline structure to NHT, with exception to some intercalated halloysite lamellar structure by MAH@DOPO. Some free DOPO crystalline were present in halloysite nanotubes.

Fig.3-4 (a) FTIR spectra and (b) XRD spectra of HNT, HNT@MAH, HNT@MAH @DOPO and DOPO

TEM observation

TEM images of HNT and HNT derivations at different magnifications were revealed in **Fig.3-5**. In

detail, HNT exhibited notable nanotube structure, with microscale length and nanoscale diameter in **Fig.3-5 (a)**. Meanwhile, the diffraction dots in the inset SAED patterns reflected the lamellar crystalline structure, which was in consistent with XRD result. Comparatively, the MAH modification of HNT did not change the morphology of HNT and SAED patterns (**Fig.3-5 (c)**). In parallel, after the incorporation of DOPO, the morphology and the main SAED patterns of HNT@MAH@DOPO remained nearly unchanged. Surprisingly, the intercalated HNT structure was slightly detected in **Fig. 3-5 (e)** due to the enlargement of the lamellar spacing relative to HNT@MAH.

Fig.3-5 TEM images with inset SAED patterns of (a) HNT, (c) HNT@MAH and (e) HNT@MAH@DOPO; EDS of (b) Si mapping of HNT, (d) C mapping of HNT@MAH and (f) P mapping of HNT@MAH@DOPO

EDS of HNT and its derivatives were carried out in **Fig.3-5**. From EDS spectra (not showed here), HNT was composed of Al, Si and O elements, with atomic ratio of 1:1:4.6., which was in good agreement with the structural formula of $\text{Al}_2\text{Si}_2\text{O}_5(\text{OH})_4 \cdot n\text{H}_2\text{O}$. Regarding HNT@MAH, C element was dispersed homogeneously on HNT surface, which manifested the existence of MAH molecules in HNT@MAH. In parallel, in terms of HNT@MAH@DOPO, P element attributed to DOPO structure was stably attached in HNT, which indicated that DOPO structure was also present along HNT nanotubes. Meanwhile, the element quantification demonstrated the P atomic percentage in Si, Al and P elements was 2.5%.

XPS analysis

XPS analysis was further employed to investigate the reactions between HNT, MAH and DOPO structure. In **Fig.3-6** (a), HNT@MAH possessed Al 2p, Si 2p, Al 2s and Si 2s peaks, which were attributed to HNT. C1s and O1s peaks evidenced the presence of MAH in HNT@MAH. In comparison, the extra P2p and P2s peaks indicated that DOPO molecules existed in HNT@MAH@DOPO (consistent with EDS result), accompanied by the increase of peak intensity ratio of C1s to O1s. In parallel, in C 1s spectra (**Fig.3-6** (b)) of HNT@MAH, the peaks at 289.7eV, 285.7eV, 284.9eV and 284.2eV were assigned to O-C=O, C-O, C=C of exterior grafting MAH and C=C of interior grafting MAH respectively [111, 313]. After grafting of DOPO molecules, C1s spectra (**Fig.3-6** (c)) exhibited the peaks at 284.5eV and 285.3 eV, which were attributed to C-C-P of the interior and exterior grafting MAH. Meanwhile, P2p spectra (**Fig.3-6** (d)) possessed the peaks at 134.1eV, 133.5eV and 132.9 eV assigned to P=O covalently connected to the exterior, interior wall and free DOPO [314], which further evidenced that DOPO structure existed in the different locations of HNT.

Fig.3-6 (a) XPS spectra of HNT@MAH and HNT@MAH@DOPO; (b) C1s spectra of HNT@MAH; (c) C1s spectra of HNT@MAH@DOPO; (d) P2p spectra of HNT@MAH@DOPO

TG analysis

The thermal degradation investigation results of DOPO, HNT, HNT@MAH, HNT@MAH-DOPO and HNT@MAH@DOPO were shown in **Fig.3-7**. In **Fig.3-7 (a)**, HNT, HNT@MAH, HNT@MAH-DOPO and HNT@MAH@DOPO both exhibited the onset degradation temperature ($T_{5wt\%}$) higher than 200°C, which evidenced their thermal stability during the mechanical processing. Meanwhile, the residue yield of HNT, HNT@MAH and HNT@MAH@DOPO at 600°C followed the sequence: HNT>HNT@MAH>HNT@MAH@DOPO, which reflected the successful incorporation of MAH and DOPO in HNT. Similarly, HNT@MAH@DOPO demonstrated higher $T_{10wt\%}$ (318°C) than that (245°C) of HNT@MAH-DOPO, which was due to the carbonization capacity of the chemical grafting DOPO.

In order to further confirm the approximate content of DOPO in HNT@MAH@DOPO, the assumption was made that the DOPO structure was totally degraded (or/and evaporated) and released during heating. Moreover, the volatiles were predominantly DOPO molecules. The calculation formula was as follows:

$$w_{DOPO} = \frac{1 - \frac{y_{HNT@MAH@DOPO}}{y_{HNT@MAH}}}{1 - \frac{y_{DOPO}}{y_{HNT@MAH}}} \quad (3-1)$$

Where w_{DOPO} , $y_{HNT@MAH@DOPO}$, $y_{HNT@MAH}$, y_{DOPO} , $y_{HNT@MAH}$ were respectively marked as DOPO weight percentage in HNT@MAH@DOPO, residue yield of HNT@MAH, DOPO and HNT@MAH at 600°C. Finally, DOPO weight percentage was calculated as 16%. Based on the calculated DOPO weight percentage of 16%, HNT@MAH-DOPO was prepared via the direct physical addition of 84% HNT@MAH and 16% DOPO.

Apart from it, the DTG curves demonstrated some interesting phenomenon. In **Fig.3-7 (b)**, DOPO and HNT@MAH possessed only one degradation (and/or evaporation) stage with the temperature at maximum degradation rate (T_m) 258°C and 485°C respectively. As for the direct physical addition of HNT@MAH and DOPO (HNT@MAH-DOPO), distinct two peaks at 258°C and 485°C emerged, which were separately attributed to DOPO and HNT@MAH degradation (and/or evaporation) process. Moreover, it also indicated that direct addition of DOPO and HNT@MAH did not generate the detectable interaction between them during thermal degradation. Very attractively, HNT@MAH@DOPO exhibited a multi-step thermal degradation process with

T_m at 194°C, 336°C, 479°C and 593°C. Actually, the peak at 479°C was assigned to thermal degradation of HNT and the peaks at 194°C, 336°C and 593°C were all attributed to the thermal degradation (and/or evaporation) of DOPO related components, including free DOPO, HNT grafted DOPO and MAH@DOPO (corresponding to DOPO locations in HNT@MAH@DOPO showed in XRD and XPS analysis).

Fig.3-7 (a) TG curves and (b) DTG curves of DOPO and HNT derivatives

TG-MS

Aiming to further evidence the temperature-controllable slow-release behavior of DOPO and DOPO derivatives, TG-MS of HNT@MAH@DOPO was carried out in **Fig. 3-8**. In **Fig.3-8** (a) and (b), phosphorous-containing fragments (PO_2 and HPO_2) emerged at roughly 100°C, 219°C, 328°C, 461°C and 619°C, which were suitably corresponding to peaks of DTG curve of HNT@MAH@DOPO. Reasonably, the PO_2 and HPO_2 fragments were originated from DOPO and DOPO derivatives (**Fig.3-8** (d)). The PO structure was not detected due to the limited lifespan and concentration, which propelled the conversion to other PO derivatives. Theoretically, $PO\cdot$ was present, which probably reacted with $\cdot O$ and $OH\cdot$ to generate PO_2 and HPO_2 .

The investigation of $m/z=76$ (**Fig.3-8** (c)) demonstrated that the degraded products contained different amount of benzene structures. The sustainable and sequential release of benzene, PO_2 and HPO_2 revealed the different locations of DOPO and DOPO derivations in HNT, which was consistent with FTIR, XRD and XPS results. The degradation sequence probably followed the order of free DOPO, DOPO derivatives grafted on HNT exterior wall, DOPO derivations intercalated in HNT and DOPO derivatives grafted on HNT interior wall with the increasing temperature. Conclusively, in combination with TG-MS and DTG curves, HNT@MAH@DOPO demonstrated a step-wise slow-release behavior of fire-retardant components (**Scheme 3-5**), which

was able to promote improvement of flame inhibition based on the aforementioned analysis.

Fig.3-8 Evolution of the m/z values of (a) 63, (b) 64 and (c) 76; (d) schematic illustration of degraded fragments

Scheme 3-5 Slow-release behavior of DOPO and its derivatives of HNT@MAH@DOPO

3.2.5 Preparation of composites

Preparation of PS/Ferrocene composites

The fractions of 1wt% and 3wt% ferrocene were blended with PS to prepare PS/1Ferrocene and PS/3Ferrocene, respectively using the micro-compounder at the temperature of 220 °C collectively for 2min. The reference sample pristine PS was also fabricated with the identical procedure. Afterwards, the obtained strips were made to sheets for CCT and smoke production.

Preparation of PS/SBA-15 and PS/SBA-15@Co₃O₄ composites

PS with SBA-15 and SBA-15@Co₃O₄ were prepared via melt blending at 220 °C for 3 min using micro-compounder. Based on this condition, series of PS composites were prepared, including neat PS, PS composites with 2wt% fractions of SBA-15 and SBA-15@Co₃O₄ with the respective labels as PS, PS/2SBA-15 and PS/2SBA-15@Co₃O₄. Subsequently, these PS composites were further hot-pressed into sheets with different dimensions for the corresponding tests.

Fabrication of PLA composites with HNT and its derivatives

5% weight fraction of HNT, HNT@MAH and HNT@MAH@DOPO was melt blended with PLA matrix for 2min at the temperature of 165°C with rotation rate of 100 rpm to obtain the products labelled as PLA/5HNT, PLA/5HNT@MAH and PLA/5HNT@MAH@DOPO respectively. According to the identical rule, the neat PLA and PLA composites with 3wt% and 7wt% HNT@MAH@DOPO were also prepared and labelled as PLA, PLA/3HNT@MAH@DOPO and PLA/7HNT@MAH@DOPO correspondingly. PLA composite with 5wt% simple mixture of HNT@MAH and DOPO was fabricated in the identical way with the label as PLA/5HNT@MAH-DOPO. Subsequently, the resultant products were hot-pressed into different samples for the following measurements.

3.3 Property and mechanism of composites

The investigation of property and mechanism was mainly associated with ignition behavior and ignition mechanism. It was emphasized that herein and hereafter the ignition mechanism was concentrated on ignition-delaying mechanism with the preference of investigation of impact of fillers on ignition behavior. Ignition delaying was defined as the difference of the ignition behavior of neat polymer and polymer composites (and/or nanocomposites). Apart from it, the analysis of ignition-delaying mechanism was focused on the three fundamental aspects of fire occurrence (volatiles, temperature and oxygen). The volatile study included the volatile species and volatile concentration, which was impacted by the thermal degradation and/or thermal-oxidation degradation of polymer composites (nanocomposites). The temperature study was stressed on the top-surface temperature with the influence of phase change, reaction heat and gasification.

Mechanism investigation was carried out, which was divided into three levels i.e., molecule level, structure level and macroscopic level. In detail, the temperature of top surface and volatile

profile above surface of samples were directly correlated to ignition time (t_{ig}). Temperature profile was correlated with ρ , c and k value, which were determined by the composition and dispersion state of polymer composites. The dispersion state was determined by the property of polymer matrix and nanofillers. In parallel, the volatile profile of specimen (in consideration of sample size) was determined by the thermal-oxidation degradation of polymer composites and the vertical temperature distribution. The thermal-oxidation degradation was mainly determined by chemical composition and structure of nanofillers and other additives. The ignition temperature (T_{ig}) was determined by the volatile profile (volatile concentration and volatile species), oxygen concentration and gasification profile (the constant value in the identical system). The assumption was made. The aforementioned analysis was based on the fact that the melt viscosity of polymer composites played a neglectable effect on the ignition [96]. In other word, the upward and downward movement of polymer melt due to bubble movement was neglectable. Herein, the dominant indicators were picked out as thermal inertia (ρck) and volatile profiles. In order to weaken the impact of other factors, the comparative experiments were elaborately designed.

3.3.1 PS/Ferrocene composites

a) Ignition behavior of PS/Ferrocene composites

Ignition time

The heat release rate (HRR) and weight percentage of PS, PS/1Ferrocene and PS/3Ferrocene at the ignition stage were exhibited in **Fig.3-9** (a) and (b) respectively with heat flux of 25kW/m². In theory, the ignition occurred at critical mass loss rate (MLR) and HRR of 1-6 g·s⁻¹·m⁻² and 20-100kW/m² respectively according to the definition of ignition as the complete flaming [164]. The transfer point from plateau zone of HRR and MLR was selected as the ignition for consistency, which probably presented the end of intensive thermal-oxidation degradation and beginning of small flashes. In detail, the addition of 1wt% and 3wt% ferrocene delayed t_{ig} value to 104±2 s and 112±2 s from 95±2 s of neat PS separately. In order to investigate the mechanism for delayed ignition, the heating process of the top surface and thermal degradation behavior were studied according to the analysis in **Section 3-1**.

Fig. 3-9 (a) HRR curves and (b) weight profile at ignition stage of PS, PS/1Ferrocene and PS/3Ferrocene

Ignition temperature

The surface temperature was illustrated in **Fig.3-10** (a). Neat PS underwent the melting process between roughly 225s and 255s and the ignition behavior at 262°C. In parallel, PS/3Ferrocene possessed similar melting process to that of PS but different heating process between roughly 275s and 375s with T_{ig} of 350°C. In consideration of the direct relationship between heating process and the physical parameters (ρ , c and k), the similar melting process indicated the neglectable impact of ferrocene on ρ , c and k . Notably, the temperature-rising process between roughly 275s and 375s did not result in the ignition, which was considered to be associated with the change of chemical parameters (volatile species and volatile concentration).

After careful analysis of the ignition behavior of PET, PP, PA6 and PLA [161, 167], the ignition temperature, volatile species, volatile concentration and gasification profile constituted the balanced system to determine ignition. In this system, the gasification profile played a weak role according to the continuous temperature-rising trend in **Fig.3-10** (a). The similar case was also detected in the PP system [167]. The molecular interpretation was considered to be relatively stronger C-C backbone of PS, which slowed down the thermal-oxidation process compared to C-O backbones of PET [161]. In parallel, the volatile concentration of PS/3Ferrocene was higher than that of PS in **Fig.3-11** (a) in combination of the prolonged degradation time (**Fig.3-10** (a)). The increased T_{ig} was predictively focused on the change of the volatile species. Based on the previous study by Linteris [302-304], the flame inhibition (or radicals quenching) of ferrocene derivatives was considered to be responsible for the heating process. The temperature of top surface kept rising at the stage of radicals quenching due to the limited gasification. When the radicals of

$H\cdot$ and $OH\cdot$ were generated from thermal-oxidation degradation of volatiles, the radicals from ferrocene terminated $H\cdot$ and $OH\cdot$. In order to evidence the reaction, the degraded products from PS/3Ferrocene were analyzed by TG and TG-MS.

In order to confirm the heating rate in TG and TG-MS, the heating rate of top surface was investigated. The derivation of temperature curves generated the temperature rising curves of PS and PS/3Ferrocene (**Fig.3-10** (b)), which revealed that the temperature-rising rate reached ca. $360^{\circ}\text{C}/\text{min}$. In order to utmost simulate the ignition behavior, the heating rate of $40^{\circ}\text{C}/\text{min}$ were selected for TG at air atmosphere respectively. TG-MS at inert atmosphere was conducted at $10^{\circ}\text{C}/\text{min}$ for the qualitative consideration.

Fig.3-10 (a) Temperature profile at the top surface of PS and PS/3Ferrocene prior to ignition and (b) temperature-rising rate at the surface of PS and PS/3Ferrocene

b) Ignition mechanism of PS/Ferrocene composites

In **Fig.3-11** (a), the addition of ferrocene into PS resulted in the earlier initial thermal-oxidation degradation before 300°C , which was due to the low sublimation temperature (ca. 100°C) of ferrocene. The micro-bubbles from the sublimation of ferrocene was also reflected in the CCT sample at ignition (**Fig.3-11** (b) and (c)). The temperature gradient along the thickness direction gave rise to the partial sublimation to air and partial residue in PS melt of ferrocene. In **Fig.3-12** (a), the specie Fe atoms were present in a large amount, which was originated from the degradation of ferrocene. In combination of **Fig.3-11** (a) and **Fig.3-12**, ferrocene molecule in the composite PS/3Ferrocene moved outward prior to total conversion to Fe atoms. Meanwhile, FeO , FeOH , $\text{Fe}(\text{OH})_2$ and FeO_2 species were generated at the inert atmosphere presumably due to the reaction of Fe atoms and the oxygen-containing impurity. It was amazing that the thermal-oxidation degradation of ferrocene occurred at roughly 400°C , nevertheless the ignition

temperature of PS and PS/3Ferrocene were both lower than 350°C. Actually, the ferrocene molecules were degraded into Fe atoms at the air above samples, where the temperature was higher 400°C.

Fig.3-11 (a) TG analysis of PS and PS/3Ferrocene at air at 40°C/min; (b) digital image of PS at ignition; (c) digital image of PS/3Ferrocene at ignition

Fig.3-12 Evolution of (a) Fe, FeO, FeOH, Fe(OH)₂ and FeO₂ and (b) FeH and ferrocene

When TG-MS results were applied in the realistic flaming zone, Fe atoms were generated from ferrocene molecules. H $\cdot$ and OH $\cdot$ radicals were obtained via thermal-oxidation degradation from PS chain and styrene molecules at the flaming zone. Fe radicals resultantly quenched H $\cdot$ and OH $\cdot$ radicals with the inhibition of ignition (**Scheme 3-6**) [315].

Scheme 3-6 (a) Schematic illustration of pre-ignition of PS/Ferrocene; (b) The radical reaction prior to ignition; (c) The proposed reaction route to consume $\text{H}\cdot$ and $\text{OH}\cdot$ [315]

3.3.2 PS/SBA@ Co_3O_4 composites

a) Ignition behavior of PS/SBA@ Co_3O_4 composites

Ignition time

The ignition time from HRR curves (**Fig.3-13** (a)) and mass profile (**Fig.3-13** (b)) demonstrated that the ignition time (t_{ig}) of PS/2SBA-15 and PS/2SBA-15@ Co_3O_4 were respectively $106\pm 1\text{s}$ and $116\pm 2\text{s}$ compared to $98\pm 1\text{s}$ of neat PS at 25kW/m^2 . The incorporation of 2wt% SBA-15 did not change the t_{ig} value of PS while the modification of SBA-15 with ultrafine Co_3O_4 remarkably delayed t_{ig} . Moreover, PS composites with 1wt% SBA-15 ($104\pm 1\text{s}$) and SBA-15@ Co_3O_4 ($112\pm 2\text{s}$) presented the identical trend of t_{ig} compared with pristine PS. The result illustrated that SBA-15 and SBA-15@ Co_3O_4 possessed the positive effect on delaying ignition. The hierarchical decoration of ultrafine Co_3O_4 on the interior wall of SBA-15 demonstrated the critical role of pores in delaying ignition.

Fig.3-13 Ignition time reflected by (a) HRR and (b) mass profile

Ignition temperature

Top-surface temperature acted as the bridge to link t_{ig} value and the structure of composites (dispersion of fillers and intrinsic structure of fillers). In **Fig.3-14** (a), the temperature measurement was not carried out in terms of PS/2SBA-15 in consideration of the almost identical physical property of SBA-15 and SBA-15@Co₃O₄. The physical property-related process (ρck) of PS/2SBA-15 was nearly identical to that of PS/2SBA-15@Co₃O₄. Addition of 2wt% SBA-15@Co₃O₄ did not notably influence the temperature-rising rate but the plateau temperature relative to neat PS (**Fig.3-14** (a)). The plateau temperature between 225s and 275s of PS/2SBA-15@Co₃O₄ was approximately 50°C higher than that of PS/2SBA-15, which reflected that the melt temperature turned higher with mesoporous material. Notably, the ignition temperature (T_{ig}) of PS and PS/2SBA-15@Co₃O₄ were 262°C and 343°C respectively. Herein, PS and PS composites were located between thermally thin and thermally thick with the preference of thermally thick attribute. According to Equation (1-10), the increased T_{ig} resulted in the longer t_{ig} without the notable change of their parameters. Meanwhile, the deeper investigation of causes in molecule level for the higher T_{ig} was required.

Fig.3-14 Top-surface temperature of PS and PS/2SBA-15@Co₃O₄ prior to ignition at 25kW/m²

b) Ignition mechanism of PS/SBA@Co₃O₄ composites

The ignition mechanism was analyzed from physical and chemical aspects. The physical parameters (ρk) of PS/2SBA-15@Co₃O₄ did not alter notably in comparison to that of PS, which indicated the weak influence of the physical parameters on ignition delaying. The exception was the increase of the plateau temperature, which nevertheless presented no impact on the ignition-delaying behavior. The mechanism investigation of the chemical aspect was concentrated on the analysis of volatile concentration and volatile species. The volatiles concentration and species were determined by the condensed-phase behavior. Herein, TG, TG-FTIR and TG-MS were performed to investigate the volatile profile. Based on the volatile profile, the mesoscopic scale behavior was obtained in terms of PLA and SBA-15 derivatives.

TG analysis

The higher T_{ig} values were considered to be affected by the gasification effect, volatile concentration and oxygen concentration. After eliminating the factors of oxygen concentration and gasification effect (weak), the volatile concentration was considered to be the dominant factor. In terms of ignition behavior, the degradation of surface polymers belonged to the combination of thermal degradation and thermal-oxidation degradation with the preference of thermal-oxidation particularly in terms of thermoplastic polymers. Thermoplastic polymers possessed higher flowing capacity upward and downward prior to ignition, which was able to inhale more air. Herein, the top-surface temperature-rising rate was roughly 360°C/min, which determined that the normal temperature-rising rate in TG was much less. The heating rate of 10°C/min was selected as the representative value.

In **Fig.3-15** and **Table 3-2**, the thermal degradation at N₂ and air atmosphere was compared. The T_{ig} value of PS and PS composites was located less than T_{max} , which determined the importance of investigation of thermal and thermal-oxidation stability ($T_{5wt\%}$ and T_{max}). In **Fig.3-15** (a), the addition of 2wt% SBA-15 and SBA-15@Co₃O₄ enhanced $T_{5wt\%}$ by 11°C and 28°C correspondingly. In DTG curves (**Fig.3-15** (c)), the incorporation of 2wt% SBA-15 into PS increased T_{max} by 6°C while in terms of PS/2SBA-15@Co₃O₄, the increase value was around 27°C. In parallel in **Fig.3-15** (b), the incorporation of 2wt% SBA-15 and SBA-15@Co₃O₄ increased $T_{5wt\%}$ from 307°C of neat PS to 318°C and 338°C respectively. In DTG curve (**Fig.3-15** (d)), T_{max}

of PS/2SBA-15@Co₃O₄ (428°C) was magnificently higher than those of PS (392°C) and PS/2SBA-15 (401°C). As the temperature rose from 250°C to 428°C (**Fig.3-15** (d)), the degradation rate increased more slowly than those of PS and PS/2SBA-15, which indicated that SBA-15@Co₃O₄ was more beneficial than that of SBA-15 in enhancing initial thermal-oxidation stability.

According to above analysis of thermal (**Fig.3-15** (b)) and thermal-oxidation stability (**Fig.3-15** (d)), in order to achieve the volatile concentration for corresponding ignition temperature (PS/2SBA-15@Co₃O₄, 343°C and PS, 262°C), PS/2SBA-15@Co₃O₄ spent more time than neat PS and PS/2SBA-15 to degrade PLA matrix. Resultantly, ignition behavior of PS/2SBA-15@Co₃O₄ was notably delayed relative to neat PS and PS/2SBA-15. The analysis process was associated with the thermal-oxidation degradation of PLA without consideration of size effect 1) thermal-oxidation degradation occurred along the thickness direction 2) temperature varied along the thickness direction. Actually, the thermal-oxidation degradation along the thickness direction was considered to self-resemble that in TG analysis.

Fig.3-15 (a) and (c) TG and DTG curves at 10°C/min at N₂ atmosphere; (b) and (d) TG and DTG curves at 10°C/min at air atmosphere of PS, PS/2SBA-15 and PS/2SBA-15@Co₃O₄

Table 3-2 Thermal degradation data of PS, PS/2SBA-15 and PS/2SBA-15@Co₃O₄ at 10°C/min

Samples	N ₂		Air	
	T _{5wt%} (°C)	T _{max} (°C)	T _{5wt%} (°C)	T _{max} (°C)
PS	372	416	307	392
PS/2SBA-15	383	422	318	401
PS/2SBA-15@Co ₃ O ₄	400	443	338	428

T_{5wt%}: Temperature at the mass loss of 5% T_{max}: Temperature at the maximum degradation rate

TG-FTIR analysis

TG-FTIR analysis was employed to analyze the volatile profile, mainly focusing on the amount and evolution time of major volatiles. In consideration of the similar case of delayed release of volatiles at N₂ and air atmosphere, the mechanism for the delayed release was investigated at the inert atmosphere at 10°C/min. In 3D profile (**Fig.3-16**), the absorbance intensity of volatiles of PS/2SBA-15@Co₃O₄ was lower than those of neat PS and PS/2SBA-15. More importantly, the main peaks of PS/2SBA-15@Co₃O₄ emerged at the later time, which indicated the delayed and reduced volatile release. The whole absorbance and selected volatile evolution were exhibited in **Fig.3-17**. Clearly, the predominant combustible gaseous components (-CH₃ compounds, -CH₂- compounds, aromatic compounds, double bond compounds) showed significant differences between PS, PS/2SBA-15 and PS/2SBA-15@Co₃O₄. However, the volatile species did not alter with addition of SBA-15 and SBA-15@Co₃O₄. Four combustible components of PS/2SBA-15@Co₃O₄ were released at the notably later time than those of PS and PS/2SBA-15, resultantly giving rise to the later time at the maximum release rate. Similarly, PS/2SBA-15 released volatiles with the later time at maximum degradation rate than that of neat PS. The main combustible gaseous components were released at increasing time in the sequence: PS/2SBA-15@Co₃O₄>PS/2SBA-15>PS. Resultantly, PS/2SBA-15@Co₃O₄ possessed more time to reach the critical volatile concentration for ignition compared with neat PS and PS/2SBA-15. The result partially supported the *t_{ig}* values sequence: PS/2SBA-15@Co₃O₄>PS/2SBA-15>PS, which indicated the important effect of mesopores and ultrafine Co₃O₄ nanoparticles decorating mesopores. In consideration of longer *t_{ig}* and weak gasification capacity of PS, PS/2SBA-15@Co₃O₄ possessed higher ignition temperature.

Fig.3-16 3D graphics of (a) PS, (b) PS/2SBA-15 and (c) PS/2SBA-15@Co₃O₄

Fig.3-17 Combustible gaseous evolution ((a) whole intensity, (b) -CH₃ compounds, (c) -CH₂- compounds, (d) aromatic compounds and (e) double bond containing compounds) of PS, PS/2SBA-15 and PS/2SBA-15@Co₃O₄

The investigation of the maximum release rate of combustible gases revealed some interesting results as well (**Fig.3-17**). As for -CH₃ compounds, the maximum release rate of PS/2SBA-15 was magnificently lower than that of PS/2SBA-15@Co₃O₄ (ca.140% reduction). On the contrary, as for the -CH₂- compounds, PS/2SBA-15@Co₃O₄ and PS/2SBA-15 had nearly identical maximum release rate. The comparison of PS/2SBA-15 and PS/2SBA-15@Co₃O₄ evidenced that Co₃O₄ promoted the transformation toward preferential yield of -CH₃ compounds rather than -CH₂- compounds. The probable cause was due to the longer time for the isomerization reaction with the volatiles

entering the mesopores and then released outward. In parallel, regarding aromatic and double-bond containing compounds, PS/2SBA-15@Co₃O₄ and PS/2SBA-15 showed nearly identical maximum release rate, which was magnificently lower than that of pure PS. The result indicated SBA-15 decreased the maximum release rate of aromatic and double-bond containing compounds. In parallel, Co₃O₄ showed no remarkable influence in decreasing the maximum release rate, but had a positive effect in prolonging the time to maximum release rate. Co₃O₄ favored the slower release of aromatic and double-bond compounds.

TG-MS analysis

More detailed investigation of the mesoscopic scale mechanism for delayed t_{ig} was carried out via TG-MS analysis (**Fig.3-18**). Results revealed that the main pyrolyzed products of PS composites with SBA-15 and SBA-15@Co₃O₄ remained unchanged relative to neat PS (identical degraded fragments). Meanwhile, the peak intensity of degraded fragments ($m/z=27, 38, 78, 91, 104$ and 118) changed in a non-monotonic manner, which manifested that the incorporation of SBA-15 and SBA-15@Co₃O₄ re-adjusted the decomposition reaction directions. In order to obtain the specific profile of fragment ions, fragment peaks ($m/z=104, 78, 40$ and 27) were chosen to analyze their intensity profile versus time (**Fig.3-19**). Clearly, the main pyrolyzed products (and fragments) of PS/2SBA-15 and PS/2SBA-15@Co₃O₄ were released into gas phase more slowly than that of PS. Moreover, PS/2SBA-15@Co₃O₄ occupied the slowest release, which was strongly consistent with the delayed ignition behavior, accompanied by TG-FTIR result.

Fig.3-18 The main gaseous decomposed fragments of PS, PS/2SBA-15 and PS/2SBA-15@Co₃O₄

Fig.3-19 The evolution of main decomposed gaseous fragments with the corresponding structure PS/2SBA-15 and PS/2SBA-15@Co₃O₄

In order to further investigate the reason why the main pyrolyzed products (and main pyrolyzed fragments) showed the slow-release behavior, the deep analysis was carried out. In the previous studies [299], it was reported that the volatiles entered the mesopores during pyrolysis. Herein, the benzyl fragment ($m/z=91$) was focused to certify the similar behavior (**Fig.3-20**). It was noted that benzyl fragment was the result of the hemolytic cleavage of benzyl dimer under the high-energy ion beam [316] (**Scheme 3-7** (a)). Herein, the benzyl fragment ion of PS/2SBA-15@Co₃O₄ showed significantly increased ion intensity and slower release than those of PS and PS/2SBA-15. Moreover, the benzyl fragment ion intensity from PS/2SBA-15 was slightly higher than that of PS, accompanied by the slower release. Therefore, it was evidenced that benzyl dimer entered SBA-15 mesopores initially and then was released into the vapor phase in the form of benzyl radical (so-called labyrinth effect). These released gaseous products subsequently underwent the combustion process and/or carbonization process [316]. Conclusively, SBA-15 had slightly strong adsorption function of the evolved products. In contrast, the incorporation of Co₃O₄ into interior walls remarkably enhanced the adsorption performance.

Fig.3-20 Evolution of the ion fragments ($m/z=91$ and 118)

Scheme 3-7 (a) Benzyl radicals from the hemolytic cleavage of benzyl dimer and (b) degradation route to produce isopropenyl benzene structure ($m/z=118$)

In addition to the ion fragment ($m/z=91$), the ion fragment isopropenyl benzene ($m/z=118$) also followed the similar rule. In detail, the intensity of isopropenyl benzene from PS/2SBA-15@Co₃O₄ was magnificently higher than those of PS and PS/2SBA-15. The isopropenyl benzene structure was the result of the tertiary carbon structure, which originated from the isomerization of primary carbon structure of PS fragmental chains (**Scheme 3-7** (b)). The increased production of isopropenyl benzene structure ($m/z=118$) indicated that the isomerization process was more intensive due to the mesopore effect, which was another direct evidence for adsorption-desorption-combustion process. Meanwhile, the re-adaption of the decomposition reaction also occurred with the preferential yield of more isopropenyl benzene structure, which was consistent with TG-FTIR results about -CH₃ compounds production. Similarly, the major volatiles underwent the same adsorption-desorption-combustion process. The reason why ultrafine Co₃O₄ nanoparticles in the mesopores remarkably increased the adsorption capacity was possibly originated from the complexation interaction of Co derivatives and benzene ring structure [317, 318]. Resultantly, the longer “walking” distance of the pyrolyzed components along the mesopore increased the time to reach the critical gaseous concentration for ignition behavior.

Ignition mechanism toward delayed ignition

The ignition mechanism toward delayed ignition was investigated in the physical factors and chemical factors. The similar heating rate of top surface indicated the absence of contribution of physical factors (ρck). The mechanism investigation was accordingly put on chemical factors (the change of volatile species and concentration) and the subsequent intensive radical reaction (ignition). The change of chemical factors was stressed on the relationship in the mesoscopic scale between nanostructure and ignition behavior (**Scheme 3-8**).

Prior to ignition of PS/SBA-15@Co₃O₄, PS was thermally decomposed into main styrene (**Fig.3-18**). Most of degraded products entered the mesopores of SBA-15 and were then released outward. Ultrafine Co₃O₄ nanoparticles on the interior wall of SBA-15 favored the adsorption and prolonged the desorption process, which resulted in the slow-release behavior of volatiles. The possible interaction between Co derivatives and benzene ring structure accounted for the enhanced adsorption and prolonged release (**Scheme 3-8** (c)). Resultantly, the longer time was spent to reach the critical concentrations, which was accompanied by the increase of ignition temperature. The main styrene located above the top surface underwent intensive pyrolysis reaction with the generation of H· and OH·. The ignition occurred at the interface between air and top surface at the critical temperature and concentration of H· and OH· (**Scheme 3-8** (b)).

Scheme 3-8 (a) Heating process of PS/SBA-15@Co₃O₄; (b) radical reaction during ignition; (c) adsorption-desorption process of volatiles

b) Fire Retardancy of PS/SBA@Co₃O₄ composites

Cone calorimeter test (CCT)

CCT result was shown in **Fig.3-21** and **Table 3-3**. In **Fig.3-21** (a), pHRR values of PS/2SBA-15 and PS/2SBA-15@Co₃O₄ showed the reduction of 15.0% and 24.1% compared with pristine PS correspondingly. Average HRR (AHRR) defined the combustion intensity and fire hazard. Herein, AHRR values at 120s of pristine PS, PS/2SBA-15 and PS/2SBA-15@Co₃O₄ were 407±12 kW/m², 261±11 kW/m² and 164±7 kW/m², respectively, which illuminated that the incorporation of SBA-15 and SBA-15@Co₃O₄ significantly decreased the combustion intensity and fire hazard of PS at the first 120s. Furthermore, Co₃O₄ incorporation imparted PS/2SBA-15 with lower pHRR and AHRR values, which manifested the important effect of Co₃O₄ nanoparticles. Similarly, AHRR values at 180s of three samples demonstrated an identical trend.

Fig.3-21 (a) HRR, (b) THR, (c) TSP and (d) weight curves of PS and PS composites

Apart from it, the fire growth rate index (FIGRA) was used to assess the fire growth situation, which was defined as the pHRR divided by the time at pHRR [319]. Herein, PS, PS/2SBA-15 and PS/2SBA-15@Co₃O₄ possessed FIGRA values of 3.6 kW/(m²·s), 2.4kW/(m²·s) and 2.0kW/(m²·s) correspondingly, which indicated that SBA-15@Co₃O₄ had the best performance in restricting fire growth. Actually, THR values of PS, PS/2SBA-15 and PS/2SBA-15@Co₃O₄ did not show

significant difference at the late stage. However, at the early stage (before 200s), PS, PS/2SBA-15 and PS/2SBA-15@Co₃O₄ possessed the THR values of 42MJ/m², 18MJ/m² and 8MJ/m², which revealed the significant distinction with the lowest THR of PS/2SBA-15@Co₃O₄.

Table 3-3 CCT data of PS, PS/2SBA-15 and PS/2SBA-15@Co₃O₄ (25kW/m²)

	t_{ig} (s)	pHRR (kW/m ²)	AHRR at 120s(kW/m ²)	AHRR at 180s(kW/m ²)	THR (MJ/m ²)	TSP (m ²)	FIGRA (kW/(m ² .s))	Residue yield (%)
PS	98±1	623±14	407±12	337±11	89±3	27±1.1	3.6	0.1±0.1
PS/2SBA-15	106±1	534±15	261±11	318±10	92±2	27±0.5	2.4	8.1±0.1
PS/2SBA-15@Co ₃ O ₄	116±2	477±13	164±7	250±8	86±3	23±0.9	2.0	10.2±0.2

t_{ig} : Time to ignition pHRR: Peak heat release rate AHRR at 120s and 180s: Average heat release rate over 120s and 180s

THR: Total heat release TSP: Total smoke production FIGRA: Fire growth index

d) Fire-retardant mechanism of PS/SBA@Co₃O₄ composites

The vapor-phase fire-retardant mechanism was absent as the radical-quenching effect and cooling effect did not exist. The mechanism investigation was accordingly transferred to condensed-phase mechanism.

Condensed-phase mechanism

The digital images (**Fig.3-22**) illustrated that the incorporation of SBA-15 and SBA-15@Co₃O₄ yielded slightly higher-quality char than that of PS, which was consistent with the result in mass percentage (**Fig.3-21** (d)). The slightly higher-quality char enabled to shield the underlying polymers from the attack of heat and oxygen, which favored fire retardancy.

Fig.3-22 Residue after CCT of (a) PS, (b) PS/2SBA-15 and (c) PS/2SBA-15@Co₃O₄

In parallel, the condensed-phase adsorption-desorption process resulted in the alteration in vapor-phase behavior. The concentration reduction of main degraded products was closely

correlated to suppressed fire intensity. TG-MS was employed to analyze the peak intensity of main degraded products (fragments). Actually, the peak intensity of main fragments ($m/z=104$, styrene; $m/z=78$, benzene ring; $m/z=27$, ethylene fragment) demonstrated the trend of $\text{PS}/\text{SBA-15}@Co_3O_4 < \text{PS}/\text{SBA-15} < \text{PS}$ due to the adsorption-desorption-combustion.

Fig.3-23 XRD results of residue from $\text{PS}/\text{SBA-15}@Co_3O_4$ at (a) small angles and (b) high angles

Scheme 3-9 Proposed mechanism for improved fire retardancy

The reason why the peak concentration of the main flammable components (fragments) was reduced was considered from two aspects. On one side, the longer release time of volatiles definitely resulted in the lower values of the maximum concentration. On the other side, the catalytic carbonization of the PS under the assistance of Co_3O_4 nanoparticles contributed to the partial reduction. It was noted that there were enormous naked Co_3O_4 nanoparticles well dispersed on the mouths of mesopores, which showed intensive catalytic carbonization effect for PS matrix [320, 321]. Even, some carbonization behavior occurred in the mesopores, which was proved by

the remarkable enlargement of the pore size after combustion of PS/2SBA-15@Co₃O₄ (**Fig.3-23**).

Finally, the schematic illustration of the integral mechanism was presented in **Scheme 3-9**.

e) Tensile strength of PS/SBA@Co₃O₄ composites

The tensile behavior was demonstrated in **Fig.3-24** and **Table 3-4**. Overall, PS composites with SBA-15 and SBA-15@Co₃O₄ possessed higher tensile strength and elongation at break than neat PS. The increased tensile strength and elongation at break were probably related with the “locking” effect between PS molecular chain and mouths of SBA-15@Co₃O₄ and uniform dispersion of fillers. In **Fig.3-25** (a) and (c), SBA-15 microparticles were dispersed well in PS matrix without aggregation via SEM and EDS. Co₃O₄ incorporation into SBA-15 did not change the dispersion state (**Fig.3-25** (b) and (d)). Meanwhile, the tensile strength (25.1±2.1 MPa) and elongation at break (1.6±0.2 %) of PS/2SBA-15@Co₃O₄ were higher than those of PS/2SBA-15 (19.4±1.8 MPa and 1.4±0.1 %), which indicated that Co₃O₄ promoted the “locking” effect. Interestingly, the tensile modulus after addition of 2wt% SBA-15 and SBA-15@Co₃O₄ was higher than that of neat PS. The probable reason was also due to the “locking” effect of between PS and mesoporous materials.

In order to further understand the “locking” behaviour, the simplified mode was used in **Fig.3-24** (b). According to Equation (3-2), after incorporation of SBA-15@Co₃O₄, stress σ was applied on both additives and interfaces between matrix and additives. Considering the probable “locking” effect to transfer stress, the tensile strength was supposed to increase. Apart from it, the underlying area in the stress-strain curve was used to assess the toughness of composites. Notably, the increase of underlying area of PS/2SBA-15@Co₃O₄ elucidated that the rubbery SBA-15@Co₃O₄ released internal stress and dissipated the energy of PS, resulting in less cracks during extension.

$$\sigma = \frac{F}{S}$$

(3-2)

Fig.3-24 (a) Tensile behaviour of PS, PS/2SBA-15 and PS/2SBA-15@Co₃O₄ (b) stress analysis of PS/2SBA-15@ Co₃O₄ (F : force; $F_{interface}$: the force at the interface; F_{PS} : force applied on PS phase; $F_{fillers}$: the force at the fillers; S : transverse size)

Table 3-4 Tensile data of PS, PS/2SBA-15 and PS/2SBA-15@Co₃O₄

Samples	Tensile Strength (MPa)	Tensile Modulus (MPa)	Elongation at break (%)
PS	10.3±0.3	2060±35	0.8±0.1
PS/2SBA-15	19.4±1.8	2100±66	1.4±0.1
PS/2SBA-15@Co ₃ O ₄	25.1±2.1	2070±38	1.6±0.2

Fig.3-25 SEM image of cryo-fractured surface of (a) PS/2SBA-15 and (b) PS/2SBA-15@Co₃O₄; EDS spectra of selected point from (a) PS/2SBA-15 and (b) PS/2SBA-15@Co₃O₄

3.3.3 PLA/HNT@MAH@DOPO composites

a) Ignition behavior

Ignition time

The t_{ig} values of PLA, PLA/5HNT, PLA/5HNT@MAH, PLA/5HNT@MAH@DOPO and PLA/5HNT@MAH-DOPO were respectively $60\pm 2s$, $60\pm 1s$, $63\pm 1s$, $75\pm 1s$ and $60\pm 2s$ at $35kW/m^2$ with PLA/5HNT@MAH@DOPO the most delayed ignition (**Fig.3-26** (a)). The addition of 5wt% HNT, HNT@MAH and HNT@MAH-DOPO did not change the t_{ig} value notably, which was the integral result of thermal-oxidation degradation and temperature-rising behavior of top surface. The addition of HNT@MAH-DOPO and HNT@MAH@DOPO separately delayed the t_{ig} value of 0s and 15s compared with that of neat PLA. Normally, the incorporation of flame-inhibition agent (DOPO) was capable to delay the ignition of polymers. The different addition ways of direct and slow-release mode resulted in remarkable t_{ig} difference of 15s. In order to unveil the mask, the first-level investigation was carried out from the top-surface temperature and thermal-oxidation degradation behavior of PLA, PLA/5HNT@MAH-DOPO and PLA/5HNT@MAH@DOPO. It was noted that the analysis of the top-surface temperature was accompanied by the analysis of physical parameters (ρ , c and k). Thermal-oxidation degradation behavior was correlated with the chemical parameters (catalysis *etc.*). The second-level investigation was conducted from the thermal degradation of fillers (HNT@MAH@DOPO and HNT@MAH-DOPO). The third-level investigation was to establish the relationship between thermal degradation behavior and nanostructure of HNT@MAH@DOPO and HNT@MAH-DOPO.

Fig.3-26 (a) HRR versus time at the ignition and (b) top-surface temperature of PLA and PLA composites prior to ignition

Ignition temperature

The top-surface temperature of PLA, PLA/5HNT@MAH-DOPO and PLA/5HNT@MAH@DOPO were selected and exhibited in **Fig.3-26** (b). The derivation of top-surface surface indicated that the peak temperature-rising rate was roughly $600^{\circ}C/min$ in

Fig.3-27 (a). Actually, the available heating rate at TG and DSC was far away from the actual value. The heating rate was selected as 10°C/min and 40°C/min to utmost simulate the ignition in TG analysis. The heating rate of 10°C/min was employed in DSC for the qualitative consideration. In detail, the heating process of PLA and PLA composites (**Fig.3-27** (b)) underwent the cold crystallization and melt stage at roughly 180°C, which was not notably reflected in **Fig.3-26** (b) due to the relatively lower crystalline degree (χ_c) and melt heat of PLA compared to that of PET. Furthermore, the heating process proceeded with the surface temperature reaching the ignition temperature (331°C), which was located above (close to) the initial thermal-oxidation degradation temperature and below the maximum thermal-oxidation degradation temperature (for both 10°C/min and 40°C/min) (**Fig.3-28** and **Table 3-5**). The analysis of thermal-oxidation degradation behavior manifested that the $T_{5wt\%}$ and T_{max} difference of different samples were approximately 20°C and 50°C at 10°C/min and 40°C/min correspondingly. Therefore, the heating rate of 40°C/min was selected to analyze the temperature profile at the top surface.

The addition of HNT@MAH-DOPO and HNT@MAH@DOPO slightly increased the temperature-rising rate (**Fig.3-27** (a)) between 250s and 300s due to probably due to the decreased thermal inertia (ρck). Between 300s and 320s (**Fig.3-26** (b)), the top-surface temperature decreased for PLA/5HNT@MAH@DOPO and remained for PLA/5HNT@MAH-DOPO. The decreased and remained temperature between 300s and 320s was considered to originate from thermal-oxidation stability (**Fig.3-28** and **Table 3-5**). The increased thermal-oxidation stability slowed down gasification process, which carried away less heat from the top surface. Meanwhile, The flame-inhibition effect to eliminate $H\cdot$ and $OH\cdot$ radicals was considered to be another factor PLA/5HNT@MAH@DOPO presented lower top-surface temperature than PLA/5HNT@MAH-DOPO between 300s and 320s, which indicated that the flame-inhibition effect in PLA/5HNT@MAH@DOPO was stronger than that of PLA/5HNT@MAH-DOPO.

Notably, PLA and PLA composite samples were inclined to be thermally thick, which determined the utilization of Equation (1-10) to predict the alteration of ignition. The physical parameter (thermal inertia, ρck) was increased with addition of HNT@MAH@DOPO. In consideration of flame inhibition, the critical heat flux (Q_{cri}) was considered to increase from the chemical aspects (chemical composition and concentration of volatiles). In combination of the physical and chemical aspects, the ignition was delayed accordingly after addition of

HNT@MAH@DOPO. In parallel, the addition of HNT@MAH-DOPO did not generate notable flame-inhibition effect.

Fig.3-27 (a) Temperature-rising rate at the top surface of PLA and PLA/5HNT@HNT@MAH@DOPO and (b) DSC curves at the heating process of PLA and PLA composites

b) Ignition mechanism of PLA/HNT@MAH@DOPO composites

TG analysis

Similar to the case in PS, the gasification heat played a weak role in stabilizing the top surface according to the temperature-rising trend. The effect of gasification heat to stabilize the surface temperature turned stronger at the higher temperature. The T_{ig} value of PLA, PLA/5HNT@MAH-DOPO and PLA/5HNT@MAH@DOPO were collectively 331°C, which was the integral result of volatile species, volatile concentration and the limited gasification. According to previous study [161], the thermoplastic PET and PET/MMT illustrated the almost constant ignition temperature of 417°C at 25kW/m². The underlying mechanism was the intensive gasification heat from degraded products of PET, which carried away the extra heat. After excluding the factors of limited gasification heat, the volatile species and concentration were analyzed. In **Fig.3-28** (c) and (d), the mass loss at T_{ig} was nearly the same in terms of PLA, PLA/5HNT@MAH-DOPO and PLA/5HNT@MAH@DOPO, which indicated that the volatile concentration of these three systems were almost identical.

Table 3-5 TG results of PLA and PLA composites at 10°C/min and 40°C/min at air atmosphere

	10°C/min		40°C/min	
	$T_{5wt\%}(^{\circ}\text{C})$	$T_{\max}(^{\circ}\text{C})$	$T_{5wt\%}(^{\circ}\text{C})$	$T_{\max}(^{\circ}\text{C})$
PLA	316	364	338	390
PLA/5HNT	306	358	332	382
PLA/5HNT@MAH	310	358	338	389
PLA/5HNT@MAH@DOPO	320	363	342	394
PLA/5HNT@MAH-DOPO	320	363	339	392

$T_{5wt\%}$: temperature at 5% mass loss $T_{\max}$: temperature at maximum degradation rate

Fig.3-28 (a) TG and (b) DTG curves at 10°C/min at air atmosphere of PLA and PLA composites; (c) TG and (d) DTG curves at 40°C/min at air atmosphere of PLA and PLA composites

In **Fig.3-26** (b), PLA/5HNT@MAH@DOPO possessed the long-time retention at ca. 331°C between roughly 305°C and 335°C, which increased the volatile concentration remarkably compared to PLA and PLA/5HNT@MAH-DOPO. The comparison of volatile concentration at identical T_{ig} revealed that the PLA/5HNT@MAH@DOPO was supposed to possess stronger flame-inhibition capacity than PLA/5HNT@MAH-DOPO. Therefore, the T_{ig} value was capable to stabilize at 331°C in combination of the increased gasification of PLA/5HNT@MAH@DOPO. In parallel, PLA/5HNT@MAH-DOPO illustrated slightly stronger flame-inhibition than that of

PLA due to the terminal plateau of the temperature. In combination of flame inhibition and slightly increased gasification, PLA/5HNT@MAH-DOPO was capable to stabilize at 331°C. It was stressed that the flame-inhibition effect determined the delaying of ignition, which further influenced the gasification process. Therefore, the flame inhibition was the key factor to incite the delayed t_{ig} and constant T_{ig} . Apart from it, the slight drop of the top-surface temperature was due to the over-saturation of flame-inhibition agents.

The relationship between slow-release and delayed ignition

The relationship between slow-release behavior of flame-inhibition agent and higher-efficient delaying of ignition (or higher-efficient flame inhibition) was investigated in **Fig.3-29**.

Fig.3-29 (a) DTG curves of PLA, PLA/5HNT@MAH@DOPO and PLA/5HNT@MAH@DOPO and (b) simplified feeding of DOPO and DOPO derivatives

In **Fig.3-29** (a), the peaks of HNT@MAH@DOPO were much wider than those of HNT@MAH-DOPO, which indicated that the release of DOPO and DOPO derivatives covered wider temperature range. Prior to ignition (331°C), three peaks of HNT@MAH@DOPO located at 100°C, 194°C and 336°C covered the temperature range of 280°C. In contrast, merely one peak of HNT@MAH-DOPO at 285°C possessed the temperature range of 110°C, which was much less than that of HNT@MAH@DOPO. The remarkably wider slow-release process generated the higher concentration of DOPO and DOPO derivatives, which then were converted into $PO\cdot$ and $HPO\cdot$ (**Fig.3-8**). Two aspects were considered 1) non-confined concentration attenuation of DOPO and DOPO derivatives were significantly weakened in the open space due to the sustainable slow-release behavior and 2) a relatively smaller amount of DOPO and DOPO derivatives did not

decrease the concentration of flame-inhibition agent relative to PLA/5HNT@MAH-DOPO.

The mechanism to delay ignition

The mechanism to delay ignition was associated with slow-release of flame-inhibition agent ($\text{PO}\cdot$) and the molecule-level radical quenching effect toward $\text{H}\cdot$ and $\text{OH}\cdot$. The specific schematic illustration was presented in **Scheme 3-10**. **Scheme 3-10** (a) presented the generation of volatiles under the heat flux, which subsequently underwent radical degradation with the formation of $\text{H}\cdot$ and $\text{OH}\cdot$ (**Scheme 3-10** (b)). Ignition behavior occurred with the critical concentration of $\text{H}\cdot$ and $\text{OH}\cdot$ and temperature. The incorporation of $\text{PO}\cdot$ radicals inhibited the circular reaction of $\text{H}\cdot$ and $\text{OH}\cdot$, which functioned in delaying ignition (**Scheme 3-10** (d)). In contrast, the enhanced concentration of $\text{PO}\cdot$ radicals from sustainable release behavior in HNT@MAH@DOPO (**Scheme 3-10** (c)) enabled the stronger quenching effect of $\text{H}\cdot$ and $\text{OH}\cdot$. Therefore, the ignition behavior was delayed.

Scheme 3-10 (a) Schematic illustration of pre-ignition of PLA/HNT@MAH@DOPO; (b) radical reaction of degraded products of PLA prior to ignition; (c) slow-release mode of

phosphorous-containing components and (d) radical-quenching process of $H\cdot$ and $OH\cdot$ [322]

c) Fire retardancy of PLA/HNT@MAH@DOPO composites

Integral fire behavior was studied via LOI, UL-94 (3.2mm), (MCC) and cone calorimeter test (CCT, 35kW/m²) at different scales.

LOI and UL-94 vertical burning test

LOI and UL-94 result were showed in **Fig.3-30** (a) and **Table 3-6**. PLA exhibited UL-94 vertical burning rating V-2 with LOI value 24.7%, accompanied by serious dripping occurrence. PLA composites with 3wt%, 5wt% and 7wt% HNT@MAH@DOPO exhibited UL-94 ratings of V-2, V-0 and V-0 separately. In principle, 5wt% HNT@MAH@DOPO was selected as the critical loading to investigate fire retardancy. 5wt% HNT and HNT@MAH imparted PLA with increased LOI values of 28.2% and 28.3% respectively and also with V-2 in UL-94 vertical burning test. Comparatively, PLA/5wt% HNT@MAH@DOPO possessed the LOI value of 38.0%, higher than those of PLA, PLA/5HNT and PLA/5HNT@MAH by 13.3%, 9.8% and 9.7% respectively. Meanwhile, PLA/5HNT@MAH@DOPO passed V-0 with dripping that did not ignite the underlying cotton. In contrast, PLA/5HNT@MAH-DOPO with direct addition of HNT@MAH and DOPO had LOI value of 30.8% with UL-94 V-0, accompanied by more serious dripping. The tremendous LOI enhancement of PLA/5HNT@MAH@DOPO compared to PLA/5HNT@MAH-DOPO illuminated that chemical grafting DOPO possessed remarkably better performance than the direct addition. Moreover, the less serious dripping behavior of PLA/5HNT@MAH@DOPO was probably attributed to the weaker thermal and/or thermal-oxidation degradation compared to that of PLA/5HNT@MAH-DOPO (**Fig.3-28**), giving rise to lower melt viscosity. Considering the slow-release behavior of DOPO derivatives in HNT@MAH@DOPO, the enhancement of LOI and UL-94 ratings was considered to be closely correlated to the sustainable slow-release behavior.

CCT

CCT was the measuring method reflecting the realistic fire situation best. The result was illustrated in **Fig.3-30** and **Table 3-6**. In **Fig.3-30** (b) and (c), the addition of 5wt% HNT and HNT@MAH did not change HRR and THR curves of PLA notably. 5wt% HTN@MAH-DOPO changed HRR curve of PLA/5HNT@MAH slightly with HRR values after 82s less than that of

PLA/5HNT@MAH, which demonstrated the occurrence of vapor phase effect of DOPO. Actually, pHRR and THR difference (4.0% and 1.7% reduction respectively) between PLA/5HNT@MAH and PLA/5HNT@MAH-DOPO were still very tiny, which illuminated unsatisfactory fire-retardant efficiency of DOPO in PLA/5HNT@MAH.

Fig.3-30 (a) LOI and UL-94 results (b) HRR, (c) THR and (d) TSP of PLA and PLA

Comparatively, 5wt% HNT@MAH@DOPO obviously decreased pHRR and THR values by 17% and 12% separately compared to PLA/5HNT@MAH, which illustrated that grafting DOPO gave rise to better fire-retardant efficiency with respect to direct physical addition. In addition, 5wt% HNT and HNT@MAH did not affect TSP in **Fig.3-30** (d), which was due to weak charring capacity of PLA (**Table 3-6**). Comparatively, the addition of 5wt% HNT@MAH@DOPO and HNT@MAH-DOPO significantly increased TSP by 65% and 57% respectively, which was due to the presence of vapor phase mechanism. Reasonably, the $\text{PO}\cdot$ radicals were able to capture hydrogen atoms on the main chains of degraded products, resulting in the unsaturated structure formation and TSP increase [323].

Table 3-6 CCT, LOI and UL-94 results of PLA and PLA composites

	t_{ig} (s)	pHRR (kW/m ²)	THR (MJ/m ²)	TSP (m ²)	Residue yield (%)	LOI (%)	UL-94 test		
							t ₁ (s)	t ₂ (s)	Dripping
PLA	60±2	397±11	57±3	0.23±0.01	3.9±0.4	24.7	5	0	Yes ^a
PLA/5HNT	61±1	368±9	55±2	0.23±0.01	7.6±0.9	28.2	6	0	Yes ^a
PLA/5HNT@MAH	63±1	386±12	59±3	0.21±0.01	7.7±0.8	28.3	7	0	Yes ^a
PLA/5HNT@MAH@DOPO	75±5	317±6	52±2	0.38±0.03	7.8±0.7	38.0	0	0	Yes
PLA/5HNT@MAH-DOPO	60±2	370±8	58±3	0.36±0.03	6.7±0.6	30.8	1	0	Yes

t_{ig} : time to ignition pHRR: peak heat release rate THR: total heat release TSP: total smoke production t₁: average time after first 10s flaming t₂: average time after first 10s flaming a: cotton ignited by dripping

d) Fire-retardant mechanism of PLA/HNT@MAH@DOPO composites

The fire-retardant mechanism was investigated by clarifying 1) fire-retardant mechanism of PLA/5HNT@MAH-DOPO compared to pure PLA 2) fire-retardant mechanism of PLA/5HNT@MAH@DOPO compared to PLA/5HNT@MAH-DOPO. Generally, fire-retardant behavior was analyzed from vapor-phase mechanism and condensed-phase mechanism. Vapor-phase mechanism was associated with the radicals-quenching effect and cooling effect of moisture. Halogenated radicals (Br· and Cl·), PO· radicals and Fe atoms consumed the H· and OH· radicals, which reduced the average efficient heat of combustion (av-EHC). Av-EHC was defined as the value of total heat release (THR) divided by total mass loss (TML). In parallel, condensed-phase mechanism was involved in the formation of mechanically robust carbonaceous layer to shield the heat and oxygen. The insightful mechanism of condensed-phase mechanism was detailed from stationary char analysis and dynamic charring reaction. The stationary char analysis included 1) appearance of carbonaceous layer (digital images, SEM, TEM and XCT *etc.*) 2) degree of ordered char (XRD and Raman spectra *etc.*) 3) chemical composition (FTIR and solid NMR *etc.*). The dynamic charring reaction covered the in-situ charring reactions (vt-FTIR, TG-GC-MS and TG-MS *etc.*) and the gas-phase results (TG-FTIR).

Vapor-phase mechanism

The vapor-phase fire-retardant mechanism presented the similarities to vapor-phase mechanism of delayed ignition in thermal degradation of PLA matrix, the thermal-oxidation degradation of

degraded products of PLA matrix in air above the samples surface and the radicals-quenching effects. The differences were located in that ignition behavior occurred prior to fire behavior. Primarily, the PLA macromolecules were pyrolyzed into H_2O , CO , CO_2 , methylketene, acetaldehyde (main components) and cyclic oligomer via the non-radical (major reaction to generate acetaldehyde) and radical degradation route (major reaction to converse oligomer to CO and CO_2) (**Scheme 3-11**) [322]. The major pyrolyzed products (acetaldehyde and oligomer) subsequently entered the vapor phase and underwent the high-temperature radical pyrolysis (combustion). The $H\cdot$ and $OH\cdot$ radicals acted as the key effect in combustion.

Scheme 3-11 Main non-radical and radical route to thermally decompose PLA

Fig.3-31 Average efficient heat of combustion (av-EHC) versus time

The nanohybrid HNT@MAH@DOPO in PLA composites was thermally decomposed to generate the $PO\cdot$ radicals (**Fig.3-8**). Compared to that of neat PLA, the volatile species of PLA/5HNT@MAH@DOPO changed with generation of $PO\cdot$ radicals [324], which inhibited the flame (**Scheme 3-10** (d)) and reduced the average efficient combustion heat (av-EHC) (**Fig.3-31**). Notably, PLA/5HNT@MAH-DOPO presented the nearly unchanged av-EHC value relative to

PLA, which manifested that the direct of DOPO component played a neglectable effect on flame-inhibition effect. The slow-release addition via nanohybrid (HNT@MAH@DOPO) possessed the higher flame-inhibition efficiency than that of direct addition (HNT@MAH-DOPO).

Condensed-phase mechanism

The condensed-phase mechanism was investigated via the digital images of chars and the comparative analysis of CCT and MCC data (**Fig.3-32**). The investigation showed that the incorporation of HNT and HNT derivatives yielded the char compared with no char of PLA. The char morphology exhibited undetected difference with lighter color in PLA/5HNT@MAH-DOPO and PLA/5HNT@MAH@DOPO compared with those of PLA/5HNT and PLA/5HNT@MAH. The color change was possibly attributed to the effect of DOPO that participated in the charring reaction and/or the impact of flame-inhibition. The comparative study of CCT and MCC data was utilized to indirectly reflect the condensed-phase behavior. Herein, the R_1 and R_2 were separately defined as the ratio of pHRR of PLA composites to neat PLA in MCC and CCT [325]. As the barrier effect was notable in CCT but not in MCC due to the size effect, R_1 exceeded R_2 in the condensed-phase fire-retardant system. In **Fig.3-32** (g), the dots of PLA composites were located at the green area, which indicated that the barrier effect was present.

$$R_1 = \frac{pHRR_{MCC}}{pHRR(pure)_{MCC}} \quad (3.3)$$

$$R_2 = \frac{pHRR_{CCT}}{pHRR(pure)_{CCT}} \quad (3.4)$$

The condensed-phase mechanism (*e.g.*, charring effect and barrier effect) directly resulted in reduction of evolved volatiles, which was investigated by TG-FTIR. The main components of volatiles of PLA and its composites included aliphatic compounds (2840cm^{-1}), carbonyl compounds (1720cm^{-1}), CO_2 (2360cm^{-1}) and CO (2180cm^{-1}) *etc.* (**Fig.3-33** (a)). In order to exclusively investigate the evolution of individual volatile, the whole intensity, carbonyl compounds, aliphatic compounds and CO were selected. In **Fig.3-33** (b) and (c), 5wt% HNT@MAH@DOPO did not affect the peak value of whole intensity while increased the time to peak intensity, which indicated that HNT@MAH@DOPO delayed the PLA degradation. Meanwhile, the integral curve of whole intensity demonstrated that PLA/5HNT@MAH@DOPO

possessed lower integral value (1.6 a.u.min) than that (2.0 a.u.min) of PLA, which indicated that the volatiles amount were reduced slightly after incorporation of HNT@MAH@DOPO. Aliphatic compounds demonstrated the identical trend to whole intensity, which revealed slightly less amounts of volatiles to fuel the combustion (Fig.3-33 (d) and (e)). Based on the above assessment, the total amount of volatiles and the amount of aliphatic compounds were reduced slightly.

Fig.3-32 Digital images of char from (a) PLA, (b) PLA/5HNT, (c) PLA/5HNT@MAH, (d) PLA/5HNT@MAH-DOPO and (e) PLA/5HNT@MAH@DOPO; (f) HRR curves in MCC of PLA and PLA composites; (g) R_2 versus R_1

Fig.3-33 (a) FTIR spectra of PLA and PLA/5HNT@MAH@DOPO; evolution of (b) whole intensity and (d) aliphatic compounds; integral values of (c) whole intensity and (e) aliphatic

compounds

Relationship between slow-release and high-efficiency fire retardancy

Based on the above analysis, the following work was to establish the relationship between the slow-release behavior of DOPO derivatives and higher-efficiency fire retardancy. The similar idea was to understand the reason why the concentration of DOPO, DOPO derivatives and $\text{PO}\cdot$ radicals were higher in the slow-release state than the simple addition. Herein, the reasons were given in two aspects 1) the mismatch of thermal degradation temperature of PLA matrix and DOPO derivations 2) the attenuation of DOPO derivatives in the non-confined space. In **Fig.3-34** (a), compared to T_{max} (390°C) of PLA, HNT@MAH-DOPO possessed T_{max} value of 258°C (releasing DOPO), which was 132°C difference. In contrast, HNT@MAH@DOPO had T_{max} of 100°C , 194°C , 336°C , 479°C and 593°C , which covered the thermal-degradation range of PLA. In the heating process of polymer melt, DOPO evaporated prior to PLA as for HNT@MAH-DOPO but constantly evaporated as for HNT@MAH@DOPO (**Fig.3-34** (b)). In parallel, according to the attenuation analysis in non-confined space, the slow-release behavior generated the longer retention time of DOPO and DOPO derivatives compared to the normal and simple addition of DOPO. Resultantly, the higher concentration of $\text{PO}\cdot$ radicals were obtained, which consumed more $\text{H}\cdot$ and $\text{OH}\cdot$.

Fig.3-34 (a) DTG curves of PLA, HNT@PDA@DOPO and HNT@MAH-DOPO; (b) schematic illustration of combustion in CCT

To be conclusive, the relationship between the nanostructure of HNT derivative and the ignition behavior and fire behavior were established. The different locations of DOPO and DOPO derivatives resulted in the different thermal degradation temperatures (slow-release behavior). The PLA composites with the nanohybrid possessed the different concentrations of DOPO and DOPO

derivatives. In terms of the ignition, the stronger flame-inhibition gave rise to the longer stage of invariable temperature and longer ignition time. In terms of fire behavior, the stronger flame inhibition reduced the fire intensity.

CHAPTER 4

Smoke suppression via vapor and condensed-phase mechanism

“It is during our darkest moments that we must focus to see the lights”

-Aristotle

4.1 Introduction

Smoke production was accompanied by the combustion of most polymers, which posed great threats to fatality and environment. In order to investigate and understand smoke-suppression behavior, the vapor and condensed-phase mechanism were put forward. However, what happened in the vapor phase and condensed phase during smoke production was still unclear. Due to the requirement that the methodology of nano-technique was employed in the thesis, the pursuit of effective or highly efficient nanofillers for smoke suppression was on the road. Meanwhile, fire retardancy in terms of heat release was in the consideration. Notably, the fire retardancy and smoke suppression demonstrated the similar tendency in terms of condensed-phase mechanism. Based on the aforementioned three aims (*i.e.*, smoke suppression, fire retardancy and nanofillers), the systematic experiments were designed, including 1) ferrocene filled PS with the aim to understanding the vapor-phase smoke-suppression mechanism 2) ferrocene-included β -CD intercalated LDH to show the combination of condensed-phase and vapor-phase mechanism in EP matrix 3) ultrafine $\text{Ni}(\text{OH})_2$ engineering LDH nanosheets to investigate condensed-phase mechanism in EP matrix. It was noted that ferrocene filled PS did not belong to nano-technique, which was intended to exclusively study the vapor-phase smoke-suppression mechanism.

The organometallic ferrocene molecules were evidenced to be effective in smoke suppression of PVC and ABS [8, 261, 326]. In terms of ABS, the vapor-phase mechanism worked. In terms of PVC, the condensed-phase mechanism played the role. As for the vapor-phase mechanism, what we knew was that the iron derivatives entered the vapor phase. The mechanistic study was carried out in this chapter. In parallel, layered double hydroxide (LDH) was one kind of anion nanoclay with the positively charged nanosheets composed of metal hydroxide and negatively charged anions located in the gallery. LDH possessed the structural formula $[\text{M}^{2+}_{1-x}\text{M}^{3+}_x(\text{OH})_2]^{x+}$

$-A^{n-}_{x/n} \cdot yH_2O$, where M^{2+} and M^{3+} signified the divalent and trivalent metal cations correspondingly. A^{n-} was the intercalated anion for neutrally charged environment with the valence $-n$. x represented the stoichiometric coefficient of M^{3+} and y the content of the crystallized water [327, 328]. As one of the most important nanoclays, LDHs obtained the great applications in water treatment [298], medicine delivery [329, 330] and fire retardancy [331]. In order to improve smoke suppression of LDH-based polymer composites, the organic intercalation modification and surface decoration of LDH nanosheets were employed based on the formation of higher-quality char structure during combustion. The combination of the vapor-phase mechanism from ferrocene and the condensed-phase mechanism from LDH-based polymer composites was considered to favor smoke suppression. Meanwhile, ferrocene tended to evaporate at ca. 100°C, which was actually not suitable for the processing temperature. The low evaporation temperature was solved if the ferrocene molecules were incorporated into the gallery of LDH. Following the idea, the hydrophobic interaction of internal cavity of β -cyclodextrin (β -CD) and ferrocene was employed. The ferrocene molecules were included into the β -CD intercalated LDH to prepare bio-based nanohybrid LDH-CD@Ferr. EP composites with LDH-CD@Ferr suppressed smoke production in the condensed phase and vapor phase. In addition to the intercalation modification, the surface engineering of LDH nanosheets with nanocatalyst (*e.g.*, transition metal oxide and transition metal hydroxide) offered a viable approach to enhancing the charring behavior for smoke suppression. Herein, the electrostatic induced assembly of ultrafine nickel hydroxide ($Ni(OH)_2$) on dodecylbenzenesulfonate intercalated LDH (LDH-DBS) was performed to prepare the hierarchical nanohybrid LDH-DBS@ $Ni(OH)_2$. EP nanocomposites with LDH-DBS@ $Ni(OH)_2$ revealed the smoke suppression via the condensed-phase mechanism.

The following investigation of smoke-suppression mechanism was presented via the condensed-phase and vapor-phase analysis. Herein, the vapor-phase smoke suppression after the incorporation of ferrocene into polymers was associated with the intensive thermal-oxidation behavior of the soot (*i.e.*, intermediate of smoke) due to the iron derivatives. The mechanistic investigation of the intensive thermal-oxidation degradation was proposed. The condensed-phase smoke suppression was involved in the formation of protective carbonaceous layers, which inhibited the release of smoke precursors (polyaromatic compounds). The mechanistic study of condensed-phase process was performed.

4.2 Preparation and characterization of targeted nanohybrid

4.2.1 Preparation of LDH-CD@Ferr

Synthesis of sulfonate β -cyclodextrin (s-CD) [112, 332]

In a 100mL single-neck flask, 9.1g β -CD, 6g NaOH and 30mL H₂O were charged with the vigorous stirring. After β -CD was completely dissolved, 1,4-butane sultone (10.9g) was added dropwise at 60°C within 2h. The additional 4h was required for the adequate reaction prior to cooling down to ambient temperature. The pH value of the resultant solution was adjusted to 7 with HCl solution. The dialysis tube with MWCO of 1000 was employed to purify the product. Finally, the white solid product s-CD was obtained after rotary evaporation and overnight drying.

Preparation of s-CD intercalated LDH (LDH-CD)

The synthesis of LDH-CD was carried out using the precipitation method. 0.1M s-CD in 300mL H₂O was charged into the 1L three-neck flask facilitated with vigorous magnetic stirring and pH meter. After the complete dissolution of s-CD at 50°C, the aqueous solution of 0.2M Mg(NO₃)₂·6H₂O and 0.1M Al(NO₃)₃·9H₂O in 300mL H₂O was dropped into the system, accompanied by the drop-wise addition of 1M NaOH aqueous solution. The pH value was controlled at 10±0.2 via adjust of the drop of NaOH solution and metal ion solution. After the drop of metal solution finished, the stirring proceeded for another 30min prior to aging treatment at 60°C for 24h. The slurry products was obtained after filtration and washing several times with 80°C water and acetone. The air dry at 80°C was applied to acquire the dry product labelled as LDH-CD. The schematic illustration was demonstrated in **Scheme 4-1**.

Preparation of ferrocene included LDH-CD (LDH-CD@Ferr)

Ferrocene molecules were inserted into the hydrophobic internal cavity of s-CD via adsorption. 80mL mixed solution of methanol and water at weight ratio of 3:2 was charged into 100mL round-bottom flask prior to addition of 4 mM ferrocene with vigorous stirring. Subsequently, 5g dry LDH-CD was dispersed into the suspension with ultrasonication and vigorous stirring, after which the adsorption process persisted for additional 24h to guarantee the adequate adsorption. Afterwards, the suspension underwent filtration and washing with ethyl ether for several times. The dry red product (LDH-CD@Ferr) was acquired after overnight drying. The schematic illustration was in **Scheme 4-1**.

Scheme 4-1 Schematic illustration of precipitation and host-guest interaction

4.2.2 Characterization of LDH-CD@Ferr

¹H-NMR spectra

¹H-NMR spectra in **Fig.4-1** (a) was employed to confirm the sulfonating reaction of β -cyclodextrin (β -CD) [332]. The location at 4.8ppm was attributed to the proton (marked a) in the fundamental element (α -D-glucopyranose) of β -cyclodextrin. The multi-peaks at 1.6ppm were assigned to the protons marked in b and c, which indicated that the BS molecules were linked to α -D-glucopyranose successfully. Furthermore, the integral area ratio of b+c to a was 3.4, which demonstrated that roughly 6 BS molecules were grafted in one β -cyclodextrin.

Fig.4-1 (a) ¹H-NMR spectra of sulfonate β -cyclodextrin (β -CD) and (b) XRD patterns of LDH-CD, LDH-CD@Ferr and Ferr

XRD spectra

XRD patterns of ferrocene (Ferr), LDH-CD and LDH-CD@Ferr were revealed in **Fig.4-1** (b). Notably, LDH-CD had the reflections at 4.3° and 8.7° , which were attributed to crystal face (003) and (006) of lamellar structure respectively [332]. After the inclusion of Ferr into the internal cavity of sulfonated β -CD intercalated LDH, the crystalline structure was absent, which presented that the Ferr lost its crystallization capacity due to the confined space. Interestingly, the crystal faces (003) and (006) shifted to the lower 2 theta degree with 3.0° and 8.4° , which were notably lower than those of LDH-CD. According to Bragg's Equation, the (003) crystalline spacing (2.89nm) of LDH-CD@Ferr was 0.86nm higher than that (2.03nm) of LDH-CD, which indicated that the hydrophobic part became larger due to the incorporation of Ferr.

XPS spectra

XPS spectra (**Fig.4-2**) offered the information about the interaction of sulfonated β -CD and Ferr. **Fig.4-2** (a) revealed that LDH-CD@Ferr contained the extra Fe element in addition to Mg, Al, S, C and O element of LDH-CD. The comparison in the inset image of **Fig.4-2** (a) revealed that the overall C1s location of LDH-CD was slightly higher than that of LDH-CD@Ferr, which demonstrated that the incorporation of ferrocene molecules with low binding-energy of C1s. In terms of the C1s spectra (**Fig.4-2** (b)), LDH-CD possessed the fitted peaks at 284.7eV (C-C), 286.3 eV (C-O) and 288.0eV (O-C-O), which was in agreement with the structure of sulfonated α -D-glucopyranose [333]. In comparison, the extra peak at 284.3 eV (C-C, π conjugation) emerged in terms of LDH-CD@Ferr (**Fig.4-2** (c)), which was assigned to C1s (284.7eV) of ferrocene [334]. The decrease of C1s binding energy of LDH-CD@Ferr compared to neat ferrocene was due to the interaction of sulfonated β -CD and Ferr. In addition, the C1s (C-C, 284.9eV) of LDH-CD@Ferr was increased relative to LDH-CD, which indicated the weakening of electron cloud around C atoms in C-C bond. In contrast, the locations in C-O and O-C-O remained invariable, which indicated that the electron cloud of sulfonated β -CD was not affected. Notably from above assessment, the non-covalent hydrophobic interaction predominantly existed between ferrocene and C-C bond. In parallel, the Fe 2p spectra of LDH-CD@Ferr (**Fig.4-2** (d)) disclosed the partial shift of Fe2p_{3/2} and Fe2p_{1/2} toward lower binding energy, which indicated the strengthening of the electron cloud around Fe atoms [334]. Hence, it was concluded that the

interaction of ferrocene and sulfonated β -CD existed with the electron transfer from C-C of β -CD to ferrocene. In addition, the atomic ratio of S and Fe was 5.8, which indicated that one ferrocene molecule was inserted into the cyclodextrin cavity.

Fig.4-2 (a) Full spectra of LDH-CD and LDH-CD@Ferr; C1s spectra of (b) LDH-CD and (c) LDH-CD@Ferr; (d) Fe2p spectra of LDH-CD@Ferr

TEM observation

TEM observation of LDH-CD and LDH-CD@Ferr were revealed in **Fig.4-3**. In **Fig.4-3** (a) and (b), LDH-CD possessed the lamellar structure with folded and curled morphology, which indicated that the layered double hydroxide was successfully synthesized. The folded and curled morphology was originated from the confined crystallization process due to limited space. In combination of XRD result, the sulfonated β -cyclodextrin was intercalated into the LDH gallery. In parallel, the observation of LDH-CD@Ferr (**Fig.4-3** (c) and (d)) revealed that the lamellar structure from the LDH boundary was maintained without notable alteration in the lateral size. **Fig.4-3** (e) presented the distribution of S and Fe along LDH sheets, which revealed that the respective s-CD and Ferrocene were located in the LDH gallery. In combination of XRD and XPS result, the ferrocene molecules were included into the hydrophobic cavity of sulfonated cyclodextrin (s-CD) located in LDH gallery. The EDS spectra and atomic percentage in the inset

table disclosed that the atomic ratio of S and Fe was 5.5. In combination of ^1H -NMR result, approximately one ferrocene molecule was inserted into one s-CD, which was in good agreement with XPS result and the previous publication [112].

Fig.4-3 TEM images of (a), (b) LDH-CD and (c), (d) LDH-CD@Ferr at different magnifications; (f) EDS spectra with atomic percentage of LDH-CD@Ferr; (e) High-angle angular dark field (HAADF) with Mg, S and Fe mapping of LDH-CD@Ferr

TG analysis

The significant barrier during the utilization of ferrocene was low sublimation temperature, which determined the design of the proper ferrocene-based molecular structure. In **Fig.4-4** (a), compared to LDH-CD with the char yield of 48.7wt% at 600°C, LDH-CD@Ferr after complete purification possessed the char yield of 46.0% at 600°C, which indicated that the percentage of ferrocene was roughly 5.6% according to the numerical calculation at 600°C. The calculation was based on the assumption that the ferrocene component in LDH-CD@Ferr was totally evaporated. In parallel, **Fig.4-4** (a) and (b) revealed the significant mass loss at 117°C LDH-CD@Ferr before purification, which was attributed to the free ferrocene. After complete purification, the peak of free ferrocene was not detected, which demonstrated the complete removal of free ferrocene. In **Fig.4-4** (b), LDH-CD@Ferr exhibited a higher weight loss rate at 300°C after purification relative to that LDH-CD with nearly identical mass loss rate at ca. 400°C. The higher weight loss rate was originated from the included ferrocene component in LDH-CD. The TG result evidenced that

ferrocene component was released at a significantly increased evaporation temperature of ca. 300°C.

Fig.4-4 (a) TG and (b) DTG curves of LDH-CD, LDH-CD@Ferr before and after purification

4.2.3 Preparation of LDH-DBS@Ni(OH)₂

Co-precipitation of LDH-DBS

In one 1000 mL three-necked flask equipped with one pH meter, two drop funnels and one magnetic agitator, 10.45 g (0.1M) SDBS was dissolved into 300 mL deionized water to form homogenous aqueous solution at 50 °C. Concurrently, 15.38 g (0.2M) Mg(NO₃)₂·6H₂O and 11.25 g (0.1M) Al(NO₃)₃·9H₂O were dissolved into 300 mL deionized water completely. 300mL NaOH solution (1M) was also prepared. The resultant MgAl and NaOH solution were respectively charged into two drop funnels. The co-precipitation occurred when MgAl and NaOH solution were dropped to SDBS solution. pH value was strictly maintained at 10±0.2 via adjustment of drop rate of NaOH solution. After completion of MgAl solution, the reaction was kept for further 30 min, followed by the aging for 18 h at 75 °C. Then the slurry underwent the filtration and washing with 80 °C water. The final product (LDH-DBS) was acquired after drying overnight. The process was illustrated in **Scheme 4-2**. Basically, the DBS intercalated LDH were co-precipitated in the electrostatic mode based on the interplay between negatively-charged DBS and positively-charged nanosheets (**Scheme 4-2** (b)).

Surface-assembly of ultrafine Ni(OH)₂ nanoparticles on LDH nanosheets

14.5 g dry LDH-DBS was well dispersed in 700mL water with ultrasonication and then poured into 1000 mL single-necked flask with vigorous stirring. 12.5 g Ni(NO₃)₂·6H₂O, 3.7 g C₆H₅Na₃O₇·2H₂O and 12.0 g urea were charged afterwards. The reaction proceeded at 100 °C with persistent time of 7 h. The product (LDH-DBS@Ni(OH)₂) was collected after sequential filtration,

washing and drying overnight. The self-assembly procedure was illustrated in **Scheme 4-2**. In terms of the mechanism, after incorporation of Ni^{2+} and citrate ions, the coordination interaction of citrate and Ni^{2+} was formed with the electricity charged negatively. The oppositely charged electricity drove the gradient motion of coordination structure to adhere to positively charged LDH nanosheets (**Scheme 4-2** (c)). Subsequently, the OH^- groups from urea hydrolysis captured Ni^{2+} from citrate- Ni^{2+} coordination structure due to higher combination capacity, which gave rise to in-situ formation of $\text{Ni}(\text{OH})_2$ nanocrystal (**Scheme 4-2** (d)). The released citrate ions then participated in repetitive process of association-dissociation process, which was accompanied by the continuous nucleation of crystallization of $\text{Ni}(\text{OH})_2$. The controllable incorporation of Ni^{2+} and OH^- was considered to favor the formation of $\text{Ni}(\text{OH})_2$ toward more uniform and fine scale.

Scheme 4-2 Schematic illustration of LDH-DBS and LDH-DBS@Ni(OH)₂

4.2.4 Characterization of LDH-DBS@Ni(OH)₂

XRD and XPS analysis

XRD and XPS results were exhibited in **Fig.4-5**. Compared to LDH-DBS (**Fig.4-5** (a)), XRD pattern of LDH-DBS@Ni(OH)₂ at small angle (1°-10°) evidenced that the lamellar structure (2.98 nm in basal spacing) remained invariable during Ni(OH)₂ crystallization. In parallel, extra peaks at 19.1°, 37.3° and 63.8° emerged at high angle (10°-70°), which were respectively attributed to (001),

(011) and (111) of hexagonally structural β -Ni(OH)₂ (JCPDS card No.14-0117) [335]. XPS full spectra (**Fig.4-6** (c)) in combination of Ni 2p (**Fig.4-6** (d)) demonstrated that the binding energy at 857.1 eV and 874.8 eV (Ni 2p_{3/2} and Ni 2p_{1/2} respectively) with separation of 17.7eV was characteristic of Ni(OH)₂ phase, accompanied by the emergence of peaks (Mg 2s, Al 2p, S 2p, C1s and O1s *etc.*) from LDH-DBS [336, 337].

Fig.4-5 XRD patterns of LDH-DBS and LDH-DBS@Ni(OH)₂ at (a) 1°-10° and (b) 10°-70°; (c) full XPS spectra of LDH-DBS@Ni(OH)₂ and (d) Ni2p spectra of LDH-DBS@Ni(OH)₂

SEM and TEM analysis

TEM observation revealed that the lamellar structure of LDH-DBS@Ni(OH)₂ (**Fig.4-6** (b)) remained unchanged in comparison to LDH-DBS (**Fig.4-6** (a)). High-magnification image (**Fig.4-6** (c)) illustrated well-dispersed heterogeneous particles of about 2-4 nm (ultrafine scale) on LDH nanosheet relative to that of LDH-DBS (**Fig.4-6** (d)). Furthermore, EDS analysis with mapping (**Fig.4-6** (e), (f), (g), (h) and (i)) evidenced that heterogeneous particles contained Ni element which was uniformly dispersed on LDH sheet (Mg, Al, and S mapping) with Ni atomic percentage of roughly 5.2% (**Fig.4-6** (i)). SEM observation (**Fig.4-7** (a) and (b)) manifested that LDH-DBS@Ni(OH)₂ possessed similar surface morphology to LDH-DBS with the LDH lamellas stacked into the aggregates, which elucidated that the incorporation of ultrafine Ni(OH)₂ did not

influence the surface morphology.

Fig.4-6 TEM images of (a) (d) LDH-DBS and (b) (c) LDH-DBS@Ni(OH)₂ at different magnifications; (e), (f), (g) and (h) Mg, Al, S, and Ni mapping of LDH-DBS@Ni(OH)₂; (i) EDS spectra of LDH-DBS@Ni(OH)₂

Fig.4-7 FIB-SEM images of (a) LDH-DBS and (b) LDH-DBS@Ni(OH)₂

N₂ sorption and TG analysis

The N₂ sorption and TG analysis (**Fig.4-8**) offered information about porosity and thermal degradation of LDH-DBS and LDH-DBS@Ni(OH)₂. N₂ sorption isothermal curves (**Fig.4-8** (a)) showed that LDH-DBS@Ni(OH)₂ possessed notably higher specific surface area (55.2 m²/g) and pore volume (0.285 mL/g) than those (11.6 m²/g and 0.047mL/g) of LDH-DBS with preferential generation of mesopore reflected by relative pressure of 0.98, which certified the hierarchical

structure induced by ultrafine $\text{Ni}(\text{OH})_2$. In parallel, the char yield (**Fig.4-8** (b)) at 700°C of $\text{LDH-DBS@Ni}(\text{OH})_2$ revealed approximately 5.2wt% increase relative to that of LDH-DBS with no notable change in DTG curve (**Fig.4-8** (b)). In combination of various results, the successful self-assembly of $\text{LDH-DBS@Ni}(\text{OH})_2$ was performed.

Fig.4-8 (a) Isothermal curves of LDH-DBS and $\text{LDH-DBS@Ni}(\text{OH})_2$ in N_2 sorption; (b) TG curves of LDH-DBS and $\text{LDH-DBS@Ni}(\text{OH})_2$

4.2.5 Preparation and characterization of composites

Preparation of PS/Ferrocene composites

The fractions of 1wt% and 3wt% ferrocene were blended with PS to prepare PS/1Ferrocene and PS/3Ferrocene, respectively using the micro-compounder at the temperature of 220°C collectively for 2min. The reference sample pristine PS was also fabricated with the identical procedure. Afterwards, the obtained strips were made to sheets for CCT and smoke production.

Characterization of PS/Ferrocene composites-DSC and TG

DSC measurement was used to investigate the glass transition behavior of PS composites and the plasticizing effect of ferrocene. As was shown in **Fig.4-9** (a), the incorporation of ferrocene noticeably decreased the glass transition temperature (T_g) of PS, which indicated that the small-molecule metal inorganic compound promoted the PS segment motion and exhibited the plasticizing effect. More addition of ferrocene yielded the more notable plasticizing effect. TGA and DTG results were shown in **Fig.4-9** (b). Apparently, the addition of 3wt% ferrocene into PS matrix slightly decreased the initial thermal degradation temperature (14°C) but did not change the temperature at the peak degradation rate. Meanwhile, the peak degradation rate of PS and PS/3Ferrocene showed identical value ($9.8\%/\text{°C}$). Considering that ferrocene was easy to undergo

sublimation at the temperature above 100 °C and start to thermally decompose until 400 °C, it was conceivable that the addition of ferrocene did not change the degradation behavior of PS in condensed phase. Moreover, the initial thermal degradation of PS/3Ferrocene was attributed to the partial sublimation of ferrocene.

Fig.4-9 (a) DSC curves of PS, PS/1Ferrocene and PS/3Ferrocene and (b) TG and DTG curves of PS and PS/3Ferrocene

Preparation of LDH-CD@Ferr-based composites

In the typical procedure, 6wt% LDH-CD and LDH-CD@Ferr were respectively added to EP monomer prior to the preliminary mixing under vigorous stirring at 50°C. Afterwards, the suspension underwent the further dispersion in triple-milling machine due to the intensive shear and extensional field. The homogenized suspension was mixed with the curing agent DDS at the stoichiometric rate at 125°C. After the complete dissolution of DDS in EP monomer, the degas treatment was applied in the vacuum oven at 115°C. The degassed suspension was subsequently casted on the silicon mold for the curing program (160°C, 1h; 180°C, 2h and 200°C, 1h). The obtained products were labelled as EP/6LDH-CD and EP/6LDH-CD@Ferr respectively. Neat EP was fabricated in the identical procedure. The schematic illustration was demonstrated in **Scheme 4-3**.

Preparation of LDH-DBS@Ni(OH)₂-based nanocomposites

The preparation of LDH-DBS@Ni(OH)₂-based nanocomposites followed the identical procedure to that of LDH-CD@Ferr-based composites. The 3wt% weight fraction of LDH-NO₃, LDH-DBS and LDH-DBS@Ni(OH)₂ were incorporated EP nanocomposites with the label as EP/3LDH-NO₃, EP/3LDH-DBS and EP/3LDH-DBS@Ni(OH)₂ respectively. Neat EP was prepared according to the identical procedure.

Scheme 4-3 Schematic illustration of preparation process of EP composites

4.3 Property and mechanism of composites

4.3.1 PS/Ferrocene composites

a) Smoke-suppression behavior of PS/Ferrocene composites

Smoke-suppression behavior of PS composites was investigated by CCT test (**Fig.4-10** and **Table 4-1**). Notably, the addition of ferrocene into pure PS matrix increased pHRR and THR values, accompanied by the increase percentage of 30% and 25.6% respectively in terms of PS/3Ferrocene. The result illuminated that the addition of ferrocene into PS increased the combustion intensity of PS. In parallel, ferrocene endowed PS with remarkably reduced smoke production profile, with the most significant decrease of 55.2% and 56.9% of PS/3Ferrocene in terms of peak SPR and TSP respectively, which demonstrated that ferrocene incorporation favored smoke suppression behavior of PS significantly.

In order to further investigate the relationship between the smoke suppression and combustion behavior, the mass profile and its differentiation result were also investigated. As was showed in **Fig.4-10** (e) and (f), the real-time weight of PS, PS/1Ferrocene and PS/3Ferrocene remained nearly identical during combustion. Moreover, the derivatives of weight also demonstrated almost identical values to that of neat PS, which disclosed that the weight loss from pristine PS (solid and liquid) to gaseous PS fragments and smoke production was not influenced by ferrocene

incorporation. Integral understanding of the combustion and smoke production process illustrated that the decreased smoke production contributed to the improved combustion behaviors with the incorporation of ferrocene.

Fig.4-10 (a) HRR, (b) THR, (c) SPR, (d) TSP, (e) derivation of weight and (f) weight profiles of PS, PS/1Ferrocene and PS/3Ferrocene

Table 4-1 CCT data of PS and PS composites

	t_{ig} (s)	pHRR (kW/m ²)	THR (MJ/m ²)	Peak SPR (m ² /m ²)	TSP (m ²)	Residue (%)
PS	100±2	577±17	90±3	0.145±0.03	24.6±0.8	4.0±0.1
PS/1Ferrocene	103±3	673±19	103±2	0.084±0.02	14.1±0.4	5.4±0.3
PS/3Ferrocene	112±1	746±24	113±3	0.065±0.01	10.6±0.3	5.4±0.2

t_{ig} : Time to ignition THR: Total heat release pHRR: peak heat release

Peak SPR: Peak smoke production rate TSP: Total smoke production

b) Smoke-suppression mechanism of PS/Ferrocene composites

Primarily, the condensed-phase behavior and mechanism was investigated. PS was a typical non-charring polymer [164, 338, 339]. Even after addition of ferrocene, PS/Ferrocene composites still showed the non-charring behavior from the weight profiles and digital images after CCT (**Fig.4-11** (a) and (b)). Even though a limited amount of iron derivatives were preserved in the char of PS/3Ferrocene due to the thermal decomposition of ferrocene in the condensed phase, the char quantity and quality exhibited no notable enhancement relative to that of neat PS. The slight

condensed-phase smoke-suppression mechanism was indirectly reflected in TG-FTIR. Therefore, the smoke production behavior was predominantly focused in the vapor phase. Imaginarily, in term of PS/3Ferrocene, PS underwent melting and thermal-oxidative process into the main component of styrene under the irradiation of cone heater. Simultaneously, ferrocene was sublimed above 100°C and then decomposed into iron derivatives in the flaming zone above 400°C. Generally, the precursors to generate smoke were involved in benzene or benzene derivatives (polycyclic aromatic hydrogen, PAH), which were confirmed by the previous report [261]. Subsequently, the smoke precursors underwent the nucleation and growth into the smoke intermediates. Hence, the decreased smoke release and increased fire intensity manifested the smoke precursors or smoke intermediates (after nucleation and preliminary growth) were combusted after incorporation of ferrocene. Additionally, the effect of ferrocene on the combustion was also shown in the oxidation of CO to CO₂ (Fig.4-12 (a) and (b)). In a similar way, ferrocene assisted in the oxidation process of benzene derivatives (PAH) and smoke intermediates during combustion. Actually, the result was consistent with the reported by Yong Ho Kim [340].

Fig.4-11 Digital images after CCT of (a) PS and (b) PS/3Ferrocene

Fig.4-12 (a) COP and (b) CO₂P of PS, PS/1Ferrocene and PS/3Ferrocene

In order to clarify the detailed smoke-suppression mechanism, the effect of ferrocene on the

production behavior of smoke precursors (condensed-phase charring and char protection) and the thermal-oxidation stability of initially formed smoke intermediates (vapor-phase mechanism) were specially considered. The vapor-phase mechanism was presented via thermal-oxidation study of smoke intermediates over the temperature range of combustion. The thermal-oxidation mechanism at the molecular level was proposed. In parallel, the condensed-phase mechanism ran via catalytic charring and char protection, which enabled the reflection of smoke precursors in TG-FTIR. Herein, in consideration of the weak condensed-phase behavior, the investigation of charring mechanism at the molecular level was neglected.

Investigation of the initially formed smoke intermediates (soot)

Inspired by the catalytic oxidative degradation of iron-containing carbon particles [340], we conceived that the initially formed smoke intermediates underwent the intensive catalytic oxidation and thus were converted into the small molecules (H_2O and CO_2) and heat. Aiming to certify the proposed process, the thermal-oxidation degradation of virgin PS was investigated (Fig.4-13). PS underwent the intensive thermal-oxidation to generate dense smoke around 400 °C due to the high thermal-oxidation rate. Meanwhile, in terms of PS/3Ferrocene composite, ferrocene started to sublime at about 100 °C and degrade at 400 °C [341], thus presumably resulting in enormous participation of ferrocene or its iron species in the formation of smoke intermediates. Subsequently, the smoke process was investigated by TEM with EDS technique.

Fig.4-13 Thermal-oxidation degradation of virgin PS

In Fig.4-14, PS smoke was composed of enormous aggregations of large numbers of carbon nanoparticles with the size of about 40nm. Intriguingly, two and more carbon nanoparticles

usually shared the identical parts, which indicated that the homogeneous nucleating and growth of smoke was restricted by the limited space. In parallel, PS/3Ferrocene yielded totally different carbon nanoparticles morphology from virgin PS. In the center of carbon nanoparticles, enormous black spots emerged, which was evidenced as the γ -Fe₂O₃ nanoparticles via EDS spectra, Fe mapping and HRTEM (Fig.4-15).

Fig.4-14 TEM images of different magnifications of the smoke from pure PS (a, c and e) and PS/3Ferrocene (b, d and f)

Fig.4-15 Selected area electron diffraction (SAED) patterns of smoke from (a) PS and (b)

PS/3Ferrocene; (c, d and f) High angle angular dark field (HAADF), Fe mapping and EDS spectrum of PS/3Ferrocene; (e) High Resolution TEM (HRTEM) of smoke intermediates of PS/3Ferrocene

Meanwhile, the selected area electron diffraction (SAED) patterns comparison disclosed that smoke of PS/3Ferrocene possessed extra diffraction dots that came from different crystal faces of γ -Fe₂O₃ phase. Interestingly, from the high-magnification TEM images of PS/3Ferrocene smoke intermediates, the γ -Fe₂O₃ phase was embedded in the core-like carbon nanoparticles and then further shell-like char layers, which was tightly correlated to the heterogeneous nucleating and growth mechanism.

In addition to the morphology difference of the initially formed smoke intermediates, the thermal-oxidation behavior of the smoke intermediates of pure PS and PS/3Ferrocene was also required to be investigated in order to confirm the smoke stability at the flaming zone. In **Fig.4-16** (a), the smoke intermediates from EP/3Ferrocene exhibited remarkably reduced $T_{5wt\%}$, T_{max} and $T_{80wt\%}$ compared to that of pure PS, illustrating that the γ -Fe₂O₃ incorporation contributed to the more intensive oxidation process [342, 343]. Notably, the smoke intermediates of PS/3Ferrocene almost totally degraded while the smoke intermediates of PS merely started to degrade at the temperature of 550 °C. The investigation of the precise temperature profile close to the flaming zone demonstrated that the temperature stayed about 550 °C in the normal combustion circumstance (**Fig.4-16** (b)). Based on the above temperature profiles, it was deduced that the initially formed smoke intermediates of PS/3Ferrocene were almost completely combusted while the virgin PS showed in the contrary way. Very understandably in the sense, the transformation of CO to CO₂ was also accelerated due to the ease of oxidation behavior with the assistance of γ -Fe₂O₃. The thermal-oxidation degradation of the smoke intermediates proceeded in the catalytic process. The iron atoms in γ -Fe₂O₃ nanoparticles possibly coordinated with peroxide moiety on the molecules of smoke intermediates from the oxygen attack on C-H (**Fig.4-19** (b)) [344]. The iron-containing complexation favored the further C-H and C-C bond activation via energy redistribution [345, 346]. Resultantly, the C-H and C-C bonds underwent the oxygen attack, giving rise to CO₂.

Fig.4-16 (a) Thermal-oxidation degradation profile of smoke intermediates from PS and PS/3Ferrocene and (b) Temperature profile of PS on the external surface during CCT

Investigation of volatile evolution

Herein, TG-FTIR technique was employed to investigate the volatiles evolution profiles in order to reflect the impact of ferrocene on the small-molecule smoke precursors (mono-substituted benzene compounds and other C=C containing compounds). In detail in **Fig.4-17**, the 3D FTIR graphics of PS and PS/3Ferrocene exhibited that the incorporation of ferrocene did not noticeably change the evolved paths. In order to gain a better understanding of the peak assignments, the detailed correspondence was illustrated in **Table 4-2**. The comparison of FTIR spectra of PS and PS/3Ferrocene at the peak intensity demonstrated that the degradation products remained identical, which included predominantly styrene and its derivatives. Notably, the peaks at 1946 cm^{-1} , 1875 cm^{-1} , 1824 cm^{-1} , 1600 cm^{-1} , 1497 cm^{-1} and 1440 cm^{-1} were attributed to the stretching vibration mode of mono-substituted benzene ring. Actually, the characteristic absorbance bands of the di-substituted and higher-substituted benzene rings were absent here, indicating that the evolved gases were composed of the mono-substituted benzene rings. Besides, the peaks at 3090 cm^{-1} and 3078 cm^{-1} confirmed the presence of $-\text{CH}=\text{CH}_2$ together with the peak located at 1630 cm^{-1} (stretching vibration of carbon double bonds). Therefore, it was obtained that the predominant evolved component was styrene. However, the limited amount of substituted styrene was also detected due to the peak location of 1639 cm^{-1} and 2929 cm^{-1} , which was in good agreement with the previous report [316].

Fig.4-17 FTIR 3D graphics of (a) PS, (b) PS/3Ferrocene and (c) FTIR spectrum at the maximum intensity of PS and PS/3Ferrocene

Table 4-2 Peak locations and their assignments

Peak locations (cm ⁻¹)	Peak assignments
3090 and 3078	Stretching vibration, =C-H (-HC=CH ₂)
3039 and 3027	Stretching vibration, C-H (Benzene ring, φ)
2978 and 2876	Stretching vibration, -C-H (CH ₃)
2929	Stretching vibration, -C-H (CH ₂)
1926, 1875, 1824, 1600, 1497 and 1440	Stretching vibration, C=C (φ)
1639	Stretching vibration, C=C (-C=CH ₂)
1630	Stretching vibration, C=C (-CH=CH ₂)
1421	In-plane deformation, =C-H
990 and 913	Out of plane deformation, C-H (-HC=CH ₂)
774	Out of plane deformation, -C-H (CH ₂)
673	Bending vibration, C-H (φ)

In order to compare the evolution of small-molecule smoke precursors, the benzene structure and double bond structure were investigated in **Fig.4-18**. The whole intensity of PS and PS/3Ferrocene showed a nearly identical curve trend with the identical peak intensity and the time to peak intensity. The integral value of whole intensity remained almost unchanged with tiny alternation after 42 min, which was corresponding to 500°C (ferrocene started to thermally degrade). In parallel, the predominated mono-substituted benzene structure (3030 cm⁻¹ and 1600

cm^{-1}) and C=C containing compounds (1630 cm^{-1}) also remained no remarkable difference between PS and PS/3Ferrocene. The neglectable alternation similarly occurred after roughly 42min. Ferrocene incorporation did not remarkably reduce the evolution of the smoke precursors of mono-substituted benzene and double bond compounds.

Fig.4-18 Volatiles evolution of (a) whole intensity, (b, c, d and e) substituted benzene and (f and h) double bond structure

In conclusion, the ferrocene molecules imparted PS with significantly reduced smoke production predominantly from the thermal-oxidation degradation of smoke intermediates (**Fig.4-19**). PS/Ferrocene composite generated the smoke intermediates with enormous $\gamma\text{-Fe}_2\text{O}_3$ nanoparticles as the inclusions. Subsequently, the included $\gamma\text{-Fe}_2\text{O}_3$ catalyzed the thermal-oxidation of smoke intermediates significantly at the temperature in flaming zone via coordination effect. The coordination effect activated the structure toward the stronger oxidation process (**Fig.4-19** (b)). The previous literature reported the mechanism of the sequential adsorption of organic matters, ligand exchange induced coordination between iron oxide surface and organic matters and the desorption of the products [347]. As thermal-oxidation process occurred in the vapor phase, the smoke-suppression proceeded based on the vapor-phase mechanism. In parallel, the catalytic charring behavior of PS at the oxygen-lacking atmosphere generated the limited residue, which slightly reduced the evolution of smoke precursors (**Fig.4-18**). The condensed-phase mechanism was notably weak, which determined the predominant vapor-phase mechanism.

Fig.4-19 (a) Illustration of different smoke-production behaviors; (b) proposed thermal-oxidation mechanism of smoke intermediate

4.3.2 EP/LDH-CD@Ferr composites

a) Dispersion of LDH-CD@Ferr in EP matrix

The dispersion of LDH-CD and LDH-CD@Ferr in EP matrix was investigated in **Fig.4-20**. In **Fig.4-20** (a), the LDH-CD nanofiller kept in the aggregate state with the interface between nanosheets and matrix distinct. The poor dispersion was supposed to be due to the incompatibility between the intercalated sulfonated cyclodextrin and EP matrix. In parallel, LDH-CD@Ferr was better nano-dispersed in EP matrix (**Fig.4-20** (b, c)) compared with EP/6LDH-CD with the interface more vague. The higher gallery spacing of LDH-CD@Ferr favored the nanodispersion and the diffusion of EP chains into LDH-CD@Ferr aggregates. Meanwhile, the S and Fe mapping in **Fig. 4-20** (d, e, f) reflected that the ferrocene included sulfonated cyclodextrin (CD@Ferr) was remained in LDH gallery without damage.

Fig.4-20 TEM images of (a) EP/6LDH-CD and (b, c) EP/6LDH-CD@Ferr; (d) HAADF image, (e) S mapping and (f) Fe mapping of EP/6LDH-CD@Ferr

b) Smoke-suppression behavior of EP/LDH-CD@Ferr composites

Smoke-production behavior of EP and EP composites were investigated in CCT and demonstrated in **Fig.4-21** and **Table 4-3**. In terms of neat EP, the smoke production was awfully harmful for fatality. 6wt% LDH-CD imparted EP ($0.28 \pm 0.02 \text{ m}^2/\text{s}$) with the decreased peak smoke production rate (peak SPR) by 10.7%. In contrast, EP/6LDH-CD@Ferr possessed peak SPR value of $0.17 \pm 0.01 \text{ m}^2/\text{s}$, which was 42.9% lower than that of neat EP. In parallel, the addition of LDH-CD and LDH-CD@Ferr decreased the total smoke production (TSP) of EP by 25.7% and 54.4% respectively. Compared to EP/6LDH-CD, EP/6LDH-CD@Ferr reduced the TSP value by 28.7%. The investigation of peak HRR and TSP demonstrated that LDH-CD suppressed the smoke production of EP. The incorporation of ferrocene into LDH-CD further suppressed the smoke production of EP matrix.

Fig.4-21 (a) Smoke production rate and (b) total smoke production of EP, EP/6LDH-CD and EP/6LDH-CD@Ferr

Table 4-3 CCT data of EP and EP composites (50kW/m²)

Sample	pHRR (kW/m ²)	THR (MJ/m ²)	Peak SPR (m ² /s)	TSP (m ²)	Residue (wt%)	AMLR (g/s)
EP	980±39	107±6	0.29±0.02	34±2	14.6±1.2	0.11±0.01
EP/6LDH-CD	910±34	86±6	0.24±0.02	25±2	18.0±1.5	0.10±0.01
EP/LDH-CD@Ferr	682±25	78±5	0.17±0.01	18±1	21.1±1.6	0.08±0.01

pHRR: Peak heat release rate

THR: total heat release

Peak SPR: Peak smoke production rate

TSP: Total smoke production

AMLR: average mass loss rate

c) Smoke-suppression mechanism of EP/LDH-CD@Ferr composites

The smoke-suppression mechanism was handled from condensed-phase and vapor-phase aspects. The condensed-phase mechanism was involved in the formation of the carbonaceous layers with the intensive protection toward the underlying polymers. Resultantly, the smoke precursors of polyaromatic compounds were reduced. It was certified in the following work that the facture of unstable carbonaceous layer did not result in the smoke production. The vapor-phase mechanism was involved in the promoted combustion of smoke intermediates (soot). The investigation of smoke intermediates (soot) disclosed the vapor-phase smoke-suppression behavior.

Condensed-phase mechanism-Carbonaceous layer analysis

The char structure was visually observed via SEM and digital images. In **Fig.4-22** (a-2) and (b-2), EP/6LDH-CD generated more char with higher size compared with that of EP. The incorporation of ferrocene further enhanced the char amount and size with better integrity and continuity relative to that of EP/6LDH-CD (**Fig.4-22** (c-1) and (c-2)). Notably, the red stuff (Fe₂O₃) covered the char

of EP/6LDH-CD@Ferr (**Fig.4-22 (c-2)**), which manifested that a part of ferrocene was transferred into Fe_2O_3 and participated in the charring process. The retention of Fe_2O_3 in chars of EP was intimately correlated with the char continuity and integrity. In order to ascertain the relationship between the macroscopic digital images and the retention of Fe_2O_3 , the microscopic char structure and charring process were investigated.

Fig.4-22 (a-1), (b-1), (c-1) side view and (a-2), (b-2), (c-2) top view of char of EP, EP/6LDH-CD and EP/6LDH-CD@Ferr

The insightful investigation of the char structure was performed via SEM (**Fig.4-23**). The incorporation of LDH-CD slightly improved the interior and exterior char structure with less holes and more integrity in comparison to that of neat EP (**Fig.4-23 (a-d)**). Notably, in **Fig.4-23 (e)** and (f), the ferrocene modification of LDH-CD further enhanced the integrity and continuity of interior char from EP/6LDH-CD with neglectable holes.

Fig.4-23 Digital images of (a), (c), (e) interior and (b), (d), (f) exterior char of EP, EP/6LDH-CD

and EP/6LDH-CD@Ferr respectively

The EDS analysis of the white area of EP/6LDH-CD@Ferr (**Fig.4-24**) revealed the composition of char particles were rich in Mg, Al and Fe elements. It was considered to stem from the promoted charring of EP resin surrounding LDH-CD@Ferr via the analysis of char yield in cone calorimeter test (CCT) (**Fig.4-24** (c)) and thermogravimetric analysis (TG) (**Fig.4-24** (d)). In parallel, the exterior char (**Fig.4-23** (f)) possessed the white char particles embedded into the carbonaceous layer. It indicated the adhesion between white char particles and carbonaceous layer was enhanced due to the catalytic charring by ferrocene and its derivatives around the pyrolyzed products of LDH-CD. Meanwhile, the enhancement of thermal stability (high temperature range in **Fig.4-24** (c) and (d)) restricted the degradation of carbonaceous layers, resulting in the stronger barrier structure. The interior and exterior char structure in SEM observation and the macroscopic structure in digital images were accordingly optimized. In parallel, the mechanical robustness was probably improved due to the formation of nanocomposite char structure with metal oxides (from LDH-CD) acting as the fillers and carbons as the matrix. The improved mechanical robustness inhabited the fracture of the carbonaceous layers and improved the integrity.

Fig.4-24 (a) SEM image of interior char of the selected area of EP/6LDH-CD@Ferr and (b) EDS spectra; Weight profile in (c) CCT and (d) TG of EP, EP/6LDH-CD and EP/6LDH-CD@Ferr

Condensed-phase mechanism-*Charring reaction analysis*

The weight curves in CCT (**Fig.4-24** (c)) and TG analysis (**Fig.4-24** (d)) verified the presence of promoted charring reaction particularly at the late stage. Herein, the charring reaction was explicitly studied. In consideration of the fact that the sample (EP and EP composites) underwent the thermal degradation at inert atmosphere during combustion, the effect of ferrocene on the degradation behavior of EP/LDH-CD was qualitatively studied via TG-FTIR (**Fig.4-25**). In **Fig.4-25**, the ratio of aliphatic and aromatic compounds of EP was higher than 1 at the degradation range. Contrastively, EP/6LDH-CD and LDH/6LDH-CD@Ferr possessed the lower ratio than 1, which indicated that the aliphatic compounds were converted into aromatic (or polyaromatic) compounds. The incorporation of ferrocene molecule slightly reduced the ratio of aliphatic and aromatic compounds compared with EP/6LDH-CD, which presented the further conversion of aliphatic to aromatic compounds under the function of ferrocene. The ratio of integral value of aliphatic and aromatic compounds (**Fig.4-25** (b)) presented the similar trend. The results certified the catalytic charring effect of ferrocene (or ferrocene derivatives) toward the conversion reaction. The generated aromatic compounds acted as the fundamental component for the charring process. Similar to the previous report, the degraded Fe_2O_3 from ferrocene contributed to the catalytic charring of EP/6LDH-CD toward formation of more protective carbonaceous layers.

Fig.4-25 (a) Ratio of transient value of and (b) ratio of integral value at the degradation period (40-55min) and of EP, EP/6LDH-CD and EP/6LDH-CD@Ferr

Condensed-phase mechanism-Volatile evolution

The direct result from condensed-phase smoke-suppression behavior was the reduction of the smoke precursor molecules. TG-FTIR (**Fig.4-26** (a)) revealed that the main smoke degraded products were released between 50min and 60min. The comparison of the peaks demonstrated that the LDH-CD and LDH-CD@Ferr did not change the species of evolved volatiles. The alteration

was focused on the re-adjustment of the degradation process with the addition of LDH-CD and LDH-CD@Ferr. In **Fig.4-26** (b), the peaks located at 3650cm^{-1} , 3034cm^{-1} , 2974cm^{-1} , 2180cm^{-1} and 1600cm^{-1} were assigned to phenol, double-bond, aliphatic, CO and aromatic compounds respectively. Amongst them, the double-bond and aromatic compounds were considered as the smoke precursors, which underwent polyaromatic reaction, nucleation and growth process.

Fig.4-27 presented the evolution profile of aromatic and double-bond compounds. In **Fig.4-27** (a) and (c), the addition of LDH-CD reduced the peak evolution intensity of aromatic and double-bond compounds. The ferrocene modification decreased the peak evolution intensity of aromatic and double-bond compound with notable reduction at the late stage of release. In parallel, **Fig.4-27** (b) and (d) illustrated the remarkable reduction of the integral intensity after addition of LDH-CD and LDH-CD@Ferr with the more notable decrease of EP/6LDH-CD@Ferr. The above evaluation presented the dual reduction of smoke precursors with the sequential addition of LDH-CD and inclusion modification of ferrocene.

Fig.4-26 (a) TG-FTIR 3D image of EP/6LDH-CD@Ferr; (b) FTIR spectra at the maximum intensity of volatiles of EP, EP/6LDH-CD and EP/6LDH-CD@Ferr

Fig.4-27 Evolved intensity of (a) aromatic and (c) double-bond compounds; Intensity integration of evolved volatiles of (b) aromatic and (d) double-bond compounds

Vapor-phase mechanism-TEM observation

The soot (smoke intermediate) was collected for the visual observation and thermal-oxidation study. In **Fig.4-28**, EP and EP/6LDH-CD@Ferr produced the soot with the similar size of carbon nanoparticle (ca. 50nm). Different from the soot of PS/Ferrocene, no notable Fe₂O₃ nanoparticles emerged in soot of EP/6LDH-CD@Ferr. The spherical and sphere-like morphology of carbon nanoparticle illuminated the homogeneous nucleation for both cases. The ordered arrangement of was detected in **Fig.4-28** (b) and (h), which was reflected by the diffraction rings in SAED images of **Fig.4-28** (c) and **Fig.4-28** (i). In both cases, the main element composition of the carbon nanoparticles was C and O (**Fig.4-28** (d, e, f) and (j, k, l) and **Fig.4-29**).

EDS spectra (**Fig.4-29** (a)) with the quantitative analysis illuminated that except the main element (C and O), a small amount of Fe and S emerged in soot of EP/6LDH-CD@Ferr with atomic ratio (1:9) of Fe and S. S element in EP/6LDH-CD@Ferr came from DDS component and sulfonated CD intercalator. The comparison of the atomic ratio of Fe and S element in LDH-CD@Ferr (1:6) and soot of EP/LDH-CD@Ferr (1:9) illustrated that a part of ferrocene molecules in LDH-CD@Ferr probably entered the vapor phase directly during combustion. Due to

relatively low amount of ferrocene molecules, the formation of Fe_2O_3 phase was inhibited. The undetected sub-nano phase of iron derivatives was possibly generated (**Fig.4-29** (b)). Apart from it, Mg and Al elements were not detected in EDS spectra (**Fig.4-29** (a)), which indicated that the smoke soot did not come from fracture of the carbonaceous layer.

Fig.4-28 (a) (b) TEM images, (c) selected area electron diffraction (SAED), (d) HAADF image and (e) (f) C and O mapping of soot of neat EP; (g) (h) TEM images, (i) SAED, (j) HAADF image and (k) (l) C and O mapping of soot of EP/6LDH-CD@Ferr

Fig.4-29 (a) EDS spectra of smoke intermediate from EP/6LDH-CD and EP/6LDH-CD@Ferr; (b) HAADF image with Fe and S mapping of smoke intermediate from EP/6LDH-CD@Ferr

Vapor-phase mechanism-TG analysis

TG analysis of the soot was illustrated in **Fig.4-30**. In **Fig.4-30** (a), the soot of EP/6LDH-CD

showed the slight decrease of temperature at 5wt% ($T_{5wt\%}$) by 33°C compared with that of neat EP. Due to the composition alteration of smoke precursors towards the lower ratio of aliphatic and aromatic compounds (**Fig.4-25** and **Fig.4-27**), the thermal stability of the soot of EP/6LDH-CD was reduced. The similar result was reflected in the wider temperature range of thermal-oxidation degradation in DTG curve (**Fig.4-30** (b)). In parallel, the soot of EP/6LDH-CD@Ferr possessed lower $T_{5wt\%}$, which was 23°C and 56°C reduced compared to those of EP/6LDH-CD and EP. The temperature at the maximum degradation rate (T_{max}) was roughly 72°C and 86°C lower than those of EP/6LDH-CD and EP respectively (**Fig.4-30** (b)). Reasonably, the lower thermal-oxidation stability of the soot (smoke intermediate) resulted in the promoted combustion and less smoke production. The temperature range of EP at 50kW/m² was measured using infrared temperature detector (**Fig.4-31** and **Fig.2-11(b)**). The combustion temperature was maintained at roughly 550°C at 35kW/m² in CCT, which determined that the majority of EP soot was retained and the majority of EP/6LDH-CD@Ferr was combusted.

Fig.4-30 (a) TG and (b) DTG curves of soot from EP, EP/6LDH-CD and EP/6LDH-CD@Ferr

Fig.4-31 Temperature at combustion zone of EP at 50kW/m²

Scheme 4-4 (a) Condensed-phase mechanism [36] and (b) vapor-phase mechanism for smoke suppression of EP/6LDH-CD@Ferr [348]

Smoke-suppression mechanism

In terms of EP/6LDH-CD@Ferr, both the condensed-phase and vapor-phase mechanism played the important roles in reducing smoke production. The condensed-phase phase was associated with the formation of mechanically robust carbonaceous layers, which facilitated the barrier effect toward heat and volatiles. The conversion of aliphatic compounds to aromatic (and/or polyaromatic) compounds (**Scheme 4-4** (a)) favored the charring reaction after the incorporation of Ferr. The TG-GC-MS result of EP matrix in **Section 4.3.3** revealed the basic aromatic structure and probable polyaromatic reaction toward the smoke intermediates and the char structure. The integral result was the notable reduction of smoke precursors (aromatic compounds) due to slightly increased aromatic compounds from the conversion reaction and remarkably reduced aromatic compound from the barrier effect. In parallel, the vapor-phase mechanism was involved in the intensive thermal-oxidation of some intermediates based on the activated C-H by iron derivatives (**Scheme 4-4** (b)) (similar to that of PS/3Ferrocene). Hence, the smoke suppression of EP/6LDH-CD@Ferr was originated from both condensed-phase and vapor-phase mechanism.

d) Fire retardancy of EP/LDH-CD@Ferr

LOI and UL-94 vertical burning test

In **Fig.4-32**, the addition of 6wt% LDH-CD increased LOI value of EP from 24.2% to 24.6%. The slight enhancement was due to the limited dispersion of LDH-CD in EP matrix. The ferrocene

modification of LDH-CD gave rise to a notable increased LOI value of 28.1%, which was 3.9% and 3.5% higher than those of EP and EP/6LDH-CD. The incorporation of ferrocene promoted the charring with higher-quality chars acting as protective barrier. Meanwhile, UL-94 vertical burning test disclosed the self-extinguishing property of EP/6LDH-CD@Ferr in contrast to the burning-to-clamp of EP and EP/6LDH-CD. However, EP/6LDH-CD@Ferr did not pass UL-94 V-2 rating, which demonstrated the limited fire retardancy.

Fig.4-32 LOI value of EP and EP composites

Cone calorimeter test (CCT)

In **Fig.4-33** (a) and **Table 4-3**, EP, EP/6LDH-CD and EP/6LDH-CD@Ferr presented the peak heat release rate (pHRR) of $980 \pm 39 \text{ kW/m}^2$, $910 \pm 34 \text{ kW/m}^2$ and $682 \pm 25 \text{ kW/m}^2$ respectively. 6wt% LDH-CD slightly reduced pHRR of EP with ignition time (t_{ig}) slightly decreased. LDH-CD@Ferr imparted EP with 30.9% reduction in pHRR. Compared with EP/6LDH-CD, EP/6LDH-CD@Ferr demonstrated notably lower pHRR (25.0% reduction), which certified the positive effect of ferrocene in suppressing fire hazard. Total heat release (THR) showed a similar trend with THR value of EP/6LDH-CD@Ferr 27.8% lower than that of neat EP. In terms of weight profile, EP/6LDH-CD@Ferr generated the highest char percentage of $21.1 \pm 1.6 \text{ wt\%}$ particularly after 250s, accompanied by the reduced average mass loss rate (AMLR) relative to neat EP.

Due to the limited release of ferrocene into the flaming zone (**Fig.4-29**), the average efficient heat of combustion (av-EHC) of EP/6LDH-CD@Ferr kept the nearly identical value of $21.0 \pm 0.5 \text{ KJ/kg}$ compared to $21.4 \pm 0.5 \text{ KJ/kg}$, which revealed the absence of vapor-phase fire-retardant mechanism. In combination of the char morphology (**Fig.4-22**, **Fig.4-23** and **Fig.4-24**) and the remained improved char yield (**Fig.4-24** (c) and (d)), the condensed-phase mechanism accounted

for the decreased fire safety. The higher-quality and higher-quantity char formed during combustion acted as the shielding barrier against volatiles and heat. Resultantly, the evolved flammable gases were reduced (*Section 4.3.2* (c)). In the molecule level, the iron nanocatalyst from thermal oxidation of ferrocene catalyzed the polyaromatic charring reaction (**Fig.4-25**). In addition, the ignition behavior of EP/6LDH-CD@Ferr occurred at the earlier moment relative to EP and EP/6LDH-CD, which was closely related to the alteration of thermal inertia and initial thermal-oxidation (and/or thermal) stability (**Fig.4-34**). The addition of LDH-CD decreased the initial thermal and thermal-oxidation stability of EP to different degrees. As the ferrocene molecules were incorporated into EP/6LDH-CD, the initial thermal and thermal-oxidation stability ($T_{5wt\%}$) was notably reduced, which contributed to the earlier ignition in case of the almost unchanged thermal inertia (a limited amount of ferrocene in EP/6LDH-CD@Ferr). The lower thermal and thermal-oxidation behavior contributed to the higher concentration of flammable gases.

Fig.4-33 (a) HRR and (b) THR of EP and EP composites

Fig.4-34 (a) TG curves and (b) DTG curves at air atmosphere of EP and EP composites

4.3.3 EP/LDH-DBS@Ni(OH)₂

a) Dispersion of LDH nanosheets in EP/LDH-DBS@Ni(OH)₂

The dispersion state of nanohybrid LDH-DBS@Ni(OH)₂ in EP matrix was investigated by TEM and XRD. In XRD pattern (Fig.4-35 (a)), the addition of 3wt% LDH-DBS and LDH-DBS@Ni(OH)₂ into EP shifted (003) reflection from 3.1° to 2.6°, which indicated that the basal spacing was enlarged to 3.45 nm from 2.98 nm for both cases. In parallel, TEM observation (Fig.4-35 (c, d, e, f, g, h)) illuminated that LDH-DBS@Ni(OH)₂ tended to be dispersed slightly more uniformly in EP than LDH-DBS, accompanied by weaker SEAD patterns due to the alteration of surface feature of LDH nanosheet. In combination of XRD and TEM result, LDH-DBS@Ni(OH)₂ formed intercalated and uniformly nano-dispersed state in EP, which was originated from shear effect in processing and internal stress during curing (Fig.4-35 (b)).

Fig.4-35 (a) XRD patterns of EP and EP nanocomposites; (b) schematic illustration of the shear-induced intercalation of LDH-DBS in EP matrix; (c), (d) and (e) TEM images of EP/3LDH-DBS with inset selected area electron diffraction (SAED); (f), (g) and (h) TEM images of EP/3LDH-DBS with SEAD

b) Smoke-suppression behavior of EP/LDH-DBS@Ni(OH)₂

The smoke-suppression behavior was demonstrated in Fig.4-36 and Table 4-4. The addition of 3wt% LDH-NO₃ did not decrease the peak SPR of neat EP (0.28±0.01 m²/g) but reduced TSP at 200s from 23.6±0.8 m² to 19.3±1.5m². In parallel, the addition of the reference sample LDH-DBS decreased the peak SPR and TSP at 200s by 32.0% and 20.3% respectively, which reflected the positive effect of LDH-DBS in suppressing the smoke production. The comparison of

EP/3LDH-NO₃ and EP/3LDH-DBS illuminated that the intercalation modification of LDH favored the improvement of smoke suppression. The better nanodispersion of LDH in EP matrix (**Fig.3-35**) contributed to the formation of higher-quality intumescent char. Furthermore, the engineering of the ultrafine Ni(OH)₂ nanoparticles on LDH-DBS nanosheets decreased the peak SPR and TSP at 200s by 26.3% and 58.0% separately, which revealed the smoke-suppression effect of Ni(OH)₂ modification. EP/3LDH-DBS@Ni(OH)₂ possessed the reduced peak SPR and TSP at 200s compared with that of neat EP by 50.0% and 65.5% correspondingly. Actually, TSP at 600s of EP/3LDH-DBS@Ni(OH)₂ was not reduced compared to that of EP/3LDH-DBS and EP/3LDH-NO₃, which was due to the promoted combustion process at the late stage (between 200s and 400s). Metal oxide was considered to promote the late-stage combustion of intumescent fire-retardant polymer composites [349-351]. The average smoke production rate was decreased due to the extended combustion time, which indicated the lowered fire hazard from smoke release.

Fig.4-36 (a) SPR and (b) TSP of EP and EP nanocomposites

Table 4-4 CCT data of EP and EP nanocomposites (50kW/m²)

Sample	Peak	pHRR	THR(MJ/m ²)	TSP(m ²)	AMLR	FIGRA
	SPR (m ² /g)	(kW/m ²)	at 200s	at 200s	(g/s)	(kW m ⁻² s ⁻¹)
EP	0.28±0.01	979±47	74.9±3.1	23.6±0.8	0.110±0.008	6.13
EP/3LDH-NO ₃	0.27±0.01	772±33	59.3±3.3	19.3±1.5	0.100±0.007	3.64
EP/3LDH-DBS	0.19±0.01	527±22	57.5±2.8	18.8±1.2	0.079±0.006	2.64
EP/3LDH-DBS@Ni(OH) ₂	0.14±0.01	372±9	25.9±1.4	7.9±0.6	0.052±0.002	1.05

Peak SPR: Peak smoke production rate pHRR: Peak heat release rate THR at 200s: Total heat release at 200s

TSP: Total smoke production AMLR: Average mass loss rate FIGRA: Fire growth rate

c) Smoke-suppression mechanism of EP/LDH-DBS@Ni(OH)₂

The smoke-suppression mechanism was investigated from the condensed-phase and vapor-phase

aspect. The condensed-phase mechanism was associated with the formation of protective carbonaceous char that inhibited the release of aromatic (and/or polyaromatic) compounds. The charring structure and charring process were stressed. The molecule-level mechanism was studied. The vapor-phase mechanism was involved in the intensive thermal-oxidation process of smoke intermediates (soot).

*Condensed-phase mechanism-**Carbonaceous layer analysis***

The digital images (**Fig.4-37** (a-1), (b-1), (c-1), (d-1) and (a-2), (b-2), (c-2), (d-2)) demonstrated that the addition of 3wt% LDH-NO₃ and LDH-DBS generated the char with notably bigger dimension and more compact and continuous structure. The char from LDH-DBS-based EP nanocomposite possessed the more integral and continuous structure than that of EP/3LDH-NO₃ due to the better nano-dispersion of LDH nanosheets. It was detectable that a layer of fluffy white stuffy were present in char of EP/3LDH-DBS@Ni(OH)₂, which was originated from the metal-oxides-rich chars. The formation of metal-oxides-rich chars was intimately correlated with the dispersion of LDH-DBS nanosheets in EP matrix (**Fig.4-35**). At the late of combustion, the organic component was combusted with the remaining of inorganic metal oxides. The incorporation of Ni(OH)₂ nanocatalyst was considered to promote the charring process with more formation of fluffy char sheets. In parallel, the investigation of the interior and exterior char (**Fig.4-37** (a-3), (b-3), (c-3), (d-3) and (a-4), (b-4), (c-4), (d-4)) disclosed that EP/3LDH-DBS@Ni(OH)₂ possessed the integral and continuous char surface with less holes and fractures compared with those of EP, EP/3LDH-NO₃ and EP/3LDH-DBS. The comparative study of char from EP/3LDH-DBS and EP/3LDH-DBS@Ni(OH)₂ revealed the critical effect of Ni(OH)₂ nano-catalyst on the formation of continuous char structure in condensed phase (**Fig.4-37** (a-3), (b-3), (c-3), (d-3)).

In order to insightfully analyze the effect of ultrafine Ni(OH)₂ on the char structure, the vertical and transverse sections were observed (**Fig.4-38** (a-d)). Compared with the compressed holes of EP/3LDH-DBS char, EP/3LDH-DBS@Ni(OH)₂ generated the more inflated pores, which probably induced the better heat insulation. Meanwhile, the more inflated pores revealed the higher mechanical robustness of char structure after the addition of Ni(OH)₂.

Fig.4-37 Horizontal view (a-1), (b-1), (c-1), (d-1) and top view (a-2), (b-2), (c-2), (d-2) of EP, EP/3LDH-NO₃, LDH-DBS and LDH-DBS@Ni(OH)₂ respectively; Interior char (a-3), (b-3), (c-3), (d-3), exterior char (a-4), (b-4), (c-4), (d-4) and EDS spectra (a-5), (b-5), (c-5), (d-5) of the interior char from EP, EP/3LDH-NO₃, EP/3LDH-DBS and EP/3LDH-DBS@Ni(OH)₂ respectively

Fig.4-38 Vertical section of char from (a) EP/3LDH-DBS and (b) EP/3LDH-DBS@Ni(OH)₂; transverse section of char from (c) EP/3LDH-DBS and (d) EP/3LDH-DBS@Ni(OH)₂

In addition to the observation in the macroscopic scale and mesoscopic scale, the measurement in the mesoscopic scale offered useful information about the mechanism of the improved char structure. The Raman spectra and XRD pattern were showed in **Fig.4-39**. The XRD pattern (**Fig.4-39** (a)) showed the inclusion of spinel $\text{MgO} \cdot \text{Al}_2\text{O}_3$ crystals [352, 353], which acted as the reinforcement of the char with improved mechanical robustness. The Raman spectra (**Fig.4-39** (b)) illustrated that the D band (ca. 1356cm^{-1} , A_{1g} breathing vibration of sp^3 hybridized carbon) and G band (ca. 1588cm^{-1} , E_{2g} in-plane stretching of six-ring sp^2 carbon) remained unchanged after addition of nanofillers [354]. The intensity ratio of D and G band (ID/IG) reflected the microcrystalline size of char with the higher ID/IG indicative of smaller size. The char of EP nanocomposites with nanofillers possessed slightly reduced ID/IG value, which presented the higher microcrystalline size. Notably, the higher microcrystalline size resulted in the better char structure in the mesoscopic scale with the smaller microcrystalline size [53]. Compared with those of EP/3LDH- NO_3 and EP/3LDH-DBS, EP/3LDH-DBS@ $\text{Ni}(\text{OH})_2$ generated the char with higher ID/IG value, which indicated the better char structure in the mesoscopic scale. In combination of the observation in the macroscopic and mesoscopic scale, ultrafine $\text{Ni}(\text{OH})_2$ nano-catalyst intensified the char structure. The improved char structure shielded the underlying polymer matrix against flammable gases and heat.

Fig.4-39 (a) XRD pattern of char from EP/3LDH-DBS@ $\text{Ni}(\text{OH})_2$; (b) Raman spectra of EP, EP/3LDH- NO_3 , EP/3LDH-DBS and EP/3LDH-DBS@ $\text{Ni}(\text{OH})_2$

Condensed-phase mechanism-Charring process

The charring process of EP and EP nanocomposites were investigated by the combustion termination in CCT and temperature detection during the combustion, accompanied by the invariable-temperature and variable-temperature charring analysis in TG. The in-situ carbonization

process by vt-FTIR was also carried out. In **Fig.4-40** (a) and (c), the addition of LDH-DBS and LDH-DBS@Ni(OH)₂ promoted the earlier degradation of EP matrix due to the lower intrinsic thermal stability of nanofillers. Aiming to investigate the effect of ultrafine Ni(OH)₂ on charring behavior of EP/3LDH-DBS, the calculated weight of EP/3LDH-DBS@Ni(OH)₂ was obtained based on the linear combination of EP/3LDH-DBS and Ni(OH)₂. The difference between experimental and calculated weight (**Fig.4-40** (b)) at the invariable-temperature thermal analysis demonstrated the slightly promoted degradation with the minimum weight difference of -0.2% at the initial 12.3min, followed by remarkable promoted charring with the maximum weight difference of 16.5% from 12.3min. The insightful analysis of the promoted charring process disclosed the strengthened charring and weakened charring periods, which revealed the dynamic change of char. The similar phenomenon was also detected in variable-temperature charring analysis (**Fig.4-40** (d)). The integration of invariable-temperature and variable-temperature charring illuminated the remarkable enhancement of ultrafine Ni(OH)₂ on the charring capacity of EP/3LDH-DBS at a given temperature and time conditions.

Fig.4-40 (a) Heating thermal degradation behavior of EP, EP/3LDH-DBS, EP/3LDH-DBS@Ni(OH)₂ and calculated EP/3LDH-DBS@Ni(OH)₂; (b) difference between experimental and calculated value at heating thermal analysis; (c) invariable-temperature thermal degradation behavior of EP, EP/3LDH-DBS, EP/3LDH-DBS@Ni(OH)₂ and calculated value of EP/3LDH-DBS@Ni(OH)₂; (d) difference between experimental and calculated value of EP/3LDH-DBS@Ni(OH)₂ at invariable-temperature thermal analysis; (e) vt-FTIR spectra of

EP/3LDH-DBS@Ni(OH)₂ at different times; (f) vt-FTIR spectra of EP, EP/3LDH-DBS and EP/3LDH-DBS@Ni(OH)₂ at 40min

The in-situ polyaromatic reaction was certified by vt-FTIR test. In **Fig.4-40** (e), the peak of EP/3LDH-DBS@Ni(OH)₂ at 1250cm⁻¹ (σ-O-C) broadened toward lower wavenumber at 40min rather than that at 0 min, 10 min and 20min, which illustrated the formation of polyaromatic structure with higher aromaticity. Similarly, EP/3LDH-DBS@Ni(OH)₂ rather than EP/3LDH-DBS illustrated higher tendency of broadening than that of EP (**Fig.4-40** (f)), which indicated the effectiveness of LDH-DBS@Ni(OH)₂ in promoting the polyaromatic reaction. The promotion of polyaromatic reaction evidenced the positive effect of Ni(OH)₂ on charring behavior, which revealed the consistent result with invariable-temperature and variable-temperature charring analysis. The higher-aromatic-degree gave rise to polyaromatic compounds that surrounded metal oxides. Resultantly, the stronger char structure was generated with metal oxides particles the effective reinforcements and aromatic compounds the interface linker.

The charring process and structure was further studied via terminating combustion at the peak heat release rate of neat EP in CCT. SPR curves (**Fig.4-36** (a)) illustrated that EP/3LDH-DBS and EP/3LDH-DBS@Ni(OH)₂ were constructing the char structure at the termination point. The digital images (**Fig.4-41**) showed that EP/3LDH-DBS@Ni(OH)₂ generated the drum-like char with remarkable integrity and nearly no holes on the surface in comparison to that of EP/3LDH-DBS with poor integrity and notable holes. The SEM observation (**Fig.4-42** (a-d)) demonstrated that EP/3LDH-DBS@Ni(OH)₂ generated the interior surface with closed pores. In contrast, EP/3LDH-DBS induced the interior surface with ruptured pores, which resulted in the stronger mass exchange through the surface. More remarkably in **Fig.4-42** (e-h), the exterior surface of char from EP/3LDH-DBS@Ni(OH)₂ possessed nearly continuous and integral structure in comparison to that of EP/3LDH-DBS with approximately 1μm holes. The comparison of digital and SEM images of EP/3LDH-DBS and EP/3LDH-DBS@Ni(OH)₂ revealed the positive effect of ultrafine Ni(OH)₂ on the dynamic construction of char structure. The result was in a good agreement with invariable-temperature charring analysis.

Fig.4-41 (a-1) front view and (a-2) top view of char of EP/3LDH-DBS; (b-1) front view and (b-2) top view of char of EP/3LDH-DBS@Ni(OH)₂ at the moment of 157s during CCT

Fig.4-42 SEM images of interior surface of char from (a), (c) EP/3LDH-DBS and (b) (d) EP/3LDH-DBS@Ni(OH)₂; exterior surface of char from (e), (g) EP/3LDH-DBS and (f) (g) EP/3LDH-DBS@Ni(OH)₂

Fig.4-43 Digital images of vertical section of char in CCT at 157s of (a) EP/3LDH-DBS and (b) EP/3LDH-DBS@Ni(OH)₂

Furthermore, the digital image (**Fig.4-43**) at the vertical section demonstrated that EP/3LDH-DBS generated the char macrostructure with hole-structure carbonaceous layer on the top and enormous pore structure in the underlying matrix. In contrast, the char of EP/3LDH-DBS@Ni(OH)₂ possessed an integral carbonaceous layer on the top, which protected the underlying matrix. The pore structure became less serious relative to that of EP/3LDH-DBS. The protection effect on degradation process enabled to be reflected by the temperature detection. In **Fig.4-44** (a) and (b), the temperature differences at the middle and bottom position between EP/3LDH-DBS and EP/3LDH-DBS@Ni(OH)₂ reached 52°C and 29°C respectively, which disclosed the critical effect of ultrafine Ni(OH)₂ on char structure of top surface.

In addition, the temperature analysis in the whole process in **Fig.4-45** and **Fig.4-44** (c) and (d) illustrated that EP/3LDH-DBS and EP/3LDH-DBS@Ni(OH)₂ possessed the significantly higher temperature difference between top and bottom surface than that of EP matrix, which revealed the thermal insulation of intumescent char. Particularly, the comparison at the 400s time interval demonstrated that EP/3LDH-DBS@Ni(OH)₂ possessed the temperature difference of 362°C, notably higher than 320°C of EP/3LDH-DBS. The result unveiled the function of Ni(OH)₂ on strengthening the intumescent structure (**Fig.4-38**).

Fig.4-44 Comparison of (a) middle temperature and (b) bottom temperature of EP, EP/3LDH-DBS and EP/3LDH-DBS@Ni(OH)₂; top, central and bottom temperature of (a)

EP/3LDH-DBS and EP/3LDH-DBS@Ni(OH)₂

Fig.4-45 Top, middle and bottom temperature of EP at CCT

Based on the dynamic process from EP bulk to drum-like char structure to the intumescent open-pore char structure with white char pieces on the surface, the basic charring process was obtained with reference to the invariable-temperature charring behavior. After imposing the intensive heat, the top surface of EP/3LDH-DBS@Ni(OH)₂ rapidly increased the temperature to ignition temperature (ca. 400°C) at ca. 360°C/min, which induced the ignition and the incident consumption of oxygen. Subsequently, the anaerobic charring behavior occurred at the certain-thickness top layer, resulting in the high-quality drum-like carbonaceous layer (**Fig.4-41** and **Fig.4-42**). The relatively high mechanical robustness of top layer facilitated the integrity during inflation to drum process by the internal stress and decomposed volatiles. The incorporation of ultrafine Ni(OH)₂ into EP/3LDH-DBS gave rise to stronger protection toward underlying matrix, which resulted in the slower thermal degradation behavior and the incident higher weight remaining (**Section 4.3.3** (d)).

After 157s, the underlying char matrix further underwent anaerobic charring behavior with the formation of intumescent and porous char structure. In terms of the intumescent structure, the intumescent behavior was dependent on the dispersion state of LDH nanosheets in EP matrix (**Fig.4-35**, **Fig.4-37** and **Fig.4-42**). The incorporation of LDH-DBS droved the transformations of carbon from stiff char of EP matrix to more robust metal oxides-filled char. It was proposed that the interplay between gases (predominantly from EP volatile) and carbon (from residue of EP and LDH-DBS) played a critical role in the intumescent process. The decoration of ultrafine Ni(OH)₂

further strengthened the mechanical robustness. The white char pieces were probably originated from the aerobic degradation of the intumescent char, especially surface char, at the late combustion stage with the formation of metal-oxide-rich structure. After the investigation of optimized charring process and charring structure, the charring reaction by $\text{Ni}(\text{OH})_2$ was evidenced to occur at the interface between EP matrix and LDH-DBS nanosheets. The dispersion of metal oxides in char was studied. In **Fig.4-46** (a-d), the notable lamella-like aggregate was observed with Mg, Al and Ni elements inside, which indicated that charring promotion reaction probably occurred at the interface. Actually, enormous Mg, Al and Ni compounds were dispersed in the char in the relatively uniform form, which reflected that the interfacial charring behavior occurred in the whole EP matrix.

Fig.4-46 (a) and (b) TEM images of char from EP/3LDH-DBS@ $\text{Ni}(\text{OH})_2$; (c) Mg mapping; (d) high angle angular dark field (HAADF) images with Ni and Al mapping

Condensed-phase mechanism-Volatile evolution

The direct result of the intensified char structure was the changed volatile evolution. Herein, EP,

EP/3LDH-DBS and EP/3LDH-DBS@Ni(OH)₂ were selected for volatile evolution. **Fig.4-47** illuminated that the species of the main pyrolyzed products (3645cm⁻¹, phenol compound; 3034cm⁻¹, double-bond compounds; 2968cm⁻¹, aliphatic compounds; 1810cm⁻¹, carbonyl compounds; 2180cm⁻¹, CO and 1600cm⁻¹, aromatic compounds) were not changed with the addition of LDH-DBS and LDH-DBS@Ni(OH)₂, accompanied by the different amounts. The main precursors of smoke included the phenol compounds, double-bond compounds and aromatic compounds, which were investigated in detail.

Fig.4-47 FTIR spectra at maximum volatile release rate of (a) EP, (b) EP/3LDH-DBS and (c) EP/3LDH-DBS@Ni(OH)₂

Fig.4-48 Volatile evolution of (a) phenol compounds, (b) aromatic compounds and (c) double-bond compounds of EP, EP/3LDH-DBS and EP/3LDH-DBS@Ni(OH)₂

In **Fig.4-48**, phenol compounds, aromatic compounds and double-bond compounds showed the similar trend. After the addition of 3wt% LDH-DBS into EP matrix, the peak release rate of phenol compounds, aromatic compounds and double-bond compounds were slightly reduced. The ultrafine Ni(OH)₂ modification remarkably reduced the peak release rate of phenol compounds,

aromatic compounds and double-bond compounds compared with that of EP/3LDH-DBS. Furthermore, the integral size of phenol compounds, aromatic compounds and double-bond compounds illustrated the similar trend to that of peak release rate, which indicated the smoke precursors were decreased significantly with the ultrafine $\text{Ni}(\text{OH})_2$ modification. In addition to invariable-temperature, variable-temperature and vt-FTIR results, TG-FTIR and TG-GC-MS results were specifically studied to understand the interface-charring catalysis.

The study in **Fig.4-49** (a) illustrated that LDH-DBS did not change the ratio of aliphatic and aromatic compounds compared to that of neat EP. LDH-DBS@ $\text{Ni}(\text{OH})_2$ notably decreased the ratio, which indicated the further conversion of aliphatic compounds to aromatic compounds. The ratio of integral value of aliphatic and aromatic compounds (**Fig.4-49** (b)) also verified the conversion toward aromatic compounds. The preferential conversion toward polyaromatic compounds contributed to the formation of the protective char. The result was consistent with the Raman spectra and vt-FTIR results in terms of improving the polyaromatic degree.

Fig.4-49 (a) Ratio of aliphatic and aromatic compounds; (b) Ratio of integral value of aliphatic and aromatic compounds in TG-FTIR

TG-GC-MS result was illustrated in **Fig.4-50**. **Fig.4-50** (a) and (e) disclosed that the main pyrolyzed products emerged at 15.7min, 20.6min, 25.5min, 29.5min and 35min. The mass spectra at 20.6min (**Fig.4-50** (b)), 25.5min (**Fig.4-50** (c)), 29.5min (**Fig.4-50** (d)) and 35.0min (**Fig.4-50** (f)) showed that the more aromatic compounds with higher polyaromatic degree were formed after addition of LDH-DBS@ $\text{Ni}(\text{OH})_2$, which was in agreement with the ratio of aliphatic and aromatic compounds. The reduction of phenol group disclosed in the GC spectra at 15.7min (**Fig.4-50** (a)) was considered to be converted to compounds with the higher polyaromatic degree. In combination the fact that ultrafine $\text{Ni}(\text{OH})_2$ nanocatalyst was located between EP matrix and LDH

nanosheets, the compounds with the higher polyaromatic degree covered the dehydrated metal oxides with better protective performance. The interfacial catalysis played an important role in contributing to the formation of the intumescent char with the higher quality.

Fig.4-50 (a) GC spectra of EP and EP/3LDH-DBS@Ni(OH)₂; mass spectra at (b) 20.6min, (c) 25.5min and (d) 29.5min; (e) GC spectra of EP and EP/10LDH-DBS@Ni(OH)₂; (f) mass spectra at 35min

Vapor-phase mechanism

The soot (intermediate smoke) was collected and measured in terms of its thermal-oxidation behavior (**Fig.4-51**). The addition of 3wt% LDH-DBS and LDH-DBS@Ni(OH)₂ did not notably change the initial thermal-oxidation stability ($T_{5wt\%}$) of EP soot (**Fig.4-51** (a)). The investigation (**Fig.4-51** (b)) illuminated that soot of EP/6LDH-DBS possessed lower temperature at maximum thermal-oxidation rate (T_{max} , 608°C) than 620°C of EP soot. The Ni(OH)₂ incorporation of LDH-DBS decreased the temperature at maximum thermal-oxidation rate by 8°C relative to that of soot of EP/6LDH-DBS. The reduction of the T_{max} value was due to the alteration of the soot composition with higher-degree aromatic degree. At the combustion temperature of roughly 550°C, less soot of EP/6LDH-DBS was combusted compared to EP soot. Comparatively, less soot of EP/6LDH-DBS@Ni(OH)₂ was combusted. The difference of EP, EP/6LDH-DBS and EP/6LDH-DBS@Ni(OH)₂ was not pronounced, which determined that the vapor-phase mechanism was not dominant.

Fig.4-51 (a) TG and (b) DTG curves of soot from EP, EP/3LDH-DBS and EP/3LDH-DBS@Ni(OH)₂

Smoke-suppression mechanism

In combination of the condensed-phase and vapor-phase analysis, the smoke-suppression mechanism was found to be merely associated with condensed-phase mechanism. In the macroscopic scale, the incorporation of LDH-DBS generated the intumescent chars, which inhibited the production of smoke precursors. The interfacial modification of Ni(OH)₂ optimized the pore structure of intumescent chars, which possessed the better barrier effect against smoke precursors. The intumescent charring process followed the basic procedures of drum-like char and subsequent thermal degradation of underlying polymers. In the microscopic scale, the intercalated dispersion of LDH-DBS nanosheets played a role in the formation of intumescent chars. The incorporation of Ni(OH)₂ slightly promoted the dispersion of LDH-DBS nanosheets in EP matrix. In terms of the chemical aspect, the addition of LDH-DBS did not induce the notable polyaromatic degree, conversely giving rise to promoted degradation reaction. The incorporation of Ni(OH)₂ strongly induced the interfacial catalysis of Ni-nanocatalyst towards polyaromatic charring reaction. As a result, the microscopic morphology of the interior and exterior surface was improved toward the higher quality. The detailed process about interface-charring catalysis was as following: The relatively higher temperature pushed the thermal degradation of EP matrix (**Scheme 4-5** (a)), the dehydration of LDH nanosheets and Ni(OH)₂. The resultant Ni nanocatalyst catalyzed the charring reaction of the decomposed products of EP (aromatic compounds) towards polyaromatic compounds at the interface (**Scheme 4-5** (b)). Furthermore, the polyaromatic chars covered and wrapped the metal oxides, which was capable to reinforce the composite char (**Scheme 4-6**). The intumescent char was improved with higher integrity, which repeatedly

promoted the polyaromatic reaction and consumed the smoke precursors (aromatic compounds). In the molecular level, nickel nanocatalyst catalyzed the polyaromatic reaction via C-C coupling reaction. Resultantly, the smoke precursors (aromatic and double-bond compounds) were reduced due to the predominant barrier effect. Overall, the smoke-suppression behavior proceeded predominantly via the condensed-phase mechanism.

Scheme 4-5 (a) Simplified thermal degradation route of EP and (b) proposed catalytic charring reaction at the interface

Scheme 4-6 Condensed-phase mechanism based on interfacial catalysis for smoke suppression

d) Fire retardancy of $\text{EP}/\text{LDH-DBS}@Ni(\text{OH})_2$

The integral fire retardancy in the bench-mark scale was investigated via LOI, UL-94 vertical burning test and CCT. The integral fire retardancy was supposed to cover different heating intensity and heating mode. The power 50kW/m^2 was selected as the typical heat flux. LOI test was performed at the relatively lower heat flux. UL-94 vertical burning test was carried out at slightly higher heat flux.

LOI and UL-94 vertical burning test

The LOI and UL-94 results were illustrated in **Fig.4-52**. The addition of LDH- NO_3 , LDH-DBS and LDH-DBS@ $\text{Ni}(\text{OH})_2$ slightly increased LOI value of EP (23%) to 23.4%, 24.8% and 24.7% respectively. Self-assembly of ultrafine $\text{Ni}(\text{OH})_2$ on LDH-DBS did not change LOI value of EP/3LDH@DBS notably. In parallel, UL-94 test revealed that LDH- NO_3 and LDH-DBS did not increase UL-94 rating of EP with the flame burning to clamp (BTC). In contrast, EP/3LDH-DBS@ $\text{Ni}(\text{OH})_2$ possessed UL-94 V-0 rating with self-extinguishing behavior (inset table of **Fig.4-52** (a) and **Fig.4-52** (b-h)), which indicated that LDH-DBS@ $\text{Ni}(\text{OH})_2$ suppressed fire hazard of EP significantly. To our knowledge, it was the first report involved in the 3wt% fraction nanofiller-type fire retardant to achieve UL-94 V-0 of EP.

Fig.4-52 (a) LOI value and UL-94 ratings with inset flaming time; (b), (c), (d) digital images at different combustion time of EP after first 10s flaming; (e), (f) digital images of EP/3LDH-DBS@ $\text{Ni}(\text{OH})_2$ after first 10s flaming; (e), (f) digital images of EP/3LDH-DBS@ $\text{Ni}(\text{OH})_2$ after second 10s flaming

Cone calorimeter test (CCT)

In **Fig.4-53** (a), the addition of LDH- NO_3 , LDH-DBS and LDH-DBS@ $\text{Ni}(\text{OH})_2$ decreased peak heat release rate (pHRR) of EP by 21.1%, 46.8% and 60.6% respectively, which demonstrated that

the fire safety of EP was remarkably increased with LDH-DBS@Ni(OH)₂. In comparison to EP/3LDH-DBS, EP/LDH-DBS@Ni(OH)₂ showed 29.4% reduction of pHRR. Similarly, total heat release (THR) at 200s were reduced by 65.4% after incorporation of LDH-DBS@Ni(OH)₂ (**Fig.4-53** (b)). Meanwhile, average mass loss rate (AMLR) that reflected integral fire intensity and fire growth index (FIGRA) that indicated fire spreading profile were respectively reduced by 52.7% and 82.9% with addition of LDH-DBS@Ni(OH)₂ (**Fig 4-53** (d) and **Table 4-4**). The study of the ratio of COP and CO₂P (**Fig.4-53** (c)) illuminated Ni(OH)₂ self-assembly on LDH-DBS significantly suppressed CO production relative to CO₂ production.

Fig.4-53 (a) HRR, (b) THR, (c) ratio of COP and CO₂P and (d) weight profiles of EP and EP nanocomposites at 50kW/m²

Fire-retardant mechanism

Fire-retardant mechanism was analyzed via vapor-phase and condensed-phase behavior. 3wt% LDH-DBS@Ni(OH)₂ did not change the av-EHC value of EP due to low loading. The condensed-phase mechanism was associated with the improved intumescent char after ultrafine Ni(OH)₂ engineering. The analysis of the formation of higher-quality intumescent char was identical to condensed-phase smoke-suppression mechanism (**Scheme 4-6**). The difference was that the flammable gases to fuel the combustion were the aliphatic-based compounds. The

precursor of smoke was aromatic-based compounds. Herein, at molecular level the ultrafine $\text{Ni}(\text{OH})_2$ modification contributed to the conversion of aliphatic to aromatic compounds, resulting in less flammable gases. Notably, the interfacial catalysis toward higher-quality char accounted for the fire retardancy (Scheme 4-5).

e) Dynamic mechanical behavior of EP/LDH-DBS@ $\text{Ni}(\text{OH})_2$

The dynamic mechanical behavior was investigated via DMA (Fig.4-54). The addition of 3wt% LDH- NO_3 enhanced the storage modulus (G') to 2090 ± 90 MPa from 1697 ± 63 MPa of pristine EP. The glass transition temperature (T_g) was slightly increased to 204°C from 201°C . Compared with EP/3LDH- NO_3 , EP/3LDH-DBS presented the nearly invariable G' of 2061 ± 63 MPa but increased T_g value to 208°C , which illustrated that the motion of EP chain was restricted due to the better intercalation structure of LDH-DBS nanosheets. In parallel, the incorporation of ultrafine $\text{Ni}(\text{OH})_2$ on LDH-DBS nanosheets further improved T_g value of EP to 216°C with nearly unchanged G' of 2040 ± 78 MPa. The notable improvement (15°C) of T_g relative to neat EP matrix was critical to heat-resistant behavior [355]. Meanwhile, the enhancement of T_g in comparison to EP/LDH-DBS illuminated further confined motion of EP chain due to the relatively improved dispersion of nanosheets. To be concluded, the addition of 3wt% LDH-DBS@ $\text{Ni}(\text{OH})_2$ effectively increased the storage modulus and glass transition temperature of EP matrix due to the better intercalation dispersion.

Fig.4-54 Storage modulus and tan delta of EP, EP/3LDH-DBS and EP/3LDH-DBS@ $\text{Ni}(\text{OH})_2$ in dynamic mechanical analysis

CHAPTER 5

Rational design of ignition-delayed and smoke-suppression system

“Ignorance, the root and stem of all evil”

-Plato

5.1 Introduction

The work in this section was focused on the combination of ignition delaying and suppressed smoke into one system with HRR value remained or reduced. Actually, ferrocene-filled PS showed the combination of ignition delaying and suppressed smoke with HRR value slightly increased. However, the rational design of ignition-delayed and smoke-suppressed nanocomposite was in great need. According to the aforementioned strategies to delaying ignition, the increase of thermal inertia (ρck) for thermally-thick sample and (ρc) for thermally-thin sample provided the solution to delaying ignition. The enhancement of the initial thermal and thermal-oxidation stability also offered the alternative solution by means of decreasing volatile release. In terms of smoke suppression, the condensed-phase mechanism toward higher-quality char and vapor-phase mechanism toward lower thermal-oxidation stability of soot offered solutions for smoke suppression. Herein, the increment of thermal inertia and condensed-phase smoke-suppression mechanism were pursued to impart targeted polymer with simultaneous smoke suppression and ignition delaying. The nanocomposite technique was adopted. Epoxy resin (EP) was chosen as the model polymer in consideration of the excellent charring capacity.

Analogous to 2D graphene nanoplatelets with carbon atom linked via sp^2 hybridization, boron nitride nanosheets showed lamellar structure with an equal quantity of boron and nitrogen atoms connected via sp^3 hybridization. Resultantly, EP nanocomposite with boron nitride nanosheets was certified to improve fire safety with delayed ignition time (t_{ig}), reduced heat release and smoke production due to its high thermal conductivity and lamellar structure [235]. Compared with other nanofillers, boron nitride nanosheets presented the superiority in simultaneously delaying ignition and reducing heat release. In order to improve the smoke-suppression and fire-retardant efficiency and systematically investigate the effect of different factors on ignition behavior, the inorganic

interfacial modification on boron nitride nanosheets was adopted [234]. However, the direct in-situ growth of inorganic nanoparticles on boron nitride nanosheets encountered the difficulty owing to lacking of essential active sites. Fortunately, the dopamine chemistry presented the strong bio-adhesion toward inert surface with polydopamine (PDA) as the bridging nano-layer. The result was the inhibition of aggregation of boron nitride nanosheets in polymer matrix, favoring the integral property. PDA facilitated the homogeneous growth of inorganic nanomaterials due to the intensive coordination interaction. Iron-derived nanoparticles (Fe) were regarded as excellent charring catalyst toward EP in consideration of intensive Lewis acidic sites. It was feasible that fire safety (heat release, smoke production and ignition) was profited after the incorporation of Fe on boron nitride surface, which synergistically combined the prominent barrier and high thermal conductivity of boron nitride and the catalytic charring capacity of Fe nanocatalyst. Meanwhile, the thermal exfoliation of boron nitride nanosheets was evidenced to possess more active sites and favor the dispersion in EP matrix. The thermally exfoliated boron nitride will act as the substrate for sequential functionalization rather than pristine boron nitride.

Exceptionally, the sequential functionalization of thermally exfoliated boron nitride nanosheets with PDA and Fe generated the alteration of parameters including thermal conductivity (k), specific heat of capacity (c) and thermal-oxidation stability, which were the key factors to influence ignition. The numerical simulation method of simplified 1D thermal conduction model was adopted to simulate the sample temperature at different downward thicknesses and times. The temperature at different thickness and times were acquired to approximately calculate pyrolysis depth along the downward thickness. Similar to the analysis process in PS/Ferrocene, PS/2SBA-15@Co₃O₄ and PLA/5HNT@MAH@DOPO, physical aspects and chemical aspects were separately studied. The numerical simulation was executed based on the mere physical consideration. The chemical reaction-inducing change of T_{ig} was investigated via the analysis of composition and concentration of volatiles. The pyrolysis depth of bulk sample connected physical and chemical factors together. The comprehensive effect of physical and chemical was reflected on the real temperature curve of top surface. In combination of experimental and numerical results, the effect of k , c and thermal-oxidation degradation on ignition was studied. The effect of iron-derived nanocatalyst (Fe) on suppressing smoke was investigated. Apart from it, the condensed-phase and vapor-phase smoke-suppression mechanism was considered. Particularly, the

interfacial catalysis of Fe nanocatalyst toward polyaromatic reaction was stressed in constructing structurally robust protective chars, which restricted the smoke production.

5.2 Preparation and characterization of targeted nanohybrid

5.2.1 Preparation of BN@PDA@Fe

Thermal exfoliation of h-BN and its PDA functionalization

In the typical procedure, thermally exfoliated boron nitride nanosheets (BN) were obtained after the treatment of h-BN powder at 1000°C in tubular furnace under air atmosphere [356]. Subsequently, 10g h-BN nanosheet was charged into 1L three-neck flask with 800mL buffer solution. The ultrasonication treatment was applied for 30min prior to the addition of 2g DA·HCl with vigorous stirring. The encapsulation and polymerization process occurred with colour turning black (**Scheme 5-1**). After the reaction for 24h, the products (BN@PDA) were collected after vacuum filtration, washing with deionized water and drying overnight.

Scheme 5-1 Preparation process of BN@PDA and BN@PDA@Fe

In-situ growth of Fe nanocatalyst on BN@PDA (BN@PDA@Fe)

10g BN@PDA was dispersed into 350mL deionized water prior to the ultrasonication for 30min. Subsequently, the addition of 2g FeCl_3 was carried out with vigorous stirring. In order to guarantee the coordination of Fe^{3+} and PDA molecules, the reaction persisted for 3h, followed by the drop-wise addition of NaBH_4 solution (1g NaBH_4 and 50mL water). During the slow dripping, the bubbles were generated, which inferred the reduction of Fe^{3+} . After additional 30min reaction, the

materials were filtrated and washed with deionized water for several times. Finally, the product was obtained after vacuum drying overnight and labelled as BN@PDA@Fe. The procedure was illustrated in **Scheme 5-1**.

5.2.2 Characterization of BN@PDA@Fe

Raman and XRD spectra

Raman and XRD spectra were illustrated in **Fig.5-1**. In terms of BN in **Fig.5-1** (a), one peak at 1366cm^{-1} was detected and assigned to E_{2g} tangential mode. The PDA modification on BN surfaces generated an additional peak at 1606cm^{-1} , which was attributed to catechol structure of PDA [357]. Actually, the catechol structure was apt to form the π - π interaction with six-member ring structure of BN, which favoured adhesion and encapsulation. The polar and hydrophilic groups (-OH) in activated BN facilitated the adhesion via hydrogen-bond interplay. However, the invariable location of E_{2g} tangential mode with PDA functionalization illuminated that the π - π interaction was relatively weak. In parallel, the incorporation of Fe did not remarkably change the specific locations of BN and PDA but generated an additional peak at 1555cm^{-1} . The new peak was originated from partial shift of catechol vibration due to the coordination effect between Fe and PDA. The coordination effect facilitated the vibration shift toward low-energy state.

XRD pattern (**Fig.5-1** (b)) of BN exhibited the peaks at 26.4° , 27.2° , 41.2° , 43.5° , 49.6° and 54.6° , which were assigned to the crystal faces of (002), (010), (100), (101), (102) and (004) respectively. Additionally, compared to the pristine BN, the new peak emerged at 27.2° from (010) reflection of B(OH)_3 due to the high-temperature thermal exfoliation. The peak presence of lamellar structure evidenced the partial rather than complete exfoliation. After PDA encapsulation, all the peaks of BN persisted with the exception of B(OH)_3 reflection [235]. The possible cause for disappearance of B(OH)_3 reflection was due to the compression-derived shrinkage from encapsulation. In parallel, the Fe growth on BN@PDA gave rise to additional peaks at 36.5° , 45.6° and 53.1° , which were corresponding to $\gamma\text{-Fe}_2\text{O}_3$, Fe^0 and $\gamma\text{-FeOOH}$ respectively with the dominant composition of $\gamma\text{-Fe}_2\text{O}_3$. After the reduction of Fe^{3+} , Fe^0 was instantly generated prior to oxidation to $\gamma\text{-FeOOH}$ and dehydration to $\gamma\text{-Fe}_2\text{O}_3$. Therefore, the iron-derived catalyst was the mixture of major $\gamma\text{-Fe}_2\text{O}_3$ and minor $\gamma\text{-FeOOH}$ and Fe^0 .

Fig.5-1 (a) Raman Spectra and (b) XRD spectra of BN, BN@PDA and BN@PDA@Fe

XPS spectra

Aiming to further confirm the composition of BN@PDA@Fe, XPS measurement was performed and showed in **Fig.5-2**. In **Fig.5-2** (a), the full XPS spectra illustrated the inclusion of B, N, C, Fe and O in BN@PDA@Fe. O1s peak fitting in **Fig.5-2** (b) displayed the C=O and C-O bands at 331.5eV and 332.5eV separately, which were attributed to catholic structure. In parallel, N1s fitting results in **Fig.5-2** (c) manifested the presence of different N sources of BN and PDA. Importantly, Fe2p spectra certified the presence of zero-valent iron at 706.5eV and γ -Fe₂O₃ (Fe2p3/2 at 712.2eV and Fe2p1/2 at 725.8eV) [358].

Fig.5-2 (a) Full XPS spectra; (b) O1s spectra; (c) N1s spectra and (d) Fe2p spectra of BN@PDA@Fe

TEM and EDS analysis

SEM, TEM and EDS mapping were displayed in **Fig.5-3**. In SEM images (**Fig.5-3** (a) and (c)), the bio-inspired engineering of PDA on BN did not influence the morphology. In contrast, the incorporation of Fe nanocatalyst generated slight alteration with stretched nanosheet (red circles in **Fig.5-3** (e)). In TEM images (**Fig.5-3** (b)), BN possessed typically lamellar structure with lateral size in micron-scale and thickness in nano-scale. The analysis of BN edge in **Fig.5-3** (b) demonstrated the ordered stacked structure with few layers (selected area electron diffraction (SAED) in inset **Fig.5-3** (b)), which reflected the limited exfoliation in combination of the single-sheet observation in **Fig.5-3** (g). Meanwhile, the high angle angular dark field (HAADF) image with B and N mapping (**Fig.5-3** (h)) and O mapping (**Fig.5-3** (i)) acquired the consistent results with XPS results. In parallel, PDA encapsulation of BN (**Fig.5-3** (d) and (j)) generated obscure edge without any change in SEAD patterns (inset in **Fig.5-3** (d)). In contrast, in **Fig.5-3** (f) and (k), Fe nanocatalyst in the strip shape was successfully in-situ grown on BN@PDA, which was demonstrated SEAD patterns (inset in **Fig.5-3** (f)). Higher magnification image (**Fig.5-3** (l)) demonstrated that Fe^0 nanoparticles ((110), 0.21nm) were surrounded by $\gamma\text{-Fe}_2\text{O}_3$.

Fig.5-3 SEM images of (a) BN, (c) BN@PDA and (e) BN@PDA@Fe; TEM images with inset (SAED) of (b) BN, (d) BN@PDA and (f, l) BN@PDA@Fe; (g) high angle angular dark field (HAADF) with (h) B and N mapping and (i) O mapping of thermally exfoliated BN; (j) HAADF

of BN@PDA; (k) Fe mapping of BN@PDA@Fe

5.2.3 Preparation of composites

EP nanocomposites with the fraction of 6wt% BN, BN@PDA and BN@PDA@Fe were respectively prepared. In the typical procedure, EP monomer was mixed with nanofillers at 60°C to acquire the preliminary dispersion. Subsequently, the triple-milling treatment was applied to generate the better nano-dispersion under the strong shear. With vigorous stirring, the curing agent DETA with stoichiometric amount was added to mixture, after which the degas treatment was executed using the ultrasonication for 5min. The degassed mixture was then casted into the silicon mold prior to the static curing process for 24h at ambient temperature. After the ambient curing, the resultant samples were transferred for heated curing at 120°C for additional 2h. In parallel, the neat EP was fabricated via the identical step.

5.2.4 Dispersion of nanofillers in EP matrix

XRD pattern

EP, EP/6BN and EP/6BN@PDA@Fe were selected for bulk XRD test (**Fig.5-4**) in consideration of the similar blending property of BN@PDA and BN@PDA@Fe. The drum peaks emerged at around 18.5° and 41.2°, which were characteristic of EP matrix. After the addition of BN and BN@PDA@Fe, the drum peaks retained. Additionally, BN and BN@PDA@Fe brought extra peaks located at 26.4°, which was assigned to (002) crystal face of BN. The invariable location of (002) reflection demonstrated that the lamellar BN nanosheets were not intercalated or exfoliated during processing and curing process, which was consistent with limited thermal exfoliation in XRD (**Fig.5-1** (b)) and TEM image (inset in **Fig.5-3** (f)).

Fig.5-4 XRD patterns of EP, EP/6BN and EP/6BN@PDA@Fe

SEM observation

The dispersion state of nanofillers in EP matrix was further investigated by SEM. EP possessed relatively smooth fractured surface (**Fig.5-5** (a)). In comparison, the addition of BN generated notable wrinkled surface with the aggregates of BN, which were confirmed by B mapping (inset in **Fig.5-5** (b)). In parallel, the PDA modification of BN generated slightly more wrinkled surface with better BN nano-dispersion (marked with arrays) (**Fig.5-5** (c)). Furthermore, EP/6BN@PDA@Fe possessed even more wrinkled surface than that of EP/6BN@PDA with more uniform nano-dispersion in EP matrix (marked with arrays). In combination with XRD result, BN, BN@PDA and BN@PDA@Fe demonstrated nano-dispersion state with BN@PDA@Fe more homogeneous in EP matrix (**Fig.5-5** (e) and (f)).

Fig.5-5 Cyro-fractured surface of (a) EP, (b) EP/6BN with inset EDS spectra and B mapping of selected area, (c) EP/6BN@PDA with inset B mapping of selected area and (d) EP/6BN@PDA@Fe; schematic illustration of (e) EP/6BN and (f) EP/6BN@PDA@Fe

5.3 Property and mechanism of EP/BN@PDA@Fe

5.3.1 Ignition behavior of EP/BN@PDA@Fe

The t_{ig} value was recorded via visualization, heat release rate (HRR) and mass profile in **Fig.5-6**. Heat flux of 35kW/m^2 was selected on behaviors of low and high heat flux based on the relationship of t_{ig} and imposed heat flux Q_{ex} ($t_{ig} \propto Q_{ex}^{-0.5}$). The t_{ig} value from three assessments showed a similar trend with visualization eventually employed to acquire t_{ig} . Compared with neat EP (t_{ig} , $80 \pm 3\text{s}$), the addition of 6wt% BN notably increased the t_{ig} value to $102 \pm 3\text{s}$. The PDA modification

on BN slightly reduced the t_{ig} value to 98 ± 3 s. In contrast, the successive modification of PDA and Fe nanocatalyst further lowered the t_{ig} value to 89 ± 1 s. However, EP/6BN, EP/6BN@PDA and EP/6BN@PDA@Fe possessed the delayed t_{ig} value relative to that of neat EP. Next work was to investigate the causes that resulted in the change of t_{ig} value via experimental and numerical approaches.

Fig.5-6 (a) Visualization assessment of t_{ig} , (b) HRR profile and (c) mass profile around ignition

5.3.2 Ignition mechanism of EP/BN@PDA@Fe

It was noted that the ignition time was determined by two processes (temperature-rising process and ignition temperature) from the surface temperature curve. In order to clearly study ignition, physical and chemical factors were separately studied. Thermal decomposition-related chemical reaction influenced aforementioned two processes (temperature-rising process and ignition temperature), which resulted in the change of temperature-rising rate particularly after thermal-oxidation degradation stage. The thermal-oxidation degradation-inducing change of T_{ig} was investigated via the analysis of composition and concentration of volatiles. Physical factors (density ρ , specific heat of capacity c , thermal conductivity k) merely affected the temperature-rising process. In order to verify the effect of physical factors on temperature-rising rate and decouple the chemical factors from physical factors, the numerical simulation was executed based on the mere physical consideration. The comprehensive effect of physical and chemical factors was reflected on the real temperature curve of top surface. The comparison of real and simulated temperature curve illuminated the effect of various factors (physical and chemical factors) on ignition.

Numerical simulation

The temperature simulation was performed using finite element with the simple one dimensional (1D) conductive equation (**Scheme 5-2**) [176]. The basic assumption was made. The change of

physical parameters (ρ , c , k) due to the chemical reaction was not considered. The heat from the thermal-oxidation degradation was regarded as zero due to the relatively low value. In terms of thermosetting EP matrix, the generation of bubbles and the mass exchange between different thick layers were neglected (**Fig.5-7**). During the heating, the heat loss from thermal conductivity, thermal convection and black-body radiation and spectroscopic adsorption of heat from volatile were considered. Temperature-dependent thermal conductivity (k) and specific heat of capacity (c) were acquired based on the linear correlation with those at ambient temperature according to the previous models [359-362]. The spectroscopic adsorption of heat from volatiles was taken into account with the heat attenuation complying with the reported rule after the sample started to thermally degrade [163, 168, 172]. In detail, 1D conductive equation governed the heat behavior (Equation (5-1)) due to the similarity to heating of solid bulk.

$$\rho c \frac{\partial T}{\partial t} = \frac{\partial}{\partial x} \left(k \frac{\partial T}{\partial x} \right) \quad (5-1)$$

The entire heating process was divided to two parts, *i.e.* from ambient temperature to thermal-oxidation degradation and from thermal-oxidation degradation to ignition temperature. The boundary conditions are respectively:

After heating: $T=T_0$, $t=0$,

Top surface:

$$-k \frac{\partial T}{\partial x} \Big|_{x=0} = (1-r)Q_{ex}$$

Before thermal-oxidation temperature: $T=T_{5wt\%}$,

Top surface:

$$-k \frac{\partial T}{\partial x} \Big|_{x=0} = (1-r)Q_{ex} - \varepsilon \sigma (T_{5wt\%}^4 - T_0^4) - h(T_{5wt\%} - T_0)$$

After thermal-oxidation temperature: $T=T_{5wt\%}$,

Top surface:

$$-k \frac{\partial T}{\partial x} \Big|_{x=0} = (1-r) \exp(-\beta(t-t_d))Q_{ex} - \varepsilon \sigma (T_{5wt\%}^4 - T_0^4) - h(T_{5wt\%} - T_0)$$

$$\beta = \beta_0 \exp(bQ_{ex})$$

Where ρ , T_0 , $T_{5wt\%}$, l_0 , Q_{ex} , t_d , β , β_0 , b , h , ε , σ and r were respectively sample density, ambient temperature (298K), temperature at 5% mass loss (607K for EP, EP/6BN and EP/6BN@PDA; 604K for EP/6BN@PDA@Fe, **Fig.5-8** and **Table 5-1**), sample thickness, external radiation power,

time to $T_{5wt\%}$, attenuation factor, initial attenuation factor (0.0025), attenuation coefficient (0.1), convection heat conductive coefficient (23), Stefan–Boltzmann radiation constant, emissivity (0.9) and heat radiation loss (0.05). In addition, the thermal conductivity and specific heat of capacity were treated as the linear dependence to temperature as $k_0+4.405\times10^{-4}(T-T_0)$ and $c_0+4.1\times10^{-3}(T-T_0)$ respectively in terms of the four samples (k_0 and c_0 thermal conductivity and specific heat of capacity at ambient temperature) .

Scheme 5-2 1D thermally-conductive model based on up-to-down microelement

Fig.5-7 Digital images at the ignition moment of (a) EP, (b) EP/6BN, (c) EP/6BN@PDA and (d) EP/6BN@PDA@Fe

Chemical factors

Volatile concentration and composition

Thermal-oxidation degradation at high heating rate was closely correlated to thermal-oxidation behavior in CCT prior to ignition. The heating rate in combustion zone of CCT at 35kW/m^2 was reported to reach roughly 150°C/min [174]. It was not completely precise but acceptable to qualitatively employ thermal-oxidation degradation in TG at heating rate of 10°C/min to qualitatively simulate realistic thermal-oxidation degradation in CCT prior to ignition in **Fig.5-8** and **Table 5-1**.

Fig.5-8 (a) TG and (b) DTG curves of EP, EP/6BN, EP/6BN@PDA and EP/6BN@PDA@Fe at 10°C/min

Table 5-1 TG result of EP, EP/6BN, EP/6BN@PDA and EP/6BN@PDA@Fe

	$T_{5wt\%}(^\circ\text{C})$	CY at T_{ig}
EP	334	76
EP/6BN	334	76
EP/6BN@PDA	334	82
EP/6BN@PDA@Fe	330	72

T_{ig} : Temperature at ignition $T_{5wt\%}$: Temperature at 5% mass loss CY: char yield

It was noted that the degradation behavior in CCT prior to ignition did not totally belong to thermal-oxidation degradation. During heating, the underlying EP matrix actually was insulated from air because of the bulk geometry and thermosetting feature of EP specimen (without movement upward and downward of polymer melts). Hence, the thermal degradation prior to ignition was the combination of thermal and thermal-oxidation degradation. In order to clarify volatile species and their profiles, TG-FTIR at N_2 atmosphere was performed in **Fig.5-9**. FTIR spectra of EP and EP nanocomposites presented the similar changing trend along time, which illustrated the unchanged degradation route after the addition of BN, BN@PDA and

BN@PDA@Fe. In **Fig.5-10**, the volatiles predominantly contained aliphatic (2972cm^{-1}), aromatic (1600cm^{-1}), carbonyl (1730cm^{-1}), double-bond (3034cm^{-1}) and phenol compounds (3644cm^{-1}). The addition of BN, BN@PDA and BN@PDA@Fe did not change the volatile species but changed the release amount.

Fig.5-9 3D diagram in TG-FTIR of (a) EP, (b) EP/6BN, (c) EP/6BN@PDA and (d) EP/6BN@PDA@Fe

Fig.5-10 FTIR spectra at maximum degradation rate of EP, EP/6BN, EP/6BN@PDA and EP/6BN@PDA@Fe

The corresponding volatile profiles were specialized in **Fig.5-11** and **Fig.5-12**. Taking the overlapping part of these compounds into account, we defined the flammable gases as the combination of aromatic and aliphatic compounds. Herein, phenol, double-bond and carbonyl compounds played a relatively less important role in the composition and concentration of volatiles compared with aromatic and aliphatic compounds. The addition of BN into EP matrix

nearly kept constant the amount of aromatic compounds and aliphatic compounds before T_{ig} (T_{ig} had the corresponding time of ca. 42min in TG-FTIR at 352 °C and 355°C). Resultantly, the amount ratio of aliphatic and aromatic compounds of EP and EP/6BN (**Fig.5-11** (c)) remained unchanged, which indicated the similar tendency of ignitability due to the unchanged C/H ratio. In combination of the nearly identical amount of aliphatic and aromatic compounds and their unchanged amount ratio, it was inferred that the ignitability of volatiles remained unchanged after the addition of BN. In parallel, the PDA modification of BN remarkably decreased the release of aliphatic and aromatic compounds compared with EP/6BN due to the promoted barrier effect from more uniform dispersion of nanofillers. The amount ratio of aliphatic and aromatic compounds revealed the reduced value, which indicated the higher C/H value. The amount of aliphatic and aromatic compounds and their ratio illustrated the notably reduced ignitability.

Fig.5-11 Integral curves of intensity versus time of (a) aromatic and (b) aliphatic compounds; (c) the integral amount ratio of aliphatic to aromatic compounds of EP, EP/6BN, EP/6BN@PDA and EP/6BN@PDA@Fe

In contrast, the incorporation of Fe nanocatalyst remarkably increased the more release of aromatic and aliphatic compounds compared with those of EP/6BN@PDA before T_{ig} , which

indicated that Fe nanocatalyst promoted the generation of more flammable gases. The amount ratio of aliphatic and aromatic compounds disclosed that the incorporation of Fe nanocatalyst promoted the polyaromatic reaction toward the much higher C/H. The increased amount of aromatic and aliphatic and the higher C/H contradictorily resulted in higher ignitability of volatiles from EP/6BN@PDA@Fe relative to EP/6BN@PDA. In this case, the comparison of EP and EP/6BN@PDA@Fe showed that EP/6BN@PDA@Fe release more aromatic compounds without notable change of aliphatic compounds. Even though the higher C/H ratio existed due to the increased amount ratio of aromatic to aliphatic compounds, the increased release of aromatic compounds resulted in the more tendency of ignitability. Hence, according to the amount of aromatic and aliphatic compounds and the amount ratio of them revealed the trend of ignitability of the volatiles from the sample: EP/6BN@PDA@Fe=EP>EP/6BN>EP/6BN@PDA. However, the isolated analysis of the amount ratio illuminated the trend of ignitability of the mixed flammable gas: EP=EP/6BN>EP/6BN@PDA>EP/6BN@PDA@Fe. The analysis result of ignitability was roughly consistent with the thermal-oxidation degradation result in **Fig.5-8** and **Table 5-1**.

Fig.5-12 Integral curves of intensity of (a) phenol, (b) double-bond and (c) carbonyl compounds of EP, EP/6BN, EP/6BN@PDA and EP/6BN@PDA@Fe in TG-FTIR test

Physical factors

The experimental and simulated temperature profile on top surface was exhibited in **Fig.5-13** and **Fig.5-14**. On the top surface, EP and EP nanocomposites exhibited continuous temperature-rising process with early and late stage at relatively higher and lower heating rate (**Fig.5-13** (a) and **Fig.5-14**), which reflected the great impact of heat dissipation at relatively high temperature. The comparison in **Fig.5-13** (b) revealed that the temperature-rising rate of EP/6BN was much lower than that of EP, which was due to the remarkably enhanced thermal conductivity (k) and specific heat of capacity (c) (**Table 5-2**). Herein, k and c were respectively linearly correlated to k_0 and c_0 values. Resultantly, the enhanced k was capable of conducting away the external heat more quickly and the slightly increased c value enabled to result in the slower temperature-rising rate.

Fig.5-13 (a) Temperature profile of EP, EP/6BN, EP/6BN@PDA and EP/6BN@PDA@Fe; comparison of (b) EP and EP/6BN, (c) EP/6BN and EP/6BN@PDA and (d) EP/6BN@PDA@Fe

In parallel, the comparison in **Fig.5-13** (c) demonstrated that the PDA modification incited nearly no change of the temperature profile at the early stage. The result was certified by the combination of increased k (induced by more homogeneous dispersion of nanofillers) and decreased c (**Table 5-2**). The increased k favored the dissipation of heat on the top surface and the remarkably decreased c benefited the rapid temperature-rising process, which reflected the similar

importance of k and c in temperature-rising process. At the late stage, the temperature of EP/6BN@PDA increased slightly more quickly than that of EP/6BN, which determined the lower t_{ig} , which was probably due to the different dependence of kc on temperature for both cases. The small difference at the late stage of surface temperature curves and resultant tiny alternation of t_{ig} reflected the neglectable impact of physical reaction at the late stage on the ignition behavior.

The comparison in **Fig.5-13** (d) illustrated that EP/6BN@PDA@Fe possessed slightly higher temperature-rising rate relative to EP/6BN@PDA at the late stage due to the reduced kc . Particularly, the temperature-rising rate above ca. 300°C turned slightly more remarkable, which was absent in the simulation (**Fig.5-14**). It was reasonable that the thermal-oxidation degradation played an important role at the period. However, the difference of surface temperature curves was adequately tiny to incite the alternation of t_{ig} . The combination of the comparative analysis between EP, EP/6BN, EP/6BN@PDA and EP/6BN@PDA@Fe demonstrated that the physical parameters (ρ , c and k) affected the heating process. The simulation result (**Fig.5-14**) presented the similar result that was in a good agreement with experimental results. The fitted results illuminated the key impact of physical factors in determining the ignition behavior. For simplicity, the sample of 4mm thickness was located between thermally thick and thermally thin sample with the preference of thermally thick sample [181]. According to rough Equation (1-10) under the circumstance of no chemical consideration, t_{ig} was determined by thermal inertia ($k\rho c$) with the invariable values of ρ , T_{ig} , T_0 , Q_{ex} and Q_{cri} in EP, EP/6BN, EP/6BN@PDA and EP/6BN@PDA@Fe. In consideration of unchanged ρ , the kc values became key factors with the value of EP, EP/6BN, EP/6BN@PDA and EP/6BN@PDA@Fe as 0.455a.u, 0.659a.u, 0.511a.u and 0.473.a.u respectively. The disclosed tendency from Equation (1-10) was in good agreement with the experimental t_{ig} value, which reflected the predominant physical factors to impact ignition.

Fig.5-14 Simulated surface temperature prior to ignition of EP, EP/6BN, EP/6BN@PDA and EP/6BN@PDA@Fe

Table 5-2 Specific heat of capacity and thermal conductivity at ambient temperature

	Thermal conductivity (k_0 , $\text{W m}^{-1} \text{K}^{-1}$)	Specific heat of capacity (c_0 , $\text{J kg}^{-1} \text{K}^{-1}$)
EP	0.261	1.361
EP/6BN	0.290	1.524
EP/6BN@PDA	0.335	1.156
EP/6BN@PDA@Fe	0.339	1.050

Pyrolysis depth to link physical and chemical factors

In the realistic bulk sample, the pyrolyzed depth connected the physical and chemical aspects together. The different physical factors resulted in different pyrolyzed depth along the thickness, which further gave rise to different volatile concentration. The realistic ignitability of flammable gases above the samples should consider the pyrolyzed depth and the composition and concentration in TG-FTIR results. The pyrolyzed depth was analyzed via the simulated temperature at different layers.

Finite element simulation offered the information of temperature at different layers (**Fig.5-15** and **Table 5-3**). The thermal-oxidation degradation temperature of EP, EP/6BN, EP/6BN@PDA and EP/6BN@PDA@Fe were 334°C, 334°C, 334°C and 330°C respectively. Clearly, the onset thermal-oxidation degradation temperature ($T_{5wt\%}$) values of EP, EP/6BN, EP/6BN@PDA and EP/6BN@PDA@Fe were located between 0mm and 0.5mm. The rough estimation of pyrolyzed thickness was determined by the temperature curves between 0mm and 0.5mm. The pyrolyzed depth of different samples at the ignition moment in **Fig.5-15** illustrated the tendency of

EP/6BN<EP=EP/6BN@PDA=EP/6BN@PDA@Fe. Therefore, the ignitability determined by pyrolyzed depth confirmed the tendency of EP/6BN<EP=EP/6BN@PDA=EP/6BN@PDA@Fe.

Table 5-3 Temperature (°C) at different downward thickness (0mm, 0.5mm, 1mm, 1.5mm, 2mm, 2.5mm, 3mm, 3.5mm, 4mm) at ignition moment of (a) EP, (b) EP/6BN, (c) EP/6BN@PDA and (d) EP/6BN@PDA@Fe

	0mm	0.5mm	1mm	1.5mm	2mm	2.5mm	3mm	3.5mm	4mm
EP	355	328	302	278	256	236	219	204	192
EP/6BN	355	327	302	279	253	240	223	209	198
EP/6BN@PDA	355	333	312	293	274	258	243	230	219
EP/6BN@PDA@Fe	352	330	307	287	269	252	237	224	213

Fig.5-15 Temperature curves at different downward thickness (0mm, 0.5mm, 1mm, 1.5mm, 2mm, 2.5mm, 3mm, 3.5mm, 4mm) of (a) EP, (b) EP/6BN, (c) EP/6BN@PDA and (d)EP/6BN@PDA@Fe

Integration of physical and chemical factors

The physical and chemical factors were integrated into the real surface temperature curves. The physical factors included thermal conductivity and specific heat of capacity, which incited different heating rate of surface temperature. The chemical factors referred to the

thermal-oxidation degradation process, which included the composition and concentration of flammable gases. Meanwhile, the pyrolyzed depth, which was determined by the physical factors, played an important role in the flammable gases. In **Table 5-4**, in terms of delayed EP/6BN relative to EP, the impact factors of ignition time were pyrolyzed depth (shortening effect), thermal conductivity (delaying effect) and specific heat of capacity (delaying effect). According to three elements of combustion, flammable gases were supposed to be the important factor of T_{ig} in condition that other environment conditions (*e.g.*, oxygen, moisture, pressure) remained invariable [363]. The identical T_{ig} value in **Fig.5-13** disclosed the weak impact of flammable gases on ignition behavior, which demonstrated the predominant impact of physical factors (k and c). In terms of EP/6BN@PDA and EP/6BN, after the chemical modification of PDA, the chemical factors delayed the ignition with the predominant physical factors (k and c) shortening the ignition. Simultaneously, the equivalent effect of specific heat of capacity (c) to thermal conductivity (k) was revealed.

In parallel, in terms of EP/6BN@PDA and EP/6BN@PDA@Fe, after the decoration of Fe, the chemical factors shortening t_{ig} and the physical factors (kc) slightly shortening t_{ig} . In combination of the heating rate at the late stage (**Fig.5-13** (c)), the chemical and physical factors acted as the weak role in decreasing t_{ig} . Above all, in terms of chemical factors, the amount and concentration of flammable gases were more important than composition in determining ignition. Moreover, the physical factors played a more important role than chemical factors.

Table 5-4 Integration of chemical and physical factors on ignition time

	Chemical factors			Physical factors		
	A	B	σ	k	c	kc
EP (reference)	□	□	□	□	□	□
EP/6BN	□	□	-	+	+	+++
EP/6BN@PDA	++	+	-	++	--	++
EP/6BN@PDA@PDA	--	+++	-	++	--	+

A : concentration of flammable gases B : composition of flammable gases σ : pyrolyzed depth k : thermal conductivity
 c : specific heat of capacity kc : k multiplied by c +: delaying effect -: shortening effect □: no change

5.3.3 Smoke-suppression behavior of EP/BN@PDA@Fe

Smoke-suppression data

The smoke production was illustrated in **Fig.5-16** and **Table 5-5**. Herein, the peak smoke production rate (peak SPR) and total smoke production (TSP) at 350s reflected the maximum smoke hazard and accumulated smoke hazard respectively. In terms of neat EP, the peak SPR and TSP at 350s reached 0.194 ± 0.020 m²/s and 21.5 ± 0.9 m² respectively. The addition of 6wt% BN imparted EP with decreased peak SPR (0.158 ± 0.020 m²) and TSP at 350s (18.2 ± 1.3 m²). In parallel, the PDA modification increased the peak SPR and TSP value at 350s to 0.225 ± 0.03 m²/s and 22.4 ± 1.4 m², which evidenced the negative effect of PDA modification. In order to clarify the causes, the thermogravimetric (TG) analysis was performed to obtain the thermal stability of the residues.

Fig.5-16 (a) SPR and (b) TSP curves of EP and EP nanocomposites

Table 5-5 CCT data of EP and EP composites (35kW/m²)

Sample	Peak SPR (m ² /s)	pHRR (kW/m ²)	THR(MJ/m ²) at 350s	TSP (m ²) at 350s	AMLR(g/s)	FIGRA (kW/(m ² ·s))
EP	0.194 ± 0.02	1208 ± 45	97.4 ± 3.7	21.5 ± 0.9	0.130 ± 0.007	6.75
EP/6BN	0.158 ± 0.02	907 ± 32	88.3 ± 3.1	18.2 ± 1.3	0.094 ± 0.006	4.72
EP/6BN@PDA	0.225 ± 0.03	1158 ± 39	106.7 ± 4.2	22.4 ± 1.4	0.131 ± 0.006	7.65
EP/6BN@PDA@Fe	0.148 ± 0.02	738 ± 27	83.2 ± 2.5	14.5 ± 0.5	0.085 ± 0.003	4.59

pHRR: Peak heat release rate THR at 350s: Total heat release at 350s TSP at 350s: Total smoke production at 350s

AMLR: Average mass loss rate FIGRA: Fire growth index Peak SPR: Peak smoke production rate

Actually, TG analysis (**Fig.5-17** and **Table 5-6**) illuminated that the PDA modification of BN decreased the char yield at 650°C, which probably resulted in the structural damage of carbonaceous layers [364]. The decoration of iron-derived nanoparticles (Fe nanocatalyst) on BN@DPA nanosheets notably reduced the peak SPR and TSP at 350s by 24.6% and 28.6% respectively compared to that of neat EP. The enhancement of smoke-suppression behavior compared with that of EP/6BN@PDA was consistent with the char yield in TG analysis.

Fig.5-17 TG curves of EP and EP nanocomposites with the amplified part

Table 5-6 TG result of EP, EP/6BN, EP/6BN@PDA and EP/6BN@PDA@Fe

	$T_{5wt\%}$ (°C)	$T_{50wt\%}$ (°C)	CY (%) at 650°C
EP	336	373	10.7
EP/6BN	336	375	18.3
EP/6BN@PDA	335	377	16.7
EP/6BN@PDA@Fe	328	363	19.8

$T_{5wt\%}$: Temperature at 5% mass loss $T_{50wt\%}$: Temperature at 50% mass loss CY: char yield

5.3.4 Smoke-suppression mechanism of EP/BN@PDA@Fe

Similar to the aforementioned method, the smoke-suppression mechanism was discussed in terms of the condensed-phase and vapor-phase mechanism. The condensed-phase mechanism was associated with the formation of the protective carbonaceous layer with the direct consequence of the reduced volatile release. The vapor-phase mechanism was involved in the promoted combustion of smoke intermediates (soot).

Condensed-phase mechanism-Carbonaceous layer analysis

During combustion, EP generated a small amount of char with isolated and loose structure (**Fig.5-18** (a1) and (a2)). The incorporation of BN resulted in larger amount of char with closer stacking and more compact structure (**Fig.5-18** (b1) and (b2)). SEM image showed fluffy surface that contained the naked particles (**Fig.5-19** (b)). After the PDA modification, the char possessed the hollows in the center with loosely stacked char pieces (**Fig.5-18** (c1) and (c2)). SEM observation of the interior surface illustrated that naked BN particles partially merged into surface with unexpected generation of macroscopic holes (**Fig.5-19** (c)). The probable cause was closely correlated to the deteriorated high-temperature stability in TG result (**Fig.5-17** and **Table 5-6**). It

was reasonable that compared to EP/6BN, the char from EP/6BN@PDA generated less protection towards the underlying unpyrolyzed EP.

Fig.5-18 Digital images of (a1) side and (a2) top views of EP, (b1) side and (b2) top views of EP/6BN, (c1) side and (c2) top views of EP/6BN@PDA and (d1) side and (d2) top views of EP/6BN@PDA@Fe

In contrast, the incorporation of Fe nanocatalyst on BN@PDA gave rise to continuous and compact char structure with less fracture, which was regarded as the excellent carbonaceous layer structure (**Fig.5-18** (d1) and (d2)). SEM analysis (**Fig.5-19** (d)) revealed that even though the holes were maintained, the naked BN nanosheets (characterized by XRD in **Fig.5-20** (a)) were almost embedded into char with generation of smoother and stronger interior surface. The detected fluffy char structure (**Fig.5-19** (d)), probably from the catalytic charring of Fe nanocatalyst, was considered to favor the strengthening of the char structure. The improved solid char structure compensated the impact of the holes. The deep analysis at the molecule scale was put forward about the interfacial catalysis of Fe. The heating process promoted the thermal degradation of EP

matrix and PDA molecule toward the small-molecule products (*i.e.*, aliphatic compounds and aromatic compounds). Furthermore, the catalytic charring reaction of small-molecule products by Fe nanocatalyst occurred toward higher polyaromatic degree, which was evidenced by the decreased ratio of aliphatic to aromatic compounds in TG-FTIR (**Fig.5-20** (b)). The primary char with higher polyaromatic degree resultantly surrounded the BN nanosheets, which reinforced the composite char. The catalytic charring reaction of Fe nanocatalyst was proposed to be originated from the C-C coupling reaction.

Fig.5-19 SEM images of interior surface with inset high-magnification images of (a) EP, (b) EP/6BN, (c) EP/6BN@PDA and (d) EP/6BN@PDA@Fe

Fig.5-20 (a) XRD pattern of the obtained char after CCT; (b) the amount ratio of aliphatic and aromatic compounds of EP, EP/6BN, EP/6BN@PDA and EP/6BN@PDA@Fe

Condensed-phase mechanism-Volatile evolution

Volatile evolution was obtained via TG-FTIR. **Fig.5-21** illustrated that the smoke precursors

(aromatic, phenol and double-bond compounds) of EP/6BN@PDA@Fe were more than those of EP, EP/6BN and EP/6BN@PDA in terms of whole release amount. It was stressed that TG-FTIR was carried out in the microgram-scale while CCT was performed in gram-scale. According to the char yield at 650°C (EP/6BN@PDA@Fe possessed higher char yield than counterparts), the gram-scale CCT test was supposed to generate the more intensive protection from the carbonaceous layer relative to the milligram-scale TG. Therefore, the actual release of smoke precursors of EP/6BN@PDA@Fe in CCT was supposed to be lower than those in TG-FTIR. Apart from it, Fig.5-11 (c) and Fig.5-20 (b) presented the conversion from aliphatic compounds to unstaturated compounds, which played an important role in the increase of aromatic compounds.

Fig.5-21 Integral curves of intensity versus time of (a) aromatic compounds, (b) phenol compounds and (c) double-bond compounds

Vapor-phase mechanism

The vapor-phase mechanism was to investigate the thermal-oxidation stability of soot of EP and EP nanocomposites. In Fig.5-22 (a), the addition of 6wt% BN, BN@PDA and BN@PDA@Fe did not decrease the initial thermal-oxidation stability ($T_{5wt\%}$, 479°C) of smoke intermediate of EP matrix. In parallel, the addition of BN and BN@PDA did not change the temperature at maximum mass loss rate (T_{max} , 608°C) (Fig.5-22 (b)). The addition of BN@PDA@Fe reduced T_{max} by 7°C

probably due to the change of the soot composition because Fe nanocatalyst with ultra-high boiling point was not capable to enter the soot. In combination of $T_{5wt\%}$ and T_{max} , a nearly identical amount of soot from EP, EP/6BN, EP/6BN@PDA and EP/6BN@PDA@Fe were combusted at the combustion temperature (about 550°C). Therefore, the vapor-phase mechanism was weak in smoke suppression of EP/6BN@PDA@Fe. The condensed-phase mechanism was the dominant mechanism to suppress smoke production.

Fig.5-22 (a) TG and (b) DTG curves of soot of EP, EP/6BN, EP/6BN@PDA and EP/6BN@PDA@Fe

5.3.5 Fire retardancy of EP/BN@PDA@Fe

The integral fire retardancy was investigated via LOI, UL-94 horizontal burning test and CCT.

LOI test and UL-94 horizontal burning test

The LOI result was showed in **Fig.5-23**. Compared with neat EP (LOI, 24.2%), EP/6BN, EP/6BN@PDA and EP/6BN@PDA@Fe presented LOI value to 31.2%, 28.5% and 34.2% respectively. The addition of BN nanosheets into EP increased LOI value, which was attributed to barrier effect and increased thermal conductivity (**Table 5-2**). The char of EP/6BN shielded the heat and flammable gases, further interrupting the combustion. The increased thermal conductivity favoured the heat dissipation, which extinguished the fire from another aspect. In contrast, the incorporation of PDA unexpectedly decreased LOI value despite thermal conductivity was increased. The probable reason was the worse char quality, which was incited by high-temperature instability of EP/6BN@PDA in TG analysis (**Fig.5-17**). The combustion of PDA (at the interface between EP and BN) possibly damaged the char structure of EP/6BN. In contrast, the incorporation of Fe nanocatalyst increased LOI value by 3.0% and 5.7% respectively compared to EP/6BN and EP/6BN@PDA. The thermal conductivity of EP/6BN@PDA and

EP/6BN@PDA@Fe remained almost equal. In the sense, the improved char quality with higher char yield (**Fig.5-17**) probably accounted for enhanced LOI value of EP/6BN@PDA@Fe relative to EP/6BN@PDA.

Fig.5-23 LOI value of EP and EP nanocomposites

Fig.5-24 Horizontal burning profiles of (a) EP, (b) EP/6BN, (c) EP/6BN@PDA and (d) EP/6BN@PDA@Fe

UL-94 horizontal burning test (**Fig.5-24**) demonstrated that EP and EP nanocomposites possessed self-extinguishing attribute with the difference in burning length and time. At 44s, EP/6BN and EP/6BN@PDA@Fe generated slightly weaker flame than EP and EP/6BN@PDA, which was in good consistency with LOI result. As the flame was at the critical point of self-extinguishment, EP, EP/6BN, EP/6BN@PDA and EP/6BN@PDA@Fe took the burning time of 3min 55s, 1min 30s, 1min 56s and 1min 16s, correspondingly. In parallel, the burning length

(marked in red dot-line rectangle) revealed the burning sequence of EP>EP/6BN@PDA>EP/6BN>EP/6BN@PDA@Fe. The burning time and length demonstrated that BN improved fire retardancy of EP but PDA modification deteriorated fire retardancy. The growth of Fe nanocatalyst enhanced fire retardancy with stronger self-extinguishment.

Cone calorimeter test (CCT)

CCT result was presented in **Fig.5-25** and **Table 5-5**. In HRR curves (**Fig.5-25** (a)), two peaks constantly emerged in terms of the four samples, which indicated the generation, damage and reconstruction of carbonaceous layer. The addition of 6wt% BN, BN@PDA and BN@PDA@Fe changed pHRR of EP ($1208 \pm 45 \text{ kW/m}^2$) to $907 \pm 32 \text{ kW/m}^2$, $1158 \pm 39 \text{ kW/m}^2$ and $738 \pm 27 \text{ kW/m}^2$. Amongst them, BN@PDA@Fe imparted EP with the most significantly reduced pHRR by 38.9%. However, the single-step PDA modification unexpectedly increased pHRR value relative to EP/6BN. In parallel, the fire growth index (FIGRA), which was defined as the pHRR divided by time to pHRR, illustrated the fire-growth behavior of polymers. EP/6BN@PDA@Fe possessed FIGRA of $4.59 \text{ kW}/(\text{m}^2 \cdot \text{s})$, which was notably reduced compared to EP ($6.75 \text{ kW}/(\text{m}^2 \cdot \text{s})$), EP/6BN ($4.72 \text{ kW}/(\text{m}^2 \cdot \text{s})$) and EP/6BN@PDA ($4.65 \text{ kW}/(\text{m}^2 \cdot \text{s})$). Reasonably, the remarkable reduction of FIGRA illuminated the suppression effect of fire growth of EP via the sequential modification of BN. Moreover, the study of THR at 350s (**Fig.5-25** (b)) disclosed that EP/6BN@PDA@Fe possessed lower value of $83.2 \pm 2.5 \text{ MJ/m}^2$ than EP (14.6% reduction), EP/6BN (5.8% reduction) and EP/6BN@DPA (22.0% reduction). The average mass loss rate (AMLR) was employed to assess the integral fire behavior. In **Fig. 5-25** (c), EP/6BN@PDA@Fe had AMLR value of 0.085 g/s , which was reduced by 34.6%, 9.6% and 34.7% respectively compared to EP, EP/6BN and EP/6BN@PDA. The lower AMLR value illuminated the lower integral fire intensity. In parallel, the char yield at flameout of EP/6BN@PDA@Fe was 29.0%, 11.3% and 21.2% higher than EP, EP/6BN and EP/6BN@PDA separately, which was in consistency with the char yield in TG (**Fig.5-17** and **Table 5-6**). The lower char yield after modification of PDA relative to EP/6BN was due to the triggering effect of PDA located at the interface of BN and EP towards worse char-stability. In contrast, the incorporation of Fe improved charring capacity of EP/6BN@PDA via catalytic process.

Fig.5-25 (a) HRR, (b) THR, (c) weight profile and (d) COP of EP and EP nanocomposites

Additionally, carbon monoxide (CO) production was the important constituent in fire safety. In **Fig.5-25** (d), EP/6BN@DPA@Fe possessed the peak CO production rate of $0.025 \pm 0.001 \text{ g/s}$, which was 40.1%, 16.7% and 39.0% lower than those of EP ($0.042 \pm 0.002 \text{ g/s}$), EP/6BN ($0.030 \pm 0.001 \text{ g/s}$) and EP/6BN/PDA ($0.041 \pm 0.002 \text{ g/s}$) respectively. Similarly, the PDA modification deteriorated CO profile with higher peak CO production rate relative to EP/6BN. In parallel, the released amount of CO (**Fig.5-26** (a)) illustrated the similar trend to peak CO production with the CO weight at 350s of EP/6BN@PDA@Fe $2.2 \pm 0.1 \text{ g}$ compared to $3.1 \pm 0.1 \text{ g}$ of neat EP. **Fig.5-26** (b) demonstrated the delayed and reduced ratio of COP and CO_2P of EP/6BN@PDA@Fe compared with neat EP at the after-flame stage. It was believable that the condensed-phase behavior toward high-quality char (**Fig.5-18** and **Fig.5-19**) accounted for the improved fire retardancy. Resultantly, the lower whole intensity and its integral value of EP/6BN@DPA@Fe than those of PE, EP/6BN and EP/6BN@PDA were generated (**Fig.5-27**). Conclusively, the sequential functionalization of BN by PDA and Fe reduced the fire hazard of EP.

Fig.5-26 (a) Weight of CO production and (b) ratio of COP and CO₂P of EP, EP/6BN, EP/6BN@PDA and EP/6BN@PDA@Fe

Fig.5-27 (a) Whole intensity and (b) integration of whole intensity of EP and EP composites

5.3.6 Fire-retardant mechanism of EP/BN@PDA@Fe

The fire-retardant mechanism was generally associated with vapor-phase flame inhibition and condensed-phase char protection. Herein, the flame-inhibition effect was absent as the av-EHC value of EP/6BN@PDA@Fe (2.72MJ/(m²·g)) remained nearly constant relative to neat EP (2.71MJ/(m²·g)). The condensed phase was accordingly focused, which was actually similar to the condensed-phase smoke-suppression mechanism. The similarity between condensed-phase fire-retardant and smoke-suppression mechanism was that the both cases were involved in the formation of protective char. The difference was that the precursor of smoke (higher polyaromatic degree) and flammable gases (mainly aliphatic compounds) differed. In detail, the condensed-phase fire-retardant mechanism (**Scheme 5-3**) account for improved fire retardancy of EP/6BN@PDA@Fe. During combustion, the Fe nanocatalyst located at the interface of EP and BN catalyzed the charring reaction (**Fig.5-17**, **Fig.3-14** (c) and **Fig.5-20** (b)) toward the promoted integrity and a larger amount of char.

The probable molecule-level interpretation was that the iron atoms promoted the generation of polyaromatic compounds from the aliphatic to aromatic compounds. The generated char with BN as the reinforcement possessed stronger barrier effect towards oxygen, heat and flammable effluents. Resultantly, heat release and CO production were improved in the case of LOI, UL-94 and CCT. In terms of delayed ignition, the increased thermal conductivity was due to the better nanodispersion of BN after PDA modification. It was noted that the better dispersion favored the transportation of heat through high thermally conductive BN, accompanied by the easier formation of the heat route.

Scheme 5-3 Proposed fire-retardant mechanism for EP/6BN@PDA@Fe

CHAPTER 6

Conclusion and future work

“There is no greater delight than to be conscious of sincerity on self-examination”

-Mencius

6.1 Conclusion

6.1.1 Ignition delaying

1) The effect of ferrocene on delaying ignition of PS was clarified. The addition of 3wt% ferrocene into PS matrix increased ignition time (t_{ig}) from 95 ± 2 s to 112 ± 2 s with the ignition temperature (T_{ig}) increasing from 262°C to 350°C (CCT, 25kW/m^2). The thermal inertia (ρck) of PS was not changed due to the identical temperature-rising curve. The radical-quenching effect of Fe species derived from ferrocene accounted for the increased t_{ig} and T_{ig} . The increase of T_{ig} was originated from the low gasification heat of PS that dissipated the surface heat.

2) Mesoporous SBA-15 silica was doped with ultrafine Co_3O_4 nanoparticles preferentially in the interior wall to prepare the nanohybrid SBA-15@ Co_3O_4 . PS composite with 2wt% SBA-15@ Co_3O_4 (PS/2SBA-15@ Co_3O_4) possessed t_{ig} of 116 ± 2 s compared to 98 ± 1 s and 106 ± 1 s of neat PS and PS/2SBA-15 (CCT, 25kW/m^2). PS/2SBA-15@ Co_3O_4 had the T_{ig} value of 343°C , which was 81°C higher than that of neat PS. The temperature curve at the early stage showed the similar temperature-rising process, which presented the similar thermal inertia of neat PS and PS/2SBA-15@ Co_3O_4 . The increase of T_{ig} and t_{ig} was originated from the significantly delayed release of volatiles (flammable gases). The process of adsorption-desorption gave rise to the delayed release of volatiles. The deep cause for the improved adsorption and desorption process was probably due to the coordination interplay between the main pyrolyzed products and Co atoms.

In parallel, 2wt% SBA-15@ Co_3O_4 imparted PS with reduced pHRR value and THR at first 200s by 24.5% and 81.0% separately. The fire-retardant mechanism was predominantly involved in the adsorption-desorption of volatiles and secondarily condensed-phase protection effect. The

tensile strength of PS was improved with addition of SBA@Co₃O₄.

3) Halloysite nanotubes (HNT) were sequentially functionalized by maleic anhydride (MAH) and 9,10-Dihydro-9-oxa-10-phosphaphenanthrene-10-oxide (DOPO) to prepare the nanohybrid HNT@MAH@DOPO. TG and TG-MS evidenced the sustainable slow-release behavior of phosphorous-containing radicals (PO· *etc.*) of HNT@MAH@DOPO compared to the simple mixture of HNT@MAH and DOPO (HNT@MAH-DOPO). 5wt% HNT@MAH@DOPO imparted PLA matrix with delayed t_{ig} ($75\pm5s$) compared to $60\pm2s$ of neat PLA and $60\pm2s$ of PLA/5HNT@MAH-DOPO (CCT, $35kW/m^2$). The T_{ig} value of PLA remained invariable ($331^\circ C$) with addition of HNT@MAH@DOPO and HNT@MAH-DOPO. The surface temperature comparison illustrated that PLA/5HNT@MAH@DOPO possessed a steady state with almost constant temperature due to the intensive radical-quenching. The sustainable slow-release behavior of PO· radicals accounted for the steady state. The temperature range (release) of PO· radicals from HNT@MAH@DOPO matched the thermal-oxidation degradation of PLA matrix.

In terms of fire behavior, 5wt% HNT@MAH@DOPO endowed EP with LOI value of 38.0% and UL-94 V-0 rating compared to LOI value of 24.7% and UL-94 V-2 rating of neat PLA. Comparative study illuminated the predominant vapor-phase mechanism and secondary condensed-phase mechanism for the improved fire retardancy. The vapor-phase mechanism was enhanced due to the sustainable slow-release behavior of PO·. The above three novel strategies to delaying ignition were illustrated in **Scheme 6-1**.

Scheme 6-1 Novel strategies to delaying ignition

6.1.2 Smoke suppression

1) The effect of ferrocene on smoke suppression of PS was systematically studied. 3wt% ferrocene into PS reduced the peak smoke production rate (peak SPR) and total smoke production (TSP) by 55.2% and 56.9% respectively. The condensed-phase mechanism associated with the slight reduction of smoke precursors was observed. In terms of vapor-phase mechanism, the smoke intermediate (soot) of PS/3Ferrocene possessed the decreased initial thermal-oxidation stability ($T_{5wt\%}$) by 175°C compared to that of PS due to the presence of $\gamma\text{-Fe}_2\text{O}_3$ nanoparticles in soot of PS/3Ferrocene. $\gamma\text{-Fe}_2\text{O}_3$ nanoparticles accelerated the combustion of soot at the combustion temperature. Resultantly, the pHRR value was slightly increased. In combination of delayed ignition, the effect of ferrocene on ignition and smoke suppression of PS was insightfully investigated for the first time.

2) Aiming to incorporate the condensed-phase and vapor-phase smoke-suppression mechanism into one system, the ferrocene molecule was included into sulfonated cyclodextrin intercalated layered double hydroxide (LDH-CD) to prepare the nanohybrid LDH-CD@Ferr. The inclusion of ferrocene into LDH-CD effectively avoided the earlier sublimation of ferrocene at 100°C. 6wt% LDH-CD@Ferr decreased the peak SPR and TSP by 42.9% and 54.4% separately relative to that of neat EP. The condensed-phase mechanism was associated with the formation of better-quality carbonaceous layer. Accordingly, the notable decrease of smoke precursors (aromatic, phenol and double-bond compounds) was observed. At the molecule level, the conversion of aliphatic to aromatic compounds was detected, which intensified the char structure. In terms of vapor-phase mechanism, the soot of EP/6LDH-CD@Ferr possessed lower $T_{5wt\%}$ by 56°C relative to that of EP due to the iron-containing derivatives. The lower thermal-oxidation stability promoted the further combustion of soots.

In terms of fire retardancy, 6wt% LDH-CD@Ferr increased the LOI value of EP from 24.2% to 28.1%. EP/6LDH-CD@Ferr presented the self-extinguishment in the vertical burning test compared to burning-to-clamp of EP/6LDH-CD and neat EP. In CCT, EP/6LDH-CD@Ferr showed the decreased pHRR and THR value by 30.9% and 27.8% respectively. The condensed-phase mechanism accounted for the improved fire retardancy with the formation of more robust char structure.

3) Intended to impart EP with highly efficiently suppressed smoke production via the condensed-phase mechanism, the ultrafine $\text{Ni}(\text{OH})_2$ nanocatalyst was engineered on external surface of dodecylbenzenesulfonate intercalating LDH (LDH-DBS) to prepare $\text{LDH-DBS@Ni}(\text{OH})_2$. 3wt% $\text{LDH-DBS@Ni}(\text{OH})_2$ formed the nanodispersion in EP matrix. $\text{LDH-DBS@Ni}(\text{OH})_2$ endowed EP with 50.0% and 65.5% reduction in peak SPR and TSP at 200s. The condensed-phase mechanism accounted for the improved smoke suppression. The better-quality char with the optimized interior and exterior structure was formed. The molecule-level study illustrated the formation of char with higher polyaromatic degree. Accordingly, the smoke precursors were reduced significantly. The soot of EP/6LDH-DBS@Ni(OH)₂ did not demonstrate the lower initial thermal-oxidation stability relative to EP/6LDH-DBS, which indicated the weak vapor-phase smoke-suppression mechanism.

In terms of fire retardancy, EP/3LDH-DBS@Ni(OH)₂ passed UL-94 vertical burning rating V-0. As far as the authors are concerned, 3% weight fraction was lowest value to reach V-0 in terms of EP nanocomposites. In CCT, EP/3LDH-DBS@Ni(OH)₂ possessed the 60.6% reduced pHRR and 65.4% reduced THR at 200s relative to those of EP. The fire-retardant mechanism was involved in the intumescent protective carbonaceous layer. At mesoscale, the intercalating nanodispersion of LDH-DBS@Ni(OH)₂ nanosheets in EP matrix and the interfacial catalysis of ultrafine $\text{Ni}(\text{OH})_2$ towards higher-quality chars optimized the intumescent structure. The mechanism was reviewed in **Scheme 6-2**.

Scheme 6-2 Vapor-phase and condensed-phase mechanism of smoke-suppression

6.1.3 Combination of ignition delaying and smoke suppression

Thermally exfoliated boron nitride nanosheets (BN) was sequentially functionalized with polydopamine (PDA) and iron-derived nanocatalyst (Fe) to prepare the BN@PDA@Fe. Compared with neat EP with t_{ig} of $80\pm 3s$, the addition of 6wt% BN, BN@PDA and BN@PDA@Fe respectively increased t_{ig} to $102\pm 3s$, $98\pm 3s$ and $89\pm 1s$. EP/6BN possessed the delayed t_{ig} relative to neat EP due to the increased thermal conductivity (k). EP/6BN@PDA showed slightly lower t_{ig} value compared to EP/6BN owing to the decreased specific heat of capacity (c). EP/6BN@PDA@Fe exhibited slightly lower t_{ig} value in comparison to EP/6BN@PDA due to the lower thermal-oxidation stability. k and c exerted a cardinal effect at the temperature-rising period. The thermal-oxidation degradation functioned at the late stage of temperature-rising process and determined the concentration and composition of flammable gases (related to T_{ig}). The pyrolyzed depth acted as the bridge to link physical and chemical factors. In terms of EP matrix, the physical factors played a more important role in determining ignition than chemical factors. The thermal conductivity and specific heat of capacity should be taken into account identically in analyzing ignition. Moreover, the concentration of flammable gases was more important than their composition.

EP/6BN@PD@Fe showed 24.6% and 28.6% reduction of peak SPR and TSP at 350s. The condensed-phase mechanism was associated with the formation of robust char with higher-quality interior structure. The interfacial catalysis of Fe (located between BN and EP) promoted the formation of homogeneously dispersed BN-reinforced carbonaceous layer. The investigation of soots illustrated no detectable vapor-phase mechanism.

In parallel, EP/6BN@PD@Fe reached LOI value of 34.2% compared to 24.2% of neat EP. The UL-94 horizontal burning test of BN@PDA@Fe exhibited lower combustion rate than those of its counterparts. In CCT, BN@PDA@Fe imparted EP with the most significantly reduced pHRR by 38.9%. THR at 350s disclosed that EP/6BN@PDA@Fe possessed lower value by 14.6% relative to EP. The notable reduction of main flammable gases (aliphatic compounds) was observed. The condensed-phase mechanism accounted for the improved fire retardancy.

6.2 Future work

6.2.1 Ignition delaying

Our future work was to further seek for the solutions to delay ignition highly efficiently. The delayed ignition time was supposed to guarantee the adequate availability to rescue. The higher-efficiency approaches were based on the aforementioned methods 1) intensive flame inhibition via highly efficient slow release of $\text{PO}\cdot$ radical 2) strong slow release of volatiles via highly efficient adsorption-desorption behavior 3) significantly increased thermal inertia (ρck) via modulation of structure and composition of polymer nanocomposites

In terms of PS/Ferrocene, PLA/HNT@MAH@DOPO and PS/SBA-15@ Co_3O_4 ignition-delayed system, the numerical simulation of the surface temperature should be carried out in order to analyze the factors to influence ignition in combination of experimental results. The simulation of surface temperature was able to guild the rational design of nanostructure for ignition-delaying system. In the simulation, the thermoplastic polymers were regarded as the solid fuel. Based on the basic governing Equation (5-1), the heating process was divided into two stages *i.e.* before thermal-oxidation degradation and after thermal-oxidation behavior. Before thermal-oxidation, melt process and in-depth adsorption (transparent samples), thermal convection and black-body emission were considered. After thermal-oxidation, thermal convection, black-body emission, attenuation of incident heat and gasification were considered. After confirming surface temperature, the T_{ig} value was predicted based on the three factors of oxygen, volatile and temperature. The concentration and composition of volatiles played a key role in T_{ig} with predominant role of volatile composition. The parameterization of T_{ig} was difficult due to the lacking of enough mechanistic investigation. Our future work was supposed to include approximate parameterization of T_{ig} . Another pursuit in the further was to impart the ignition-delayed system with multifunctions (weather-resistance and anti-oxidation *etc.*).

In order to solve the difficulty in investigating thermal-oxidation behavior prior to ignition in CCT, the in-situ detection of volatile composition and concentration was in need. The most recent apparatus with infrared spectroscopy connected with CCT would be selected in **Fig.6-1** [365]. In consideration of the high-molecule-weight in the degraded products, the acquisition site of volatiles was selected beside the sample surface.

Fig.6-1 In-situ detection of volatiles in (a) CCT with (b) FTIR spectroscopy

6.2.2 Smoke suppression

Ferrocene and its analogue were certified as the excellent smoke suppressant with vapor-phase smoke-suppression mechanism. Its low sublimation temperature caused the significant barrier for the industrial application. The future work was to continue seeking for the appropriate nano-carrier to drive the release temperature of ferrocene molecules to the combustion temperature. Our work to use the host-guest chemistry was the first step.

The pursuit of highly efficient smoke suppression was on the road. The comparison of vapor-phase and condensed-phase smoke suppression illuminated that both cases possessed the trait of high efficiency. The authors considered that the balance of vapor-phase and condensed-phase smoke suppression was able to be achieved for the most optimized smoke suppression, accompanied by the excellent flame retardancy. The future work was to seek for the solution to execute the strategy via the combination of vapor-phase and condensed-phase smoke suppressants.

The kinetics of smoke production was within the future investigation. The compounds with low aromatic degree were conversed to that with high aromatic degree, which was influenced by the degradation temperature. The nucleation process proceeded with the high-aromatic-degree compounds to nanoscale carbon particles, which was tightly related to the volatile analysis. The resultant carbon nanoparticles continued to grow with formation of aggregates, which was defined as the soot. The investigation of kinetics was focused on the analysis of these three processes. In parallel, the visual observation of smoke and smoke intermediates was required. In the chimney of

CCT, the specific pipe was addressed to incorporate the smoke, which underwent the analysis of smoke particle size and distribution by electric low pressure impactor (ELPI) [366]. As the specific pipe was addressed in the flame during combustion, the smoke intermediate was acquired and analyzed.

CHAPTER 7

List of publications and conferences

“If I have seen further than others, it is by standing upon the shoulder of the giants”

-Isaac Newton

1) The listed papers are direct results of this doctoral thesis. The listed papers have been published or at the submission stage.

[1] Li Z, Wang D-Y. Nano-architected mesoporous silica decorated with ultrafine Co_3O_4 toward an efficient way to delaying ignition and improving fire retardancy of polystyrene. *Materials & Design*. 2017;129:69-81.

[2] Li Z, Expósito DF, González AJ, Wang D-Y. Natural Halloysite Nanotube Based Functionalized Nanohybrid Assembled via Phosphorus-containing Slow Release Method: A Highly Efficient Way to Impart Flame Retardancy to Polylactide. *European Polymer Journal*. 2017;93: 458-470.

[3] Li Z, Expósito DF, González AJ, Wang DY. Insightful investigation of smoke suppression behavior and mechanism of polystyrene with ferrocene: An important role of intermediate smoke. *Fire and Materials*. 2018; 42; 286-295.

[4] Li Z, Wang D-Y, Ultrafine Ni catalyst-Assembling Layered Double Hydroxide-derived Nanohybrid towards Super-efficiently Fire-safe Epoxy Resin, *Journal of Materials Chemistry A*, DOI: 10.1039/C8TA00910D

[5] Li Z, Wang D-Y, Bio-inspired Engineering of Boron Nitride with Zero-valent Iron Nanocatalyst toward Enhanced Fire Safety and Delayed Ignition of Epoxy Resin. *Polymer Degradation and Stability*, Under Review

[6] Li Z, Wang D-Y, Systematic Investigation of Ignition Behavior of Epoxy Resin Nanocomposites via Hierarchical Functionalization of Boron Nitride Nanosheets *Combustion and Flame*, Under Review

[7] **Li Z**, Wang D-Y, Bio-based Layered Double Hydroxide Nanocarrier toward Fire-retardant Epoxy Resin with Efficiently Improved Smoke Suppression, *Chemical Engineering Journal*, Under Review

[8] **Li Z**, Wang D-Y, Insightful Investigation of Slow-release Behavior of Fire Retardant and Pyrolyzed Products: Effect on Ignition, *Polymer Degradation and Stability*. To be submitted

2) Presentation and poster in international conferences

[1] **Li Z**, Wang D-Y, Hierarchical Engineering of Halloysite Nanotube and Its Enhancement in Fire Safety and Mechanical Property of Epoxy Resin, **Polymer Processing Society (PPS) Europe & Africa Conference**, June 26-29, 2017, Dresden, Germany

[2] **Li Z**, Wang D-Y, Micro-nano combination of functionalized MCM-41 nanospheres and APP to enhance flame retardancy of epoxy resin, **COST MP1105 SCIENTIFIC WORKSHOP**, March 26-27, 2015, Bucharest, Romania

[3] **Li Z**, Wang D-Y, Micro-nano combination of functionalized MCM-41 nanospheres and APP to enhance flame retardancy of epoxy resin, **7th Asia-Europe Symposium on Processing and Properties of Reinforced Polymers (AESP7) & COST MP1105 FLAME RETARDANT WORKSHOP**, February 2-6, Madrid, 2015

[4] Wang D-Y, **Li Z**, Functionalization of Nanomaterials vs Time to Ignition of Polymeric Materials, **FRPM17**, July 3-6, Manchester, UK, 2017

3) The listed papers are relevant to the fire safety (mainly heat release rate) and other multifunctions of polymeric materials

[1] **Li Z**, Liu L, González AJ, Wang D-Y, Bioinspired Polydopamine Induced Assembly of Ultrafine Fe(OH)₃ Nanoparticles on Halloysite toward Highly Efficient Fire Retardancy of Epoxy Resin via An Action of Interfacial Catalysis. *Polymer Chemistry*, 2017; 8:3926-3936

[2] **Li Z**, González AJ, Heeralal VB, Wang D-Y, Covalent Assembly of MCM-41 Nanospheres on Graphene Oxide for Improving Fire Retardancy and Mechanical Property of Epoxy Resin

Composites Part B:Engineering, 2017; 138:101-112

[3] Li Z, Wang D-Y, Transparent Carrageenan Nanocomposite Film Based on Carrageenan Intercalated Layered Double Hydroxide with Enhanced Thermal Stability, Fire Safety, Gas Barrier and Mechanical Property, *Composites Communications*, 2018; 9:1-5

[4] Xiao D, Li Z, Gohs U, Wagenknecht U, Voit B, Wang D-Y, Functionalized allylamine polyphosphate as a novel multifunctional highly efficient fire retardant for polypropylene. *Polymer Chemistry*, 2017; 8(40):6309-18.

[5] Xiao D, Li Z, Zhao X, Gohs U, Wagenknecht U, Voit B, Wang D-Y, Functional organoclay with high thermal stability and its synergistic effect on intumescent flame retardant polypropylene. *Applied Clay Science*, 2017; 143:192-198

[6] Xiao D, Li Z, De Juan S, Gohs U, Wagenknecht U, Voit B, Wang D-Y, Preparation, fire behavior and thermal stability of a novel flame retardant polypropylene system. *Journals of Thermal and Analytical Calorimetry*, 2016; 125:321-329

[7] Li Z, Wang D-Y, Electrostatic Induced Engineering of Silica on Intercalated Layered Double Hydroxide for Epoxy Resin Nanocomposite with Enhanced Fire Safety. *Composites Part B: Engineering*, Under Review

[8] Li Z, Wang D-Y, POSS Engineering Organic Layered Double Hydroxide via Bio-inspired Michael Reaction for Improving Fire Safety of Epoxy Resin, *Composites Part A: Applied Science and Manufacturing*, To be submitted

[9] Li Z, Wang D-Y, Multifunctional Ammonia Polyphosphate Intercalated Layered Double Hydroxide-based Poly(vinyl alcohol) Nanocomposites Films with Improved Fire Safety, Mechanical Property, Barrier Performance and Moisture-induced Shape Memory Behavior, *Materials Letters*, To be submitted.

[10] Li Z, Wang D-Y, A Facile One-step Preparation of Stannate Nanocubes Decorating Layered Double Hydroxide toward Enhanced Fire Retardancy and Mechanical Performance of Poly(vinyl chloride), *Journals of Hazardous Materials*, To be submitted

[11] Li Z, Wang D-Y. Bioinspired Engineering of Ultrafine Zero-valent Iron Nanoparticles in Mesoporous SBA-15 and Its Effect on Polystyrene: Thermal Stability and Fire Retardancy, *Journals of Thermal and Analytical Calorimetry*, To be submitted

[12] Li Z, Wang D-Y. Core-shell Assembly of Spherical Ammonia Polyphosphate and

Mesoporous MCM-41 nanoparticles Toward Fire-safe and Mechanically Robust Epoxy Resin via Interfacial Effect, *ACS Applied Materials & Interfaces*, To be submitted

[13] Li Z, Wang D-Y, Bioinspired Zero-valent Iron Nanoparticles Engineered Halloysite toward High-effective Fire Safety of Epoxy Resin via Interfacial Catalysis, *ACS Sustainable Chemistry & Engineering*, To be submitted

[14] Li Z, Wang D-Y, Polydopamine-Assistant Assembly of Layered Double Hydroxide on Halloysite Nanotubes for Improving Fire Safety of Epoxy Resin, *Composites Part B: Engineering*, To be submitted

[15] Li Z, Wang D-Y, Effect of Cobalt Induced Coordination on Polyvinyl Pyrrolidone Modified Graphene Nanoplates-filled Poly(vinyl alcohol) Film: Investigation of Thermal Stability, Fire Retardancy, Tensile behavior and Barrier Effect, *Materials Letters*, To be submitted

[16] Wan J, Gan B, Li C, Molina-Aldareguia J, Li Z, Wang X, et al. A novel biobased epoxy resin with high mechanical stiffness and low flammability: synthesis, characterization and properties. *Journal of Materials Chemistry A*, 2015; 3(43):21907-21

[17] Pan Y-T, Wang X, Li Z, Wang D-Y. A facile approach towards large-scale synthesis of hierarchically nanoporous SnO₂@Fe₂O₃ 0D/1D hybrid and its effect on flammability, thermal stability and mechanical property of flexible poly (vinyl chloride), *Composites Part B: Engineering*, 2017;110:46-55

[18] Kalali EN, Montes A, Wang X, Zhang L, Shabestari ME, Li Z, et al. Effect of phytic acid–modified layered double hydroxide on flammability and mechanical properties of intumescent flame retardant polypropylene system. *Fire and Materials*, 2018; 42; 213-220

Reference

- [1] Karter MJ. Fire loss in the United States during 2011: NFPA Quincy; 2012.
- [2] Mellins RB, Park S. Respiratory complications of smoke inhalation in victims of fires. *The Journal of pediatrics*. 1975;87(1):1-7.
- [3] Hirschler M. Heat release from plastic materials. *Heat release in fires*. 1992:375-422.
- [4] Lyon RE, Janssens ML. Polymer flammability: Wiley Online Library; 2005.
- [5] Schartel B, Wilkie CA, Camino G. Recommendations on the scientific approach to polymer flame retardancy: Part 2-Concepts. *J Fire Sci*. 2017;35(1):3-20.
- [6] Schartel B, Wilkie CA, Camino G. Recommendations on the scientific approach to polymer flame retardancy: Part 1-Scientific terms and methods. *J Fire Sci*. 2016;34(6):447-67.
- [7] ISO13943 B. Fire safety-vocabulary (ISO 13943: 2008). British Standard Institution, London. 2010.
- [8] 欧育湘. 阻燃剂: 性能, 制造及应用: 化学工业出版社; 2006.
- [9] Suzanne M, Ramani A, Ukleja S, McKee M, Zhang J, Delichatsios M, et al. Fire performance of brominated and halogen- free flame retardants in glass- fiber reinforced poly (butylene terephthalate). *Fire Mater*. 2018; 42(1):18-27.
- [10] Wilkie CA, Morgan AB. Fire retardancy of polymeric materials: CRC press; 2009.
- [11] Morgan AB, Gilman JW. An overview of flame retardancy of polymeric materials: application, technology, and future directions. *Fire Mater*. 2013;37(4):259-79.
- [12] Teuten EL, Xu L, Reddy CM. Two abundant bioaccumulated halogenated compounds are natural products. *Science*. 2005;307(5711):917-20.
- [13] She Y-Z, Wu J-P, Zhang Y, Peng Y, Mo L, Luo X-J, et al. Bioaccumulation of polybrominated diphenyl ethers and several alternative halogenated flame retardants in a small herbivorous food chain. *Environ Pollut*. 2013;174:164-70.
- [14] Law K, Halldorson T, Danell R, Stern G, Gewurtz S, Alae M, et al. Bioaccumulation and trophic transfer of some brominated flame retardants in a Lake Winnipeg (Canada) food web. *Environ Toxicol Chem*. 2006;25(8):2177-86.
- [15] Schartel B, Perret B, Dittrich B, Ciesielski M, Krämer J, Müller P, et al. Flame retardancy of polymers: the role of specific reactions in the condensed phase. *Macromol Mater Eng*.

REFERENCE

2016;301(1):9-35.

[16] Gaan S, Sun G. Effect of phosphorus flame retardants on thermo-oxidative decomposition of cotton. *Polym Degrad Stabil.* 2007;92(6):968-74.

[17] Lorenzetti A, Modesti M, Besco S, Hrelja D, Donadi S. Influence of phosphorus valency on thermal behaviour of flame retarded polyurethane foams. *Polym Degrad Stabil.* 2011;96(8):1455-61.

[18] Zhao X, Babu HV, Llorca J, Wang D-Y. Impact of halogen-free flame retardant with varied phosphorus chemical surrounding on the properties of diglycidyl ether of bisphenol-A type epoxy resin: synthesis, fire behaviour, flame-retardant mechanism and mechanical properties. *RSC Adv.* 2016;6(64):59226-36.

[19] Braun U, Balabanovich AI, Scharrel B, Knoll U, Artner J, Ciesielski M, et al. Influence of the oxidation state of phosphorus on the decomposition and fire behaviour of flame-retarded epoxy resin composites. *Polymer.* 2006;47(26):8495-508.

[20] Shao Z-B, Deng C, Tan Y, Chen M-J, Chen L, Wang Y-Z. Flame retardation of polypropylene via a novel intumescent flame retardant: ethylenediamine-modified ammonium polyphosphate. *Polym Degrad Stabil.* 2014;106:88-96.

[21] Wang Z, Liu Y, Li J. Regulating Effects of Nitrogenous Bases on the Char Structure and Flame Retardancy of Polypropylene/Intumescent Flame Retardant Composites. *ACS Sustain Chem Eng.* 2017;5(3):2375-83.

[22] Qian Y, Wei P, Jiang P, Zhao X, Yu H. Synthesis of a novel hybrid synergistic flame retardant and its application in PP/IFR. *Polym Degrad Stabil.* 2011;96(6):1134-40.

[23] Qian Y, Wei P, Jiang P, Hao J, Du J. Preparation of hybrid phosphamide containing polysilsesquioxane and its effect on flame retardancy and mechanical properties of polypropylene composites. *Compos Part B-Eng.* 2013;45(1):1541-7.

[24] Bourbigot S, Flambard X. Heat resistance and flammability of high performance fibres: A review. *Fire Mater.* 2002;26(4-5):155-68.

[25] Fu T, Guo D-M, Wu J-N, Wang X-L, Wang X-L, Chen L, et al. Inherent flame retardation of semi-aromatic polyesters via binding small-molecule free radicals and charring. *Polym Chem.* 2016;7(8):1584-92.

[26] Toldy A, Anna P, Csontos I, Szabó A, Marosi G. Intrinsically flame retardant epoxy resin-Fire

- p>performance and background-Part I.
- Polym Degrad Stabil.*
- 2007;92(12):2223-30.
- [27] Sablong R, Duchateau R, Koning CE, Pospiech D, Korwitz A, Komber H, et al. Incorporation of a flame retardancy enhancing phosphorus-containing diol into poly (butylene terephthalate) via solid state polycondensation: A comparative study. *Polym Degrad Stabil.* 2011;96(3):334-41.
- [28] Chang YL, Wang YZ, Ban DM, Yang B, Zhao GM. A Novel Phosphorus- Containing Polymer as a Highly Effective Flame Retardant. *Macromol Mater Eng.* 2004;289(8):703-7.
- [29] Wang D-Y, Song Y-P, Lin L, Wang X-L, Wang Y-Z. A novel phosphorus-containing poly (lactic acid) toward its flame retardation. *Polymer.* 2011;52(2):233-8.
- [30] Chang SJ, Chang FC. Synthesis and characterization of copolyesters containing the phosphorus linking pendent groups. *J Appl Polym Sci.* 1999;72(1):109-22.
- [31] Hornsby PR, Watson CL. A study of the mechanism of flame retardance and smoke suppression in polymers filled with magnesium hydroxide. *Polym Degrad Stabil.* 1990;30(1):73-87.
- [32] Costache MC, Heidecker MJ, Manias E, Camino G, Frache A, Beyer G, et al. The influence of carbon nanotubes, organically modified montmorillonites and layered double hydroxides on the thermal degradation and fire retardancy of polyethylene, ethylene-vinyl acetate copolymer and polystyrene. *Polymer.* 2007;48(22):6532-45.
- [33] Monticelli O, Musina Z, Frache A, Bellucci F, Camino G, Russo S. Influence of compatibilizer degradation on formation and properties of PA6/organoclay nanocomposites. *Polym Degrad Stabil.* 2007;92(3):370-8.
- [34] Samyn F, Bourbigot S, Jama C, Bellayer S, Nazare S, Hull R, et al. Crossed characterisation of polymer-layered silicate (PLS) nanocomposite morphology: TEM, X-ray diffraction, rheology and solid-state nuclear magnetic resonance measurements. *Eur Polym J.* 2008;44(6):1642-53.
- [35] Zanetti M, Camino G, Thomann R, Mülhaupt R. Synthesis and thermal behaviour of layered silicate-EVA nanocomposites. *Polymer.* 2001;42(10):4501-7.
- [36] Li Z, Liu L, González AJ, Wang D-Y. Bioinspired Polydopamine Induced Assembly of Ultrafine Fe(OH)₃ Nanoparticles on Halloysite toward Highly Efficient Fire Retardancy of Epoxy Resin via An Action of Interfacial Catalysis. *Polym Chem.* 2017;8:3926-3936.
- [37] Alongi J, Carletto RA, Di Blasio A, Carosio F, Bosco F, Malucelli G. DNA: a novel, green, natural flame retardant and suppressant for cotton. *J Mater Chem A.* 2013;1(15):4779-85.

- [38] Alongi J, Ciobanu M, Malucelli G. Novel flame retardant finishing systems for cotton fabrics based on phosphorus-containing compounds and silica derived from sol–gel processes. *Carbohydr Polym.* 2011;85(3):599-608.
- [39] Li YC, Mannen S, Morgan AB, Chang S, Yang YH, Condon B, et al. Intumescent All-Polymer Multilayer Nanocoating Capable of Extinguishing Flame on Fabric. *Adv Mater.* 2011;23(34):3926-31.
- [40] Li Y-C, Schulz J, Mannen S, Delhom C, Condon B, Chang S, et al. Flame retardant behavior of polyelectrolyte– clay thin film assemblies on cotton fabric. *ACS Nano.* 2010;4(6):3325-37.
- [41] Carosio F, Alongi J, Malucelli G. α -Zirconium phosphate-based nanoarchitectures on polyester fabrics through layer-by-layer assembly. *J Mater Chem.* 2011;21(28):10370-6.
- [42] Alongi J, Carosio F, Malucelli G. Layer by layer complex architectures based on ammonium polyphosphate, chitosan and silica on polyester-cotton blends: flammability and combustion behaviour. *Cellulose.* 2012;19(3):1041-50.
- [43] Carosio F, Di Blasio A, Alongi J, Malucelli G. Green DNA-based flame retardant coatings assembled through layer by layer. *Polymer.* 2013;54(19):5148-53.
- [44] Alongi J, Carosio F, Frache A, Malucelli G. Layer by layer coatings assembled through dipping, vertical or horizontal spray for cotton flame retardancy. *Carbohydr Polym.* 2013;92(1):114-9.
- [45] Illeperuma WR, Rothmund P, Suo Z, Vlassak JJ. Fire-Resistant Hydrogel-Fabric Laminates: A Simple Concept That May Save Lives. *ACS Appl Mater Inter.* 2016;8(3):2071-7.
- [46] Wu Q, Zhang Q, Zhao L, Li S-N, Wu L-B, Jiang J-X, et al. A novel and facile strategy for highly flame retardant polymer foam composite materials: Transforming silicone resin coating into silica self-extinguishing layer. *J Hazard Mater.* 2017;336:222-31.
- [47] Huang G, Li Y, Han L, Gao J, Wang X. A novel intumescent flame retardant-functionalized montmorillonite: Preparation, characterization, and flammability properties. *Appl Clay Sci.* 2011;51(3):360-5.
- [48] Camino G, Costa L, Martinasso G. Intumescent fire-retardant systems. *Polym Degrad Stabil.* 1989;23(4):359-76.
- [49] Camino G, Costa L, Trossarelli L, Costanzi F, Landoni G. Study of the mechanism of intumescence in fire retardant polymers: part IV-evidence of ester formation in ammonium

- polyphosphate-pentaerythritol mixtures. *Polym Degrad Stabil.* 1984;8(1):13-22.
- [50] Camino G, Costa L, Trossarelli L, Costanzi F, Pagliari A. Study of the mechanism of intumescence in fire retardant polymers: Part VI-Mechanism of ester formation in ammonium polyphosphate-pentaerythritol mixtures. *Polym Degrad Stabil.* 1985;12(3):213-28.
- [51] Bourbigot S, Le Bras M, Delobel R, Decressain R, Amoureux J-P. Synergistic effect of zeolite in an intumescence process: study of the carbonaceous structures using solid-state NMR. *Journal of the Chemical Society, Faraday Transactions.* 1996;92(1):149-58.
- [52] Bourbigot S, Le Bras M, Delobel R, Gengembre L. XPS study of an intumescent coating: II. Application to the ammonium polyphosphate/pentaerythritol/ethylenic terpolymer fire retardant system with and without synergistic agent. *Appl Surf Sci.* 1997;120(1):15-29.
- [53] Bourbigot S, Le Bras M, Delobel R, Trémillon J-M. Synergistic effect of zeolite in an intumescence process. Study of the interactions between the polymer and the additives. *Journal of the Chemical Society, Faraday Transactions.* 1996;92(18):3435-44.
- [54] Bourbigot S, Le Bras M, Gengembre L, Delobel R. XPS study of an intumescent coating application to the ammonium polyphosphate/pentaerythritol fire-retardant system. *Appl Surf Sci.* 1994;81(3):299-307.
- [55] Bourbigot S, Samyn F, Turf T, Duquesne S. Nanomorphology and reaction to fire of polyurethane and polyamide nanocomposites containing flame retardants. *Polym Degrad Stabil.* 2010;95(3):320-6.
- [56] Bourbigot S, Duquesne S, Leroy J-M. Modeling of heat transfer of a polypropylene-based intumescent system during combustion. *J Fire Sci.* 1999;17(1):42-56.
- [57] Bourbigot S, Turf T, Bellayer S, Duquesne S. Polyhedral oligomeric silsesquioxane as flame retardant for thermoplastic polyurethane. *Polym Degrad Stabil.* 2009;94(8):1230-7.
- [58] Muller M, Bourbigot S, Duquesne S, Klein R, Giannini G, Lindsay C, et al. Investigation of the synergy in intumescent polyurethane by 3D computed tomography. *Polym Degrad Stabil.* 2013;98(9):1638-47.
- [59] Camino G, Costa L, Trossarelli L. Study of the mechanism of intumescence in fire retardant polymers: Part I-Thermal degradation of ammonium polyphosphate-pentaerythritol mixtures. *Polym Degrad Stabil.* 1984;6(4):243-52.
- [60] Camino G, Costa L, Trossarelli L. Study of the mechanism of intumescence in fire retardant

REFERENCE

polymers: Part II-Mechanism of action in polypropylene-ammonium polyphosphate-pentaerythritol mixtures. *Polym Degrad Stabil.* 1984;7(1):25-31.

[61] Camino G, Costa L, Trossarelli L. Study of the mechanism of intumescence in fire retardant polymers: Part V-Mechanism of formation of gaseous products in the thermal degradation of ammonium polyphosphate. *Polym Degrad Stabil.* 1985;12(3):203-11.

[62] Camino G, Costa L, Trossarelli L. Study of the mechanism of intumescence in fire retardant polymers: Part III-Effect of urea on the ammonium polyphosphate-pentaerythritol system. *Polym Degrad Stabil.* 1984;7(4):221-9.

[63] Braun U, ScharTEL B, Fichera MA, Jäger C. Flame retardancy mechanisms of aluminium phosphinate in combination with melamine polyphosphate and zinc borate in glass-fibre reinforced polyamide 6, 6. *Polym Degrad Stabil.* 2007;92(8):1528-45.

[64] Alongi J, Ciobanu M, Malucelli G. Sol-gel treatments for enhancing flame retardancy and thermal stability of cotton fabrics: optimisation of the process and evaluation of the durability. *Cellulose.* 2011;18(1):167-77.

[65] Wu Q, Lü J, Qu B. Preparation and characterization of microcapsulated red phosphorus and its flame-retardant mechanism in halogen-free flame retardant polyolefins. *Polym Int.* 2003;52(8):1326-31.

[66] Zhan J, Song L, Nie S, Hu Y. Combustion properties and thermal degradation behavior of polylactide with an effective intumescent flame retardant. *Polym Degrad Stabil.* 2009;94(3):291-6.

[67] Kunze R, ScharTEL B, Bartholmai M, Neubert D, Schrieffer R. TG-MS and TG-FTIR applied for an unambiguous thermal analysis of intumescent coatings. *J Therm Anal Calorim.* 2002;70(3):897-909.

[68] Riva A, Camino G, Fomperie L, Amigouet P. Fire retardant mechanism in intumescent ethylene vinyl acetate compositions. *Polym Degrad Stabil.* 2003;82(2):341-6.

[69] Nie S, Song L, Guo Y, Wu K, Xing W, Lu H, et al. Intumescent flame retardation of starch containing polypropylene semibiocomposites: flame retardancy and thermal degradation. *Ind Eng Chem Res.* 2009;48(24):10751-8.

[70] Bugajny M, Bras ML, Bourbigot S. New approach to the dynamic properties of an intumescent material. *Fire Mater.* 1999;23(1):49-51.

[71] Anna P, Marosi G, Bourbigot S, Le Bras M, Delobel R. Intumescent flame retardant systems

of modified rheology. *Polym Degrad Stabil.* 2002;77(2):243-7.

[72] Brehme S, Schartel B, Goebbels J, Fischer O, Pospiech D, Bykov Y, et al. Phosphorus polyester versus aluminium phosphinate in poly (butylene terephthalate)(PBT): flame retardancy performance and mechanisms. *Polym Degrad Stabil.* 2011;96(5):875-84.

[73] Shao Z-B, Deng C, Tan Y, Yu L, Chen M-J, Chen L, et al. Ammonium polyphosphate chemically-modified with ethanolamine as an efficient intumescent flame retardant for polypropylene. *J Mater Chem A.* 2014;2(34):13955-65.

[74] Wang Y-T, Liao S-F, Shang K, Chen M-J, Huang J-Q, Wang Y-Z, et al. Efficient approach to improving the flame retardancy of poly (vinyl alcohol)/clay aerogels: incorporating piperazine-modified ammonium polyphosphate. *ACS Appl Mater Inter.* 2015;7(3):1780-6.

[75] Shao Z-B, Deng C, Tan Y, Chen M-J, Chen L, Wang Y-Z. An efficient mono-component polymeric intumescent flame retardant for polypropylene: preparation and application. *ACS Appl Mater Inter.* 2014;6(10):7363-70.

[76] Chen S, Li J, Zhu Y, Guo Z, Su S. Increasing the efficiency of intumescent flame retardant polypropylene catalyzed by polyoxometalate based ionic liquid. *J Mater Chem A.* 2013;1(48):15242-6.

[77] Wang J, Chen Y. Microencapsulation of intumescent flame- retardant agent: Application to flame-retardant natural rubber composite. *J Appl Polym Sci.* 2007;104(3):1828-38.

[78] Wu K, Zhang Y, Hu W, Lian J, Hu Y. Influence of ammonium polyphosphate microencapsulation on flame retardancy, thermal degradation and crystal structure of polypropylene composite. *Compos Sci Technol.* 2013;81:17-23.

[79] Wu K, Wang Z. Intumescent flame retardation of EVA using microencapsulated ammonium polyphosphate and pentaerythritols. *Polym-plast Technol.* 2008;47(3):247-54.

[80] Ni J, Chen L, Zhao K, Hu Y, Song L. Preparation of gel-silica/ammonium polyphosphate core- shell flame retardant and properties of polyurethane composites. *Polym Advan Technol.* 2011;22(12):1824-31.

[81] Wu K, Song L, Wang Z, Hu Y. Microencapsulation of ammonium polyphosphate with PVA–melamine–formaldehyde resin and its flame retardance in polypropylene. *Polym Advan Technol.* 2008;19(12):1914-21.

[82] Wang B, Qian X, Shi Y, Yu B, Hong N, Song L, et al. Cyclodextrin microencapsulated

REFERENCE

- ammonium polyphosphate: Preparation and its performance on the thermal, flame retardancy and mechanical properties of ethylene vinyl acetate copolymer. *Compos Part B-Eng.* 2015;69:22-30.
- [83] Gaan S, Rupper P, Salimova V, Heuberger M, Rabe S, Vogel F. Thermal decomposition and burning behavior of cellulose treated with ethyl ester phosphoramidates: Effect of alkyl substituent on nitrogen atom. *Polym Degrad Stabil.* 2009;94(7):1125-34.
- [84] Liang S, Hemberger P, Levalois-Grützmacher J, Grützmacher H, Gaan S. Probing Phosphorus Nitride ($P\equiv N$) and Other Elusive Species Formed upon Pyrolysis of Dimethyl Phosphoramidate. *Chem-Eur J.* 2017;23(23):5595-601.
- [85] Braun U, ScharTEL B. Flame retardancy mechanisms of aluminium phosphinate in combination with melamine cyanurate in glass-fibre-reinforced poly (1, 4- butylene terephthalate). *Macromol Mater Eng.* 2008;293(3):206-17.
- [86] Gallo E, ScharTEL B, Braun U, Russo P, Acierno D. Fire retardant synergisms between nanometric Fe_2O_3 and aluminum phosphinate in poly (butylene terephthalate). *Polym Advan Technol.* 2011;22(12):2382-91.
- [87] Samyn F, Bourbigot S. Thermal decomposition of flame retarded formulations PA6/aluminum phosphinate/melamine polyphosphate/organomodified clay: Interactions between the constituents? *Polym Degrad Stabil.* 2012;97(11):2217-30.
- [88] Zhao B, Chen L, Long J-W, Chen H-B, Wang Y-Z. Aluminum hypophosphite versus alkyl-substituted phosphinate in polyamide 6: flame retardance, thermal degradation, and pyrolysis behavior. *Ind Eng Chem Res.* 2013;52(8):2875-86.
- [89] Zhao H-B, Chen L, Yang J-C, Ge X-G, Wang Y-Z. A novel flame-retardant-free copolyester: cross-linking towards self extinguishing and non-dripping. *J Mater Chem.* 2012;22(37):19849-57.
- [90] Jing X-K, Wang X-S, Guo D-M, Zhang Y, Zhai F-Y, Wang X-L, et al. The high-temperature self-crosslinking contribution of azobenzene groups to the flame retardance and anti-dripping of copolyesters. *J Mater Chem A.* 2013;1(32):9264-72.
- [91] Liu B-W, Zhao H-B, Tan Y, Chen L, Wang Y-Z. Novel crosslinkable epoxy resins containing phenylacetylene and azobenzene groups: From thermal crosslinking to flame retardance. *Polym Degrad Stabil.* 2015;122:66-76.
- [92] Aragay G, Pons J, Merkoçi A. Recent trends in macro-, micro-, and nanomaterial-based tools and strategies for heavy-metal detection. *Chem Rev.* 2011;111(5):3433-58.

REFERENCE

- [93] Kashiwagi T, Du F, Winey KI, Groth KM, Shields JR, Bellayer SP, et al. Flammability properties of polymer nanocomposites with single-walled carbon nanotubes: effects of nanotube dispersion and concentration. *Polymer*. 2005;46(2):471-81.
- [94] Kashiwagi T, Mu M, Winey K, Cipriano B, Raghavan S, Pack S, et al. Relation between the viscoelastic and flammability properties of polymer nanocomposites. *Polymer*. 2008;49(20):4358-68.
- [95] Kashiwagi T, Omori A. Effects of thermal stability and melt viscosity of thermoplastics on piloted ignition. *Symposium (International) on Combustion*: Elsevier; 1989. p. 1329-38.
- [96] Kashiwagi T, Omori A, Nanbu H. Effects of melt viscosity and thermal stability on polymer gasification. *Combust Flame*. 1990;81(2):188-201.
- [97] Jiang S-D, Bai Z-M, Tang G, Song L, Stec AA, Hull TR, et al. Synthesis of mesoporous silica@Co-Al layered double hydroxide spheres: layer-by-layer method and their effects on the flame retardancy of epoxy resins. *ACS Appl Mater Inter*. 2014;6(16):14076-86.
- [98] Einstein A. *Annalen Phys*. 19, 289 (1906). *Annalen Phys*. 1911;34:591.
- [99] Einstein A. Eine neue bestimmung der moleküldimensionen. *Ann Phys-berlin*. 1906;324(2):289-306.
- [100] Batchelor G, Green J-T. The hydrodynamic interaction of two small freely-moving spheres in a linear flow field. *J Fluid Mech*. 1972;56(2):375-400.
- [101] Batchelor G, Green J. The determination of the bulk stress in a suspension of spherical particles to order c^2 . *J Fluid Mech*. 1972;56(3):401-27.
- [102] Batchelor G. The effect of Brownian motion on the bulk stress in a suspension of spherical particles. *J Fluid Mech*. 1977;83(1):97-117.
- [103] Krieger IM, Dougherty TJ. A mechanism for no-Newtonian flow in suspensions of rigid spheres. *Transactions of the Society of Rheology*. 1959;3(1):137-52.
- [104] Yu W, Zhou W, Zhou C. Linear viscoelasticity of polymer blends with co-continuous morphology. *Polymer*. 2010;51(9):2091-8.
- [105] Schmidt L. A special mold and tracer technique for studying shear and extensional flows in a mold cavity during injection molding. *Polym Eng Sci*. 1974;14(11):797-800.
- [106] Anna P, Marosi G, Csontos I, Bourbigot S, Le Bras M, Delobel R. Influence of modified rheology on the efficiency of intumescent flame retardant systems. *Polym Degrad Stabil*.

2001;74(3):423-6.

[107] Wen X, Tian N, Gong J, Chen Q, Qi Y, Liu Z, et al. Effect of nanosized carbon black on thermal stability and flame retardancy of polypropylene/carbon nanotubes nanocomposites. *Polym Advan Technol.* 2013;24(11):971-7.

[108] Wen X, Wang Y, Gong J, Liu J, Tian N, Wang Y, et al. Thermal and flammability properties of polypropylene/carbon black nanocomposites. *Polym Degrad Stabil.* 2012;97(5):793-801.

[109] Dittrich B, Wartig K-A, Hofmann D, Mülhaupt R, Scharrel B. Flame retardancy through carbon nanomaterials: carbon black, multiwall nanotubes, expanded graphite, multi-layer graphene and graphene in polypropylene. *Polym Degrad Stabil.* 2013;98(8):1495-505.

[110] Cipiriano BH, Kashiwagi T, Raghavan SR, Yang Y, Grulke EA, Yamamoto K, et al. Effects of aspect ratio of MWNT on the flammability properties of polymer nanocomposites. *Polymer.* 2007;48(20):6086-96.

[111] Wang X, Song L, Yang H, Xing W, Kandola B, Hu Y. Simultaneous reduction and surface functionalization of graphene oxide with POSS for reducing fire hazards in epoxy composites. *J Mater Chem.* 2012;22(41):22037-43.

[112] Kalali EN, Wang X, Wang D-Y. Functionalized layered double hydroxide-based epoxy nanocomposites with improved flame retardancy and mechanical properties. *J Mater Chem A.* 2015;3(13):6819-26.

[113] Kalali EN, Wang X, Wang D-Y. Multifunctional intercalation in layered double hydroxide: toward multifunctional nanohybrids for epoxy resin. *J Mater Chem A.* 2016;4(6):2147-57.

[114] Kango S, Kalia S, Celli A, Njuguna J, Habibi Y, Kumar R. Surface modification of inorganic nanoparticles for development of organic–inorganic nanocomposites-A review. *Prog Polym Sci.* 2013;38(8):1232-61.

[115] Song Pa, Liu H, Shen Y, Du B, Fang Z, Wu Y. Fabrication of dendrimer-like fullerene (C₆₀)-decorated oligomeric intumescent flame retardant for reducing the thermal oxidation and flammability of polypropylene nanocomposites. *J Mater Chem.* 2009;19(9):1305-13.

[116] Chen W, Qu B. Structural characteristics and thermal properties of PE-g-MA/MgAl-LDH exfoliation nanocomposites synthesized by solution intercalation. *Chem Mater.* 2003;15(16):3208-13.

[117] Wang W, Kan Y, Pan H, Pan Y, Li B, Liew K, et al. Phosphorylated cellulose applied for the

REFERENCE

exfoliation of LDH: An advanced reinforcement for polyvinyl alcohol. *Compos Part A-Appl S.* 2017;94:170-7.

[118] Zhang Q, Jiao Q, Leroux F, Tang P, Li D, Feng Y. Antioxidant intercalated hydrocalumite as multifunction nanofiller for Poly (propylene): Synthesis, thermal stability, light stability, and anti-migration property. *Polym Degrad Stabil.* 2017;140:9-16.

[119] Li B, He J, Evans DG, Duan X. Inorganic layered double hydroxides as a drug delivery system-intercalation and in vitro release of fenbufen. *Appl Clay Sci.* 2004;27(3):199-207.

[120] Li Z, Expósito DF, González AJ, Wang D-Y. Natural Halloysite Nanotube Based Functionalized Nanohybrid Assembled via Phosphorus-containing Slow Release Method: A Highly Efficient Way to Impart Flame Retardancy to Polylactide. *Eur Polym J.* 2017;93:458-470

[121] Wang X, Song L, Yang H, Xing W, Lu H, Hu Y. Cobalt oxide/graphene composite for highly efficient CO oxidation and its application in reducing the fire hazards of aliphatic polyesters. *J Mater Chem.* 2012;22(8):3426-31.

[122] Sun Y, Ding C, Cheng W, Wang X. Simultaneous adsorption and reduction of U(VI) on reduced graphene oxide-supported nanoscale zerovalent iron. *J Hazard Mater.* 2014;280:399-408.

[123] An Q, Lv F, Liu Q, Han C, Zhao K, Sheng J, et al. Amorphous vanadium oxide matrixes supporting hierarchical porous Fe₃O₄/graphene nanowires as a high-rate lithium storage anode. *Nano letters.* 2014;14(11):6250-6.

[124] Subramanian P, Niedziolka-Jonsson J, Lesniewski A, Wang Q, Li M, Boukherroub R, et al. Preparation of reduced graphene oxide-Ni(OH)₂ composites by electrophoretic deposition: application for non-enzymatic glucose sensing. *J Mater Chem A.* 2014;2(15):5525-33.

[125] Paulus GL, Wang QH, Strano MS. Covalent electron transfer chemistry of graphene with diazonium salts. *Accounts Chem Res.* 2012;46(1):160-70.

[126] Gunjekar JL, Kim IY, Lee JM, Lee N-S, Hwang S-J. Self-assembly of layered double hydroxide 2D nanoplates with graphene nanosheets: an effective way to improve the photocatalytic activity of 2D nanostructured materials for visible light-induced O₂ generation. *Energ Environ Sci.* 2013;6(3):1008-17.

[127] Jahan M, Bao Q, Loh KP. Electrocatalytically active graphene-porphyrin MOF composite for oxygen reduction reaction. *J Am Chem Soc.* 2012;134(15):6707-13.

[128] Lin Y, Bunker CE, Fernando KS, Connell JW. Aqueously dispersed silver

REFERENCE

- nanoparticle-decorated boron nitride nanosheets for reusable, thermal oxidation-resistant surface enhanced Raman spectroscopy (SERS) devices. *ACS Appl Mater Inter.* 2012;4(2):1110-7.
- [129] Chen R, Zhi C, Yang H, Bando Y, Zhang Z, Sugiur N, et al. Arsenic (V) adsorption on Fe₃O₄ nanoparticle-coated boron nitride nanotubes. *J Colloid Interf Sci.* 2011;359(1):261-8.
- [130] Chen Y, Song B, Tang X, Lu L, Xue J. Ultrasmall Fe₃O₄ nanoparticle/MoS₂ nanosheet composites with superior performances for lithium ion batteries. *small.* 2014;10(8):1536-43.
- [131] Liang J, Xu Y, Sui D, Zhang L, Huang Y, Ma Y, et al. Flexible, magnetic, and electrically conductive graphene/Fe₃O₄ paper and its application for magnetic-controlled switches. *J Phys Chem C.* 2010;114(41):17465-71.
- [132] Huang Z, Li J, Chen Q, Wang H. A facile carboxylation of CNT/Fe₃O₄ composite nanofibers for biomedical applications. *Mater Chem Phys.* 2009;114(1):33-6.
- [133] Li X, Wang Z, Wu L. Preparation of a silica nanospheres/graphene oxide hybrid and its application in phenolic foams with improved mechanical strengths, friability and flame retardancy. *RSC Adv.* 2015;5(121):99907-13.
- [134] Bao C, Song L, Wilkie CA, Yuan B, Guo Y, Hu Y, et al. Graphite oxide, graphene, and metal-loaded graphene for fire safety applications of polystyrene. *J Mater Chem.* 2012;22(32):16399-406.
- [135] Jiang S-D, Bai Z-M, Tang G, Song L, Stec AA, Hull TR, et al. Fabrication of Ce-doped MnO₂ decorated graphene sheets for fire safety applications of epoxy composites: flame retardancy, smoke suppression and mechanism. *J Mater Chem A.* 2014;2(41):17341-51.
- [136] Jiang S-D, Bai Z-M, Tang G, Hu Y, Song L. Synthesis of ZnS decorated graphene sheets for reducing fire hazards of epoxy composites. *Ind Eng Chem Res.* 2014;53(16):6708-17.
- [137] Wang D, Kan Y, Yu X, Liu J, Song L, Hu Y. In situ loading ultra-small Cu₂O nanoparticles on 2D hierarchical TiO₂-graphene oxide dual-nanosheets: Towards reducing fire hazards of unsaturated polyester resin. *J Hazard Mater.* 2016;320:504-12.
- [138] Wang D, Zhou K, Yang W, Xing W, Hu Y, Gong X. Surface modification of graphene with layered molybdenum disulfide and their synergistic reinforcement on reducing fire hazards of epoxy resins. *Ind Eng Chem Res.* 2013;52(50):17882-90.
- [139] Zhou K, Wang B, Liu J, Jiang S, Shi Y, Zhang Q, et al. The influence of α -FeOOH/rGO hybrids on the improved thermal stability and smoke suppression properties in polystyrene. *Mater*

REFERENCE

Res Bull. 2014;53:272-9.

[140] Jiang S-D, Song L, Zeng W-R, Huang Z-Q, Zhan J, Stec AA, et al. Self-assembly fabrication of hollow mesoporous silica@Co-Al layered double hydroxide@graphene and application in toxic effluents elimination. *ACS Appl Mater Inter.* 2015;7(16):8506-14.

[141] Mu X, Zhan J, Feng X, Yuan B, Qiu S, Song L, et al. Novel Melamine/o-Phthalaldehyde Covalent Organic Frameworks Nanosheets: Enhancement Flame Retardant and Mechanical Performances of Thermoplastic Polyurethanes. *ACS Appl Mater Inter.* 2017;9(27):23017-26.

[142] Hou Y, Hu W, Gui Z, Hu Y. Preparation of Metal–Organic Frameworks and Their Application as Flame Retardants for Polystyrene. *Ind Eng Chem Res.* 2017;56(8):2036-45.

[143] Qiu S, Xing W, Mu X, Feng X, Ma C, Yuen RK, et al. A 3D Nanostructure Based on Transition-Metal Phosphide Decorated Heteroatom-Doped Mesoporous Nanospheres Interconnected with Graphene: Synthesis and Applications. *ACS Appl Mater Inter.* 2016;8(47):32528-40.

[144] Zhang W, Li X, Yang R. Blowing- out effect and temperature profile in condensed phase in flame retarding epoxy resins by phosphorus- containing oligomeric silsesquioxane. *Polym Advan Technol.* 2013;24(11):951-61.

[145] Ni Y, Zheng S, Nie K. Morphology and thermal properties of inorganic–organic hybrids involving epoxy resin and polyhedral oligomeric silsesquioxanes. *Polymer.* 2004;45(16):5557-68.

[146] Fina A, Tabuani D, Frache A, Camino G. Polypropylene–polyhedral oligomeric silsesquioxanes (POSS) nanocomposites. *Polymer.* 2005;46(19):7855-66.

[147] Fina A, Monticelli O, Camino G. POSS-based hybrids by melt/reactive blending. *J Mater Chem.* 2010;20(42):9297-305.

[148] Qian Y, Wei P, Zhao X, Jiang P, Yu H. Flame retardancy and thermal stability of polyhedral oligomeric silsesquioxane nanocomposites. *Fire Mater.* 2013;37(1):1-16.

[149] Fina A, Abbenhuis HC, Tabuani D, Camino G. Metal functionalized POSS as fire retardants in polypropylene. *Polym Degrad Stabil.* 2006;91(10):2275-81.

[150] Devaux E, Rochery M, Bourbigot S. Polyurethane/clay and polyurethane/POSS nanocomposites as flame retarded coating for polyester and cotton fabrics. *Fire Mater.* 2002;26(4-5):149-54.

[151] Song L, Xuan S, Wang X, Hu Y. Flame retardancy and thermal degradation behaviors of

REFERENCE

- phosphate in combination with POSS in polylactide composites. *Thermochim Acta*. 2012;527:1-7.
- [152] Fox DM, Lee J, Citro CJ, Novy M. Flame retarded poly (lactic acid) using POSS-modified cellulose. 1. Thermal and combustion properties of intumescent composites. *Polym Degrad Stabil*. 2013;98(2):590-6.
- [153] Zhang W, Li X, Yang R. Novel flame retardancy effects of DOPO-POSS on epoxy resins. *Polym Degrad Stabil*. 2011;96(12):2167-73.
- [154] Wang X, Hu Y, Song L, Xing W, Lu H. Thermal degradation behaviors of epoxy resin/POSS hybrids and phosphorus-silicon synergism of flame retardancy. *Journal of Polymer Science Part B: Polymer Physics*. 2010;48(6):693-705.
- [155] Song S, Ma J, Cao K, Chang G, Huang Y, Yang J. Synthesis of a novel dicyclic silicon-phosphorus hybrid and its performance on flame retardancy of epoxy resin. *Polym Degrad Stabil*. 2014;99:43-52.
- [156] Simms D. Ignition of cellulosic materials by radiation. *Combust Flame*. 1960;4:293-300.
- [157] Welker J, Wesson H, Sliepcevich C. Ignition of alpha-cellulose and cotton fabric by flame radiation. *Fire Technol*. 1969;5(1):59-66.
- [158] Hallman J, Welker JR, Sliepcevich C. Ignition of polymers. *SPE Journal*. 1972;28(43):1972.
- [159] Choi M, Hamins A, Mulholland GW, Kashiwagi T. Simultaneous optical measurement of soot volume fraction and temperature in premixed flames. *Combust Flame*. 1994;99(1):174-86.
- [160] Kashiwagi T. Radiative ignition mechanism of solid fuels. *Fire Safety J*. 1981;3(3):185-200.
- [161] Fina A, Camino G. Ignition mechanisms in polymers and polymer nanocomposites. *Polym Advan Technol*. 2011;22(7):1147-55.
- [162] Thomson H, Drysdale D. Flammability of plastics I: ignition temperatures. *Fire Mater*. 1987;11(4):163-72.
- [163] KASHIWAGI T. Effects of attenuation of radiation on surface temperature for radiative ignition. *Combust Sci Technol*. 1979;20(5-6):225-34.
- [164] Scharrel B, Hull T. Development of fire-retarded materials-Interpretation of cone calorimeter data. *Fire Mater*. 2007;31(5):327-54.
- [165] Safronava N, Lyon RE, Crowley S, Stoliarov SI. Effect of moisture on ignition time of polymers. *Fire Technol*. 2015;51(5):1093-112.
- [166] Li J, Gong J, Stoliarov SI. Gasification experiments for pyrolysis model parameterization

REFERENCE

- and validation. *Int J Heat Mass Tran.* 2014;77:738-44.
- [167] Fina A, Cuttica F, Camino G. Ignition of polypropylene/montmorillonite nanocomposites. *Polym Degrad Stabil.* 2012;97(12):2619-26.
- [168] Kashiwagi T. Experimental observation of radiative ignition mechanisms. *Combust Flame.* 1979;34:231-44.
- [169] Balakrishnan E, Nelson M, Wake G. Radiative ignition of combustible materials I. Polymeric materials undergoing nonflaming thermal degradation-the critical storage problem. *Math Comput Model.* 1999;30(11-12):177-95.
- [170] Di Blasi C, Crescitelli S, Russo G, Cinque G. Numerical model of ignition processes of polymeric materials including gas-phase absorption of radiation. *Combust Flame.* 1991;83(3-4):333-44.
- [171] Rasbash D, Drysdale D, Deepak D. Critical heat and mass transfer at pilot ignition and extinction of a material. *Fire Safety J.* 1986;10(1):1-10.
- [172] Kashiwagi T. A radiative ignition model of a solid fuel. *Combust Sci Technol.* 1973;8(5-6):225-36.
- [173] Kashiwagi T. Effects of sample orientation on radiative ignition. *Combust Flame.* 1982;44(1-3):223-45.
- [174] Wu GM, Scharrel B, Bahr H, Kleemeier M, Yu D, Hartwig A. Experimental and quantitative assessment of flame retardancy by the shielding effect in layered silicate epoxy nanocomposites. *Combust Flame.* 2012;159(12):3616-23.
- [175] Sonnier R, Bokobza L, Concha- Lozano N. Influence of multiwall carbon nanotube (MWCNT) dispersion on ignition of poly (dimethylsiloxane)-MWCNT composites. *Polym Advan Technol.* 2015;26(3):277-86.
- [176] Zhang J, Delichatsios MA, Bourbigot S. Experimental and numerical study of the effects of nanoparticles on pyrolysis of a polyamide 6 (PA6) nanocomposite in the cone calorimeter. *Combust Flame.* 2009;156(11):2056-62.
- [177] Li J, Gong J, Stoliarov SI. Development of pyrolysis models for charring polymers. *Polym Degrad Stabil.* 2015;115:138-52.
- [178] Li J, Stoliarov SI. Measurement of kinetics and thermodynamics of the thermal degradation for charring polymers. *Polym Degrad Stabil.* 2014;106:2-15.

REFERENCE

- [179] Li J, Stoliarov SI. Measurement of kinetics and thermodynamics of the thermal degradation for non-charring polymers. *Combust Flame*. 2013;160(7):1287-97.
- [180] Kurylyk BL, McKenzie JM, MacQuarrie KT, Voss CI. Analytical solutions for benchmarking cold regions subsurface water flow and energy transport models: One-dimensional soil thaw with conduction and advection. *Adv Water Resour*. 2014;70:172-84.
- [181] Zhou Y, Fernandez-Pello A. Numerical modeling of endothermic pyrolysis and ignition delay of composite materials exposed to an external radiant heat flux. *P Combust Inst*. 2000;28(2):2769-75.
- [182] Pan Y-T, Wang D-Y. One-step hydrothermal synthesis of nano zinc carbonate and its use as a promising substitute for antimony trioxide in flame retardant flexible poly (vinyl chloride). *RSC Adv*. 2015;5(35):27837-43.
- [183] Chigwada G, Jash P, Jiang DD, Wilkie CA. Synergy between nanocomposite formation and low levels of bromine on fire retardancy in polystyrenes. *Polym Degrad Stabil*. 2005;88(3):382-93.
- [184] Westbrook CK. Inhibition of hydrocarbon oxidation in laminar flames and detonations by halogenated compounds. *Symposium (International) on Combustion*: Elsevier; 1982. p. 127-41.
- [185] Borisov A, Kosenkov V, Mailkov A, Mikhalkin V, Khomik S. Effect of flame inhibitors on detonation characteristics of fuel-air mixtures. *Progress in Astronautics and Aeronautics*. 1993;153:312-.
- [186] Rotheron R, Hornsby P. Flame retardant effects of magnesium hydroxide. *Polym Degrad Stabil*. 1996;54(2-3):383-5.
- [187] Sain M, Park S, Suhara F, Law S. Flame retardant and mechanical properties of natural fibre-PP composites containing magnesium hydroxide. *Polym Degrad Stabil*. 2004;83(2):363-7.
- [188] El Hage R, Viretto A, Sonnier R, Ferry L, Lopez-Cuesta J-M. Flame retardancy of ethylene vinyl acetate (EVA) using new aluminum-based fillers. *Polym Degrad Stabil*. 2014;108:56-67.
- [189] Pan Y-T, Zhang L, Zhao X, Wang D-Y. Interfacial engineering of renewable metal organic framework derived honeycomb-like nanoporous aluminum hydroxide with tunable porosity. *Chem Sci*. 2017;8(5):3399-409.
- [190] Braun U, Scharrel B. Flame retardant mechanisms of red phosphorus and magnesium hydroxide in high impact polystyrene. *Macromol Chem Phys*. 2004;205(16):2185-96.

REFERENCE

- [191] Nyambo C, Songtipya P, Manias E, Jimenez-Gasco MM, Wilkie CA. Effect of MgAl-layered double hydroxide exchanged with linear alkyl carboxylates on fire-retardancy of PMMA and PS. *J Mater Chem*. 2008;18(40):4827-38.
- [192] Laoutid F, Sonnier R, Francois D, Bonnaud L, Cinausero N, Cuesta JML, et al. Effect of magnesium dihydroxide nanoparticles on thermal degradation and flame resistance of PMMA nanocomposites. *Polym Advan Technol*. 2011;22(12):1713-9.
- [193] Hamdani-Devarennnes S, Longuet C, Sonnier R, Ganachaud F, Lopez-Cuesta J-M. Calcium and aluminum-based fillers as flame-retardant additives in silicone matrices. III. Investigations on fire reaction. *Polym Degrad Stabil*. 2013;98(10):2021-32.
- [194] Hamdani-Devarennnes S, Pommier A, Longuet C, Lopez-Cuesta J-M, Ganachaud F. Calcium and aluminium-based fillers as flame-retardant additives in silicone matrices II. Analyses on composite residues from an industrial-based pyrolysis test. *Polym Degrad Stabil*. 2011;96(9):1562-72.
- [195] Laachachi A, Ferriol M, Cochez M, Cuesta J-ML, Ruch D. A comparison of the role of boehmite (AlOOH) and alumina (Al_2O_3) in the thermal stability and flammability of poly (methyl methacrylate). *Polym Degrad Stabil*. 2009;94(9):1373-8.
- [196] Feng Y, Hu J, Xue Y, He C-E, Zhou X, Xie X, et al. Simultaneous improvement in flame resistance and thermal conductivity of epoxy/ Al_2O_3 composites by incorporating polymeric flame retardant-functionalized graphene. *J Mater Chem A*. 2017.
- [197] Guan F-L, Gui C-X, Zhang H-B, Jiang Z-G, Jiang Y, Yu Z-Z. Enhanced thermal conductivity and satisfactory flame retardancy of epoxy/alumina composites by combination with graphene nanoplatelets and magnesium hydroxide. *Compos Part B-Eng*. 2016;98:134-40.
- [198] Levchik SV, Weil ED. A review of recent progress in phosphorus-based flame retardants. *J Fire Sci*. 2006;24(5):345-64.
- [199] Green J. A review of phosphorus-containing flame retardants. *J Fire Sci*. 1992;10(6):470-87.
- [200] Li Z, Wei P, Yang Y, Yan Y, Shi D. Synthesis of a hyperbranched poly (phosphamide ester) oligomer and its high-effective flame retardancy and accelerated nucleation effect in polylactide composites. *Polym Degrad Stabil*. 2014;110:104-12.
- [201] Liang S, Hemberger P, Neisius NM, Bodi A, Grützmacher H, Levalois-Grützmacher J, et al. Elucidating the Thermal Decomposition of Dimethyl Methylphosphonate by Vacuum Ultraviolet

(VUV) Photoionization: Pathways to the PO Radical, a Key Species in Flame- Retardant Mechanisms. *Chem-Eur J.* 2015;21(3):1073-80.

[202] Feng F, Qian L. The flame retardant behaviors and synergistic effect of expandable graphite and dimethyl methylphosphonate in rigid polyurethane foams. *Polym Composite.* 2014;35(2):301-9.

[203] Pawlowski KH, ScharTEL B. Flame retardancy mechanisms of triphenyl phosphate, resorcinol bis (diphenyl phosphate) and bisphenol A bis (diphenyl phosphate) in polycarbonate/acrylonitrile-butadiene-styrene blends. *Polym Int.* 2007;56(11):1404-14.

[204] Pawlowski KH, ScharTEL B, Fichera MA, Jäger C. Flame retardancy mechanisms of bisphenol A bis (diphenyl phosphate) in combination with zinc borate in bisphenol A polycarbonate/acrylonitrile-butadiene-styrene blends. *Thermochim Acta.* 2010;498(1):92-9.

[205] Chigwada G, Jash P, Jiang DD, Wilkie CA. Fire retardancy of vinyl ester nanocomposites: synergy with phosphorus-based fire retardants. *Polym Degrad Stabil.* 2005;89(1):85-100.

[206] Ma H, Wang J, Fang Z. Cross-linking of a novel reactive polymeric intumescent flame retardant to ABS copolymer and its flame retardancy properties. *Polym Degrad Stabil.* 2012;97(9):1596-605.

[207] Jing X-K, Guo D-M, Zhang J-B, Zhai F-Y, Wang X-L, Chen L, et al. Thermal transition behavior, thermal stability, and flame retardancy of low-melting-temperature copolyester: Comonomer effect. *Ind Eng Chem Res.* 2013;52(12):4539-46.

[208] Price D, Pyrah K, Hull TR, Milnes GJ, Ebdon JR, Hunt BJ, et al. Flame retardance of poly (methyl methacrylate) modified with phosphorus-containing compounds. *Polym Degrad Stabil.* 2002;77(2):227-33.

[209] Zhao X, Guerrero FR, Llorca J, Wang D-Y. New Superefficiently Flame-Retardant Bioplastic Poly (lactic acid): Flammability, Thermal Decomposition Behavior, and Tensile Properties. *ACS Sustain Chem Eng.* 2015;4(1):202-9.

[210] Braun U, Bahr H, Sturm H, ScharTEL B. Flame retardancy mechanisms of metal phosphinates and metal phosphinates in combination with melamine cyanurate in glass- fiber reinforced poly (1, 4-butylene terephthalate): the influence of metal cation. *Polym Advan Technol.* 2008;19(6):680-92.

[211] Tang G, Wang X, Zhang R, Wang B, Hong N, Hu Y, et al. Effect of rare earth hypophosphite

REFERENCE

- salts on the fire performance of biobased polylactide composites. *Ind Eng Chem Res.* 2013;52(22):7362-72.
- [212] Tang G, Wang X, Zhang R, Yang W, Hu Y, Song L, et al. Facile synthesis of lanthanum hypophosphite and its application in glass-fiber reinforced polyamide 6 as a novel flame retardant. *Compos Part A-Appl S.* 2013;54:1-9.
- [213] Tang G, Huang X, Ding H, Wang X, Jiang S, Zhou K, et al. Combustion properties and thermal degradation behaviors of biobased polylactide composites filled with calcium hypophosphite. *RSC Adv.* 2014;4(18):8985-93.
- [214] Li B, Jia H, Guan L, Bing B, Dai J. A novel intumescent flame- retardant system for flame-retarded LLDPE/EVA composites. *J Appl Polym Sci.* 2009;114(6):3626-35.
- [215] Nyambo C, Kandare E, Wang D, Wilkie CA. Flame-retarded polystyrene: Investigating chemical interactions between ammonium polyphosphate and MgAl layered double hydroxide. *Polym Degrad Stabil.* 2008;93(9):1656-63.
- [216] Du B, Guo Z, Fang Z. Effects of organo-clay and sodium dodecyl sulfonate intercalated layered double hydroxide on thermal and flame behaviour of intumescent flame retarded polypropylene. *Polym Degrad Stabil.* 2009;94(11):1979-85.
- [217] Zhao W, Li B, Xu M, Yang K, Lin L. Novel intumescent flame retardants: synthesis and application in polycarbonate. *Fire Mater.* 2013;37(7):530-46.
- [218] Tan Y, Shao Z-B, Yu L-X, Long J-W, Qi M, Chen L, et al. Piperazine-modified ammonium polyphosphate as monocomponent flame-retardant hardener for epoxy resin: flame retardance, curing behavior and mechanical property. *Polym Chem.* 2016;7(17):3003-12.
- [219] Yang K, Xu M-J, Li B. Synthesis of N-ethyl triazine-piperazine copolymer and flame retardancy and water resistance of intumescent flame retardant polypropylene. *Polym Degrad Stabil.* 2013;98(7):1397-406.
- [220] Zhang W, He X, Song T, Jiao Q, Yang R. Comparison of intumescence mechanism and blowing-out effect in flame-retarded epoxy resins. *Polym Degrad Stabil.* 2015;112:43-51.
- [221] Song L, Wu K, Wang Y, Wang Z, Hu Y. Flammability and thermo-oxidative decomposition of epoxy resin containing ammonium polyphosphate and metallic oxide. *J MACROMOL SCI A.* 2009;46(3):290-5.
- [222] Qu H, Wu W, Hao J, Wang C, Xu J. Inorganic-organic hybrid coating-encapsulated

REFERENCE

ammonium polyphosphate and its flame retardancy and water resistance in epoxy resin. *Fire Mater.* 2014;38(3):312-22.

[223] Wang J-S, Liu Y, Zhao H-B, Liu J, Wang D-Y, Song Y-P, et al. Metal compound-enhanced flame retardancy of intumescent epoxy resins containing ammonium polyphosphate. *Polym Degrad Stabil.* 2009;94(4):625-31.

[224] Wang JS, Wang DY, Liu Y, Ge XG, Wang YZ. Polyamide- enhanced flame retardancy of ammonium polyphosphate on epoxy resin. *J Appl Polym Sci.* 2008;108(4):2644-53.

[225] Ren H, Sun J, Wu B, Zhou Q. Synthesis and properties of a phosphorus-containing flame retardant epoxy resin based on bis-phenoxy (3-hydroxy) phenyl phosphine oxide. *Polym Degrad Stabil.* 2007;92(6):956-61.

[226] Wang X, Xing W, Wang B, Wen P, Song L, Hu Y, et al. Comparative study on the effect of beta-cyclodextrin and polypseudorotaxane as carbon sources on the thermal stability and flame retardance of polylactic acid. *Ind Eng Chem Res.* 2013;52(9):3287-94.

[227] Wang D-Y, Liu Y, Ge X-G, Wang Y-Z, Stec A, Biswas B, et al. Effect of metal chelates on the ignition and early flaming behaviour of intumescent fire-retarded polyethylene systems. *Polym Degrad Stabil.* 2008;93(5):1024-30.

[228] Wen P, Wang X, Wang B, Yuan B, Zhou K, Song L, et al. One-pot synthesis of a novel s-triazine-based hyperbranched charring foaming agent and its enhancement on flame retardancy and water resistance of polypropylene. *Polym Degrad Stabil.* 2014;110:165-74.

[229] Huang G, Wang S, Song Pa, Wu C, Chen S, Wang X. Combination effect of carbon nanotubes with graphene on intumescent flame-retardant polypropylene nanocomposites. *Compos Part A-Appl S.* 2014;59:18-25.

[230] Shi Y, Xing W, Wang B, Hong N, Zhu Y, Wang C, et al. Synergistic effect of graphitic carbon nitride and ammonium polyphosphate for enhanced thermal and flame retardant properties of polystyrene. *Mater Chem Phys.* 2016;177:283-92.

[231] Zhang W, He X, Song T, Jiao Q, Yang R. The influence of the phosphorus-based flame retardant on the flame retardancy of the epoxy resins. *Polym Degrad Stabil.* 2014;109:209-17.

[232] Zhang W, Li X, Yang R. Study on the change of silicon and phosphorus content in the condensed phase during the combustion of epoxy resin with OPS/DOPO. *Polym Degrad Stabil.* 2014;99:298-303.

REFERENCE

- [233] Zhang W, Li X, Fan H, Yang R. Study on mechanism of phosphorus–silicon synergistic flame retardancy on epoxy resins. *Polym Degrad Stabil.* 2012;97(11):2241-8.
- [234] Jin W, Yuan L, Liang G, Gu A. Multifunctional cyclotriphosphazene/hexagonal boron nitride hybrids and their flame retarding bismaleimide resins with high thermal conductivity and thermal stability. *ACS Appl Mater Inter.* 2014;6(17):14931-44.
- [235] Yu B, Xing W, Guo W, Qiu S, Wang X, Lo S, et al. Thermal exfoliation of hexagonal boron nitride for effective enhancements on thermal stability, flame retardancy and smoke suppression of epoxy resin nanocomposites via sol-gel process. *J Mater Chem A.* 2016;4(19):7330-40.
- [236] Wang X, Zhou S, Xing W, Yu B, Feng X, Song L, et al. Self-assembly of Ni–Fe layered double hydroxide/graphene hybrids for reducing fire hazard in epoxy composites. *J Mater Chem A.* 2013;1(13):4383-90.
- [237] Song Pa, Zhu Y, Tong L, Fang Z. C60 reduces the flammability of polypropylene nanocomposites by in situ forming a gelled-ball network. *Nanotechnology.* 2008;19(22):225707.
- [238] Hausner J, Fischer B, Stöter M, Edenharter A, Schmid J, Kunz R, et al. Increasing time of ignition for PS-clay nanocomposites filled with $[\text{Fe}(\text{bpy})_3]^{2+}$ -modified hectorite. *Polym Degrad Stabil.* 2016;128:141-8.
- [239] Galgano A, Branca C, Di Blasi C, Vollaro P, Milella E. Modeling the ignition of poly (methyl methacrylate)/carbon nanotube nanocomposites. *Polym Degrad Stabil.* 2017;144:344-53.
- [240] Alongi J, Carosio F, Malucelli G. Current emerging techniques to impart flame retardancy to fabrics: an overview. *Polym Degrad Stabil.* 2014;106:138-49.
- [241] Alongi J, Tata J, Carosio F, Rosace G, Frache A, Camino G. A comparative analysis of nanoparticle adsorption as fire-protection approach for fabrics. *Polymers.* 2014;7(1):47-68.
- [242] Smith RJ, Holder KM, Ruiz S, Hahn W, Song Y, Lvov YM, et al. Environmentally Benign Halloysite Nanotube Multilayer Assembly Significantly Reduces Polyurethane Flammability. *Adv Funct Mater.* 2017.
- [243] Huang G, Liang H, Wang X, Gao J. Poly (acrylic acid)/clay thin films assembled by layer-by-layer deposition for improving the flame retardancy properties of cotton. *Ind Eng Chem Res.* 2012;51(38):12299-309.
- [244] Ma H, Peng J, Zhou B, Han Z, Feng Y. Luminescent multilayer film based on mixed-addenda polyoxometalates and polyethyleneimine by layer-by-layer assembly. *Appl Surf*

REFERENCE

Sci. 2004;233(1):14-9.

[245] Carosio F, Alongi J, Malucelli G. Layer by layer ammonium polyphosphate-based coatings for flame retardancy of polyester–cotton blends. *Carbohydr Polym.* 2012;88(4):1460-9.

[246] Li Y-C, Yang Y-H, Shields JR, Davis RD. Layered double hydroxide-based fire resistant coatings for flexible polyurethane foam. *Polymer.* 2015;56:284-92.

[247] Carosio F, Di Blasio A, Cuttica F, Alongi J, Frache A, Malucelli G. Flame retardancy of polyester fabrics treated by spray-assisted layer-by-layer silica architectures. *Ind Eng Chem Res.* 2013;52(28):9544-50.

[248] Li Y-C, Mannen S, Schulz J, Grunlan JC. Growth and fire protection behavior of POSS-based multilayer thin films. *J Mater Chem.* 2011;21(9):3060-9.

[249] Zhang T, Yan H, Peng M, Wang L, Ding H, Fang Z. Construction of flame retardant nanocoating on ramie fabric via layer-by-layer assembly of carbon nanotube and ammonium polyphosphate. *Nanoscale.* 2013;5(7):3013-21.

[250] Huang G, Yang J, Gao J, Wang X. Thin films of intumescent flame retardant-polyacrylamide and exfoliated graphene oxide fabricated via layer-by-layer assembly for improving flame retardant properties of cotton fabric. *Ind Eng Chem Res.* 2012;51(38):12355-66.

[251] Laufer G, Carosio F, Martinez R, Camino G, Grunlan JC. Growth and fire resistance of colloidal silica-polyelectrolyte thin film assemblies. *J Colloid Interf Sci.* 2011;356(1):69-77.

[252] Wang X, Romero MQ, Zhang X-Q, Wang R, Wang D-Y. Intumescent multilayer hybrid coating for flame retardant cotton fabrics based on layer-by-layer assembly and sol-gel process. *RSC Adv.* 2015;5(14):10647-55.

[253] Alongi J, Carletto RA, Di Blasio A, Cuttica F, Carosio F, Bosco F, et al. Intrinsic intumescent-like flame retardant properties of DNA-treated cotton fabrics. *Carbohydr Polym.* 2013;96(1):296-304.

[254] Friedlander SK. Smoke, dust and haze: Fundamentals of aerosol behavior. New York, Wiley-Interscience, 1977 333 p. 1977.

[255] Zhou K, Jiang S, Shi Y, Liu J, Wang B, Hu Y, et al. Multigram-scale fabrication of organic modified MoS₂ nanosheets dispersed in polystyrene with improved thermal stability, fire resistance, and smoke suppression properties. *RSC Adv.* 2014;4(76):40170-80.

[256] Carty P, Metcalfe E, White S. A review of the role of iron containing compounds in char

REFERENCE

forming/smoke suppressing reactions during the thermal decomposition of semi-rigid poly (vinyl chloride) formulations. *Polymer*. 1992;33(13):2704-8.

[257] Lattimer RP, Kroenke WJ. The functional role of molybdenum trioxide as a smoke retarder additive in rigid poly (vinyl chloride). *J Appl Polym Sci*. 1981;26(4):1191-210.

[258] Michel A, Bert M, Van Hoang T, Bussiere P, Guyot A. Main functions of iron compounds as smoke suppressant in poly (vinyl chloride) combustion. *J Appl Polym Sci*. 1983;28(5):1573-84.

[259] Wang W, Pan H, Shi Y, Pan Y, Yang W, Liew K, et al. Fabrication of LDH nanosheets on β -FeOOH rods and applications for improving the fire safety of epoxy resin. *Compos Part A-Appl S*. 2016;80:259-69.

[260] Zhou K, Gui Z, Hu Y. The influence of graphene based smoke suppression agents on reduced fire hazards of polystyrene composites. *Composites Part A: Applied Science and Manufacturing*. 2016;80:217-27.

[261] Lecomte L, Bert M, Michel A, Guyot A. Mechanism of smoke reduction by ferrocene in PVC combustion. *Journal of Macromolecular Science-Chemistry*. 1977;11(8):1467-89.

[262] Zhang J, Megaridis CM. Soot suppression by ferrocene in laminar ethylene/air nonpremixed flames. *Combust Flame*. 1996;105(4):528-40.

[263] Hirschler MM. Soot from fires: III. Soot suppression. *J Fire Sci*. 1986;4(1):42-72.

[264] Xu Y-J, Wang J, Tan Y, Qi M, Chen L, Wang Y-Z. A novel and feasible approach for one-pack flame-retardant epoxy resin with long pot life and fast curing. *Chem Eng J*. 2018;337:30-9.

[265] Bankston C, Zinn B, Browner R, Powell E. Aspects of the mechanisms of smoke generation by burning materials. *Combust Flame*. 1981;41:273-92.

[266] Starnes Jr WH, Pike RD, Cole JR, Doyal AS, Kimlin EJ, Lee JT, et al. Cone calorimetric study of copper-promoted smoke suppression and fire retardance of poly (vinyl chloride). *Polym Degrad Stabil*. 2003;82(1):15-24.

[267] MARSH* ND, Preciado I, Eddings EG, Sarofim AF, Palotas AB, Robertson JD. Evaluation of organometallic fuel additives for soot suppression. *Combust Sci Technol*. 2007;179(5):987-1001.

[268] Chen X, Jiang Y, Jiao C. Smoke suppression properties of ferrite yellow on flame retardant thermoplastic polyurethane based on ammonium polyphosphate. *J Hazard Mater*.

REFERENCE

2014;266:114-21.

[269] Linteris GT, Rumminger MD, Babushok VI. Catalytic inhibition of laminar flames by transition metal compounds. *Prog Energ Combust*. 2008;34(3):288-329.

[270] Neuse EW, Woodhouse JR, Montaudo G, Puglisi C. An iron–organic polymeric smoke suppressant for poly (vinyl chloride). *Appl Organomet Chem*. 1988;2(1):53-7.

[271] Bonczyk P. Effect of ferrocene on soot in a prevaporized iso-octane/air diffusion flame. *Combust Flame*. 1991;87(3-4):233-44.

[272] Lawson DF. Investigation of the mechanistic basis for ferrocene activity during the combustion of vinyl polymers. *J Appl Polym Sci*. 1976;20(8):2183-92.

[273] Carty P, Grant J, Metcalfe E. Flame-retardancy and Smoke-suppression Studies on Ferrocene Derivatives in PVC. *Appl Organomet Chem*. 1996;10(2):101-11.

[274] Xu J, Liu C, Qu H, Ma H, Jiao Y, Xie J. Investigation on the thermal degradation of flexible poly (vinyl chloride) filled with ferrites as flame retardant and smoke suppressant using TGA-FTIR and TGA-MS. *Polym Degrad Stabil*. 2013;98(8):1506-14.

[275] Carty P, Docherty A. Iron-containing compounds as flame retarding/smoke-suppressing additives for PVC. *Fire Mater*. 1988;12(3):109-13.

[276] Zhang Y, Hu Y, Song L, Wu J, Fang S. Influence of Fe-MMT on the fire retarding behavior and mechanical property of (ethylene- vinyl acetate copolymer/magnesium hydroxide) composite. *Polym Advan Technol*. 2008;19(8):960-6.

[277] Xu S, Zhang L, Lin Y, Li R, Zhang F. Layered double hydroxides used as flame retardant for engineering plastic acrylonitrile–butadiene–styrene (ABS). *J Phys Chem Solids*. 2012;73(12):1514-7.

[278] Wang L, Song L, Hu Y, Yuen RK. Influence of Different Metal Oxides on the Thermal, Combustion Properties and Smoke Suppression in Ethylene-Vinyl Acetate. *Ind Eng Chem Res*. 2013;52(23):8062-9.

[279] Hirschler M. Reduction of smoke formation from and flammability of thermoplastic polymers by metal oxides. *Polymer*. 1984;25(3):405-11.

[280] Shi Y, Qian X, Zhou K, Tang Q, Jiang S, Wang B, et al. CuO/graphene nanohybrids: preparation and enhancement on thermal stability and smoke suppression of polypropylene. *Ind Eng Chem Res*. 2013;52(38):13654-60.

REFERENCE

- [281] Li Z, Wang D-Y. Nano-architected mesoporous silica decorated with ultrafine Co_3O_4 toward an efficient way to delaying ignition and improving fire retardancy of polystyrene. *Mater Design*. 2017;129:69-81.
- [282] Xu W, Liu L, Zhang B, Hu Y, Xu B. Effect of molybdenum trioxide-loaded graphene and cuprous oxide-loaded graphene on flame retardancy and smoke suppression of polyurethane elastomer. *Ind Eng Chem Res*. 2016;55(17):4930-41.
- [283] Li Z, González AJ, Heeralal VB, Wang D-Y. Covalent assembly of MCM-41 nanospheres on graphene oxide for improving fire retardancy and mechanical property of epoxy resin. *Composites Part B: Engineering*. 2018;138:101-12.
- [284] Kim S. Flame retardancy and smoke suppression of magnesium hydroxide filled polyethylene. *Journal of Polymer Science Part B: Polymer Physics*. 2003;41(9):936-44.
- [285] Babrauskas V. Development of the cone calorimeter-a bench- scale heat release rate apparatus based on oxygen consumption. *Fire Mater*. 1984;8(2):81-95.
- [286] Bohac V, Gustavsson MK, Kubicar L, Gustafsson SE. Parameter estimations for measurements of thermal transport properties with the hot disk thermal constants analyzer. *Rev Sci Instrum*. 2000;71(6):2452-5.
- [287] Gustavsson M, Karawacki E, Gustafsson SE. Thermal conductivity, thermal diffusivity, and specific heat of thin samples from transient measurements with hot disk sensors. *Rev Sci Instrum*. 1994;65(12):3856-9.
- [288] Du M, Guo B, Jia D. Newly emerging applications of halloysite nanotubes: a review. *Polym Int*. 2010;59(5):574-82.
- [289] Lvov Y, Wang W, Zhang L, Fakhrullin R. Halloysite clay nanotubes for loading and sustained release of functional compounds. *Adv Mater*. 2016;28(6):1227-50.
- [290] Abdullayev E, Price R, Shchukin D, Lvov Y. Halloysite tubes as nanocontainers for anticorrosion coating with benzotriazole. *ACS Appl Mater Inter*. 2009;1(7):1437-43.
- [291] Lvov YM, Shchukin DG, Mohwald H, Price RR. Halloysite clay nanotubes for controlled release of protective agents. *ACS Nano*. 2008;2(5):814-20.
- [292] Zheng T, Ni X. Loading an organophosphorous flame retardant into halloysite nanotubes for modifying UV-curable epoxy resin. *RSC Adv*. 2016;6(62):57122-30.
- [293] Du M, Guo B, Jia D. Thermal stability and flame retardant effects of halloysite nanotubes on

REFERENCE

- poly (propylene). *Eur Polym J*. 2006;42(6):1362-9.
- [294] Marney D, Russell L, Wu D, Nguyen T, Cramm D, Rigopoulos N, et al. The suitability of halloysite nanotubes as a fire retardant for nylon 6. *Polym Degrad Stabil*. 2008;93(10):1971-8.
- [295] Ning N-y, Yin Q-j, Luo F, Zhang Q, Du R, Fu Q. Crystallization behavior and mechanical properties of polypropylene/halloysite composites. *Polymer*. 2007;48(25):7374-84.
- [296] Tang Y, Deng S, Ye L, Yang C, Yuan Q, Zhang J, et al. Effects of unfolded and intercalated halloysites on mechanical properties of halloysite–epoxy nanocomposites. *Compos Part A-Appl S*. 2011;42(4):345-54.
- [297] Ismail H, Pasbakhsh P, Fauzi MA, Bakar AA. Morphological, thermal and tensile properties of halloysite nanotubes filled ethylene propylene diene monomer (EPDM) nanocomposites. *Polym Test*. 2008;27(7):841-50.
- [298] Ji X, Hampsey JE, Hu Q, He J, Yang Z, Lu Y. Mesoporous silica-reinforced polymer nanocomposites. *Chem Mater*. 2003;15(19):3656-62.
- [299] Zhang F-A, Lee D-K, Pinnavaia TJ. PMMA/mesoporous silica nanocomposites: effect of framework structure and pore size on thermomechanical properties. *Polym Chem*. 2010;1(1):107-13.
- [300] Zhang F-A, Lee D-K, Pinnavaia TJ. PMMA-mesocellular foam silica nanocomposites prepared through batch emulsion polymerization and compression molding. *Polymer*. 2009;50(20):4768-74.
- [301] Qian Y, Wei P, Jiang P, Li Z, Yan Y, Ji K. Aluminated mesoporous silica as novel high-effective flame retardant in polylactide. *Compos Sci Technol*. 2013;82:1-7.
- [302] Linteris GT, Katta VR, Takahashi F. Experimental and numerical evaluation of metallic compounds for suppressing cup-burner flames. *Combust Flame*. 2004;138(1):78-96.
- [303] Linteris GT, Rumminger M, Babushok V, Tsang W. Flame inhibition by ferrocene and blends of inert and catalytic agents. *Proceedings of the Combustion Institute*. 2000;28(2):2965-72.
- [304] Koshiba Y, Takahashi Y, Ohtani H. Flame suppression ability of metallocenes (nickelocene, cobaltocene, ferrocene, manganocene, and chromocene). *Fire Safety J*. 2012;51:10-7.
- [305] Tian K, Li Z, Staude S, Li B, Sun Z, Lantz A, et al. Influence of ferrocene addition to a laminar premixed propene flame: Laser diagnostics, mass spectrometry and numerical simulations. *Proceedings of the Combustion Institute*. 2009;32(1):445-52.

REFERENCE

- [306] Johansson EM, Ballem MA, Córdoba JM, Odén M. Rapid synthesis of SBA-15 rods with variable lengths, widths, and tunable large pores. *Langmuir*. 2011;27(8):4994-9.
- [307] Luan Z, Fournier JA. In situ FTIR spectroscopic investigation of active sites and adsorbate interactions in mesoporous aluminosilicate SBA-15 molecular sieves. *Micropor Mesopor Mat*. 2005;79(1):235-40.
- [308] Jiang J, Li L. Synthesis of sphere-like Co_3O_4 nanocrystals via a simple polyol route. *Mater Lett*. 2007;61(27):4894-6.
- [309] Yan J, Wei T, Qiao W, Shao B, Zhao Q, Zhang L, et al. Rapid microwave-assisted synthesis of graphene nanosheet/ Co_3O_4 composite for supercapacitors. *Electrochim Acta*. 2010;55(23):6973-8.
- [310] Qiu JF, Zhang MQ, Rong MZ, Wu SP, Karger-Kocsis J. Rigid bio-foam plastics with intrinsic flame retardancy derived from soybean oil. *J Mater Chem A*. 2013;1(7):2533-42.
- [311] Joo Y, Jeon Y, Lee SU, Sim JH, Ryu J, Lee S, et al. Aggregation and stabilization of carboxylic acid functionalized halloysite nanotubes (HNT-COOH). *J Phys Chem C*. 2012;116(34):18230-5.
- [312] Liu YL. Flame-retardant epoxy resins from novel phosphorus-containing novolac. *Polymer*. 2001;42(8):3445-54.
- [313] Liao S-H, Liu P-L, Hsiao M-C, Teng C-C, Wang C-A, Ger M-D, et al. One-step reduction and functionalization of graphene oxide with phosphorus-based compound to produce flame-retardant epoxy nanocomposite. *Ind Eng Chem Res*. 2012;51(12):4573-81.
- [314] Vasiljević J, Jerman I, Jakša G, Alongi J, Malucelli G, Zorko M, et al. Functionalization of cellulose fibres with DOPO-polysilsesquioxane flame retardant nanocoating. *Cellulose*. 2015;22(3):1893-910.
- [315] Rumminger M, Reinelt D, Babushok V, Linteris GT. Numerical study of the inhibition of premixed and diffusion flames by iron pentacarbonyl. *Combust Flame*. 1999;116(1):207-19.
- [316] Jang BN, Wilkie CA. The thermal degradation of polystyrene nanocomposite. *Polymer*. 2005;46(9):2933-42.
- [317] Jaeger TD, van Heijnsbergen D, Klippenstein SJ, von Helden G, Meijer G, Duncan MA. Vibrational spectroscopy and density functional theory of transition-metal ion-benzene and dibenzene complexes in the gas phase. *J Am Chem Soc*. 2004;126(35):10981-91.

REFERENCE

- [318] Willey K, Yeh C, Robbins D, Duncan M. Charge-transfer in the photodissociation of metal ion-benzene complexes. *J Phys Chem.* 1992;96(23):9106-11.
- [319] Bourbigot S, Flambard X, Poutch F, Duquesne S. Cone calorimeter study of high performance fibres-application to polybenzazole and p-aramid fibres. *Polym Degrad Stabil.* 2001;74(3):481-6.
- [320] Gong J, Liu J, Jiang Z, Chen X, Wen X, Mijowska E, et al. Converting mixed plastics into mesoporous hollow carbon spheres with controllable diameter. *Appl Catal B-Environ.* 2014;152:289-99.
- [321] Gong J, Liu J, Chen X, Wen X, Jiang Z, Mijowska E, et al. Synthesis, characterization and growth mechanism of mesoporous hollow carbon nanospheres by catalytic carbonization of polystyrene. *Micropor Mesopor Mat.* 2013;176:31-40.
- [322] Kopinke F-D, Remmler M, Mackenzie K, Möder M, Wachsen O. Thermal decomposition of biodegradable polyesters-II. Poly (lactic acid). *Polym Degrad Stabil.* 1996;53(3):329-42.
- [323] Qian L, Ye L, Qiu Y, Qu S. Thermal degradation behavior of the compound containing phosphaphenanthrene and phosphazene groups and its flame retardant mechanism on epoxy resin. *Polymer.* 2011;52(24):5486-93.
- [324] Wang X, Hu Y, Song L, Xing W, Lu H. Thermal degradation mechanism of flame retarded epoxy resins with a DOPO-substitued organophosphorus oligomer by TG-FTIR and DP-MS. *J Anal Appl Pyrol.* 2011;92(1):164-70.
- [325] Sonnier R, Ferry L, Longuet C, Laoutid F, Friederich B, Laachachi A, et al. Combining cone calorimeter and PCFC to determine the mode of action of flame- retardant additives. *Polym Advan Technol.* 2011;22(7):1091-9.
- [326] Carty P, White S. A synergistic organoiron flame-retarding/smoke-suppressing system for ABS. *Appl Organomet Chem.* 1991;5(1):51-6.
- [327] Wang Q, O'Hare D. Recent advances in the synthesis and application of layered double hydroxide (LDH) nanosheets. *Chem Rev.* 2012;112(7):4124-55.
- [328] Williams GR, O'Hare D. Towards understanding, control and application of layered double hydroxide chemistry. *J Mater Chem.* 2006;16(30):3065-74.
- [329] Evans DG, Duan X. Preparation of layered double hydroxides and their applications as additives in polymers, as precursors to magnetic materials and in biology and medicine. *Chem*

Commun. 2006(5):485-96.

[330] Ladewig K, Xu ZP, Lu GQ. Layered double hydroxide nanoparticles in gene and drug delivery. *Expert Opinion on Drug Delivery*. 2009;6(9):907-22.

[331] Wang D-Y, Das A, Costa FR, Leuteritz A, Wang Y-Z, Wagenknecht U, et al. Synthesis of organo cobalt-aluminum layered double hydroxide via a novel single-step self-assembling method and its use as flame retardant nanofiller in PP. *Langmuir*. 2010;26(17):14162-9.

[332] Kang N-J, Wang D-Y, Kutlu B, Zhao P-C, Leuteritz A, Wagenknecht U, et al. A new approach to reducing the flammability of layered double hydroxide (LDH)-based polymer composites: preparation and characterization of dye structure-intercalated LDH and its effect on the flammability of polypropylene-grafted maleic anhydride/d-LDH composites. *ACS Appl Mater Inter*. 2013;5(18):8991-7.

[333] Mazzaglia A, Scolaro LM, Mezzi A, Kaciulis S, Caro TD, Ingo GM, et al. Supramolecular colloidal systems of gold nanoparticles/amphiphilic cyclodextrin: a FE-SEM and XPS investigation of nanostructures assembled onto solid surface. *J Phys Chem C*. 2009;113(29):12772-7.

[334] Woodbridge C, Pugmire D, Johnson R, Boag N, Langell M. HREELS and XPS Studies of Ferrocene on Ag (100). *J Phys Chem B*. 2000;104(14):3085-93.

[335] Li J, Zhao W, Huang F, Manivannan A, Wu N. Single-crystalline Ni(OH)₂ and NiO nanoplatelet arrays as supercapacitor electrodes. *Nanoscale*. 2011;3(12):5103-9.

[336] Li H, Yu M, Wang F, Liu P, Liang Y, Xiao J, et al. Amorphous nickel hydroxide nanospheres with ultrahigh capacitance and energy density as electrochemical pseudocapacitor materials. *Nat commun*. 2013;4:1894.

[337] Yan J, Fan Z, Sun W, Ning G, Wei T, Zhang Q, et al. Advanced asymmetric supercapacitors based on Ni(OH)₂/graphene and porous graphene electrodes with high energy density. *Adv Funct Mater*. 2012;22(12):2632-41.

[338] Stoliarov SI, Crowley S, Lyon RE, Linteris GT. Prediction of the burning rates of non-charring polymers. *Combust Flame*. 2009;156(5):1068-83.

[339] Hoang D, Kim J, Jang BN. Synthesis and performance of cyclic phosphorus-containing flame retardants. *Polym Degrad Stabil*. 2008;93(11):2042-7.

[340] Kim YH, Kim Y-T, Kim SH, Lee D. Catalytic oxidation kinetics of iron-containing carbon

REFERENCE

particles generated by spraying ferrocene-mixed with diesel fuel into a hydrogen–air diffusion flame. *Carbon*. 2010;48(7):2072-84.

[341] Barreiro A, Hampel S, Rummeli MH, Kramberger C, Grüneis A, Biedermann K, et al. Thermal decomposition of ferrocene as a method for production of single-walled carbon nanotubes without additional carbon sources. *J Phys Chem B*. 2006;110(42):20973-7.

[342] Weil ED, Hansen RH, Patel N. Prospective approaches to more efficient flame-retardant systems. ACS Publications; 1990.

[343] Weil ED, Patel NG, Said M, Hirschler MM, Shakir S. Oxygen index: correlations to other fire tests. *Fire Mater*. 1992;16(4):159-67.

[344] Roelfes G, Lubben M, Hage R, Que Jr L, Feringa BL. Catalytic oxidation with a non-heme iron complex that generates a low-spin Fe^{III}OOH intermediate. *CHEMISTRY-WEINHEIM-EUROPEAN JOURNAL*-. 2000;6(12):2152-9.

[345] Fu Q, Li W-X, Yao Y, Liu H, Su H-Y, Ma D, et al. Interface-confined ferrous centers for catalytic oxidation. *Science*. 2010;328(5982):1141-4.

[346] Nakamura E, Yoshikai N. Low-Valent Iron-Catalyzed C-C Bond Formation-Addition, Substitution, and C-H Bond Activation. *J Org Chem*. 2010;75(18):6061-7.

[347] Gu B, Schmitt J, Chen Z, Liang L, McCarthy JF. Adsorption and desorption of natural organic matter on iron oxide: mechanisms and models. *Environ Sci Technol*. 1994;28(1):38-46.

[348] Li Z, Expósito DF, González AJ, Wang DY. Insightful investigation of smoke suppression behavior and mechanism of polystyrene with ferrocene: An important role of intermediate smoke. *Fire Mater*. 2018; 42(3):286-295

[349] Li Y, Li B, Dai J, Jia H, Gao S. Synergistic effects of lanthanum oxide on a novel intumescent flame retardant polypropylene system. *Polym Degrad Stabil*. 2008;93(1):9-16.

[350] Wu N, Yang R. Effects of metal oxides on intumescent flame-retardant polypropylene. *Polym Advan Technol*. 2011;22(5):495-501.

[351] Lin M, Li B, Li Q, Li S, Zhang S. Synergistic effect of metal oxides on the flame retardancy and thermal degradation of novel intumescent flame-retardant thermoplastic polyurethanes. *J Appl Polym Sci*. 2011;121(4):1951-60.

[352] Ram Reddy M, Xu Z, Lu G, Diniz da Costa J. Layered double hydroxides for CO₂ capture: structure evolution and regeneration. *Ind Eng Chem Res*. 2006;45(22):7504-9.

REFERENCE

- [353] Morgan AB, Wilkie CA. Flame retardant polymer nanocomposites: John Wiley & Sons; 2007.
- [354] Guo Y, Bao C, Song L, Yuan B, Hu Y. In situ polymerization of graphene, graphite oxide, and functionalized graphite oxide into epoxy resin and comparison study of on-the-flame behavior. *Ind Eng Chem Res.* 2011;50(13):7772-83.
- [355] Ren H, Sun J, Zhao Q, Zhou Q, Ling Q. Synthesis and characterization of a novel heat resistant epoxy resin based on N, N'-bis (5-hydroxy-1-naphthyl) pyromellitic diimide. *Polymer.* 2008;49(24):5249-53.
- [356] Cui Z, Oyer AJ, Glover AJ, Schniepp HC, Adamson DH. Large scale thermal exfoliation and functionalization of boron nitride. *small.* 2014;10(12):2352-5.
- [357] Thakur VK, Yan J, Lin M-F, Zhi C, Golberg D, Bando Y, et al. Novel polymer nanocomposites from bioinspired green aqueous functionalization of BNNTs. *Polym Chem.* 2012;3(4):962-9.
- [358] Chen H, Cao Y, Wei E, Gong T, Xian Q. Facile synthesis of graphene nano zero-valent iron composites and their efficient removal of trichloronitromethane from drinking water. *Chemosphere.* 2016;146:32-9.
- [359] Lattimer BY, Ouellette J, Trelles J. Thermal response of composite materials to elevated temperatures. *Fire Technol.* 2011;47(4):823-50.
- [360] McGurn MT, DesJardin PE, Dodd AB. Numerical simulation of expansion and charring of carbon-epoxy laminates in fire environments. *Int J Heat Mass Tran.* 2012;55(1):272-81.
- [361] Tranchard P, Samyn F, Duquesne S, Estèbe B, Bourbigot S. Modelling behaviour of a carbon epoxy composite exposed to fire: Part I-Characterisation of thermophysical properties. *Materials.* 2017;10(5):494.
- [362] Yu J, Huang X, Wu C, Wu X, Wang G, Jiang P. Interfacial modification of boron nitride nanoplatelets for epoxy composites with improved thermal properties. *Polymer.* 2012;53(2):471-80.
- [363] McAllister S, Fernandez-Pello C, Urban D, Ruff G. The combined effect of pressure and oxygen concentration on piloted ignition of a solid combustible. *Combust Flame.* 2010;157(9):1753-9.
- [364] Yang L, Phua SL, Teo JKH, Toh CL, Lau SK, Ma J, et al. A biomimetic approach to

REFERENCE

enhancing interfacial interactions: polydopamine-coated clay as reinforcement for epoxy resin. ACS Appl Mater Inter. 2011;3(8):3026-32.

[365] Hakkarainen T, Mikkola E, Laperre J, Gensous F, Fardell P, Le Tallec Y, et al. Smoke gas analysis by Fourier Transform Infrared Spectroscopy–Summary of the SAFIR project results. Fire Mater. 2000;24(2):101-12.

[366] Ngohang F-E, Fontaine G, Gay L, Bourbigot S. Smoke composition using MLC/FTIR/ELPI: Application to flame retarded ethylene vinyl acetate. Polym Degrad Stabil. 2015;115:89-109.